



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 17636-2:2011**  
**01-april-2011**

---

**Neporušitvene preiskave zvarnih spojev - Radiografske preiskave - 2. del : X- in gama žarki z uporabo digitalnih detektorjev (ISO/DIS 17636-2:2010)**

Non-destructive testing of welds - Radiographic testing - Part 2: X- and gamma-ray techniques with digital detectors (ISO/DIS 17636-2:2010)

Zerstörungsfreie Prüfung von Schweißverbindungen - Durchstrahlungsprüfung - Teil 2: Röntgen- und Gammastrahlungstechniken unter Anwendung digitaler Detektoren (ISO/DIS 17636-2:2010)

Contrôle non destructif des assemblages soudés - Contrôle par radiographie - Partie 2: Techniques par rayons X ou gamma à l'aide de détecteurs numériques (ISO/DIS 17636-2:2010)

**Ta slovenski standard je istoveten z: prEN ISO 17636-2**

---

**ICS:**

25.160.40      Varjeni spoji in vari      Welded joints

**oSIST prEN ISO 17636-2:2011      en,fr,de**



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN ISO 17636-2**

November 2010

ICS 25.160.40

Will supersede EN 1435:1997

English Version

**Non-destructive testing of welds - Radiographic testing - Part 2:  
X- and gamma-ray techniques with digital detectors (ISO/DIS  
17636-2:2010)**

Contrôle non destructif des assemblages soudés - Contrôle  
par radiographie - Partie 2: Techniques par rayons X ou  
gamma à l'aide de détecteurs numériques (ISO/DIS  
17636-2:2010)

Zerstörungsfreie Prüfung von Schweißverbindungen -  
Durchstrahlungsprüfung - Teil 2: Röntgen- und  
Gammastrahlungstechniken unter Anwendung digitaler  
Detektoren (ISO/DIS 17636-2:2010)

This draft European Standard is submitted to CEN members for parallel enquiry. It has been drawn up by the Technical Committee CEN/TC 121.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

<https://standards.iteh.ai/>  
SIST EN ISO 17636-2:2013

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	3
---------------	---

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

[SIST EN ISO 17636-2:2013](https://standards.iteh.ai/catalog/standards/sist/c889514a-cb81-4b81-9e00-cf031402459c/sist-en-iso-17636-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/c889514a-cb81-4b81-9e00-cf031402459c/sist-en-iso-17636-2-2013>

## Foreword

This document (prEN ISO 17636-2:2010) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This document is currently submitted to the parallel Enquiry.

This document will supersede EN 1435:1997.

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[SIST EN ISO 17636-2:2013](https://standards.iteh.ai/catalog/standards/sist/c889514a-cb81-4b81-9e00-cf031402459e/sist-en-iso-17636-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/c889514a-cb81-4b81-9e00-cf031402459e/sist-en-iso-17636-2-2013>





## DRAFT INTERNATIONAL STANDARD ISO/DIS 17636-2

ISO/TC 44/SC 5

Secretariat: ANSI

Voting begins on:  
2010-11-04Voting terminates on:  
2011-04-04

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

# Non-destructive testing of welds — Radiographic testing —

## Part 2:

### X- and gamma-ray techniques with digital detectors

*Contrôle non destructif des assemblages soudés — Contrôle par radiographie —**Partie 2: Techniques par rayons X ou gamma à l'aide de détecteurs numériques*

ICS 25.160.40

## iTeh Standards

## ISO/CEN PARALLEL PROCESSING

This draft has been developed within the European Committee for Standardization (CEN), and processed under the **CEN-lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

**To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.**

**Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.**

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

## SIST EN ISO 17636-2:2013

<https://standards.iteh.ai/catalog/standards/sist/e889514a-cb81-4b81-9e00-cf031402459e/sist-en-iso-17636-2-2013>

**Copyright notice**

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.



# Contents

Page

Foreword .....	v
Introduction.....	vi
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Symbols and terms .....	5
5 Classification of radiographic techniques .....	6
6 General .....	6
6.1 Protection against ionizing radiation .....	6
6.2 Surface preparation and stage of manufacture .....	6
6.3 Location of the weld in the radiograph .....	6
6.4 Identification of radiographs .....	6
6.5 Marking .....	7
6.6 Overlap of digital images .....	7
6.7 Types and positions of image quality indicators (IQI) .....	7
6.8 Minimum image quality values .....	8
6.9 Personnel qualification .....	8
7 Recommended techniques for making digital radiographs .....	8
7.1 Test arrangements .....	8
7.1.1 General .....	8
7.1.2 Radiation source located in front of the object and with the detector at the opposite side (see Figure 1) .....	9
7.1.3 Radiation source located outside the object and detector inside (see Figures 2 to 4) .....	9
7.1.4 Radiation source centrally located inside the object and with the detector outside (see Figures 5 to 7) .....	10
7.1.5 Radiation source located off-centre inside the object and detector outside (see figures 8 to 10) .....	11
7.1.6 Elliptic technique (see Figure 11) .....	12
7.1.7 Perpendicular technique (see Figure 12) .....	12
7.1.8 Radiation source located outside the object and detector on the other side (see Figures 13 to 18) .....	13
7.1.9 Technique for different material thicknesses (see Figure 19) .....	15
7.2 Choice of tube voltage and radiation source .....	15
7.2.1 X-ray devices up to 1000 kV .....	15
7.2.2 Other radiation sources .....	16
7.3 Detector systems and metal screens .....	17
7.3.1 Minimum normalized Signal-to-Noise-Ratio ( $SNR_N$ ) .....	17
7.3.2 Compensation principle (II) .....	18
7.3.3 Screens for IPs and shielding .....	18
7.4 Alignment of beam .....	20
7.5 Reduction of scattered radiation .....	20
7.5.1 Metal filters and collimators .....	20
7.5.2 Interception of backscattered radiation .....	20
7.6 Source-to-object distance .....	21
7.7 Magnification technique .....	23
7.8 Maximum area for a single exposure .....	24
7.9 Processing .....	24
7.9.1 Scan and read out of image .....	24

## prEN ISO 17636-2:2010 (E)

7.9.2	Calibration of DDAs .....	25
7.9.3	Bad pixel interpolation .....	25
7.9.4	Image processing .....	25
7.10	Monitor viewing conditions and storage of digital radiographs.....	26
8	Examination report .....	26
Annex A (normative)	Recommended number of exposures which give an acceptable examination of a circumferential butt weld.....	28
Annex B (normative)	Minimum image quality values.....	33
Annex C (normative)	Determination of basic spatial resolution .....	41
Annex D (normative)	Determination of minimum grey values for CR practice .....	43
D.1	Determination of normalized $SNR_N$ from $SNR_{measured}$ .....	43
D.2	Determination of minimum grey values .....	44
Annex E (informative)	Grey values, general remarks .....	48
Bibliography	.....	50

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

SIST EN ISO 17636-2:2013

<https://standards.iteh.ai/catalog/standards/sist/c889714a-cb81-4b81-9e00-cf031402459e/sist-en-iso-17636-2-2013>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17636-1 was prepared by Technical Committee CEN/TC 121, *Welding* and by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5 in collaboration.

This second edition cancels and replaces the first edition ISO 17636: 2003 which has been technically revised.

The main changes are :

- normative references were updated;
- document was divided into two parts where the present part is applicable for radiographic testing with digital detectors;
- X-ray devices up to 1 000 kV were included;
- normative Annex C on determination of basic spatial resolution was added;
- normative Annex D on determination of minimum grey values for CR practice was introduced;
- informative Annex E with general remarks on grey values was added;
- document was editorially revised.

ISO 17636 consists of the following parts, under the general title *Non-destructive testing of welds — Radiographic testing*:

- Part 1: *X- and gamma ray techniques with film*
- Part 2: *X- and gamma ray techniques with digital detectors*

## Introduction

This standard specifies fundamental techniques of radiography with the object of enabling satisfactory and repeatable results to be obtained economically. The techniques are based on generally recognized practice and fundamental theory of the subject, inspection of fusion welded joints with digital radiographic detectors.

Digital detectors provide a digital grey value image which can be viewed and evaluated with a computer only. The practice describes the recommended procedure for detector selection and radiographic practice. Selection of computer, software, monitor, printer and viewing conditions are important but not in the main focus of this standard.

The procedure specified in this standard, provides the minimum requirements and practice which permits to expose and acquire digital radiographs with equivalent sensitivity for detection of imperfections as film radiography, specified in part 1 of this standard.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

SIST EN ISO 17636-2:2013

<https://standards.iteh.ai/catalog/standards/sist/c889714a-cb81-4b81-9e00-cf031402459e/sist-en-iso-17636-2-2013>

# Non-destructive testing of welds — Radiographic testing —

## Part 2:

## X- and gamma-ray techniques with digital detectors

### 1 Scope

This European Standard specifies fundamental techniques of digital radiography with the object of enabling satisfactory and repeatable results to be obtained economically. The techniques are based on generally recognized practice and fundamental theory of the subject.

This standard applies to the digital radiographic examination of fusion welded joints in metallic materials.

It applies to the joints of plates or pipes. Besides its conventional meaning, "pipe" as used in this standard should be understood to cover other cylindrical bodies such as tubes, penstocks, boiler drums and pressure vessels. This standard complies with EN 14784-2.

This Part of ISO 17636 specifies the requirements for digital radiographic X- and gamma ray testing by either computed radiography (CR) or radiography with digital detector arrays (DDA), of the welded joints of metallic tubes for the detection of imperfections.

Digital detectors provide a digital grey value image which can be viewed and evaluated on basis of a computer only. This practice describes the recommended procedure for detector selection and radiographic practice. Selection of computer, software, monitor, printer and viewing conditions are important but not in the main focus of this standard. The procedure specified in this standard, provides the minimum requirements and practice which permits to expose and acquire digital radiographs with equivalent sensitivity for detection of imperfections as film radiography and as specified in Part 1 of this standard.

This standard does not specify acceptance levels of the indications.

If contracting parties apply lower test criteria, the quality achieved may be significantly lower than when this standard is strictly applied.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 462-1, Non-destructive testing. Image quality of radiographs. Part 1 : Image quality indicators (wire type), determination of image quality value.

EN 462-2, Non-destructive testing. Image quality of radiographs. Part 2 : Image quality indicators (step/hole type). Determination of image quality value.

EN 462-5, Non-destructive testing. Image quality of radiographs. Part 5 : Image quality indicators (duplex wire type), determination of image unsharpness value.

EN 473, *Non-destructive testing — Qualification and certification of NDT personnel — General principles*

## prEN ISO 17636-2:2010 (E)

EN 12543 (all parts), *Non-destructive testing — Characteristics of focal spots in industrial X-ray systems for use in non-destructive testing*

EN 12679, *Non-destructive testing — Determination of the size of industrial radiographic sources — Radiographic method*

EN 14784-1:2005, *Non-destructive testing — Industrial computed radiography with storage phosphor imaging plates — Part 1: Classification of systems*

ISO 5576, *Non-destructive testing — Industrial X-ray and gamma-ray radiology — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of personnel*

ISO 19232-1, *Non-destructive testing — Image quality of radiographs — Part 1: Image quality indicators (wire type) - Determination of image quality value*

ISO 19232-2, *Non-destructive testing — Image quality of radiographs — Part 2: Image quality indicators (step/hole type) - Determination of image quality value*

ISO 19232-3, *Non-destructive testing — Image quality of radiographs — Part 3: Image quality classes for ferrous metals*

ISO 19232-4, *Non-destructive testing — Image quality of radiographs — Part 4: Experimental evaluation of image quality values and image quality tables*

ISO 19232-5, *Non-destructive testing — Image quality of radiographs — Part 5: Image quality indicators (duplex wire type) - Determination of image unsharpness value*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5576:1997 and the following apply.

#### 3.1

##### **computed radiography**

##### **storage phosphor imaging plate system**

complete system of a storage phosphor imaging plate (IP) and a corresponding read out unit (scanner or reader), which converts the information of the IP into a digital image

#### 3.2

##### **storage phosphor imaging plate**

##### **IP**

photostimulable luminescent material that is capable of storing a latent radiographic image of a material being examined and, upon stimulation by a source of red spectrum light of appropriate wavelength, will generate luminescence proportional to radiation absorbed

**NOTE** When performing computed radiography, an IP is used in lieu of a film. When establishing techniques related to source focal geometries, the IP is referred to as a detector (i.e. source-to detector-distance or SDD).

#### 3.3

##### **digital detector array system**

##### **DDA system**

electronic device that converts ionizing or penetrating radiation into a discrete array of analog signals which are subsequently digitised and transferred to a computer for display as a digital image corresponding to the radiologic energy pattern imparted upon the input region of the device

#### 3.4

##### **structure noise of IP**

structure due to inhomogeneties in the sensitive layer (graininess) and surface of an IP