



Designation: D 1327 – 97a

Standard Specification for Bitumen-Saturated Woven Burlap Fabrics Used in Roofing and Waterproofing¹

This standard is issued under the fixed designation D 1327; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers woven burlap fabrics, saturated with either asphalt or refined coal-tar, as specified by the purchaser, for use in the membrane system of roofing or waterproofing or as specified by the manufacturer.

1.1.1 *Asphalt-saturated burlap fabric* shall be used with asphalt base plying cement; typical ones are mopping asphalts conforming to Specifications D 312, D 449, or appropriate solvent bearing bituminous materials.

1.1.2 *Coal-tar-saturated burlap fabric* shall be used with coal-tar base plying cements; typical ones are coal-tar pitches conforming to Specification D 450, or appropriate solvent bearing bituminous materials.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

D 146 Test Methods for Sampling and Testing Bitumen-Saturated Felts and Woven Fabrics for Roofing and Waterproofing²

D 312 Specification for Asphalt Used in Roofing²

D 449 Specification for Asphalt Used in Dampproofing and Waterproofing²

D 450 Specification for Coal-Tar Pitch Used in Roofing, Dampproofing, and Waterproofing²

D 1079 Terminology Relating to Roofing, Waterproofing, and Bituminous Materials²

2.2 AATCC Standard:

Method 30-1974 Test for Resistance of Textiles to Mildew and Rot³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology D 1079.

4. Materials and Manufacture

4.1 The fabric to be saturated shall be composed of 100 % jute fiber except for two cotton threads in each selvage. If the selvage is used, it shall be no more than 1/4 in. (6 mm) wide. The minimum fabric construction used shall be 5.4 oz/yd² (180 g/m²) minimum burlap.

4.2 In the process of manufacture, the dry burlap fabric shall be saturated with bitumen.

5. Physical Properties

5.1 The material shall conform to the physical properties prescribed in Table 1.

5.2 The rolls shall not crack nor be so sticky as to cause tearing or material damage upon being unrolled at temperatures between 50 and 140°F (10 and 60°C).

5.3 *Resistance to Rotting*—The average percentage of the original strength retained by the saturated product shall be at least 1.75 times that retained by the control sample after 1 week.

6. Workmanship, Finish, and Appearance

6.1 The burlap fabric shall be thoroughly and uniformly saturated in such a manner that every fiber shall be visibly stained through by the saturant.

6.2 The meshes of the fabric shall not be completely closed or sealed by the process of saturation. There shall be sufficient porosity maintained to allow successive moppings of the plying cement to seep through.

¹ This specification is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.04 on Felts and Fabrics for Bituminous Roofing and Waterproofing.

Current edition approved July 10, 1997. Published January 1998. Originally published as D 1327 – 54 T. Last previous edition D 1327 – 97.

² *Annual Book of ASTM Standards*, Vol 04.04.

³ Available from American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.