



Designation: ~~A1008/A1008M-03~~ Designation: A 1008/A 1008M - 04

Standard Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy and High-Strength Low-Alloy with Improved Formability¹

This standard is issued under the fixed designation A 1008/A 1008M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers cold-rolled structural, high-strength low-alloy, and high-strength low-alloy with improved formability steel sheet, in coils and cut lengths.

1.2 Cold rolled steel sheet is available in the designations as listed in 4.1.

1.3 This specification does not apply to steel strip as described in Specification A 109.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other.

2. Referenced Documents

2.1 *ASTM Standards:*²

A 109/A 109M [Specification for Steel, Strip, Carbon \(0.25 Maximum Percent\), Cold Rolled](#)

A 366/A 366M [Specification for Commercial Steel \(CS\), Sheet, Carbon \(0.15 Maximum Percentage\), Cold-Rolled³](#)

A 370 [Test Methods and Definitions for Mechanical Testing of Steel Products](#)

A 568/A 568M [Specification for Steel, Sheet, Carbon, and High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, General Requirements for](#)

A 620/A 620M [Specification for Drawing Steel \(DS\), Sheet, Carbon, Cold-Rolled³](#)

A 941 [Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#) ~~Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys~~

E 18 [Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials](#)

E 517 [Test Method for Plastic Strain Ratio \$r\$ for Sheet Metal](#)

E 646 [Test Method for Tensile Strain-Hardening Exponents \(n-Values\) of Metallic Sheet Materials](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of other terms used in this specification, refer to Terminology A 941.

3.1.2 *stabilization*—the addition of one or more nitride- or carbide-forming elements, or both, such as titanium and columbium, to control the level of the interstitial elements of carbon and nitrogen in the steel.

3.1.2.1 *Discussion*—Stabilizing improves formability and increases resistance to aging.

3.1.3 *vacuum degassing*—a process of refining liquid steel in which the liquid is exposed to a vacuum as part of a special technique for removing impurities or for decarburizing the steel.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *aging*—loss of ductility with an increase in hardness, yield strength, and tensile strength that occurs when steel that has been slightly cold worked (such as by temper rolling) is stored for some time.

3.2.1.1 *Discussion*—Aging increases the tendency of a steel to exhibit stretcher strains and fluting.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved April 10, 2003. Published May 2003. Originally approved in 2000. Last previous edition approved in 2002 as A1008/A1008M-02^{ε1}.

Current edition approved Feb. 1, 2004. Published February 2004. Originally approved in 2000. Last previous edition approved in 2003 as A 1008/A 1008M - 03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* Vol 01-03 volume information, refer to the standard's Document Summary page on the ASTM website.

³ Discontinued; see *2000 Annual Book of ASTM Standards*, Vol 01.03. Replaced by A1008/A1008M.

^ε Withdrawn.

*A Summary of Changes section appears at the end of this standard.

4. Classification

4.1 Cold-rolled steel sheet is available in the following designations:

4.1.1 Commercial Steel (CS Types A, B, and C),

4.1.2 Drawing Steel (DS Types A and B),

NOTE 1—CS Type B and DS Type B describe the most common product previously included, respectively, in Specifications A 366/A 366M and A 620/A 620M.

4.1.3 Deep Drawing Steel (DDS),

4.1.4 Extra Deep Drawing Steel (EDDS),

4.1.5 Structural Steel (SS grades 25[170], 30[205], 33[230] Types 1 and 2, 40[275] Types 1 and 2, 50[340], 60[410], 70[480], and 80[550]), ~~80[550]~~).

4.1.6 High-Strength Low-Alloy Steel (HSLAS, in classes 1 and 2, in grades 45[310], 50[340], 55[380], 60[410], 65[450], and 70[480] in Classes 1 and 2), and

4.1.7 High-Strength Low-Alloy Steel with Improved Formability (HSLAS-F grades 50[340], 60[410], 70[480], and 80[550]).

4.1.7.1 HSLAS-F steel has improved formability when compared to HSLAS. The steel is fully deoxidized, made to fine grain practice and includes microalloying elements such as columbium, vanadium, zirconium, etc. The steel shall be treated to achieve inclusion control.

~~4.2~~

4.2 When required for HSLAS and HSLAS-F steels, limitations on the use of one or more of the microalloy elements shall be specified on the order.

4.3 Cold-rolled steel sheet is supplied for either exposed or unexposed applications. Within the latter category, cold-rolled sheet is specified either “temper rolled” or “annealed last.” For details on processing, attributes and limitations, and inspection standards, refer to Specification A 568/A 568M.

5. Ordering Information

5.1 It is the purchaser’s responsibility to specify in the purchase order all ordering information necessary to describe the required material. Examples of such information include, but are not limited to, the following:

5.1.1 ASTM specification number and year of issue;

5.1.2 Name of material and designation (cold-rolled steel sheet) (include grade, type, and class, as appropriate, for CS, DS, DDS, EDDS, SS, HSLAS, or HSLAS-F) (see 4.1);

5.1.2.1 When a type is not specified for CS or DS, Type B will be furnished (see 4.1);

5.1.2.2 When a class is not specified for HSLAS, Class 1 will be furnished (see 4.1);

5.1.2.3 When a type is not specified for SS33[230] and SS40[275], Type 1 will be furnished (see 4.1);

5.1.3 Classification (either exposed, unexposed, temper rolled, or annealed last) (see ~~4.2.4.3~~);

5.1.4 Finish (see 9.1);

5.1.5 Oiled or not oiled, as required (see 9.2);

5.1.6 Dimensions (thickness, thickness tolerance table (see 5.1.6.1), width, and whether cut lengths or coils);

5.1.6.1 As agreed upon between the purchaser and the producer, material ordered to this specification will be supplied to meet the applicable thickness tolerance table shown in Specification A 568/A 568M;

NOTE 2—Not all producers are capable of meeting all the limitations of the thickness tolerance tables in Specification A 568/A 568M. The purchaser should contact the producer regarding possible limitations prior to placing an order.

5.1.7 Coil size (must include inside diameter, outside diameter, and maximum weight);

5.1.8 Copper bearing steel (if required);

5.1.9 Quantity;

5.1.10 Application (part identification and description);

~~5.1.11 Special requirements (if required), or supplementary requirement S1 for HSLAS; and~~

5.1.11 Special requirements (if required), and

5.1.12 A report of heat analysis will be supplied, if requested, for CS, DS, DDS, and EDDS. For materials with required mechanical properties, SS, HSLAS, and HSLAS-F, a report is required of heat analysis and mechanical properties as determined by the tension test.

NOTE 3—A typical ordering description is as follows: ASTM A 1008-XX, cold rolled steel sheet, CS Type A, exposed, matte finish, oiled, 0.035 by 30 in. by coil, ID 24 in., OD 48 in., max weight 15 000 lbs, thickness tolerance Table 18 of Specification A 568/A 568M, 100 000 lb, for part No. 4560, Door Panel.

or:

ASTM A 1008M-XX, cold-rolled steel sheet, SS grade 275, unexposed, matte finish, oiled, 0.88 mm by 760 mm by 2440 mm, thickness tolerance Table A1.15 of Specification A 568/A 568M, 10 000 kg, for shelf bracket.

6. General Requirements for Delivery

6.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of

Specification A 568/A 568M unless otherwise provided herein.

7. Chemical Composition

7.1 The heat analysis of the steel shall conform to the chemical composition requirements of the appropriate designation shown in Table 1 for CS, DS, DDS, and EDDS and in Table 2 for SS, HSLAS, and HSLAS-F.

7.2 Each of the elements listed in Table 1 and Table 2 shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium, or molybdenum is less than 0.02 %, report the analysis as <0.02 % or the actual determined value. When the amount of vanadium, columbium, or titanium is less than 0.008 %, report the analysis as <0.008 % or the actual determined value.

7.3 Sheet steel grades defined by this specification are suitable for welding if appropriate welding conditions are selected. For certain welding processes, if more restrictive composition limits are desirable, they shall be specified at the time of inquiry and confirmed at the time of ordering.

8. Mechanical Properties

8.1 CS, DS, DDS, and EDDS:

8.1.1 Typical nonmandatory mechanical properties for CS, DS, DDS and EDDS are shown in Table 3.

8.1.2 The material shall be capable of being bent, at room temperature, in any direction through 180° flat on itself without cracking on the outside of the bent portion (see Section 14 of Test Methods and Definitions A 370).

8.1.3 Sheet of these designations except for EDDS are subject to aging dependent upon processing factors such as the method of annealing (continuous annealing or box annealing), and chemical composition. For additional information on aging, see Appendix X1 of Specification A 568/A 568M.

8.1.4 EDDS steel is stabilized to be nonaging and so is not subject to stretcher strains and fluting. Other steels are processed to be nonaging; please consult your supplier.

8.2 SS, HSLAS and HSLAS-F:

8.2.1 The available strength grades for SS, HSLAS and HSLAS-F are shown in Table 4.

8.2.2 Tension Tests:

8.2.2.1 *Requirements*— Material as represented by the test specimen shall conform to the mechanical property requirements specified in Table 4. These requirements do not apply to the uncropped ends of unprocessed coils.

8.2.2.2 *Number of Tests*— Two tension tests shall be made from each heat or from each 50 tons [45 000 kg]. When the amount of finished material from a heat is less than 50 tons [45 000 kg], one test shall be made. When material rolled from heat differs 0.050 in. [1.27 mm] or more in thickness, one tension test shall be made from the thickest and thinnest material regardless of the weight represented.

8.2.2.3 Tension test specimens shall be taken at a point immediately adjacent to the material to be qualified.

8.2.2.4 Tension test specimens shall be taken from the full thickness of the sheet.

8.2.2.5 Tension test specimens shall be taken from a location approximately halfway between the center of the sheet and the edge of the material as rolled.

**TABLE 1 Chemical Composition^A
For Cold Rolled Steel Sheet Designations CS, DS, DDS, and EDDS**

Designation	Composition, % Heat Analysis (Element Maximum Unless Otherwise Shown)													
	C	Mn	P	S	Al	Si	Cu ^B	Ni ^B	Cr ^{B,C}	Mo ^B	V	Cb	Ti	N
CS Type A ^{D,E,F,G}	0.10	0.60	0.030	0.035	0.20 ^H	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
CS Type B ^D	0.02 to 0.15	0.60	0.030	0.035	0.20 ^H	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
CS Type C ^{D,E,F,G}	0.08	0.60	0.10	0.035	0.20 ^H	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
DS Type A ^{E,J}	0.08	0.50	0.020	0.030	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
DS Type B	0.02 to 0.08	0.50	0.020	0.030	0.02 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
DDS ^{F,G}	0.06	0.50	0.020	0.025	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.008 ^I	...
EDDS ^K	0.02	0.40	0.020	0.020	0.01 min	...	0.10	0.10	0.15	0.03	0.008	0.10	0.15	...

^A Where an ellipsis (. . .) appears in the table, there is no requirement, but the analysis result shall be reported.

^B The sum of copper, nickel, chromium, and molybdenum shall not exceed 0.50 % on heat analysis. When one or more of these elements is specified by the purchaser, the sum does not apply, in which case only the individual limits on the remaining elements shall apply.

^C Chromium is permitted, at the producer's option, to 0.25 % maximum when the carbon content is less than or equal to 0.05 %. In such case the limit on the sum of the four elements in Footnote B does not apply.

^D When an aluminum deoxidized steel is required for the application, it is permissible to order Commercial Steel (CS) to a minimum of 0.01 % total aluminum.

^E Specify Type B to avoid carbon levels below 0.02 %.

^F It is permissible to furnish as a vacuum degassed or chemically stabilized steel, or both, at the producer's option.

^G For carbon levels less than or equal to 0.02 %, it is permissible to use columbium or titanium, or both, as stabilizing elements at the producer's option. In such cases, the applicable limit for columbium shall be 0.10 % max. and the limit on titanium shall be 0.15 % max.

^H When copper steel is specified, the copper limit is a minimum requirement. When copper steel is not specified, the copper limit is a maximum requirement.

^I Except for EDDS, titanium is permitted, at producer's option, to 0.025 % provided the ratio of % titanium to % nitrogen does not exceed 3.4.

^J It is permissible to furnish DS Type A as a vacuum degassed steel, at the producers option.

^K Shall be furnished as a vacuum degassed and stabilized steel.



TABLE 2 Chemical Composition^A
For Cold Rolled Steel Sheet Designations SS, HSLAS, and HSLAS-F

Designation	% Heat Analysis, Element Maximum unless otherwise shown												
	C	Mn	P	S	Al	Si	Cu ^{B,C}	Ni ^B	Cr ^B	Mo ^B	V	Cb	N
SS:													
Grade 25 [170]	0.20	0.60	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 30 [205]	0.20	0.60	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 33 [230] Type 1	0.20	0.60	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 33 [230] Type 2	0.15	0.60	0.20	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 40 [275] Type 1	0.20	0.90	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 40 [275] Type 2	0.15	0.60	0.20	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 50 [340]	0.20	0.70	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 60 [410]	0.20	0.70	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 70 [480]	0.20	0.70	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
Grade 80 [550]	0.20	0.60	0.035	0.035	0.20	0.20	0.15	0.06	0.008	0.008	...
HSLAS: ^D													
Grade 45 [310] Class 1	0.22	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 45 [310] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 50 [340] Class 1	0.23	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 50 [340] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 55 [380] Class 1	0.25	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 55 [380] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 60 [410] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	...
Grade 60 [410] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.020 ^E
Grade 60 [410] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 65 [450] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 65 [450] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 65 [450] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.020 ^E
Grade 65 [450] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 70 [480] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 70 [480] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.012 ^E
Grade 70 [480] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.020 ^E
Grade 70 [480] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.06	0.01 min	0.005 min	0.020 ^E
—HSLAS-F: ^E													
HSLAS-F: ^F													
Grade 50[340], 60[410], 70[480], and 80[550]	0.15	1.65	0.020	0.025	0.20	0.20	0.15	0.06
Grade 50[340], 60[410], 70[480], and 80[550]	0.15	1.65	0.020	0.025	0.20	0.20	0.15	0.06	^E

^A Where an ellipsis (. . .) appears in the table, there is no requirement but, the analysis shall be reported.

^B The sum of copper, nickel, chromium, and molybdenum shall not exceed 0.50 %. When one or more of these elements are specified by the purchaser, the sum does not apply, in which case, only the individual limits on the remaining unspecified elements will apply.

^C When copper is specified, the copper limit is a minimum requirement. When copper steel is not specified, the copper limit is a maximum requirement.

^D For HSLAS steels, it is permissible to add columbium and vanadium singly or in combination.

^E The purchaser has the option of restricting the nitrogen content. It should be noted that, depending on the microalloying scheme (for example, use of Vanadium) of the producer, nitrogen may be a deliberate addition. Consideration should be made for the use of nitrogen binding elements (for example, Vanadium, Titanium).

^F These steels shall also contain one or more of the following elements: Vanadium, Titanium, and Columbium. Other alloying elements are permissible, but are not required.

TABLE 3 Typical Ranges of Mechanical Properties^A
(Nonmandatory)^B
For Cold Rolled Steel Sheet Designations CS, DS, DDS and EDDS

Designation	Yield Strength ^C		Elongation in 2 in. [50 mm] % ^C	<i>r_m</i> Value ^D	<i>n</i> -Value ^E
	ksi	MPa			
CS Types A, B, and C	20 to 40	[140 to 275]	≥ 30	^F	^F
DS Types A and B	22 to 35	[150 to 240]	≥ 36	1.3 to 1.7	0.17 to 0.22
DDS	17 to 29	[115 to 200]	≥ 38	1.4 to 1.8	0.20 to 0.25
EDDS	15 to 25	[105 to 170]	≥ 40	1.7 to 2.1	0.23 to 0.27

^A These typical mechanical properties apply to the full range of steel sheet thicknesses. The yield strength tends to increase, the elongation decreases and some of the formability values tend to decrease as the sheet thickness decreases.

^B The typical mechanical property values presented here are nonmandatory. They are provided to assist the purchaser in specifying a suitable steel for a given application. Values outside of these ranges are to be expected.

^C Yield Strength and elongation are measured in the longitudinal direction in accordance with Test Methods A 370.

^D Average plastic strain ratio (*r_m* value) as determined by Test Method E 517.

^E The strain hardening exponent (*n*-value) as determined by Test Method E 646.

^F No typical properties have been established.

8.2.2.6 Tension test samples shall be taken with the lengthwise axis of the test specimen parallel to the rolling direction (longitudinal test).

**TABLE 4 Mechanical Property Requirements^A
For Cold Rolled Steel Sheet Designations SS, HSLAS, and HSLAS-F**

Designation	Yield Strength, min		Tensile Strength, min		Elongation in 2 in. or 50 mm, min, %
	ksi	[MPa]	ksi	[MPa]	
SS:					
Grade 25 [170]	25	[170]	42	[290]	26
Grade 30 [205]	30	[205]	45	[310]	24
Grade 33 [230] Types 1 and 2	33	[230]	48	[330]	22
Grade 40 [275] Types 1 and 2	40	[275]	52	[360]	20
Grade 50 [340]	50	[340]	65	[410]	18
Grade 60 [410]	60	[410]	75	[480]	12
Grade 70 [480]	70	[480]	85	[540]	6 ^c
Grade 80 [550]	80 ^B	[550]	82	[565]	2 ^c
HSLAS:					
Grade 45 [310] Class 1	45	[310]	60	[410]	22
Grade 45 [310] Class 2	45	[310]	55	[380]	22
Grade 50 [340] Class 1	50	[340]	65	[450]	20
Grade 50 [340] Class 2	50	[340]	60	[410]	20
Grade 55 [380] Class 1	55	[380]	70	[480]	18
Grade 55 [380] Class 2	55	[380]	65	[450]	18
Grade 60 [410] Class 1	60	[410]	75	[520]	16
Grade 60 [410] Class 2	60	[410]	70	[480]	16
Grade 65 [450] Class 1	65	[450]	80	[550]	15
Grade 65 [450] Class 2	65	[450]	75	[520]	15
Grade 70 [480] Class 1	70	[480]	85	[585]	14
Grade 70 [480] Class 2	70	[480]	80	[550]	14
HSLAS-F:					
Grade 50 [340]	50	[340]	60	[410]	22
Grade 60 [410]	60	[410]	70	[480]	18
Grade 70 [480]	70	[480]	80	[550]	16
Grade 80 [550]	80	[550]	90	[620]	14

^A For coil products, testing by the producer is limited to the end of the coil. Mechanical properties throughout the coil shall comply with the minimum values specified.

^B On this full-hard product, the yield strength approaches the tensile strength and since there is no halt in the gage or drop in the beam, the yield point shall be taken as the yield stress at 0.5 % extension under load.

^C There is no requirement for elongation in 2 in. for SS Grade 80.

8.2.2.7 *Test Method*—Yield strength shall be determined by either the 0.2 % offset method or the 0.5 % extension under load method unless otherwise specified.

8.2.3 *Bending Properties:*

8.2.3.1 The suggested minimum inside radii for cold bending are listed in Appendix X1 and is discussed in more detail in Specification A 568/A 568M (Section 6). Where a tighter bend radius is required, where curved or offset bends are involved, or where stretching or drawing are also a consideration, the producer shall be consulted.

9. Finish and Appearance

9.1 *Surface Finish:*

9.1.1 Unless otherwise specified, the sheet shall have a matte finish. When required, specify the appropriate surface texture and condition. For additional information, see the “Finish and Condition” section of Specification A 568/A 568M.

For additional information see “Finish and Condition” section of Specification A 568/A 568M.

9.2 *Oiling:*

9.2.1 Unless otherwise specified, the sheet shall be oiled.

9.2.2 When required, specify the sheet to be furnished not oiled (dry).

10. Retests and Resamples

10.1 *Retests*—If the results on an original tension test specimen are within 2 ksi [14 MPa] of the required tensile strength, within 1 ksi [7 MPa] of the required yield point, or within two percentage points of the required elongation, a retest shall be permitted for which one test specimen selected at random shall be tested. If the results of this retest specimen satisfy the specified mechanical properties and all other requirements of the applicable specification are satisfied, the material shall be accepted. Retests are permitted in accordance with Specification A 568/A 568M.

10.2 *Resamples*—Resamples are permitted in accordance with Specification A 568/A 568M.

11. Certification

11.1 A report of heat analysis shall be supplied, if requested, for CS, DS, DDS, and EDDS steels. For material with required mechanical properties, SS, HSLAS, and HSLAS-F, a report is required of heat analysis and mechanical properties as determined by the tension test.

11.2 The report shall include the purchase order number, the ASTM designation number and year date, product designation, grade, type or class, as applicable, the heat number, and as required, heat analysis and mechanical properties as indicated by the tension test.

11.3 A signature is not required on the test report. However, the document shall clearly identify the organization submitting the report. Notwithstanding the absence of a signature, the organization submitting the report is responsible for the content of the report.

11.4 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document must meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the supplier. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

12. Product Marking

12.1 In addition to the requirements of Specification A 568/A 568M, each lift or coil shall be marked with the designation shown on the order (CS (Type A, B, or C), DS (Type A or B), DDS, EDDS, SS, HSLAS, or HSLAS-F). The designation shall be legibly stenciled on the top of each lift or shown on a tag attached to each coil or shipping unit.

13. Keywords

~~13.1 carbon steel sheet; cold-rolled steel sheet; steel sheet; commercial steel; drawing steel; deep drawing steel; extra deep drawing steel; high-strength low-alloy steel; high-strength low-alloy steel with improved formability; structural steel~~

~~SUPPLEMENTARY REQUIREMENTS~~

~~FOR COLD ROLLED HSLAS STEEL SHEET~~

~~The following supplementary requirements shall apply when specified in the order or contract:~~

~~S1. Elements~~

~~S1.1 When a purchaser prefers to designate the specific elements (columbium, vanadium, nitrogen, or combinations thereof), one of the types listed below shall be specified. The type, in addition to the grade, must be shown on the order:~~

~~<https://standards.iteh.ai/catalog/standards/sist/6d9bf0a9-0fdc-4bea-9ac8-6101d0cc3775/astm-a1008-a1008m-04>~~