

**SLOVENSKI STANDARD  
SIST EN ISO 15156-3:2010****01-januar-2010****BUXca Yý U****SIST EN ISO 15156-3:2004****SIST EN ISO 15156-3:2004/AC:2007**

---

**Industrija za predelavo nafte in zemeljskega plina - Materiali za uporabo v okoljih s H<sub>2</sub>S v proizvodnji olja in plina - 3. del: Visokolegirana jekla (CRAs) in druge zlitine (ISO 15156-3:2009)**

Petroleum and natural gas industries - Materials for use in H<sub>2</sub>S-containing environments in oil and gas production - Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys (ISO 15156-3:2009)

(standards.iteh.ai)

Erdöl- und Erdgasindustrie - Werkstoffe für den Einsatz in H<sub>2</sub>S-haltiger Umgebung bei der Öl- und Gasgewinnung - Teil 3: Hochlegierte Stähle (CRAs) und andere Legierungen (ISO 15156-3:2009)

Industries du pétrole et du gaz naturel - Matériaux pour utilisation dans des environnements contenant de l'hydrogène sulfuré (H<sub>2</sub>S) dans la production de pétrole et de gaz - Partie 3: ARC (alliages résistants à la corrosion) et autres alliages résistants à la fissuration (ISO 15156-3:2009)

**Ta slovenski standard je istoveten z: EN ISO 15156-3:2009**

---

**ICS:**

75.180.10	Oprema za raziskovanje in odkopavanje	Exploratory and extraction equipment
77.060	Korozija kovin	Corrosion of metals

**SIST EN ISO 15156-3:2010****en,fr**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 15156-3:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

EUROPEAN STANDARD

**EN ISO 15156-3**

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2009

ICS 75.180.01

Supersedes EN ISO 15156-3:2003

English Version

**Petroleum and natural gas industries - Materials for use in H<sub>2</sub>S-containing environments in oil and gas production - Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys (ISO 15156-3:2009)**

Industries du pétrole et du gaz naturel - Matériaux pour utilisation dans des environnements contenant de l'hydrogène sulfuré (H<sub>2</sub>S) dans la production de pétrole et de gaz - Partie 3: ARC (alliages résistants à la corrosion) et autres alliages résistants à la fissuration (ISO 15156-3:2009)

Erdöl- und Erdgasindustrie - Werkstoffe für den Einsatz in H<sub>2</sub>S-haltiger Umgebung bei der Öl- und Gasgewinnung - Teil 3: Hochlegierte Stähle (CRAs) und andere Legierungen (ISO 15156-3:2009)

This European Standard was approved by CEN on 29 September 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

Page

Foreword.....3

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

[SIST EN ISO 15156-3:2010](https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

## Foreword

This document (EN ISO 15156-3:2009) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2010, and conflicting national standards shall be withdrawn at the latest by April 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15156-3:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)  
Endorsement notice

The text of ISO 15156-3:2009 has been approved by CEN as a EN ISO 15156-3:2009 without any modification.

SIST EN ISO 15156-3:2010  
<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 15156-3:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

INTERNATIONAL  
STANDARDISO  
15156-3Second edition  
2009-10-15

---

---

**Petroleum and natural gas industries —  
Materials for use in H<sub>2</sub>S-containing  
environments in oil and gas  
production —**

Part 3:

**Cracking-resistant CRAs (corrosion-  
resistant alloys) and other alloys****(standards.iteh.ai)***Industries du pétrole et du gaz naturel — Matériaux pour utilisation dans  
des environnements contenant de l'hydrogène sulfuré (H<sub>2</sub>S) dans la  
production de pétrole et de gaz —*[https://standards.iteh.ai/catalog/standards/sist/658a156a-07e1-460f-87b7-](https://standards.iteh.ai/catalog/standards/sist/658a156a-07e1-460f-87b7-123574b0849c/sist-15156-3-2010)

123574b0849c/sist-15156-3-2010

*Partie 3: ARC (alliages résistants à la corrosion) et autres alliages  
résistants à la fissuration*Reference number  
ISO 15156-3:2009(E)

© ISO 2009

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15156-3:2010](https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland



## Contents

Page

Foreword .....	iv
Introduction.....	v
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>2</b>
<b>3 Terms and definitions .....</b>	<b>3</b>
<b>4 Symbols and abbreviated terms .....</b>	<b>5</b>
<b>5 Factors affecting the cracking resistance of CRAs and other alloys in H<sub>2</sub>S-containing environments .....</b>	<b>5</b>
<b>6 Qualification and selection of CRAs and other alloys with respect to SSC, SCC and GHSC in H<sub>2</sub>S-containing environments.....</b>	<b>6</b>
6.1 General .....	6
6.2 Evaluation of materials properties .....	6
6.3 PREN.....	8
<b>7 Purchasing information and marking.....</b>	<b>9</b>
7.1 Information that should be supplied for material purchasing.....	9
7.2 Marking, labelling and documentation.....	9
<b>Annex A (normative) Environmental cracking-resistant CRAs and other alloys (including Table A.1 — Guidance on the use of the materials selection tables) .....</b>	<b>10</b>
<b>Annex B (normative) Qualification of CRAs for H<sub>2</sub>S-service by laboratory testing.....</b>	<b>48</b>
<b>Annex C (informative) Information that should be supplied for material purchasing .....</b>	<b>58</b>
<b>Annex D (informative) Materials chemical compositions and other information.....</b>	<b>60</b>
<b>Annex E (informative) Nominated sets of test conditions .....</b>	<b>72</b>
<b>Bibliography.....</b>	<b>73</b>

## ISO 15156-3:2009(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15156-3 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*.

This second edition cancels and replaces the first edition (ISO 15156-3:2003), of which it constitutes a minor revision, specifically by the following:

- inclusion of new materials, and revised limits for other materials, in the tables of Annex A;
- inclusion of ISO equivalent ASTM hardness standards;
- correction of the conversion from NaCl % mass fraction used in Annex E to Cl<sup>-</sup> milligrams per litre as used in Annex A;
- inclusion of a small number of other technical changes;
- inclusion of changes to make the intent of the text clearer and to correct typographical errors.

ISO 15156 consists of the following parts, under the general title *Petroleum and natural gas industries — Materials for use in H<sub>2</sub>S-containing environments in oil and gas production*:

- *Part 1: General principles for selection of cracking-resistant materials*
- *Part 2: Cracking-resistant carbon and low-alloy steels, and the use of cast irons*
- *Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys*

## Introduction

The consequences of sudden failures of metallic oil and gas field components, associated with their exposure to H<sub>2</sub>S-containing production fluids, led to the preparation of the first edition of NACE MR0175, which was published in 1975 by the National Association of Corrosion Engineers, now known as NACE International.

The original and subsequent editions of NACE MR0175 established limits of H<sub>2</sub>S partial pressure above which precautions against sulfide stress-cracking (SSC) were always considered necessary. They also provided guidance for the selection and specification of SSC-resistant materials when the H<sub>2</sub>S thresholds were exceeded. In more recent editions, NACE MR0175 has also provided application limits for some corrosion-resistant alloys, in terms of environmental composition and pH, temperature and H<sub>2</sub>S partial pressures.

In separate developments, the European Federation of Corrosion issued EFC Publication 16 in 1995 and EFC Publication 17 in 1996. These documents are generally complementary to those of NACE though they differed in scope and detail.

In 2003, the publication of the three parts of ISO 15156 and NACE MR0175/ISO 15156 was completed for the first time. These technically identical documents utilized the above sources to provide requirements and recommendations for materials qualification and selection for application in environments containing wet H<sub>2</sub>S in oil and gas production systems. They are complemented by NACE TM0177 and NACE TM0284 test methods.

The revision of this part of ISO 15156 involves a consolidation of all changes agreed and published in the Technical Corrigenda 1 and 2, ISO 15156-3:2003/Cor.1:2005 and ISO 15156-3:2003/Cor.2:2005 and by the Technical Circulars 1 and 2, ISO 15156-3:2001/Cir.1:2007(E) and ISO 15156-3:2001/Cir.2:2008(E), published by the ISO 15156 maintenance agency secretariat at DIN, Berlin.

The changes were developed by, and approved by the ballot of, representative groups from within the oil and gas production industry. The great majority of these changes stem from issues raised by document users. A description of the process by which these changes were approved can be found at the ISO 15156 maintenance website [www.iso.org/iso15156maintenance](http://www.iso.org/iso15156maintenance).

When found necessary by oil and gas production industry experts, future interim changes to this part of ISO 15156 will be processed in the same way and will lead to interim updates to this part of ISO 15156 in the form of Technical Corrigenda or Technical Circulars. Document users should be aware that such documents can exist and can impact the validity of the dated references in this part of ISO 15156.

The ISO 15156 maintenance agency at DIN was set up after approval by the ISO Technical Management Board given in document 34/2007. This document describes the make up of the agency, which includes experts from NACE, EFC and ISO/TC 67/WG 7, and the process for approval of amendments. It is available from the ISO 15156 maintenance website and from the ISO/TC 67 Secretariat. The website also provides access to related documents that provide more detail of ISO 15156 maintenance activities.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 15156-3:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

# Petroleum and natural gas industries — Materials for use in H<sub>2</sub>S-containing environments in oil and gas production —

## Part 3: Cracking-resistant CRAs (corrosion-resistant alloys) and other alloys

**WARNING — CRAs (corrosion-resistant alloys) and other alloys selected using this part of ISO 15156 are resistant to cracking in defined H<sub>2</sub>S-containing environments in oil and gas production but not necessarily immune to cracking under all service conditions. It is the equipment user's responsibility to select the CRAs and other alloys suitable for the intended service.**

### 1 Scope

This part of ISO 15156 gives requirements and recommendations for the selection and qualification of CRAs (corrosion-resistant alloys) and other alloys for service in equipment used in oil and natural gas production and natural gas treatment plants in H<sub>2</sub>S-containing environments, whose failure can pose a risk to the health and safety of the public and personnel or to the environment. It can be applied to help to avoid costly corrosion damage to the equipment itself. It supplements, but does not replace, the materials requirements of the appropriate design codes, standards or regulations.

<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-212222222222/iso-15156-3-2009>

This part of ISO 15156 addresses the resistance of these materials to damage that can be caused by sulfide stress-cracking (SSC), stress-corrosion cracking (SCC) and galvanically-induced hydrogen stress cracking (GHSC).

This part of ISO 15156 is concerned only with cracking. Loss of material by general (mass loss) or localized corrosion is not addressed.

Table 1 provides a non-exhaustive list of equipment to which this part of ISO 15156 is applicable, including permitted exclusions.

This part of ISO 15156 applies to the qualification and selection of materials for equipment designed and constructed using conventional elastic design criteria. For designs utilizing plastic criteria (e.g. strain-based and limit-state designs), see ISO 15156-1:2009, Clause 5.

This part of ISO 15156 is not necessarily suitable for application to equipment used in refining or downstream processes and equipment.

## ISO 15156-3:2009(E)

Table 1 — List of equipment

ISO 15156 is applicable to materials used for the following equipment	Permitted exclusions
Drilling, well construction and well-servicing equipment	Equipment exposed only to drilling fluids of controlled composition <sup>a</sup> Drill bits Blowout-preventer (BOP) shear blades <sup>b</sup> Drilling riser systems Work strings Wireline and wireline equipment <sup>c</sup> Surface and intermediate casing
Wells, including subsurface equipment, gas lift equipment, wellheads and christmas trees	Sucker rod pumps and sucker rods <sup>d</sup> Electric submersible pumps Other artificial lift equipment Slips
Flow-lines, gathering lines, field facilities and field processing plants	Crude oil storage and handling facilities operating at a total absolute pressure below 0,45 MPa (65 psi)
Water-handling equipment	Water-handling facilities operating at a total absolute pressure below 0,45 MPa (65 psi) Water injection and water disposal equipment
Natural gas treatment plants	—
Transportation pipelines for liquids, gases and multiphase fluids	Lines handling gas prepared for general commercial and domestic use
For all equipment above	Components loaded only in compression
<sup>a</sup> See ISO 15156-2:2009, A.2.3.2.3 for more information. <sup>b</sup> See ISO 15156-2:2009, A.2.3.2.1 for more information. <sup>c</sup> Wireline lubricators and lubricator connecting devices are not permitted exclusions. <sup>d</sup> For sucker rod pumps and sucker rods, reference can be made to NACE MR0176.	

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Test method (scales A, B, C, D, E, F, G, H, K, N, T)*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7539-7, *Corrosion of metals and alloys — Stress corrosion testing — Part 7: Method for slow strain rate testing*

ISO 10423, *Petroleum and natural gas industries — Drilling and production equipment — Wellhead and christmas tree equipment*

ISO 11960, *Petroleum and natural gas industries — Steel pipes for use as casing or tubing for wells*

ISO 15156-1:2009, *Petroleum and natural gas industries — Materials for use in H<sub>2</sub>S-containing environments in oil and gas production — Part 1: General principles for selection of cracking-resistant materials*

ISO 15156-2:2009, *Petroleum and natural gas industries — Materials for use in H<sub>2</sub>S-containing environments in oil and gas production — Part 2: Cracking-resistant carbon and low alloy steels, and the use of cast irons*

ASTM A747/A747M <sup>1)</sup>, *Standard Specification for Steel Castings, Stainless, Precipitation Hardening*

ASTM E562, *Standard Test Method for Determining Volume Fraction by Systematic Manual Point Count*

EFC Publications Number 17 <sup>2)</sup>, *Corrosion resistant alloys for oil and gas production: guidelines on general requirements and test methods for H<sub>2</sub>S service*

NACE CORROSION/95 <sup>3)</sup>, Paper 47, (Houston), 1995, Test methodology for elemental sulfur-resistant advanced materials for oil and gas field equipment, by G. STEINBECK, W. BRUCKHOFF, M. KÖHLER, H. SCHLERKMANN, G. SCHMITT

NACE CORROSION/97 Paper 58, *Rippled strain rate test for CRA sour service materials selection*, (Houston), 1997

NACE TM0177-96, *Laboratory testing of metals for resistance to sulfide stress cracking and stress corrosion cracking in H<sub>2</sub>S environments*

NACE TM0198, *Slow strain rate test method for screening corrosion resistant alloys (CRAs) for stress corrosion cracking in sour oilfield service*

SAE <sup>4)</sup> — ASTM, *Metals and alloys in the Unified Numbering System*, ISBN 0-7680-04074

SAE AMS2430P, *Shot Peening, Automatic*  
<https://standards.iteh.ai/catalog/standards/sist/638af30a-01e1-460f-87b7-12352acbc0d9/sist-en-iso-15156-3-2010>

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 15156-1 and ISO 15156-2 and the following apply.

#### 3.1 ageing

change in metallurgical properties that generally occurs slowly at room temperature (natural ageing) and more rapidly at higher temperature (artificial ageing)

#### 3.2 anneal

heat to and hold at a temperature appropriate for the specific material and then cool at a suitable rate, for such purposes as reducing hardness, improving machineability, or obtaining desired properties

1) ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, USA.

2) European Federation for Corrosion, available from The Institute of Materials, 1 Carlton House Terrace, London SW1Y 5DB, UK [ISBN 0-901716-95-2].

3) NACE International, P.O. Box 2183140, Houston, TX 77218-8340, USA.

4) Society of Automotive Engineers (SAE), 400 Commonwealth Drive, Warrendale, PA 15096-0001, USA.