



Designation: E 514 – 04

Standard Test Method for Water Penetration and Leakage Through Masonry¹

This standard is issued under the fixed designation E 514; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This laboratory test method² provides a procedure for determining the resistance to water penetration and leakage through unit masonry subjected to wind-driven rain.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement see Section 5.

2. Referenced Documents

- 2.1 *American Concrete Institute Standard:*³
ACI 530/ASCE 5/TMS 402 Building Code Requirements for Masonry Structures
ACI 530.1/ASCE 6/TMS 602 Specifications for Masonry Structures

3. Significance and Use

3.1 This test method provides information that aids in evaluating the effect of four principal variables: materials, coatings, wall design, and workmanship.

3.2 Water penetration and leakage through masonry is significantly affected by air pressure in the test chamber. Data from tests made at different pressures are not comparable.

3.3 The performance of a masonry wall is a function of materials, construction, wall design, and maintenance. In service the performance will also depend on the rigidity of supporting structure and on the resistance of components to deterioration by various causes, such as corrosion, vibration, thermal expansion and contraction, curing, and others. It is

impossible to simulate the complex conditions encountered in service, such as variations in wind velocity, negative pressure, and lateral or upward moving air and water. Factors such as location, exposure, and wall openings should be considered.

3.4 Given the complexity of variables noted above, this test method establishes comparative behavior between various masonry wall constructions in a given laboratory.

3.5 Even when a single laboratory tests the same wall design utilizing the same wall materials and the same construction practices, variables such as the level of skill of the mason building the specimen, the temperature and humidity in the laboratory at the time of construction, curing of the specimen, the moisture contents of the materials used to build the specimen, and even the use or lack of use of a lime and water wash on the back of the specimen can affect the results of the test making reliable comparisons dubious. For these reasons and the multi-variables listed in 3.1, 3.2, and 3.3, a meaningful, useful, absolute wall leakage rating standard is impractical and discouraged.

4. Apparatus

4.1 *Test Chamber*—Use a test chamber similar to that shown in Fig. 1 and Fig. 2. Provide an opening with a minimum area of 1.08 m² (12 ft²). For example, 900 mm (36 in.) wide and 1200 mm (48 in.) high is suitable. Line the edges of the chamber in contact with the specimen with a closed-cell compressible gasket material or appropriate sealant. Provide an observation port in the face of the chamber. Provide a 19.0-mm ($\frac{3}{4}$ -in.) diameter corrosion-resistant spray pipe with a single line of 1.0-mm (0.04-in.) diameter holes spaced 25.0 mm (1 in.) apart.

4.2 *Fixtures and Appurtenances to Chamber*—Fixtures and appurtenances to the chamber shall include an air line with manometer, a water line with valves, a flow meter and manometer and a water drain pipe at the bottom of the chamber. Position the water spray pipe so that the water impinges the specimen not more than 75.0 mm (3.00 in.) below the top of the test chamber.

NOTE 1—A drain pipe that discharges into a reservoir equipped with an adjustable depth air outlet pipe and top baffles has been found to reduce surge.

¹ This test method is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.04 on Research.

Current edition approved January 1, 2004. Published February 2004. Originally approved in 1974. Last previous edition approved in 2003 as E 514 – 03.

² This test method is based upon those used by the National Bureau of Standards and described in *NBS Report BMS7*, "Water Permeability of Masonry Walls," 1933, and *NBS Report BMS82*, "Water Permeability of Walls Built of Masonry Units," 1942.

³ Published by The Masonry Society, www.masonrysociety.org; American Concrete Institute, www.aci-int.org; and American Society of Civil Engineers, www.asce.org.

*A Summary of Changes section appears at the end of this standard.




FIG. 1 Isometric Projection of Testing Chamber

4.3 *Manometer*—Measure the air pressure in the chamber using a manometer or other device capable of measuring air pressures of at least 51 mm (2.0 in.) of water (71.7 kPa) (10.4 psf) to an accuracy of 2.5 mm (0.1 in.) or 3.6 kPa (0.52 psf). Connect the manometer or other device to the chamber away from the air inlet so that the air flow will not significantly influence the pressure reading.

4.4 Other equipment includes devices for handling the specimen and measuring time, water quantities, temperature, and humidity.

5. Hazards

5.1 The use of this test method will require careful design consideration of both air chamber and support of the wall system to avoid possible injury due to equipment or specimen failure.

6. Temperature and Humidity Conditions

6.1 Maintain the air in the laboratory at a temperature of $24 \pm 8^\circ\text{C}$ ($75 \pm 15^\circ\text{F}$) and a relative humidity of $55\% \pm 25\%$.

7. Test Specimens

7.1 *Masonry Materials*—Masonry and associated materials shall be representative of the construction or the materials that are being considered for the construction. Precondition all materials to a stable condition by storing in laboratory environment for not less than 5 days before use.

7.2 *Size of Test Walls*—The height and length of the specimen shall provide a minimum of 1.08 m^2 (12 ft^2) exposed

to the test, plus at least a 200-mm (8-in.) overlap on all edges. The minimum height or length of the specimen shall be 1.22 m (4 ft). The length of the specimen shall be such that at least one head joint in each course of masonry is exposed to the test.

7.3 *Building Wall Specimens*—Methods and workmanship used in the construction of the specimen shall be representative of the construction (Note 2). Build the wall specimen on an inverted steel channel section so that the face of the wall to be exposed to test is flush with the outside face of one flange of the channel. As shown in Fig. 3 attach to, or build flashing into masonry forming a trough to collect water that may pass through to the back side of the wall.

NOTE 2—Standards for masonry construction are contained in the following documents: ACI Standard 530/ASCE 5/TMS 402 Building Code Requirements for Masonry Structures and ACI 530.1/ASCE 6/TMS 602 Specifications for Masonry Structures.

7.4 *Number of Specimens*—The test shall consist of at least 3 specimens.

7.5 *Storage of Specimens*—Specimens shall be retained in the laboratory during storage and shall be enclosed in an impervious plastic wrap immediately after construction and cured in this manner for 7 days. After 7 days, the wrap shall be removed and aging shall continue for at least 7 more days in laboratory air as stated in 6.1.

8. Procedure

8.1 *Mounting Chamber*—Position the test chamber on the specimen and clamp firmly in place, compressing the gasket to form a seal.