

SLOVENSKI STANDARD SIST-TS CEN/TS 14464:2010

01-december-2010

Nadomešča: SIST ENV 14464:2003

Žagani les - Metoda ocenjevanja zaskorjenosti

Sawn timber - Method for assessment of case-hardening

Schnittholz - Verfahren zur Ermittlung der Verschalung

iTeh STANDARD PREVIEW Bois sciés - Méthode de mesure de la cémentation (standards.iteh.ai)

Ta slovenski standard je istovet<u>en z:rs CENCEN/TS:144</u>64:2010 https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0-

<u>ICS:</u>

79.040 Les, hlodovina in žagan les W

Wood, sawlogs and sawn timber

SIST-TS CEN/TS 14464:2010

en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 14464:2010 https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0f3c94ec5265a/sist-ts-cen-ts-14464-2010

SIST-TS CEN/TS 14464:2010

TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN/TS 14464

July 2010

ICS 79.040

Supersedes ENV 14464:2002

English Version

Sawn timber - Method for assessment of case-hardening

Bois sciés - Méthode de mesure de la cémentation

Schnittholz - Verfahren zur Ermittlung der Verschalung

This Technical Specification (CEN/TS) was approved by CEN on 15 May 2010 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom, H

(standards.iteh.ai)

<u>SIST-TS CEN/TS 14464:2010</u> https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0f3c94ec5265a/sist-ts-cen-ts-14464-2010



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2010 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. CEN/TS 14464:2010: E

SIST-TS CEN/TS 14464:2010

CEN/TS 14464:2010 (E)

Contents

Forew	ord	.3
1	Scope	.4
2	Normative references	.4
3	Terms and definitions	.4
4 4.1 4.2 4 3	Slicing test method Apparatus Procedure Calculation and expression of results	.5 .5 .5

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 14464:2010 https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0f3c94ec5265a/sist-ts-cen-ts-14464-2010

Foreword

This document (CEN/TS 14464:2010) has been prepared by Technical Committee CEN/TC 175 "Round and sawn timber", the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes ENV 14464:2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TS CEN/TS 14464:2010 https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0f3c94ec5265a/sist-ts-cen-ts-14464-2010

1 Scope

This Technical Specification defines a destructive method of assessing the case-hardening of a piece of sawn timber with reference to the distortion measured in a slice taken from the piece.

This Technical Specification is applicable to sawn timber and timber which has been planed or surfaced by other means. It applies to both hardwood and softwood with a thickness not greater than 100 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 844-1:1995, Round and sawn timber — Terminology — Part 1: General terms common to round timber and sawn timber

EN 844-2:1997, Round and sawn timber — Terminology — Part 2: General terms relating to round timber

EN 844-3:1995, Round and sawn timber — Terminology — Part 3: General terms relating to sawn timber

EN 844-4:1997, Round and sawn timber — Terminology — Part 4: Terms relating to moisture content

EN 844-5:1997, Round and sawn timber — Terminology — Part 5: Terms relating to dimensions of round timber (standards.iteh.ai)

EN 844-6:1997, Round and sawn timber — Terminology — Part 6: Terms relating to dimensions of sawn timber <u>SIST-TS CEN/TS 14464:2010</u> https://standards.iteh.ai/catalog/standards/sist/81983382-51e7-4547-a2b0-

EN 844-7:1997, Round and sawn timber ^{13c9} Terminology^{15-co}Part¹7.4</sup> Terms⁰ relating to anatomical structure of timber

EN 844-8:1997, Round and sawn timber — Terminology — Part 8: Terms relating to features of round timber

EN 844-9:1997, Round and sawn timber — Terminology — Part 9: Terms relating to features of sawn timber

EN 844-10:1998, Round and sawn timber — Terminology — Part 10: Terms relating to stain and fungal attack

EN 844-11:1998, Round and sawn timber — Terminology — Part 11: Terms relating to degrade by insects

EN 844-12:2000, Round and sawn timber — Terminology — Part 12: Additional terms and general index

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 844-1:1995, EN 844-2:1997, EN 844-3:1995, EN 844-4:1997, EN 844-5:1997, EN 844-6:1997, EN 844-7:1997, EN 844-8:1997, EN 844-10:1998, EN 844-11:1998, EN 844-12:2000 and the following apply.

3.1

conditioning

additional treatment after a drying process, during which the possible case-hardening is reduced by re-wetting the surface layers of the timber by means of elevated relative humidity and temperature

CEN/TS 14464:2010 (E)

4 Slicing test method

4.1 Apparatus

- 4.1.1 Calibrated measuring device, graduated in at least 0,1 mm steps.
- **4.1.2** Jig, as shown in Figure 1.

Dimensions in millimetres



4.1.3 Slicing device.

Band saw or circular saw to cut a cross section from a piece of sawn timber.

Sharp knife or saw to divide the test slice into two equal parts.

4.2 Procedure

Saw a test slice, full cross section with 15 mm length taken in the direction of the grain at least 30 cm from either end of the piece of timber or at mid-point of pieces less than 600 mm long, according to Figure 2.

Dimensions in millimetres



Figure 2 — Preparation of test slice

The test slice shall be clean and free from features such as bark, knots, resin pockets and reaction wood. Resin wood shall be avoided. If defects exist, cut the test slice from the nearest defect free area towards the centre of the piece of timber. **iTeh STANDARD PREVIEW**

Divide the test slice into two equal parts parallel to the face of the piece of sawn timber from which the test slice has been taken. Mark the two parts, as shown in Figure 3, in such a way that the two parts can be placed on top of each other again in its original position.





Place the two parts of the test slice in a plastic bag and seal it. Keep at room temperature for 24 h for softwood test slices, 48 h for hardwood test slices in order to equalise the moisture gradient. At the end of this period remove the two parts from the bag and place them centred on the test jig, as shown in Figure 4.