



# Standard Test Method for Contact Compatibility Between Asphaltic Materials (Oliensis Test)<sup>1</sup>

This standard is issued under the fixed designation D 1370; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method provides a means for evaluating contact compatibility between asphaltic materials. It is generally used to determine compatibility between the saturant and coating used in the manufacture of prepared roofings.<sup>2</sup> Coating and saturant will be referred to, but comparable asphaltic materials may be tested where this test procedure seems applicable.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

E 11 Specification for Wire-Cloth Sieves for Testing Purposes<sup>3</sup>

## 3. Summary of Test Method

3.1 A small drop of molten saturant is placed on the freshly talced surface of the coating, and compatibility is judged by the degree to which an oily ring develops in the talc surrounding the drop.<sup>2</sup>

## 4. Significance and Use

4.1 This test method assesses the degree to which asphalts interact with one another. It can indicate possible future problems, especially blistering, in a roofing product if incompatible asphalts are in contact in the product.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.02 on Prepared Roofings, Shingles, and Siding Materials.

Current edition approved Jan. 10, 2000. Published March 2000. Originally published as D 1370-84. Last previous edition D 1370-84(99) $\epsilon$ <sup>1</sup>.

<sup>2</sup> This test determines only exudative incompatibility. For application of this procedure to determination of insudative incompatibility, see "Compatibility Between Bitumens—Exudation versus Insudation," by Oliensis, G. L., *Materials Research and Standards*, Vol 1, No. 9, September 1961, p. 723.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 14.02.

## 5. Apparatus

5.1 *Container*, lid of 85-g (3-oz) ointment box, or equivalent container.

5.2 *Analytical Balance*, having an accuracy of  $\pm 1.0$  mg.

5.3 *Sieve* 45- $\mu$ m (No. 325). Detailed requirements for these sieves are given in Specification E 11.

5.4 *Dropping Device*, a fine wire 1.0 mm (0.04 in.) in diameter.

5.5 *Oven*, constant-temperature, capable of maintaining the test temperature within  $\pm 1.0^\circ\text{C}$  ( $\pm 1.8^\circ\text{F}$ ).

5.6 *Small Scale*, graduated in 0.1 mm divisions.

5.7 *Magnifying Glass or Stereo Microscope*, approximate minimum of 4 $\times$ .

5.8 *Talc*, pure, of the soapstone variety, ground so that at least 70 % passes the 45- $\mu$ m (No. 325) sieve, and oven-dried at 110°C (230°F).

NOTE 1—When this test method is being used in purchase specifications, both the purchaser and the seller shall use the same talc. Talc from Luzenac America, Inc.<sup>4</sup> has been found to be suitable for this test.

## 6. Procedure

6.1 Melt a portion of the coating at the minimum temperature required to render it fluid, stirring with the fine wire to eliminate bubbles, and pour it into the clean 85-g (3 oz) tin lid to a thickness of 3.0 to 6.0 mm ( $\frac{1}{8}$  to  $\frac{1}{4}$  in.). Pour carefully, so as to provide a substantially smooth surface free of bubbles and other surface blemishes. After the coating material has cooled, determine the weight and surface area of the filled container.

6.2 Make a preliminary dusting of talc by covering the coating surface with talc and removing the excess, nonadherent dust by inverting the container and dropping it approximately 25 mm (1 in.) onto the table top.

6.3 Make a final application of talc through the 45- $\mu$ m (No. 325) sieve, held 20 to 25 mm ( $\frac{3}{4}$  to 1 in.) above the surface of the coating, by gently shaking or tapping the sieve until a smooth, uniform film of talc, weighing 0.004 g  $\pm$  10 % per square centimetre, has been applied.

6.4 Place 3 drops of molten saturant, each about 3.0  $\pm$  0.5 mm ( $\frac{1}{8}$   $\pm$   $\frac{1}{64}$  in.) in diameter, on the talced surface of the

<sup>4</sup> The sole source of supply known to the committee at this time is the Luzenac America, Inc., 9000 East Nichols Avenue, Englewood, CO, 80112. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.