



Designation: A 414/A 414M – 04

Standard Specification for Steel, Sheet, Carbon, for Pressure Vessels¹

This standard is issued under the fixed designation A 414/A 414M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification² covers hot-rolled carbon steel sheet for pressure vessels involving fusion welding or brazing. Welding and brazing technique is of fundamental importance and shall be in accordance with commercial practices.

1.2 The following grades are included in this specification:

Mechanical Requirements

Grade	Yield Strength, min		Tensile Strength, min	
	ksi	MPa	ksi	MPa
A	25	170	45	310
B	30	205	50	345
C	33	230	55	380
D	35	240	60	415
E	38	260	65	450
F	42	290	70	485
G	45	310	75	515

1.3 Hot-rolled carbon steel sheet is generally furnished in cut lengths and to decimal thickness only. Coils may be furnished, provided tension test specimens are taken to represent the middle of the slab as required by 5.1.4. The purchaser should recognize this requires cutting the coils to obtain test samples and results in half-size coils. The sheet is furnished to the following size limits:

Thickness, in. [mm]	Width, in. [mm]	
	Over 12 to 48 [Over 300 to 1200]	Over 48 [Over 1200]
0.270 to 0.230 [7.0 to 6.0]	sheet (coils only)	sheet (coils only)
Under 0.230 to 0.180 [6.0 to 4.5]	sheet	sheet (coils only)
Under 0.180 to 0.057 [under 4.5 to 1.5]	sheet	sheet

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall

be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.5 Tolerances are found in General Requirements Specifications A 568/A 568M and A 635/A 635M. The appropriate General Requirements specification is applied based on the thickness and width of the product ordered.

2. Referenced Documents

2.1 *ASTM Standards:*³

A 568/A 568M Specification for Steel, Sheet, Carbon, and High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, General Requirements for

A 635/A 635M Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Carbon, Hot Rolled

3. Ordering Information

3.1 Orders for material under this specification shall include the following information, as required, to describe the material adequately:

3.1.1 Designation or specification number, date of issue, and grade,

3.1.2 Copper bearing steel, when required,

3.1.3 Special requirements, if required,

3.1.4 Condition—pickled (or blast cleaned), if required. (Material so ordered will be oiled unless ordered dry.), and

3.1.5 Dimensions, including type of edges.

3.1.5.1 As agreed upon between the purchaser and the producer, material ordered to this specification will be supplied to meet the appropriate standard or restricted thickness tolerance table shown in Specification A 568/A 568M.

NOTE 1—Not all producers are capable of meeting all of the limitations of the thickness tolerance tables in Specification A 568/A 568M. The purchaser should contact the producer regarding possible limitations prior to placing an order.

3.1.6 Cast or heat analysis, or test report request, or both, if required.

NOTE 2—A typical ordering description is as follows: “ASTM A 414,

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved March 1, 2004. Published March 2004. Originally approved in 1971. Last previous edition approved in 2001 as A 414/A 414M – 01.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-414 in Section 11 of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.