



# SLOVENSKI STANDARD

## oSIST prEN 12201-1:2010

01-marec-2010

---

### Cevni sistemi iz polimernih materialov za oskrbo z vodo in za odvodnjavanje in kanalizacijo pod tlakom - Polietilen (PE) - 1. del: Splošno

Plastics piping systems for water supply, and for drainage and sewerage under pressure - Polyethylene (PE) - Part 1: General

Kunststoff-Rohrleitungssysteme für die Wasserversorgung und für Entwässerungs- und Abwasserdruckleitungen - Polyethylen (PE) - Teil 1: Allgemeines

<https://standards.iteh.ai>  
Document Preview

Ta slovenski standard je istoveten z: prEN 12201-1

SIST EN 12201-1:2011

<https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011>

#### **ICS:**

23.040.20	Cevi iz polimernih materialov	Plastics pipes
91.140.60	Sistemi za oskrbo z vodo	Water supply systems
93.030	Zunanji sistemi za odpadno vodo	External sewage systems

oSIST prEN 12201-1:2010

en,fr,de



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 12201-1**

January 2010

ICS 23.040.01

Will supersede EN 12201-1:2003, EN 13244-1:2002

English Version

## Plastics piping systems for water supply, and for drainage and sewerage under pressure - Polyethylene (PE) - Part 1: General

Kunststoff-Rohrleitungssysteme für die Wasserversorgung  
und für Entwässerungs- und Abwasserdruckleitungen -  
Polyethylen (PE) - Teil 1: Allgemeines

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 155.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.

[SIST EN 12201-1:2011](https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## prEN 12201-1:2010 (E)

**Contents**

<b>Foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions, symbols and abbreviations</b> .....	<b>6</b>
3.1 Terms and definitions.....	7
3.1.1 Geometrical characteristics.....	7
3.1.2 Material definitions .....	9
3.1.3 Definitions related to material characteristics .....	9
3.2 Symbols .....	10
3.3 Abbreviations .....	11
<b>4 Compound</b> .....	<b>11</b>
4.1 Additives.....	11
4.2 Colour.....	12
4.2.1 General .....	12
4.3 Characteristics .....	12
4.3.1 Characteristics of the compound in the form of granules .....	12
4.3.2 Characteristics of the compound in the form of pipe .....	13
4.4 Fusion compatibility for PE 80 and PE 100 materials.....	15
4.5 Classification and designation .....	16
<b>5 Effect on water quality</b> .....	<b>17</b>
<b>Annex A normative Pressure reduction coefficients</b> .....	<b>18</b>
<b>Bibliography</b> .....	<b>19</b>

SIST EN 12201-1:2011

<https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011>

## Foreword

This document (prEN 12201-1:2010) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 12201-1:2003, EN 13244-1:2002.

System Standards are based on the results of the work being undertaken in ISO/TC 138 "*Plastics pipes, fittings and valves for the transport of fluids*", which is a Technical Committee of the International Organization for Standardization (ISO).

EN 12201 consists of the following Parts, under the general title *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE)*:

- *Part 1: General* (this standard).
- *Part 2: Pipes*.
- *Part 3: Fittings*.
- *Part 4: Valves*.
- *Part 5: Fitness for purpose of the system*.
- *Part 7: Guidance for the assessment of conformity* (CEN/TR).

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

[SIST EN 12201-1:2011](https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011>

**prEN 12201-1:2010 (E)****Introduction**

The System Standard, of which this is Part 1, specifies the requirements for a piping system and its components when made from polyethylene (PE). The piping system is intended to be used for water supply intended for human consumption, including the conveyance of raw water prior to treatment, drainage and sewerage under pressure, vacuum sewer systems, and water for other purposes.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the products covered by EN 12201:

- a) this standard provides no information as to whether the products may be used without restriction in any of the Member States of the EU or EFTA;
- b) products intended for use in water supply systems must comply, when existing, with national regulations and testing arrangements that ensure fitness for contact with drinking water.

**NOTE** On April 2006, EC Commission set up a revised mandate (M/136) asking CEN to propose harmonised product standards and support standards for test methods which could be used for assessing the fitness for contact with drinking water. In parallel, EC Commission has launched processes for a regulation of construction products (CPR) to be substituted to CP directive (89/106/EC) and for the revision of drinking water directive (98/83/EC). If relevant, when the outputs of these processes will be known, European Product Standards will be amended by the addition of an Annex Z under Mandate M136 which will contain formal references to the applicable requirements. Until such amendments, the current national regulations remain applicable.

Requirements and test methods for components of the piping system are specified in prEN 12201-2:2010, prEN 12201-3:2010 and prEN 12201-4:2009.

Characteristics for fitness for purpose are covered in prEN 12201-5:2010. CEN/TR 12201-7 [5] gives guidance for the assessment of conformity.

This Part of EN 12201 covers the general aspects of the plastics piping system.

[SIST EN 12201-1:2011](https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/dc49024e-5f65-49fd-b6e9-05a18e28b438/sist-en-12201-1-2011>

## 1 Scope

This Part of EN 12201 specifies the general aspects of polyethylene (PE) pressure piping systems (mains and service pipes) for buried or above ground applications, intended for the conveyance of water for human consumption, including raw water prior to treatment, drainage and sewerage under pressure, vacuum sewer systems, and water for other purposes

NOTE 1 For PE components intended for the conveyance of water intended for human consumption and raw water prior to treatment attention is drawn to clause 5 of this part of EN 12201. Components manufactured for water for other purposes, drainage and sewerage may not be suitable for water supply for human consumption.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with Parts 2 to 5 of EN 12201, it is applicable to PE pipes, fittings, valves, their joints and to joints with components of other materials intended to be used under the following conditions:

- a) allowable operating pressure, PFA, up to 25 bar <sup>1)</sup>;
- b) an operating temperature of 20 °C as a reference temperature;
- c) buried in the ground;
- d) sea outfalls;
- e) laid in water;
- f) above ground, including pipes suspended below bridges.

NOTE 2 For applications operating at constant temperatures greater than 20 °C and up to 40 °C, see Annex A.

EN 12201 covers a range of allowable operating pressures and gives requirements concerning colours and additives.

NOTE 3 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national guidance or regulations and installation practices or codes.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12099, *Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content*

prEN 12201-2:2010, *Plastics piping systems for water supply — Polyethylene (PE) — Part 2: Pipes*

EN ISO 472:2001, *Plastics — Vocabulary (ISO 472:1999)*

EN ISO 1043-1:2001, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1:2001)*

EN ISO 1133:2005, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133:2005)*

EN ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*

<sup>1)</sup> 1 bar = 0,1 MPa = 10<sup>5</sup> Pa; 1 MPa = 1 N/mm<sup>2</sup>

**prEN 12201-1:2010 (E)**

EN ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces (ISO 1167-2:2006)*

EN ISO 1183-1:2004, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1:2004)*

EN ISO 1183-2:2004, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2:2004)*

EN ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method (ISO 6259-1:1997)*

prEN ISO 9080:2009, *Thermoplastics pipes for the transport of fluids — Methods of extrapolation of hydrostatic stress rupture data to determine the long-term hydrostatic strength of thermoplastics pipe materials. (ISO/DIS 9080:2008)*

prEN ISO 12162:2008, *Thermoplastics materials for pipes and fittings for pressure applications — Classification and designation — Overall service (design) coefficient (ISO/DIS 12162: 2008).*

EN ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test) (ISO 13477:2008)*

EN ISO 13478, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full-scale test (FST) (ISO 13478:2008)*

prEN ISO 13479:2009, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes (notch test) (ISO/FDIS 13479:2009)*

EN ISO 15512:2003, *Plastics — Determination of water content*

EN ISO 16871, *Plastics piping and ducting systems — Plastics pipes and fittings — Method for exposure to direct (natural) weathering (ISO 16871:2003)*

ISO 6259-3:1997, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes*

ISO 6964:1986, *Polyolefin pipes and fittings — Determination of carbon black content by calcination and pyrolysis — Test method and basic specification*

ISO 11357-6:2008, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

ISO 11413:2008, *Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting*

ISO 11414:2009, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion*

ISO 13953:2001, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 13954:1997, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*

ISO 18553:2002, *Method for the assessment of the degree of pigment or carbon black dispersion in polyolefin pipes, fittings and compounds*

### **3 Terms and definitions, symbols and abbreviations**

For the purposes of this European Standard, the following terms and definitions, symbols and abbreviations apply.



### 3.1 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN ISO 472:2001, and EN ISO 1043-1:2001 apply in addition to the following.

#### 3.1.1 Geometrical characteristics

##### 3.1.1.1

##### **nominal size**

DN/OD

numerical designation of the size of a component, other than a component designated by a thread size, which is a convenient round number, approximately equal to the manufacturing dimension in millimetres (mm) and related to the outside diameter.

##### 3.1.1.2

##### **nominal outside diameter**

$d_n$

specified outside diameter, in millimetres, assigned to a nominal size DN/OD

##### 3.1.1.3

##### **outside diameter at any point**

$d_e$

value of the measurement of the outside diameter through its cross-section at any point of the pipe or spigot end, rounded to the next greater 0,1 mm

##### 3.1.1.4

##### **mean outside diameter**

$d_{em}$

value of the measurement of the outer circumference of the pipe or spigot end of a fitting in any cross section divided by  $\pi$  (= 3,142), rounded to the next greater 0,1 mm

##### 3.1.1.5

##### **minimum mean outside diameter**

$d_{em,min}$

minimum value of the outside diameter as specified for a given nominal size

##### 3.1.1.6

##### **maximum mean outside diameter**

$d_{em,max}$

maximum value of the outside diameter as specified for a given nominal size

##### 3.1.1.7

##### **out-of-roundness**

ovality

difference between the maximum outside diameter and the minimum outside diameter in the same cross-section of the pipe or spigot

##### 3.1.1.8

##### **nominal wall thickness**

$e_n$

numerical designation of the wall thickness of a component, which is a convenient round number, approximately equal to the manufacturing dimension in millimetres

NOTE For thermoplastics components conforming to the different parts of EN 12201, the value of the nominal wall thickness,  $e_n$ , is identical to the specified minimum wall thickness at any point,  $e_{min}$ .

**prEN 12201-1:2010 (E)****3.1.1.9****wall thickness at any point** $e$ 

wall thickness at any point around the circumference of a component rounded to the next greater 0,05 mm

NOTE The symbol for the wall thickness of the fittings and valves body at any point is  $E$ .

**3.1.1.10****minimum wall thickness at any point** $e_{\min}$ 

minimum value of the wall thickness at any point around the circumference of a component as specified

**3.1.1.11****maximum wall thickness at any point** $e_{\max}$ 

maximum value of the wall thickness at any point around the circumference of a component as specified

**3.1.1.12****mean wall thickness** $e_m$ 

arithmetic mean of a number of measurements of the wall thickness, regularly spaced around the circumference and in the same cross-section of a component, including the measured minimum and the measured maximum values of the wall thickness in that cross-section

**3.1.1.13****tolerance**

permitted variation of the specified value of a quantity expressed as the difference between the permissible maximum and permitted minimum values

**3.1.1.14****wall thickness tolerance** $t_y$ 

permitted difference between the wall thickness at any point,  $e$ , and the nominal wall thickness,  $e_n$

NOTE  $e_n \leq e \leq e_n + t_y$

**3.1.1.15****pipe series**

S

dimensionless number for pipe designation.

NOTE The relationship between the pipe series S and the standard dimension ratio SDR is given by the following equation as specified in ISO 4065:1996 [3].

$$S = \frac{\text{SDR} - 1}{2}$$

**3.1.1.16****standard dimension ratio**

SDR

numerical designation of a pipe series, which is a convenient round number, approximately equal to the dimension ratio of the nominal outside diameter,  $d_n$ , and the nominal wall thickness,  $e_n$