



**SLOVENSKI STANDARD**  
**oSIST prEN 10217-1:2009**  
**01-december-2009**

---

**Varjene jeklene cevi za tlačne posode - Tehnični dobavni pogoji - 1. del: Nelegirane jeklene cevi s specificiranimi lastnostmi za delo pri sobni temperaturi**

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 1: Non-alloy steel tubes with specified room temperature properties

Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen - Teil 1: Rohre aus unlegierten Stählen mit festgelegten Eigenschaften bei Raumtemperatur

Tubes soudés en acier pour service sous pression - Conditions techniques de livraison - Partie 1: Tubes en acier non allié avec caractéristiques spécifiées à température ambiante

**Ta slovenski standard je istoveten z: prEN 10217-1**

---

**ICS:**

23.020.30	Tlačne posode, plinske jeklenke	Pressure vessels, gas cylinders
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

**oSIST prEN 10217-1:2009**

**en,de**



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 10217-1**

October 2009

ICS 23.040.10; 77.140.75

Will supersede EN 10217-1:2002

English Version

## Welded steel tubes for pressure purposes - Technical delivery conditions - Part 1: Non-alloy steel tubes with specified room temperature properties

Tubes soudés en acier pour service sous pression -  
 Conditions techniques de livraison - Partie 1: Tubes en  
 acier non allié avec caractéristiques spécifiées à  
 température ambiante

Geschweißte Stahlrohre für Druckbeanspruchungen -  
 Technische Lieferbedingungen - Teil 1: Rohre aus  
 unlegierten Stählen mit festgelegten Eigenschaften bei  
 Raumtemperatur

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ECISS/TC 29.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Foreword .....	4
1 Scope .....	5
2 Normative references .....	6
3 Terms and definitions .....	7
4 Symbols .....	7
5 Classification and designation .....	7
6 Information to be supplied by the purchaser .....	8
7 Manufacturing process .....	9
8 Requirements .....	11
9 Inspection .....	21
10 Sampling .....	24
11 Test methods .....	27
12 Marking .....	30
13 Protection .....	31
Annex A (normative) .....	32
A.1 General .....	32
A.2 Welding procedure specification .....	32
A.2.1 Parent metal .....	32
A.2.2 Weld preparation .....	32
A.2.3 Filler wires and fluxes .....	32
A.2.4 Electrical parameters .....	32
A.2.5 Mechanical parameters .....	33
A.2.6 Heat input (kJ/mm) .....	33
A.2.7 Preheat temperature .....	33
A.2.8 Interpass temperature .....	33
A.2.9 Postweld heat treatment .....	33
A.2.10 Example of welding procedure specification form .....	33
A.3 Preparation of sample tube and sample .....	34
A.3.1 Sample tube .....	34
A.3.2 Sample .....	34
A.4 Inspection and testing of the weld .....	34
A.5 Weld test pieces .....	35
A.5.1 Bend test pieces .....	35
A.5.2 Macro-examination .....	35
A.5.3 Transverse tensile test .....	35
A.5.4 Impact test .....	35
A.6 Test methods .....	35
A.6.1 Visual examination .....	35
A.6.2 Radiographic test .....	35
A.6.3 Weld bend test .....	36
A.6.4 Macro-examination .....	36
A.6.5 Transverse weld tensile test .....	36
A.6.6 Weld impact test .....	36
A.7 Test acceptance levels .....	36
A.7.1 Visual examination .....	36
A.7.2 Radiographic test .....	36
A.7.3 Weld bend test .....	36
A.7.4 Macro-examination .....	36
A.7.5 Transverse weld tensile test .....	37
A.7.6 Weld impact test .....	37

A.7.7	Example of test result document .....	37
A.8	Range of use of qualified procedures .....	39
A.8.1	Materials Groups .....	39
A.8.2	Materials thickness.....	39
A.8.3	Filler wire classification .....	39
A.8.4	Welding flux .....	39
A.8.5	Other parameters.....	40
A.9	Qualification record.....	40
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of 97/23/EC .....		41
Bibliography .....		42

iTeh Standards  
 (https://standards.iteh.ai)  
 Document Preview

[SIST EN 10217-1:2019](https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019)

<https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019>

prEN 10217-1:2009 (E)

## Foreword

This document (prEN 10217-1:2009) has been prepared by Technical Committee ECISS/TC 29 “Steel tubes and fittings for steel tubes”, the secretariat of which is held by UNI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 10217-1:2002.

This European Standard consists of the following parts, under the general title *Welded steel tubes for pressure purposes – Technical delivery conditions*:

*Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties.*

*Part 3: Alloy fine grain steel tubes.*

*Part 4 : Electric welded non-alloy and alloy steel tubes with specified low temperature properties*

*Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties.*

*Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties.*

*Part 7: Stainless steel tubes.*

Another European Standard series covering tubes for pressure purposes is:

*EN 10216: Seamless steel tubes for pressure purposes.*

[SIST EN 10217-1:2019](https://standards.iteh.ai/)

<https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019>

## 1 Scope

This Part of EN 10217 specifies the technical delivery conditions for two qualities TR1 and TR2 of welded tubes of circular cross section, made of non-alloy quality steel and with specified room temperature properties.

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[SIST EN 10217-1:2019](https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019)

<https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019>

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 760, *Welding consumables - Fluxes for submerged arc welding – Classification*

EN 895, *Destructive tests on welds in metallic materials - Transverse tensile test*

EN 910, *Destructive tests on weld in metallic materials -Bend test*

EN 1321, *Destructive tests on welds in metallic materials - Macroscopic and microscopic examination of welds*

EN 10002-1, *Metallic materials - Tensile testing - Part 1 : Method of test (at ambient temperature)*

EN 10020, *Definitions and classification of grades of steel*

EN 10021, *General technical delivery requirements for steel and iron products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names.*

EN 10027-2, *Designation systems for steels Part 2 : Numerical systems.*

EN 10045-1, *Metallic materials - Charpy impact test - Part 1 : Test method*

EN 10052, *Vocabulary of heat treatment terms for ferrous products*

EN 10168, *Iron and steel products - Inspection documents - List of information and description*

EN 10204, *Metallic products - Types of inspection documents*

EN 10220, *Seamless and welded steel tubes - Dimensions and masses per unit length*

EN 10246-1, *Non-Destructive Testing of steel tubes Part 1 : Automatic electromagnetic testing of seamless and welded (except submerged arc welded) ferromagnetic steel tubes for verification of hydraulic leak-tightness*

EN 10246-3, *Non-Destructive Testing of steel tubes - Part 3 :Automatic eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections*

EN 10246-5, *Non-Destructive Testing of steel tubes – Part 5: Automatic full peripheral magnetic transducer/flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal imperfections*

EN 10246-7, *Non-Destructive Testing of steel tubes - Part 7 : Automatic full peripheral ultrasonic testing of seamless and welded (except submerged arc welded) steel tubes for the detection of longitudinal imperfections*

EN 10246-8, *Non-Destructive Testing of steel tubes – Part 8: Automatic ultrasonic testing of the weld seam of electric welded tubes for the detection of longitudinal imperfections*

EN 10246-9, *Non-Destructive Testing of steel tubes – Part 9: Automatic ultrasonic testing of the weld seam of submerged arc-welded steel tubes for the detection of longitudinal and/or transverse imperfections*

EN 10246-10, *Non-Destructive Testing of steel tubes – Part.10: Radiographic testing of the weld seam of automatic fusion arc-welded steel tubes for the detection of imperfections.*



EN 10256, *Non-Destructive Testing of steel tubes - Qualification and competence of level 1 and level 2 NDT personnel*

EN 10266, *Steel tubes, fittings and structural hollow sections - Symbols and definition of terms for use in product standards*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing*

EN ISO 2566-1, *Steel - Conversion of elongation values – Part 1: Carbon and low-alloy steels*

EN ISO 8492, *Metallic materials - Tubes - Flattening test*

EN ISO 8493, *Metallic materials - Tubes - Drift expanding test*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition*

CEN/TR 10261, *Iron and steel - Review of available methods of chemical analysis.*

### 3 Terms and definitions

For the purposes of this Part of EN 10217, the definitions given in EN 10020, EN 10021, EN 10052, EN 10266 and the following apply.

#### 3.1

##### **employer**

organisation for which a person works on a regular basis.

NOTE The employer may be either the tube manufacturer or a third party organisation providing Non-Destructive Testing (NDT) services.

#### 3.2

##### **qualification of welding procedure**

testing and inspection of the welding procedure for submerged arc welded (SAW) tubes by the manufacturer in accordance with annex A.

#### 3.3

##### **approval of welding procedure**

testing and inspection of the welding procedure for SAW tubes witnessed and approved in accordance with Annex A by an authorised body.

### 4 Symbols

For the purposes of this Part of EN 10217, the symbols given in prEN 10266 and the following apply:

- C1, C2 category conformity indicators (see clauses 7.3.1 and 7.3.3.)
- TC test category.

### 5 Classification and designation

#### 5.1 Classification

In accordance with the classification system in EN 10020, the steel grades are classified as non-alloy quality steels.

**prEN 10217-1:2009 (E)****5.2 Designation**

**5.2.1** For the tubes covered by this Part of EN 10217 the steel designation consists of:

a) the number of this Part of EN 10217;

plus either:

a) the steel name in accordance with EN 10027-1;

or:

a) the steel number allocated in accordance with EN 10027-2 .

**5.2.2** The steel name is designated by:

a) the capital letter P for pressure purposes;

b) the indication of the specified minimum yield strength for thickness less than or equal to 16 mm, expressed in MPa (see Table 4);

plus either:

a) the alphanumeric TR1 for qualities without specified aluminium content, impact properties and specific inspection and testing requirements (see 9.1);

or:

a) the alphanumeric TR2 for qualities with specified aluminium content, impact properties and specific inspection and testing requirements.

**6 Information to be supplied by the purchaser****6.1 Mandatory information**

[SIST EN 10217-1:2019](https://standards.sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019)

The following information shall be supplied by the purchaser at the time of enquiry and order :

a) the quantity (mass or total length or number);

b) the term 'tube';

c) the dimensions (outside diameter D and wall thickness T) (see Table 5).

d) the designation of the steel grade in accordance with this Part of EN 10217 (see 5.2);

**6.2 Options**

A number of options are specified in this Part of EN 10217 and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 6.1):

1) Tube manufacturing process and/or route (see 7.3.2).

2) Selection of the delivery condition (see 7.3.5).

3) Restriction on copper and tin content (see Table 2).

4) Product analysis (see 8.2.2).

- 5) Longitudinal impact testing at  $-10\text{ }^{\circ}\text{C}$  for quality TR2 (see Table 4).
- 6) Selection of leak-tightness test method (see 8.4.3.1).
- 7) Special end preparation (see 8.6).
- 8) Exact lengths (see 8.7.3).
- 9) Specific inspection for quality TR1 (see 9.1).
- 10) Type of inspection document other than the standard document (see 9.2.1).
- 11) Tensile test on the weld for tubes with  $219,1 < D \leq 508\text{ mm}$  (see Table 11).
- 12) Test unit restriction for tubes with  $D \leq 76,1\text{ mm}$  of quality TR2 (see 10.1.1).
- 13) Wall thickness measurement away from the ends (see 11.9).
- 14) Non-Destructive Testing method (see either 11.11.1 or 11.11.2).
- 15) Additional marking (see 12.2).
- 16) Protection (see 13).

### 6.3 Example of an order

100 t of welded steel tube with an outside diameter of 168,3 mm, a wall thickness of 4,5 mm in accordance with EN 10217-1, made of steel grade P235TR2 with a 3.1.C inspection certificate in accordance with EN 10204:

100 t – Tube – 168,3 × 4,5 – EN 10217-1 – P235TR2 – Option 10: 3.1

## 7 Manufacturing process

SIST EN 10217-1:2019

<https://standards.iteh.ai/catalog/standards/sist/a8341db7-4025-458b-9ed2-f6137481d75a/sist-en-10217-1-2019>

### 7.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer.

### 7.2 Deoxidation process

Steels shall be fully killed.

### 7.3 Tube manufacture and delivery conditions

**7.3.1** All NDT activities shall be carried out by qualified and competent level 1,2 and/or 3 personnel authorised to operate by the employer.

The qualification shall be in accordance with EN 10256 or, at least, an equivalent to it.

It is recommended that the level 3 personnel be certified in accordance with EN 473 or, at least, an equivalent to it.

The operating authorisation issued by the employer shall be in accordance with a written procedure.

NDT operations shall be authorised by a level 3 NDT individual approved by the employer.

NOTE The definition of level 1,2 and 3 can be found in appropriate Standards, e.g. EN 473 and EN 10256.

**prEN 10217-1:2009 (E)**

For pressure equipment in categories III and IV (of Directive 97/23-EC) the personnel shall be approved by a recognised third-party organisation. Tubes not conforming to this requirement shall be marked "C 2", unless a requirement to mark "C1" (see 7.3.3) applies

**7.3.2** The tubes shall be manufactured by the manufacturing processes and routes as specified in Table 1.

Unless Option 1 is specified the manufacturing process and route is at the discretion of the manufacturer.

**Option 1:** *The manufacturing process and/or route is specified by the purchaser.*

The submerged arc weld of SAW tubes shall be made using at least one weld run on the inside and one weld run on the outside of the tube.

The strip used for the manufacture of the helically submerged arc welded (SAWH) tubes shall have a width of not less than 0.8 times or more than 3.0 times the outside diameter of the tube.

The finished tubes shall not include welds used for joining together lengths of the hot or cold rolled strip or plate prior to forming except that for helically welded.

For helically welded submerged arc welded (SAWH) tubes, when the weld joining lengths of strip are part of the delivered tube, they shall have the welding procedure qualified in accordance with annex A and the weld shall be subjected to the same inspection and testing as the helical weld.

**7.3.3** Welding shall be carried out by suitably qualified personnel in accordance with suitable operating procedures.

For pressure equipment in categories II, III, and IV, (of Directive 97/23 EC) the operating procedures and the personnel shall be approved by a competent third-party. Tubes not conforming to this requirement shall be marked "C 1".

**7.3.4** The welding procedure for SAW tubes shall be qualified in accordance with Annex A.

**7.3.5** The delivery conditions of tubes covered by this Part of EN 10217 are shown in Table 1.

Unless Option 2 is specified at the time of enquiry and order the choice of the delivery condition is at the discretion of the manufacturer.

**Option 2:** *The delivery condition is chosen by the purchaser.*