
Preskušanje keramičnih surovin in osnovnih materialov - Ugotavljanje žvepla v praških in zrnih (granulah) neoksidativnih keramičnih surovin in osnovnih materialov - 2. del: Atomska emisijska spektrometrija z induktivno sklopljeno plazmo (AES ICP) ali ionska kromatografija (IC) po izpostavitvi ognju v pretoku kisika (ISO 14720-2:2013)

Testing of ceramic raw and basic materials - Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials - Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow (ISO 14720-2:2013)

Prüfung keramischer Roh- und Werkstoffe - Bestimmung des Schwefel-gehaltes in pulver- und kornförmigen nichtoxidischen keramischen Roh- und Werkstoffen - Teil 2: Atomemissionsspektroskopie mit induktiv gekoppeltem Plasma (ICP AES) oder Ionenchromatographie (IC) nach Verbrennung im Sauerstoffstrom (ISO 14720-2:2013)

Essais des matières premières et matériaux de base céramiques - Dosage du soufre dans des matières premières et matériaux de base céramiques non oxydiques sous forme de poudre et de granulés - Partie 2: Spectrométrie d'émission atomique avec plasma induit par haute fréquence (ICP/AES) ou chromatographie ionique après combustion dans un courant d'oxygène (ISO 14720-2:2013)

Ta slovenski standard je istoveten z: EN ISO 14720-2:2013

ICS:

81.060.10 Surovine Raw materials

SIST EN ISO 14720-2:2013

en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14720-2:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013>

EUROPEAN STANDARD

EN ISO 14720-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2013

ICS 81.060.10

English Version

Testing of ceramic raw and basic materials - Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials - Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow (ISO 14720-2:2013)

Essais des matières premières pour produits réfractaires - Dosage du soufre dans les matières premières non oxydantes sous forme de poudre et de granulés - Partie 2: Spectrométrie d'émission optique avec plasma induit par haute fréquence (ICP/OES) ou chromatographie ionique après combustion dans un courant d'oxygène (ISO 14720-2:2013)

Prüfung keramischer Roh- und Werkstoffe - Bestimmung des Schwefelgehaltes in pulver- und kornförmigen nichtoxidischen keramischen Roh- und Werkstoffen - Teil 2: Optische Emissionsspektrometrie mit induktiv gekoppeltem Plasma (ICP OES) oder Ionenchromatographie (IC) nach Verbrennung im Sauerstoffstrom (ISO 14720-2:2013)

iTeh STANDARD PREVIEW

This European Standard was approved by CEN on 16 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14720-2:2013](https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013)
<https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013>

Foreword

This document (EN ISO 14720-2:2013) has been prepared by Technical Committee ISO/TC 33 "Refractories" in collaboration with Technical Committee CEN/TC 187 "Refractory products and materials" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2013, and conflicting national standards shall be withdrawn at the latest by September 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of ISO 14720-2:2013 has been approved by CEN as EN ISO 14720-2:2013 without any modification.

[SIST EN ISO 14720-2:2013
https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013](https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14720-2:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013>

**INTERNATIONAL
STANDARD**

**ISO
14720-2**

First edition
2013-03-01

**Testing of ceramic raw and basic
materials — Determination of sulfur
in powders and granules of non-oxidic
ceramic raw and basic materials —**

Part 2:

**Inductively coupled plasma optical
emission spectrometry (ICP/OES) or
ion chromatography after burning in
an oxygen flow**

[https://standards.itih.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-](https://standards.itih.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-6890f6847431)

*Essais des matières premières pour produits réfractaires — Dosage
du soufre dans les matières premières non oxydantes sous forme de
poudre et de granulés —*

*Partie 2: Spectrométrie d'émission optique avec plasma induit par
haute fréquence (ICP/OES) ou chromatographie ionique après
combustion dans un courant d'oxygène*



Reference number
ISO 14720-2:2013(E)

© ISO 2013

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14720-2:2013](https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013)

<https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Interferences	2
5.1 ICP/OES.....	2
5.2 Ion chromatography.....	2
6 Apparatus	3
7 Reagents	3
8 Sampling and sample preparation	4
9 Preparation	4
9.1 Combustion device.....	4
9.2 Oxygen (7.10).....	4
9.3 Inductively coupled plasma optical emission spectrometer (6.7).....	4
9.4 Ion chromatograph (6.8).....	4
10 Calibration	4
10.1 Inductively coupled plasma optical emission spectrometer.....	4
10.2 Ion chromatograph.....	4
11 Performance	5
11.1 Determination of the blank value.....	5
11.2 Determination of the sulfur content.....	5
12 Calculation and report of the results	5
13 Precision	6
13.1 Repeatability.....	6
13.2 Reproducibility.....	6
14 Test report	6
Annex A (informative) Example of a combustion device	7
Annex B (informative) Example for suitable operating parameters for the determination of sulfur by ion chromatography	8
Annex C (informative) Example for suitable operating parameters for the determination of sulfur by inductively coupled plasma optical emission spectroscopy	9
Annex D (informative) Results of the round-robin test	10
Annex E (informative) Information regarding the validation of the uncertainty of the mean value	13
Annex F (informative) Commercial Certified Reference Materials (CRM)	14
Bibliography	15

ISO 14720-2:2013(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14720-2 was prepared by Technical Committee ISO/TC 33, *Refractories*.

ISO 14720 consists of the following parts, under the general title *Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials*:

- *Part 1: Infrared measurement methods*
- *Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow*

iTech STANDARD PREVIEW
(standards.iteh.ai)
SIST EN ISO 14720-2:2013
<https://standards.iteh.ai/catalog/standards/sist/95ab3312-24ff-488b-902e-689065b311c6/sist-en-iso-14720-2-2013>

Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials —

Part 2:

Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow

1 Scope

This part of ISO 14720 defines a method for the determination of sulfur in powdered and granular non-oxidic ceramic raw materials and materials, which are completely oxidized at a higher temperature in an oxygen atmosphere, e.g. carbon and graphite materials.

For materials which are not completely oxidizable under these conditions, it is possible to determine sulfur that can be released under these conditions, e.g. the adherent sulfur.

This part of ISO 14720 is applicable for materials with mass fractions of sulfur $\leq 10\%$ and mass fractions of ash $< 20\%$. The defined method is limited for materials with mass fractions of barium $< 10\text{ mg/kg}$, because the sulfur bonded in barium sulfate is not detectable with this method.

For the lower detection limit of this method, a mass fraction of sulfur of $0,5\text{ mg/kg}$ in the case of inductively coupled plasma optical emission spectrometry (ICP/OES) and 5 mg/kg in the case of ion chromatography (IC) has to be considered as a recommended value.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

ISO 10304-1, *Water quality — Determination of dissolved anions by liquid chromatography of ions — Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

sulfur content

mass fraction of inorganic and organic bound sulfur

4 Principle

The dried sample is oxidized in a flow of oxygen at a temperature of $1\ 100\text{ }^{\circ}\text{C}$ using a porcelain crucible. The resulting sulfur oxides are absorbed in a solution of sodium hydroxide and hydrogen peroxide. The