

SLOVENSKI STANDARD

SIST EN 772-11:2011

01-julij-2011

Nadomešča:

SIST EN 772-11:2000

SIST EN 772-11:2000/A1:2004

Metode preskušanja zidakov - 11. del: Ugotavljanje kapilarnega vpijanja vode betonskih zidakov, zidakov iz avtoklaviranega celičastega betona ter zidakov iz umetnega in naravnega kamna in začetna stopnja vpijanja vode opečnih zidakov

Methods of test for masonry units - Part 11: Determination of water absorption of aggregate concrete, autoclaved aerated concrete, manufactured stone and natural stone masonry units due to capillary action and the initial rate of water absorption of clay masonry units

Prüfverfahren für Mauersteine - Teil 11: Bestimmung der kapillaren Wasseraufnahme von Mauersteinen aus Beton, Porenbetonsteinen, Betonwerksteinen und Natursteinen sowie der anfänglichen Wasseraufnahme von Mauerziegeln

Méthodes d'essai des éléments de maçonnerie - Partie 11: Détermination de l'absorption de l'eau par capillarité des éléments de maçonnerie en béton de granulats, en béton cellulaire autoclavé, en pierre reconstituée et naturelle et du taux initial d'absorption d'eau des éléments de maçonnerie en terre cuite

Ta slovenski standard je istoveten z: EN 772-11:2011

ICS:

91.100.15	Mineralni materiali in izdelki	Mineral materials and products
91.100.30	Beton in betonski izdelki	Concrete and concrete products

SIST EN 772-11:2011

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 772-11:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011>

EUROPEAN STANDARD

EN 772-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2011

ICS 91.100.15; 91.100.30

Supersedes EN 772-11:2000

English Version

Methods of test for masonry units - Part 11: Determination of water absorption of aggregate concrete, autoclaved aerated concrete, manufactured stone and natural stone masonry units due to capillary action and the initial rate of water absorption of clay masonry units

Méthodes d'essai des éléments de maçonnerie - Partie 11:
Détermination de l'absorption de l'eau par capillarité des éléments de maçonnerie en béton de granulats, en béton cellulaire autoclavé, en pierre reconstituée et naturelle et du taux initial d'absorption d'eau des éléments de maçonnerie en terre cuite

Prüfverfahren für Mauersteine - Teil 11: Bestimmung der kapillaren Wasseraufnahme von Mauersteinen aus Beton, Porenbetonsteinen, Betonwerksteinen und Natursteinen sowie der anfänglichen Wasseraufnahme von Mauerziegeln

This European Standard was approved by CEN on 25 December 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Symbols	4
5	Apparatus.....	5
6	Preparation of specimens.....	5
7	Test procedure.....	5
8	Calculation and expression of results	6
9	Evaluation of results	6
10	Test report	7
Annex A (informative) Significant technical changes between this European standard and the previous edition		8

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 772-11:2011

<https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011>

Foreword

This document (EN 772-11:2011) has been prepared by Technical Committee CEN/TC 125 "Masonry", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2011, and conflicting national standards shall be withdrawn at the latest by November 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 772-11:2000.

Annex A provides details of significant technical changes between this European Standard and the previous edition.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

(standards.iteh.ai)

[SIST EN 772-11:2011](https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011)

<https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011>

EN 772-11:2011 (E)**1 Scope**

This European Standard specifies a method of determining the water absorption coefficient due to capillary action for aggregate concrete, autoclaved aerated concrete, natural stone and manufactured stone masonry units and the initial rate of water absorption for clay masonry units.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 771-1, *Specification for masonry units — Part 1: Clay masonry units*

EN 771-2, *Specification for masonry units — Part 2: Calcium silicate masonry units*

EN 771-3, *Specification for masonry units — Part 3: Aggregate concrete masonry units (Dense and light-weight aggregates)*

EN 771-4, *Specification for masonry units — Part 4: Autoclaved aerated concrete masonry units*

EN 771-5, *Specification for masonry units — Part 5: Manufactured stone masonry units*

EN 771-6, *Specification for masonry units — Part 6: Natural stone masonry units*

EN 772-16, *Methods of test for masonry units — Part 16: Determination of dimensions*

[SIST EN 772-11:2011](https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011)

<https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011>

3 Principle

After drying to constant mass, a face of the masonry unit is immersed in water for a specific period of time and the increase in mass is determined.

In the case of clay masonry units the initial rate of absorption of the bed face is measured. In the case of aggregate concrete, autoclaved aerated concrete, natural stone and manufactured stone masonry units the water absorption of face of the unit to be exposed is measured, as described in the relevant product standard.

4 Symbols

$m_{\text{dry},s}$ is the mass of the specimen after drying, (g);

$m_{\text{so},s}$ is the mass of the specimen in grams after soaking for time t , (g);

A_s is the gross area of the face of the specimen immersed in water, (mm^2);

t_{so} is the time of soaking, (s);

NOTE Specified in the relevant part of EN 771.

$c_{w,s}$ is the coefficient of water absorption due to capillary action for aggregate concrete autoclaved aerated concrete, natural stone and manufactured stone masonry units;

$c_{wi,s}$ is the initial rate of water absorption for clay masonry units, [$\text{kg}/(\text{m}^2 \times \text{min})$].

5 Apparatus

5.1 Large tray of minimum depth of 20 mm and of plan area larger than the face of the masonry unit to be immersed, fitted with a means of maintaining constant water level.

5.2 Supporting device of 400 mm² maximum plan area to keep each specimen clear of the base of the tray.

5.3 Stopwatch graduated in seconds.

5.4 Ventilated oven capable of maintaining a temperature of 70 °C ± 5 °C for aggregate concrete, autoclaved aerated concrete, natural stone and manufactured stone units or 105 °C ± 5 °C for clay units.

5.5 Weighing instrument capable of weighing the specimens to an accuracy of 0,1 % of their mass when dry.

6 Preparation of specimens

6.1 Sampling

The method of sampling shall be in accordance with the relevant part of EN 771. The minimum number of specimens shall be six, but a larger minimum number may be specified in the product specification, in which case that larger number shall be used.

6.2 Drying

Dry the test specimens to constant mass $m_{dry,s}$ in a ventilated oven (5.4) at a temperature of 70 °C ± 5 °C for aggregate concrete, autoclaved aerated concrete, natural stone and manufactured stone masonry units or 105 °C ± 5 °C for clay masonry units. Constant mass is reached, if during the drying process in two subsequent weighings with a 24 h interval, the loss in mass between the two determinations is not more than 0,1 % of the total mass.

7 Test procedure

Allow the specimens to cool at room temperature. When cool, measure the dimensions of the faces to be immersed in accordance with the principle incorporated in EN 772-16 and calculate the gross area A_s . Place the specimens with their faces (bed faces in the case of clay units) supported on a supporting device (5.2) so that they are clear of the base of the tray (5.1) and immerse in water to a depth of 5 mm ± 1 mm for the duration of the test. In the case of masonry units with an extremely irregular face, raise the water-level in such a way that the complete surface just makes contact with the water surface. For natural stone masonry units record whether the test face is parallel or perpendicular to the bedding planes.

Activate the timing device. Maintain the water level constant throughout the test. For aggregate concrete, autoclaved aerated concrete, natural stone and manufactured stone units, cover the tank to avoid evaporation from the wet specimens.

After the immersion time (t_{so}) specified in EN 771-1, EN 771-3, EN 771-4, EN 771-5 or EN 771-6 remove the specimens, wipe off surface water and weigh them ($m_{so,s}$).

For natural stone masonry units, remove the specimens from the water at regular intervals, wipe off the water, weigh them, then re-immerses them. Continue this procedure until no further increase in mass is observed. For some clay masonry units the initial rate of water absorption can differ for the two bed faces, in which case it will be necessary to measure on both faces.

EN 772-11:2011 (E)

8 Calculation and expression of results

8.1 Coefficient of water absorption due to capillary action of aggregate concrete and manufactured stone units

Calculate the coefficient of water absorption of the masonry units due to capillary action to the nearest 0,1 g/m²·s using the following formula:

$$c_{w,s} = \frac{m_{so,s} - m_{dry,s}}{A_s \cdot t_{so}} \times 10^6 \left[\text{g} / (\text{m}^2 \cdot \text{s}) \right]$$

8.2 Coefficient of water absorption due to capillary action of autoclaved aerated concrete and natural stone masonry units

Calculate the coefficient of water absorption of the masonry units due to capillary action of each specimen to the nearest 1 g/(m² × s^{0,5}) using the following formula:

$$c_{w,s} = \frac{m_{so,s} - m_{dry,s}}{A_s \sqrt{t_{so}}} \times 10^6 \left[\text{g} / (\text{m}^2 \times \text{s}^{0,5}) \right]$$

In the case of natural stone masonry units, plot a graph of $\frac{m_{so,s} - m_{dry,s}}{A_s}$ against the square root of the time immersed, in seconds. Calculate $c_{w,s}$ as the gradient over the initial linear portion of the graph.

8.3 Initial rate of water absorption of clay masonry units

Calculate the initial rate of water absorption of each clay masonry unit to the nearest 0,1 kg/(m² × min) using the following formula:

$$c_{w,i} = \frac{m_{so,s} - m_{dry,s}}{A_s t} \times 10^3 \left[\text{kg} / (\text{m}^2 \times \text{min}) \right]$$

where $t = 1$ min.

9 Evaluation of results

For aggregate concrete and manufactured stone masonry units calculate the mean of the coefficients of water absorption due to capillary action to the nearest 0,1 g/(m² × s).

For autoclaved aerated concrete and natural stone masonry units calculate the mean of the coefficients of water absorption due to capillary action to the nearest 1 g/(m² × s^{0,5}).

For clay masonry units calculate the mean of the initial rates of water absorption to the nearest 0,1 kg/(m² × min).

10 Test report

The test report shall contain the following information:

- a) number, title and date of issue of this European Standard;
- b) name of the organization that carried out the sampling and the method used;
- c) date of testing (in the case of aggregate concrete, autoclaved aerated concrete and manufactured stone masonry units only);
- d) description of the specimens to the relevant part of EN 771;
- e) number of specimens in the sample and whether these are whole units or representative portions thereof;
- f) date of receipt of the specimens in the testing laboratory;
- g) for aggregate concrete and manufactured stone masonry units, the individual values of water absorption coefficient due to capillary action to the nearest $0,1 \text{ g}/(\text{m}^2 \times \text{s})$ for each unit, the length of time of immersion and the mean water absorption coefficient due to capillary action to the nearest $0,1 \text{ g}/(\text{m}^2 \times \text{s})$;
- h) for autoclaved aerated concrete and natural stone masonry units, the individual values of water absorption coefficient due to capillary action to the nearest $1 \text{ g}/(\text{m}^2 \times \text{s}^{0,5})$ for each unit, the length of time of immersion and the mean water absorption coefficient due to capillary action to the nearest $1 \text{ g}/(\text{m}^2 \times \text{s}^{0,5})$. For natural stone masonry units state whether the test face was parallel or perpendicular to the bedding planes;
- i) for clay masonry units, the individual values of initial rate of water absorption to the nearest $0,1 \text{ kg}/(\text{m}^2 \times \text{min})$, and the mean of the initial rates of water absorption to the nearest $0,1 \text{ kg}/(\text{m}^2 \times \text{min})$;
- j) remarks, if any.

<https://standards.iteh.ai/catalog/standards/sist/7992335f-12d1-47b4-ac75-0974d85f98d4/sist-en-772-11-2011>