
**Welding and allied processes —
Recommendations for joint
preparation —**

Part 1:

**Manual metal-arc welding, gas-shielded
metal-arc welding, gas welding, TIG
welding and beam welding of steels**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Soudage et techniques connexes — Recommandations pour la
préparation de joints —*

[https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-](https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-752080339420/iso-9692-1:2003)

*Partie 1: Soudage manuel à l'arc avec électrode enrobée, soudage à
l'arc avec électrode fusible sous protection gazeuse, soudage aux gaz,
soudage TIG et soudage par faisceau des aciers*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9692-1:2003

<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Materials	1
4 Welding processes	2
5 Finish	2
6 Type of joint preparation	2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9692-1:2003](https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003)

<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9692-1 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 7, *Representation and terms*.

This first edition of ISO 9692-1 cancels and replaces ISO 9692:1992 which has been technically revised.

ISO 9692 consists of the following parts, under the general title *Welding and allied processes — Recommendations for joint preparation*:

- *Part 1: Manual metal-arc welding, gas-shielded metal-arc welding, gas welding, TIG welding and beam welding of steels*
- *Part 2: Submerged arc welding of steels*
- *Part 3: Metal inert gas welding and tungsten inert gas welding of aluminium and its alloys*
- *Part 4: Clad steels*

Introduction

This part of ISO 9692 defines the parameters characterizing the joint preparation and the collection of frequently recurring values and shapes.

The recommendations given in this part of ISO 9692 have been compiled on the basis of experience and contain dimensions for types of joint preparation that are generally found to lead to suitable welding conditions. However, the extended field of application makes it necessary to give a range of dimensions. The dimension ranges specified represent design limits and are not tolerances for manufacturing purposes. Manufacturing limits depend, for instance, on welding process, parent metal, welding position, quality level, etc. Because of the common character of this part of ISO 9692, the examples given cannot be regarded as the only solution for the selection of a joint type.

Specific fields of application and manufacturing requirements (e.g. pipeline construction) may be covered by selected ranges specified in other standards adapted from this basic part of ISO 9692.

Request for an official interpretation of technical aspects of this part of ISO 9692 should be directed to the relevant secretariat of ISO/TC 44/SC 7 via the user's national standardization body; a listing of these bodies can be found at www.iso.org.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9692-1:2003](https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003)

<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9692-1:2003

<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

Welding and allied processes — Recommendations for joint preparation —

Part 1:

Manual metal-arc welding, gas-shielded metal-arc welding, gas welding, TIG welding and beam welding of steels

1 Scope

This part of ISO 9692 specifies types of joint preparation for metal-arc welding with covered electrode, gas-shielded metal-arc welding, gas welding, TIG welding and beam welding of steel (see Clauses 3 and 4).

It applies to joint preparation for full penetration butt welds and for fillet welds. For partial penetration butt welds, types of joint preparation and dimensions differing from those specified in this part of ISO 9692 may be stipulated.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The root gaps referred to in this part of ISO 9692 are those gaps presented after tack welding, if used.

Consideration should be given to altering the joint preparation details (where appropriate) to facilitate temporary backing, “one-sided welding”, etc. [ISO 9692-1:2003](https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003)

<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2553:1992, *Welded, brazed and soldered joints — Symbolic representation on drawings*

ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

ISO 6947, *Welds — Working positions — Definitions of angles of slope and rotation*

3 Materials

Joint preparations recommended in this part of ISO 9692 are suitable for all kinds of steel.

4 Welding processes

Joint preparations recommended in this part of ISO 9692 are suitable for welding carried out in accordance with the following processes as specified in Tables 1 to 4; combinations of different processes are possible.

- a) (3) gas welding; oxyfuel gas welding;
- b) (111) manual metal arc welding (metal arc welding with covered electrode); shielded metal arc welding;
- c) (13) gas-shielded metal arc welding; gas metal arc welding includes:
 - (131) metal inert gas welding; MIG welding; gas metal arc welding;
 - (135) metal active gas welding; MAG welding; gas metal arc welding;
 - (136) tubular cored metal arc welding with active gas shield; flux cored arc welding;
 - (137) tubular cored metal arc welding with inert gas shield; flux cored arc welding;
- d) (141) tungsten inert gas welding; TIG welding; gas tungsten arc welding;
- e) (5) beam welding:
 - (51) electron beam welding;
 - (512) electron beam welding in atmosphere;
 - (52) laser welding; laser beam welding.

NOTE The numbers in parentheses refer to the reference number of the welding process specified in ISO 4063.
<https://standards.iteh.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

5 Finish

The longitudinal edges of the root face should be de-burred and may be chamfered (up to 2 mm).

6 Type of joint preparation

The recommended types of joint preparation and dimensions are specified in Tables 1 to 4.

Table 1 — Joint preparations for butt welds, welded from one side

Ref. No.	Material thickness	Type of preparation	Symbol (in accordance with ISO 2553)	Cross-section	Angle ^a	Dimensions			Depth of preparation	Recommended welding process (reference number in accordance with ISO 4063)	Weld illustration	Remarks
						Gap ^b	Thick-ness of root face	Thick-ness of root face				
1.1	t mm ≤ 2	raised edges			α, β	b mm —	c mm —	h mm —	3 111 141 512		Usually without filler metal	
1.2.1	≤ 4	Square preparation			—	$\approx t$	—	—	3 111 141		—	
1.2.2	$3 < t \leq 8$ ≤ 15				—	$6 \leq b \leq 8$	$\approx t$	$\leq 1^d$	13 141 ^c		Where applicable with backing strip	
												0










iTech STANDARD PREVIEW
(standards.itech.ai)
ISO 9692-1:2003
<https://standards.itech.ai/catalog/standards/sist/c00ebcff-11e0-4ab6-b280-7b25c7863500/iso-9692-1-2003>

Table 1 (continued)

Ref. No.	Material thickness t mm	Type of preparation	Symbol (in accordance with ISO 2553)	Cross-section	Angle ^a α, β	Dimensions			Recommended welding process (reference number in accordance with ISO 4063)	Weld illustration	Remarks
						Gap ^b b mm	Thickness of root face c mm	Depth of preparation h mm			
1.2.3	≤ 100	Square preparation with backing			—	—	—	51		—	
1.2.4		Square preparation with centering lip									
1.3	$3 < t \leq 10$	Single-V preparation			$40^\circ \leq \alpha \leq 60^\circ$	—	—	3 111 13 141		Where applicable with backing strip	
	$8 < t \leq 12$										$6^\circ \leq \alpha \leq 8^\circ$
1.4	> 16	Steep-flanked single-V preparation			$5^\circ \leq \beta \leq 20^\circ$	—	—	111 13		With backing strip	

Teh STANDARD PREVIEW
(standards.iteh.ai)
ISO 9692-1:2003
<https://standards.iteh.ai/catalog/standards/sist/c00eb2ff-11e0-42b6-b280-7b25c1863500/iso-9692-1-2003>

Table 1 (continued)

Ref. No.	Material thickness t mm	Type of preparation	Symbol (in accordance with ISO 2553)	Cross-section	Dimensions			Depth of preparation	Recommended welding process (reference number in accordance with ISO 4063)	Weld illustration	Remarks
					Angle ^a α, β	Gap ^b b mm	Thickness of root face c mm				
1.5	$5 \leq t \leq 40$	Single-V preparation with broad root face			$\alpha \approx 60^\circ$ $1 \leq b \leq 4$ $2 \leq c \leq 4$	b mm	h mm	111 13 141		—	
1.6	> 12	Single-U preparation with V root			$60^\circ \leq \alpha \leq 90^\circ$ $8^\circ \leq \beta \leq 12^\circ$ $1 \leq b \leq 3$	b mm	≈ 4	111 13 141		$6 \leq R \leq 9$	
1.7	> 12	Single-V preparation with V root			$60^\circ \leq \alpha \leq 90^\circ$ $10^\circ \leq \beta \leq 15^\circ$ $2 \leq b \leq 4$	b mm	—	111 13 141		—	