



SLOVENSKI STANDARD
oSIST prEN 13936:2012
01-november-2012

Izpostavljenost na delovnem mestu - Merjenje kemičnih agensov, prisotnih kot zmesi lebdečih delcev in par - Zahteve in preskusne metode

Workplace exposure - Procedures for measuring a chemical agent present as a mixture of airborne particles and vapour - Requirements and test methods

Exposition am Arbeitsplatz - Messung eines als Mischung aus luftgetragenen Partikeln und Dampf vorliegenden chemischen Arbeitsstoffes - Anforderungen und Prüfverfahren

Exposition sur les lieux de travail - Mesurage de l'agent chimique sous forme de mélange de particules aériennes et de vapeur - Exigences et méthodes d'essai

Ta slovenski standard je istoveten z: prEN 13936

ICS:

13.040.30 Kakovost zraka na delovnem Workplace atmospheres
mestu

oSIST prEN 13936:2012

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13936

July 2012

ICS 13.040.30

English Version

Workplace exposure - Procedures for measuring a chemical agent present as a mixture of airborne particles and vapour - Requirements and test methods

Exposition sur les lieux de travail - Mesurage de l'agent chimique sous forme de mélange de particules aériennes et de vapeurs - Exigences et méthodes d'essai

Exposition am Arbeitsplatz - Messung eines als Mischung aus luftgetragenen Partikeln und Dampf vorliegenden chemischen Arbeitsstoffes - Anforderungen und Prüfverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 137.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

cc71c45d9cf2/sist-en-13936-2014

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Requirements	7
4.1 General.....	7
4.2 Sampler requirements.....	7
4.2.1 Inhalable sampler.....	7
4.2.2 Vapour sampler.....	7
4.2.3 Mixed-phase sampler	7
4.3 Pumps	7
4.4 Measurement procedure requirements for mixtures of airborne particles and vapour.....	8
4.4.1 Storage test	8
4.4.2 Expanded uncertainty	8
4.4.3 Method description.....	8
5 Test methods.....	8
5.1 Sample distribution between the collection substrate for airborne particles and the collection substrate for vapour.....	8
5.2 Test for compliance with EN 1076.....	9
5.3 Storage test	9
5.4 Uncertainty of the measurement.....	10
5.4.1 Calculation of the combined standard uncertainty.....	10
5.4.2 Calculation of the expanded uncertainty	10
6 Test report	10
Annex A (normative) Possible approaches to sample mixtures of airborne particles and vapour	11
A.1 General.....	11
A.2 Filter plus pumped sorbent tube.....	11
A.2.1 General.....	11
A.2.2 Sampling flow rate	11
A.3 Reagent-impregnated systems	12
A.4 Transportation and storage	12
Annex B (informative) Physical behaviour of a mixture of airborne particles and vapour	13
B.1 Generation of a mixture of airborne particles and vapour	13
B.2 Sampling of chemical agents having a vapour pressure of more than 100 Pa at room temperature (process temperature).....	13
B.3 Sampling of chemical agents having a vapour pressure of more than 0,001 Pa and less than or equal to 100 Pa at room temperature	13
B.4 Sampling of chemical agents having a vapour pressure of less than 0,001 Pa at room temperature	14
Annex C (informative) Estimation of uncertainty of measurement.....	16
C.1 Uncertainty components.....	16
C.2 Two collection substrates for airborne particles and vapour.....	16
C.2.1 Sampled air volume and sampling efficiency.....	16
C.2.2 Sample storage	16
C.2.3 Effects of temperature and humidity	16
C.2.4 Analysis	17

C.2.5	Bias of sample distribution between the collection substrate for airborne particles and the collection substrate for vapour (distribution bias).....	17
C.2.6	Calculation of the relative combined uncertainty	17
C.3	One collection substrate for airborne particles and vapour.....	19
C.3.1	General	19
C.3.2	Sampling.....	19
C.3.3	Analysis.....	19
C.3.4	Calculation of the relative combined standard uncertainty.....	20
	Bibliography.....	21

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 13936:2014

<https://standards.iteh.ai/catalog/standards/sist/66aa31a3-7253-4e3c-b4cc-cc71c45d9cf2/sist-en-13936-2014>

prEN 13936:2012 (E)

Foreword

This document (prEN 13936:2012) has been prepared by Technical Committee CEN/TC 137 “Assessment of workplace exposure to chemical and biological agents”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13936:2014

<https://standards.iteh.ai/catalog/standards/sist/66aa31a3-7253-4e3c-b4cc-cc71c45d9cf2/sist-en-13936-2014>

Introduction

EN 482 specifies general requirements for the performance of procedures that methods for the measurement of the concentration of chemical agents in workplace atmospheres should meet. These performance criteria include maximum values of expanded uncertainty achievable under prescribed laboratory conditions for the methods to be used. Chemical agents in workplace air are often present in both gaseous and non-gaseous phases at the same time and therefore validated methods are required that can measure the combined concentration of the chemical agent in both phases. Examples include: processes that generate aerosols of volatile or semi-volatile liquids or solids such as paint spraying, metalworking with coolants and lubricants, acid pickling etc.; and hot processes as that generates vapours of chemical agents that are normally in the liquid or solid phase under ambient conditions, e. g. road surfacing with bitumen.

For health-related sampling of mixed-phase aerosols, it is necessary to measure the mass concentration of the inhalable fraction of hazardous chemical agents, regardless of whether they are present as airborne particles or vapour. This generally means drawing air through two or more collection media in series. If a chemical agent is collected in the form of airborne particles and it has a significant vapour pressure under ambient conditions, it will wholly or partly volatilise during sampling and the resulting vapour needs to be subsequently collected, in order that the total mass of the chemical agent is measured; similarly, the chemical agent can also be lost from the collected airborne particles after sampling if it is not stabilised.

In some cases it can also be necessary to measure the distribution of chemical agents between the particulate and vapour phases as well as the mass concentration of the inhalable fraction. For example, there can be compounds whose toxicology is known to differ significantly depending on whether they exist as airborne particles or vapour. In addition, control measures in the workplace can depend on which phase dominates. Exposure limits can be phase-specific. However the separate quantification of airborne particles and vapour is technically complex and subject to error using existing sampling technologies. For this reason this European Standard is not applicable to methods that differentiate between the sampled airborne particles and vapour.

[SIST EN 13936:2014](https://standards.iteh.ai/catalog/standards/sist/66aa31a3-7253-4e3c-b4cc-cc71c45d9cf2/sist-en-13936-2014)

<https://standards.iteh.ai/catalog/standards/sist/66aa31a3-7253-4e3c-b4cc-cc71c45d9cf2/sist-en-13936-2014>

1 Scope

This European Standard specifies performance requirements and test methods for the evaluation of procedures for measuring a chemical agent present as a mixture of airborne particles and vapour in workplace air.

This European Standard establishes general principles to enable developers and users of mixed-phase samplers and methods to adopt a consistent approach to method validation and provides a framework for the assessment of method performance in accordance with EN 482.

This European Standard also gives guidance on approaches to sample a mixture of airborne particles and vapour and their advantages and limitations.

This European Standard is not applicable to methods that differentiate between the sampled airborne particles and vapour.

This European Standard is not applicable to a chemical agent present in different chemical and physical forms (for example, mercury in the form of Hg (0) and Hg (II)).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 481, *Workplace atmospheres — Size fraction definitions for measurement of airborne particles.*

EN 482, *Workplace exposure — General requirements for the performance of procedures for the measurement of chemical agents.*

EN 838, *Workplace exposure — Procedures for measuring gases and vapours using diffusive samplers — Requirements and test methods.*

EN 1076:2009, *Workplace exposure — Procedures for measuring gases and vapours using pumped samplers — Requirements and test methods.*

EN 1232¹⁾, *Workplace atmospheres — Pumps for personal sampling of chemical agents — Requirements and test methods.*

EN 1540, *Workplace exposure — Terminology.*

EN 12919¹⁾, *Workplace atmospheres — Pumps for the sampling of chemical agents with a volume flow rate of over 5 l/min — Requirements and test methods.*

EN 13205, *Workplace atmospheres — Assessment of performance of instruments for measurement of airborne particle concentrations.*

EN 13890, *Workplace exposure — Procedures for measuring metals and metalloids in airborne particles — Requirements and test methods.*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1540 and the following apply.

¹⁾ An International Standard, ISO 13137, is being elaborated which it is foreseen will replace this document.

3.1

single component aerosol

aerosol in which the airborne particles and vapour are composed of the same chemical agent

3.2

multiple component aerosol

aerosol containing more than one chemical agent, each of which can be present in the form of airborne particles and/or vapour

3.3

vapour sampler

pumped sampler or diffusive sampler that is used to collect the vapour

4 Requirements

4.1 General

Regardless of the combination of samplers used, the measurement procedure used shall comply with the requirements of EN 482 and with the requirements of EN 838, EN 1076, EN 1232, EN 12919, EN 13205 and EN 13890, as appropriate.

It is the responsibility of the manufacturer or of those who assemble mixed-phase samplers to ensure that the method complies with the requirements for expanded uncertainty under the specified laboratory conditions given in this document, including the environmental influences that can be expected to affect performance.

4.2 Sampler requirements

4.2.1 Inhalable sampler

Measurement procedures shall specify the use of a sampler designed to collect the inhalable fraction of airborne particles, as defined in EN 481, and complying with EN 13205. The inhalable sampler shall operate at a flow rate that is compatible with that of the vapour sampler.

4.2.2 Vapour sampler

Measurement procedures shall specify the use of a pumped sampler or diffusive sampler that complies with the requirements specified in EN 1076 or EN 838, respectively. The vapour sampler shall be capable of operating at a flow rate that is compatible with that of the inhalable sampler.

4.2.3 Mixed-phase sampler

The back pressure of the mixed-phase sampler shall not exceed the pump requirements specified in EN 1232 or EN 12919, as appropriate.

When a mixed-phase sampler comprises of an inhalable sampler in combination with one or more vapour samplers, the dead volume of the sampling train shall be kept to a minimum and any connection shall be made of an inert material that does not retain the chemical agent of interest.

NOTE When a mixed-phase sampler comprises of a vapour sampler in combination with an inhalable sampler and there are flow rate compatibility issues, it is possible to split the air flow from the inhalable sampler through more than one vapour sampler.

4.3 Pumps

Measurement procedures shall specify the use of pumps complying with EN 1232 or EN 12919, as appropriate.

prEN 13936:2012 (E)**4.4 Measurement procedure requirements for mixtures of airborne particles and vapour****4.4.1 Storage test**

When tested in accordance with the procedure prescribed in 5.1, the mean analytical recovery after storage shall be at least 90 %.

4.4.2 Expanded uncertainty

The expanded uncertainty of the measurement procedure as a whole, including the measurement of airborne particles and vapour, shall comply with the requirements of EN 482.

4.4.3 Method description

The method description shall contain at least the following information:

- a) a general description of the principles of the method, the approach followed to sample mixtures of airborne particles and vapour and any relevant assumptions;
- b) a detailed description and identification of the system components, including all collection substrates and, for commercial devices, the name of the manufacturer(s) and the product identification(s);
- c) if applicable, the recommended shelf life of the collection substrate(s);
- d) the design flow rate, pressure drop across the mixed-phase sampler at the design flow rate;
- e) the recommended sampling time and, if applicable, the sampler capacity for a specific analyte;
- f) methods for handling, transportation and storage of samples, including storage times;
- g) information on analytical methods to be applied and instructions as to whether and how wall deposits are to be included in the analysis of the collected sample;
- h) the recovery efficiency for specific analytes, including the effects of concentration, loading, temperature and humidity, where applicable;
- i) any known interference.

5 Test methods**5.1 Sample distribution between the collection substrate for airborne particles and the collection substrate for vapour**

Set up at least six mixed-phase samplers and add a known mass of analyte to the collection substrates or, where the mixed-phase sampler includes more than one collection substrate, to the first collection substrate. The mass of analyte is calculated from the limit value and the recommended sampling volume. Add the analyte using a micropipette or syringe, if necessary, with the analyte diluted in a non-interfering solvent. Repeat for each sample loading.

Immediately after adding the calculated mass of analyte according to Table 1, draw conditioned air through the mixed-phase samplers under the following test conditions:

- relative humidity: (50 ± 5) %;
- temperature: (10 ± 2) °C and (40 ± 2) °C;
- flow rate: recommended flow rate.

NOTE One way to obtain air with the required conditions of temperature and relative humidity is to use a climatic test chamber as defined in EN 60068-3-11.

Table 1 — Concentration and time used for calculation of mass of analyte

Reference period	Concentration	Time
long-term	0,1 times limit value	8 h or recommended sampling time
	2 times limit value	
short-term	1 time limit value	e.g. 15 min

Analyze each collection substrate and, for each substrate, calculate the distribution coefficients for vapour and airborne particles according to Formulae (1) and (2):

$$\gamma_{d,p} = \frac{m_p}{m_v + m_p} \cdot 100 \quad (1)$$

$$\gamma_{d,v} = 100 - \gamma_{d,p} \quad (2)$$

where

$\gamma_{d,p}$ is the distribution coefficient for airborne particles, in percent;

$\gamma_{d,v}$ is the distribution coefficient for vapour, in percent;

m_p is the mass determined on the collection substrate for airborne particles, in milligrams;

m_v is the mass determined on the collection substrate for vapour, in milligrams;

Calculate the mean and the coefficient of variation of the replicate samples.

Consider the distribution coefficients between the collections substrates used:

- if, in all cases, $\gamma_{d,p} < 10$ % the collection substrate for airborne particles does not need to be analysed;
- if, in some cases $10 \% \leq \gamma_{d,p} \leq 90$ % the collection substrates for airborne particles and vapour shall be analysed;
- if, in all cases $\gamma_{d,p} > 90$ % only the collection substrate for airborne particles needs to be analysed.

Depending on the storage test (see 5.3) a stabilisation procedure can be required afterwards.

5.2 Test for compliance with EN 1076

Perform the tests given in EN 1076:2009, Clause 8 with the mixed-phase sampler as described in 5.1.

5.3 Storage test

Verify that the analytical recovery determined from the combined results from the collection substrate for airborne particles and the collection substrate for vapour meets the requirements of 4.4.1.

For a chemical agent present as a mixture of airborne particles and vapour, sampled airborne particles cannot normally be stored for a long period of time without sample loss. They need to be stabilised, e.g. by sample dissolution immediately after sampling. See A.7.