

SLOVENSKI STANDARD SIST-TP CEN/TR 15985:2010

01-april-2010

Toplotnoizolacijski proizvodi - Proizvodi iz ekspandiranega polistirena (EPS) - Prostovoljno certificiranje surovin	
Thermal insulating products - Factory made products of expanded polystyrene (EPS) Voluntary certification of the raw material	-
Wärmedämmstoffe - Werkmäßig hergestellte Produkte aus expandiertem Polystyrol (EPS) - Freiwillige Zertifizierung des Ausgangsstoffes REVIEW	

Produits isolants - Produits manufacturés en polystyrène expansé (EPS) - Certification volontaire du matériau de base <u>SIST-TP CEN/TR 15985:2010</u> https://standards.iteh.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-

Ta slovenski standard je istoveten z: CEN/TR 15985-2010

<u>ICS:</u>

91.100.60 Materiali za toplotno in zvočno izolacijo

Thermal and sound insulating materials

SIST-TP CEN/TR 15985:2010

en,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN/TR 15985:2010 https://standards.iteh.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-78fe86113838/sist-tp-cen-tr-15985-2010

SIST-TP CEN/TR 15985:2010

TECHNICAL REPORT RAPPORT TECHNIQUE TECHNISCHER BERICHT

CEN/TR 15985

January 2010

ICS 13.220.50; 91.100.01

English Version

Thermal insulating products - Factory made products of expanded polystyrene (EPS) - Voluntary certification of the raw material

Produits isolants - Produits manufacturés en polystyrène expansé (EPS) - Certification volontaire du matériau de base Wärmedämmstoffe - Werkmäßig hergestellte Produkte aus expandiertem Polystyrol (EPS) - Freiwillige Zertifizierung des Ausgangsstoffes

This Technical Report was approved by CEN on 7 December 2009. It has been drawn up by the Technical Committee CEN/TC 88.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN/TR 15985:2010 https://standards.iteh.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-78fe86113838/sist-tp-cen-tr-15985-2010



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2010 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. CEN/TR 15985:2010: E

SIST-TP CEN/TR 15985:2010

CEN/TR 15985:2010 (E)

Contents

Forewo	ord	.3
Introdu	uction	.4
1	Scope	.5
2	Normative references	.5
3	Terms and definitions	.5
4	Preparation of samples	.6
5	Initial tests	.6
6 6.1 6.2	Factory Production Control (FPC) for EPS raw material General Testing frequency	.6 6. 6.
7 7.1 7.2 7.3	Certification of conformity for raw material Bodies involved in the evaluation of conformity procedure Test specimens Initial test for EPS raw material	.7 .7 .7 .7
8 8.1 8.2	Continuous surveillance of EPS raw material Production	.7 .7 .7
9	Certificate of conformity	.8
10 10.1 10 2	Responsibility of the raw material supplier standards/sist/d8e974ab-ea8b-438b-b691- Declaration by the raw material supplier 38/sist-tp-cen-tr-15985-2010	.9 .9 9
10.2		

Foreword

This document (CEN/TR 15985:2010) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN/TR 15985:2010 https://standards.iteh.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-78fe86113838/sist-tp-cen-tr-15985-2010 CEN/TR 15985:2010 (E)

Introduction

EN 13163 contains an option in Annex B, Table B.2 to change the frequency for the reaction to fire test according to EN ISO 11925-2 from once per day to once per week. A reduction of the frequency in the FPC is possible according to note to table h of Table B.2, if a certified raw material has been used.

Since rules on how to certify EPS raw material are still missing this option could not be chosen yet. That is why the following rules have been developed and issued by TC 88. These rules may be applied by the raw material suppliers and the involved bodies to certify the raw materials until the following text has been incorporated in the next revision of EN 13163:2008.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST-TP CEN/TR 15985:2010 https://standards.iteh.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-78fe86113838/sist-tp-cen-tr-15985-2010

1 Scope

It is essential that EPS products with a reaction to fire performance better than Euroclass F be manufactured from raw materials with a chemical composition, which is under the control of the raw material producer.

This Technical Report specifies the conditions allowing reduction of the FPC frequency for testing the reaction to fire of specimens made from flame retardant EPS raw material. The preconditions are that products are manufactured solely from a specified, certified raw material, within defined density limits, and produced in the way specified by the raw material supplier.

The frequency of testing the final product can be reduced in accordance with EN 13163:2008, Annex B, Table B.2 footnote to table h. It is essential that the reaction to fire performance of the raw material be labelled according to 9.2 in the certificate from an approved body (see EN 13172:2008, 5.3.3 and Annex A).

The certification of the raw material relates only to products for which the reaction to fire Euroclass E according to EN 13501-1 is being claimed. The manufacturer of the EPS boards / products continues to be responsible for the FPC of the EPS boards / products.

This Technical Report is in accordance with the general rules of EN 13172.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies res.iten.ai)

EN 1602, Thermal insulating products for building applications — Determination of the apparent density <u>SIST-TP CEN/TR 15985:2010</u>

EN 13163:2008, Thermal insulation products for buildings 8-9 Factory made products of expanded polystyrene (EPS) — Specification 78fe86113838/sist-tp-cen-tr-15985-2010

EN 13172:2008, Thermal insulating products — Evaluation of conformity

EN 13501-1, Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests

EN ISO 11925-2, Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2:2002)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

EPS raw material with flame retardant

non-expanded polystyrene beads containing additives such as a flame retardant treatment and a blowing agent

3.2

EPS test specimen

EPS foam in a finished form with its final product properties (without facing)

NOTE ITT = Initial Type Test.

CEN/TR 15985:2010 (E)

4 **Preparation of samples**

The raw material supplier shall produce samples of the expanded raw material using all the procedures of the normal production process for EPS.

Thickness, density and exposure to thermal attack shall be measured and reported when making the ignitability test in accordance with EN ISO 11925-2. The specimens shall be cut from samples as described in EN ISO 11925-2.

NOTE Since EPS is an isotropic material the direction of the samples is irrelevant.

The thickness of all test specimens shall be 10 mm and 60 mm for ITT.

5 Initial tests

Initial type tests shall be carried out on samples as described in Clause 4.

Test specimens, in thickness of 10 mm and 60 mm shall be made from the minimum and maximum density of EPS product sample. The tests shall be performed in accordance with EN ISO 11925-2 with the thermal attack on the edge.

6 Factory Production Control (FPC) for EPS raw material

6.1 General

(standards.iteh.ai)

iTeh STANDARD PREVIEW

The raw material supplier shall have a factory production control system in place as described in EN 13172 to ensure the quality of production.

thtps://standards.itch.ai/catalog/standards/sist/d8e974ab-ea8b-438b-b691-The continuous FPC of the raw materials shall be carried out by sampling EPS products produced at densities between 15 kg/m³ and 20 kg/m³.

The density of all samples prepared shall be determined in accordance with EN 1602.

The tests shall be made and the results recorded in accordance with EN ISO 11925-2 with an exposure time of 15 s and an observation time of 20 s; edge attack only.

All tests results shall fulfil the requirements to meet Euroclass E according to EN 13501-1.

6.2 Testing frequency

The tests shall be performed on one set of specimens per batch (or per production day whichever gives the highest frequency) and per plant and type of polymer at a density between 15 kg/m³ and 20 kg/m³. The thickness of the samples shall be 20 mm.

In addition, the minimum and maximum density shall be tested and recorded every 3 months. The thickness of the samples shall be 20 mm.

In case EN 13172 specifies applicable rules, the testing frequency can be reduced in agreement with the notified body if the raw material supplier has demonstrated reliable performance.

CEN/TR 15985:2010 (E)

7 Certification of conformity for raw material

7.1 Bodies involved in the evaluation of conformity procedure

Bodies involved are specified in EN 13172:2008, Annex A.

7.2 Test specimens

The number of test specimens to obtain one test result is specified in EN 13501-1 and EN ISO 11925-2.

The raw material supplier shall send the samples to the approved body.

7.3 Initial test for EPS raw material

For the initial type test the tests shall be performed by an approved body taking into account the more critical edge flame attack only (not the surface attack).

NOTE EN ISO 11925-2 requires both testing with surface and edge flame attack, but for this purpose here only the more critical test is performed.

The specimen thickness shall be 10 mm and 60 mm, for both the minimum and maximum density.

These two densities specify the density range for which the certificate is valid.

A classification report according to EN 13501-1 from an approved body is required for the initial test only.

This test shall be repeated every 5 (years.ndards.iteh.ai)

SIST-TP CEN/TR 15985:2010

8 Continuous surveillance of EPS/raw material 74ab-ea8b-438b-b691-

78fe86113838/sist-tp-cen-tr-15985-2010

8.1 Production

Plant and polymer samples, at the minimum and maximum density shall be tested by an approved body once per year with a specimen thickness of 20 mm. Different fractions of one production line can be grouped together within the defined density range.

8.2 Factory production control

The FPC shall be checked by an approved body once per year.