



Designation: D 1462 – 92 (Reapproved 1998)

Standard Specification for Refined Soybean Oil¹

This standard is issued under the fixed designation D 1462; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers refined soybean oil suitable for use in the paint and varnish industry.

2. Referenced Documents

2.1 ASTM Standards:

- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids²
- D 555 Guide for Testing Drying Oils³
- D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products⁴
- D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)⁴
- D 1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method³
- D 1639 Test Method for Acid Value of Organic Coating Materials³
- D 1952 Test Method for Quantitative Determination of Break in Drying Oils³
- D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids³
- D 1960 Test Method for Loss on Heating of Drying Oils³
- D 1962 Test Method for Saponification Value of Drying Oils, Fatty Acids, and Polymerized Fatty Acids³
- D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C³
- D 1965 Test Method for Unsaponifiable Matter in Drying

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.32 on Drying Oils.

Current edition approved March 15, 1992. Published May 1992. Originally published as D 1462 – 57. Last previous edition D 1462 – 87.

² Annual Book of ASTM Standards, Vol 05.01.

³ Annual Book of ASTM Standards, Vol 06.03.

⁴ Annual Book of ASTM Standards, Vol 06.01.

TABLE 1 Physical Properties

Property	Requirements	ASTM Method
Specific gravity, 25/25°C	0.917 to 0.924	D 1963, D 1475
Acid value, max	0.3	D 1639
Saponification value	189 to 195	D 1962
Unsaponifiable matter, max, %	1.5	D 1965
Iodine value (Wijs), min	126	D 1959
Loss on heating at 105 to 110°C, max, %	0.3	D 1960
Clarity	clear and transparent at 65°C	D 2090
Color (Gardner), max	6	D 1544
Color (after heating), max	4	D 1967
Break, max, %	0.02	D 1952
Viscosity, approximate stokes	0.32 to 0.50	D 1545, D 445

Oils, Fatty Acids, and Polymerized Fatty Acids³

D 1967 Test Method for Measuring Color After Heating of Drying Oils³

D 2090 Test Method for Clarity and Cleanness of Paint and Ink Liquids³

3. Properties

3.1 Refined soybean oil shall conform to the requirements in Table 1.

4. Test Methods

4.1 *Sampling*—Sampling shall be conducted in accordance with Test Method D 1466.

4.2 The properties enumerated in this specification shall be determined in accordance with the applicable ASTM test methods listed in Table 1. The significance of the test methods enumerated under properties in this specification is discussed in Guide D 555.

5. Keywords

5.1 drying oils; refined soybean oil; soybean oil

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.