

SLOVENSKI STANDARD

SIST EN 12492:2012

01-julij-2012

Nadomešča:

SIST EN 12492:2000

SIST EN 12492:2000/A1:2003

Alpinistična oprema - Alpinistične čelade - Varnostne zahteve in preskusne metode

Mountaineering equipment - Helmets for mountaineers - Safety requirements and test methods

Bergsteigerausrüstung - Bergsteigerhelme - Sicherheitstechnische Anforderungen und Prüfverfahren

Equipements d'alpinisme et d'escalade - Casques d'alpinistes - Exigences de sécurité et méthodes d'essai

Ta slovenski standard je istoveten z: EN 12492:2012

ICS:

13.340.20	Varovalna oprema za glavo	Head protective equipment
97.220.40	Oprema za športe na prostem in vodne športe	Outdoor and water sports equipment

SIST EN 12492:2012

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 12492:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012>

EUROPEAN STANDARD

EN 12492

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2012

ICS 13.340.20

Supersedes EN 12492:2000

English Version

Mountaineering equipment - Helmets for mountaineers - Safety requirements and test methods

Equipements d'alpinisme et d'escalade - Casques
d'alpinistes - Exigences de sécurité et méthodes d'essai

Bergsteigerausrüstung - Bergsteigerhelme -
Sicherheitstechnische Anforderungen und Prüfverfahren

This European Standard was approved by CEN on 17 December 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 12492:2012

<https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Requirements	7
4.1 Construction requirements.....	7
4.1.1 Materials	7
4.1.2 Projections	7
4.1.3 Retention system	7
4.1.4 Ventilation.....	7
4.2 Performance requirements	7
4.2.1 Shock absorption.....	7
4.2.2 Penetration	8
4.2.3 Retention system strength	8
4.2.4 Retention system effectiveness (roll off)	8
5 Test methods.....	8
5.1 Sampling	8
5.2 Helmet adjustment.....	8
5.3 Conditioning.....	9
5.3.1 General.....	9
5.3.2 U.V. ageing	9
5.3.3 'Thermal plus' conditioning	9
5.3.4 'Thermal minus' conditioning.....	9
5.4 Headforms	9
5.5 Shock absorption.....	10
5.5.1 Impact points.....	10
5.5.2 Principle	10
5.5.3 Apparatus	10
5.5.4 Procedure	12
5.5.5 Report	12
5.6 Resistance to penetration	12
5.6.1 Impact area	12
5.6.2 Principle	12
5.6.3 Apparatus	12
5.6.4 Procedure	13
5.6.5 Report	13
5.7 Retention system strength	13
5.7.1 Principle	13
5.7.2 Apparatus	14
5.7.3 Procedure	14
5.7.4 Report	14
5.8 Retention system effectiveness	14
5.8.1 General.....	14
5.8.2 Principle	15
5.8.3 Apparatus	15
5.8.4 Procedure	16
5.8.5 Report	16
6 Marking and labelling	21
6.1 Marking	21

6.2	Labelling	21
7	Information supplied by the manufacturer	21
Annex A	(informative) Alternative test method for artificial ageing	22
Annex B	(informative) Significant technical changes between this European Standard and EN 12492:2000	23
Annex ZA	(informative) Relationship between this European Standard and the Essential Requirements of EU Directive 89/686/EEC Personal Protective Equipment	24
	Bibliography	25

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 12492:2012](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012)

<https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012>

Foreword

This document (EN 12492:2012) has been prepared by Technical Committee CEN/TC 158 "Head protection", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12492:2000.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Annex B provides details of significant technical changes between this European Standard and the previous edition.

iTeh STANDARD PREVIEW

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The protection given by a helmet depends on the circumstances of the accident and wearing a helmet cannot always prevent death or long term disability.

A proportion of the energy of an impact is absorbed by the helmet, thereby reducing the force of the blow sustained by the head. The structure of the helmet may be damaged in absorbing this energy and any helmet that sustains a severe blow needs to be replaced even if damage is not apparent.

Mountaineers' helmets are fitted with a retention system to retain the helmet on the head. However, there may be a foreseeable risk that helmets could become trapped and thereby cause a risk of strangulation.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 12492:2012](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012)

<https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012>

1 Scope

This European Standard specifies safety requirements and test methods for safety helmets for use in mountaineering.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 960:2006, *Headforms for use in the testing of protective helmets*

ISO 6487, *Road vehicles — Measurement techniques in impact tests — Instrumentation*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

helmet for mountaineers (hereafter referred to as helmet)

headwear primarily intended to protect the upper part of a wearer's head against hazards which might occur during activities carried out by mountaineers

3.2

shell

hard, smoothly finished material that provides the general outer form of the helmet

<https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012>

3.3

helmet type

helmet which is characterized by:

- a) the tradename or mark;
- b) the materials and dimensions of the shell;
- c) the materials and dimensions of the protective padding;
- d) the materials and dimensions of the retention system

3.4

protective padding

material which is used to absorb impact energy

3.5

comfort padding

liner material provided for the wearer's comfort

3.6

sizing padding

liner material used for adjustment of the helmet size

3.7

retention system

complete assembly by means of which the helmet is maintained in position on the head, including any devices for adjustment of the system or to enhance the wearer's comfort

3.8

chin strap

part of the retention system consisting of a strap which passes under the wearer's jaw to retain the helmet in position

3.9

headform

shape replacing the head which is used for testing certain characteristics

Note 1 to entry: The headform is designed in accordance with EN 960:2006.

4 Requirements

4.1 Construction requirements

4.1.1 Materials

For those parts of the helmet that come into contact with the skin, materials which are known to be likely to cause skin irritation or any adverse effect on health shall not be used. For a material not in general use, advice as to its suitability shall be sought before its introduction.

4.1.2 Projections

There shall be no sharp edges, roughness or projection on any part of the helmet which is in contact or potential contact with the wearer when the helmet is worn, such as is likely to cause injury to the wearer.

4.1.3 Retention system

The helmet shall be fitted with a retention system, including a chin strap. The retention system shall have at least three separate points of attachment to the shell. The chin strap shall be adjustable in length. That part of the chin strap which comes into contact with the jaw shall have a minimum width of 15 mm under a load of 250 N.

4.1.4 Ventilation

All helmets shall be ventilated.

The sum of the cross-sectional areas of such ventilation shall not be less than 4 cm² when measured on the surface of the helmet.

4.2 Performance requirements

4.2.1 Shock absorption

4.2.1.1 Vertical energy absorption capacity

When a helmet is tested by the method described in 5.5, the force transmitted to the headform shall not exceed 10 kN, for a drop height of (2 000 ± 10) mm of the hemispherical striker described in 5.5.3.4.

4.2.1.2 Front energy absorption capacity

When a helmet is tested by the method described in 5.5, the force transmitted to the headform shall not exceed 10 kN, for a drop height of (500 ± 10) mm of the flat striker described in 5.5.3.4.

EN 12492:2012 (E)

4.2.1.3 Side energy absorption capacity

When a helmet is tested by the method described in 5.5, the force transmitted to the headform shall not exceed 10 kN, for a drop height of (500 ± 10) mm of the flat striker described in 5.5.3.4.

4.2.1.4 Rear energy absorption capacity

When a helmet is tested by the method described in 5.5, the force transmitted to the headform shall not exceed 10 kN, for a drop height of (500 ± 10) mm of the flat striker described in 5.5.3.4.

4.2.2 Penetration

When a helmet is tested on two points of impact, apart from each other as at least 50 mm, by the method described in 5.6, there shall be no contact between the striker and the headform, for a drop height of $(1\ 000 \pm 5)$ mm of the conical striker described in 5.6.3.4.

4.2.3 Retention system strength

When a helmet is tested by the method described in 5.7, the maximum elongation of the whole system shall not exceed 25 mm.

4.2.4 Retention system effectiveness (roll off)

When a helmet is tested by the method described in 5.8, for the front way and rear way tests, the helmet shall not come off the headform.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5 Test methods**5.1 Sampling**

[SIST EN 12492:2012](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012)

[https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012)

[6582413a4db7/sist-en-12492-2012](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-6582413a4db7/sist-en-12492-2012)

For every type of helmet, helmet samples shall be submitted for testing in the condition in which they are offered for sale, including any requisite holes in the shell and any means of attachment for accessories specified by the manufacturer.

No helmet that has been subjected to testing shall be offered for sale.

For every type of helmet, 11 helmet samples are required for the tests (see Table 1):

- 6 of the smallest size of the range of the helmet type; and
- 5 of the largest size of the range of the helmet type.

5.2 Helmet adjustment

Before any testing on a headform, the helmet shall be adjusted to the headform size and positioned in accordance with the manufacturer's instructions.

The smallest headform is the smallest size, in accordance with 5.4, which is within the size range specified by the manufacturer for the particular size and type of helmet.

The largest headform is the largest size, in accordance with 5.4, which is within the size range specified by the manufacturer for the particular size and type of helmet.

5.3 Conditioning

5.3.1 General

Before any testing the helmet shall be conditioned in accordance with the conditioning defined in Table 1 and the relevant specifications defined in 5.3.2 to 5.3.4.

Table 1 — Conditioning of test samples and size of test headforms

	Stabilizing procedure	UV ageing	Thermal plus +35 °C	Thermal minus -20 °C	Ambient +20 °C	Helmet N°
Top impact	Yes	Smallest	Largest	Largest		1-2-3
Front impact	Yes	Size and conditioning to be chosen by the laboratory				4
Side impact	Yes	Size and conditioning to be chosen by the laboratory				5
Back impact	Yes	Size and conditioning to be chosen by the laboratory				6
Penetration	Yes	Largest	Smallest	Smallest		7-8-9
Retention strength	Yes	--	--	--	Smallest	10
Roll off front and back	Yes	--	--	--	Smallest	11

5.3.2 U.V. ageing

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.3.2.1 Apparatus

A high pressure xenon 450 Watt lamp with quartz casing, operated in accordance with the lamp manufacturer's instructions.

[SIST EN 12492:2012](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-11e1-40507900000000000000)

[https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-](https://standards.iteh.ai/catalog/standards/sist/aa6be225-8f0d-4102-be17-11e1-40507900000000000000)

A means to support the helmet so that it is exposed to the radiation.

5.3.2.2 Procedure

Secure the helmet so that the vertical axis through the crown of the helmet (as worn) is perpendicular to the axis of the lamp and the distance between the crown of the helmet and the axis of the lamp is (150 ± 5) mm.

Expose the helmet to the radiation for (400 ± 4) h. It shall then be removed and allowed to return to laboratory ambient conditions.

NOTE The method described in Annex A may be used as an alternative.

5.3.3 'Thermal plus' conditioning

The helmet shall be exposed to a temperature of (35 ± 2) °C for between 4 h and 24 h.

5.3.4 'Thermal minus' conditioning

The helmet shall be exposed to a temperature of (-20 ± 2) °C for between 4 h and 24 h.

5.4 Headforms

The head forms used shall comply with EN 960:2006. The sizes in Table 2 shall be used, except for determination of shock absorbing capacity, for which only size designations 495, 535, 575, 605 and 625 shall be used.