



SLOVENSKI STANDARD

SIST EN 13087-10:2012

01-julij-2012

Nadomešča:

SIST EN 13087-10:2001

Varovalne čelade - Preskusne metode - 10. del: Odpornost proti toplotnemu sevanju

Protective helmets - Test methods - Part 10: Resistance to radiant heat

Schutzhelme - Prüfverfahren - Teil 10: Beständigkeit gegen Strahlungswärme

Casques de protection - Méthodes d'essai - Partie 10: Résistance à la chaleur radiante

Ta slovenski standard je istoveten z: EN 13087-10:2012

ICS:

13.340.20 Varovalna oprema za glavo Head protective equipment

SIST EN 13087-10:2012

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13087-10:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13087-10

February 2012

ICS 13.340.20

Supersedes EN 13087-10:2000

English Version

Protective helmets - Test methods - Part 10: Resistance to radiant heat

Casques de protection - Méthodes d'essai - Partie 10:
Résistance à la chaleur radiante

Schutzhelme - Prüfverfahren - Teil 10: Beständigkeit gegen
Strahlungswärme

This European Standard was approved by CEN on 17 December 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 13087-10:2012](https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012)

<https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Prerequisites	5
5 Methods	5
5.1 General.....	5
5.2 Principle.....	6
5.3 Apparatus	6
5.3.1 General.....	6
5.3.2 Heater.....	6
5.3.3 Calibrated calorimeter/radiometer	6
5.3.4 Headform	6
5.3.5 Temperature sensing elements.....	6
5.4 Procedure	7
5.5 Report	7
Annex A (normative) Test results – Uncertainty of measurement.....	9
Annex B (informative) Significant technical changes between this European Standard and EN 13087-10:2000.....	10
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 89/686/EEC Personal Protective Equipment	11

Foreword

This document (EN 13087-10:2012) has been prepared by Technical Committee CEN/TC 158 "Head protection", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13087-10:2000.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Annex B provides details of significant technical changes between this European Standard and the previous edition.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This European Standard consists of ten parts as follows:

Part 1 : Conditions and conditioning;

[SIST EN 13087-10:2012](#)

Part 2 : Shock absorption;

<https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012>

Part 3 : Resistance to penetration;

Part 4 : Retention system effectiveness;

Part 5 : Retention system strength;

Part 6 : Field of vision;

Part 7 : Flame resistance;

Part 8 : Electrical properties;

Part 9 : Mechanical rigidity¹;

Part 10 : Resistance to radiant heat.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

¹ To be published.

Introduction

This European Standard is intended as a supplement to the specific product standards for protective helmets (helmet standards). Test methods may be applicable to complete helmets or parts thereof, and may be referenced in the other helmet standards.

Performance requirements are given in the appropriate helmet standard, as are such details as the number of samples, preconditioning, preparation of samples for the tests, sequence and duration of testing and assessment of test results. If deviations from the test method given in this standard are necessary, these deviations will be specified in the appropriate helmet standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13087-10:2012](https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012)

<https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012>

1 Scope

This European Standard specifies methods of test for protective helmets. The purpose of these tests is to enable assessment of the performance of the helmet as specified in the appropriate helmet standard.

This European Standard specifies the method of test for resistance to radiant heat.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 960:2006, *Headforms for use in the testing of protective helmets*

EN 13087-1, *Protective helmets — Test methods — Part 1: Conditions and conditioning*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in this standard may be found in the appropriate helmet standard.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

4 Prerequisites

In order to implement this part of EN 13087, at least the following parameters shall be specified in the appropriate helmet standard:

- a) performance requirements;
- b) number of samples;
- c) preparation of samples;
- d) sequence of conditioning;
- e) sequence of tests;
- f) the heat flux intensity to be used;
- g) fitting instructions.

5 Methods

5.1 General

Testing shall be performed in ambient conditions specified in EN 13087-1.

The intensity to be used is specified in the helmet standard.

EN 13087-10:2012 (E)

5.2 Principle

Heat radiation of a known intensity from an infra-red source is allowed to fall onto the outer surface of a helmet mounted on an instrumented headform. The temperature of the headform surface is measured.

5.3 Apparatus

5.3.1 General

The apparatus shall include:

- a heater;
- a calibrated radiometer/calorimeter;
- a test headform;
- a set of temperature sensing elements and temperature indicator.

The principle of a suitable apparatus is shown in Figure 1.

5.3.2 Heater

A heater is mounted with its radiating surface horizontal and facing downwards. The radiating surface shall be flat with dimensions (250 ± 5) mm by (250 ± 5) mm.

The peak wavelength of the emitted heat radiation shall be between $2 \mu\text{m}$ and $3 \mu\text{m}$. The intensity of radiation shall be uniform and shall be adjustable.

5.3.3 Calibrated calorimeter/radiometer

A calibrated (see notes) calorimeter/radiometer is mounted with its sensing surface horizontal and facing upwards. It is free to move horizontally so that the centre of its sensing surface can be brought centrally underneath the heater.

NOTE 1 The test equipment should be located away from surfaces which reflect the radiant heat which may fall on them or allow passage of measurable quantities of heat into the test equipment area.

NOTE 2 The effects of draughts should be minimized.

5.3.4 Headform

A headform, constructed of hardwood or of any material with an equivalent thermal conductivity and complying with EN 960:2006, shall be mounted on a movable and adjustable device.

The test site shall be as specified in the helmet standard, corresponding to a nominal 30° lateral inclination of the headform relative to the vertical.

NOTE All supports for headform and radiometer/calorimeter should be of low heat conductivity and reflectivity.

5.3.5 Temperature sensing elements

Three calibrated (see notes) temperature sensing elements (each preferably consisting of a thermocouple mounted on a circular copper disc of (7 ± 1) mm diameter) are secured by electrically insulating adhesive to the headform surface on the side to be exposed to the heat.

Their centres shall lie within 5 mm of the points defined by the intersection of a transverse vertical plane passing through the test site and:

- a) the central vertical axis;
- b) the AA' plane (as defined in EN 960:2006, 2.4);
- c) midway between position a) and b) measured along the headform surface.

NOTE Suitable ISO or CEN standards should be selected, when available, for these calibration requirements.

5.4 Procedure

5.4.1 Mount the helmet on the headform in the manner it is intended to be worn on the head, with the test site lying centrally beneath the heater and measure the distance, d (see Figure 1) from the radiating surface. Record the temperatures on the headform.

5.4.2 Move the helmeted headform aside to allow setting of the radiant heat intensity.

5.4.3 Move the radiometer/calorimeter centrally beneath the heater and adjust the distance, d (see Figure 1) from the radiating surface to correspond with that measured in 5.4.1. Adjust the heater controls until the heat flux intensity measured is as specified in the appropriate helmet standard. Remove the radiometer/calorimeter.

5.4.4 Replace the helmeted headform in the position determined in 5.4.1 and expose the helmet to the radiant heat for (180 ± 2) s. At the end of this period, record the temperatures on the headform.

5.4.5 Switch off the heater and remove the helmet. Allow the helmet to cool to ambient temperature for at least 4 h before performing any further tests.

5.5 Report

[SIST EN 13087-10:2012
https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012](https://standards.iteh.ai/catalog/standards/sist/dee430bb-501a-4d83-a0a1-504c072ca088/sist-en-13087-10-2012)

Report the maximum difference between the temperatures measured in 5.4.1 and 5.4.4.