



SLOVENSKI STANDARD
kSIST FprEN 548:2010

01-november-2010

Netekstilne talne obloge - Specifikacija za linolej brez vzorca in z vzorcem

Resilient floor coverings - Specification for plain and decorative linoleum

Elastische Bodenbeläge - Spezifikation für Linoleum mit und ohne Muster

Revêtements de sol résilients - Spécification pour le linoléum uni et décoratif

Ta slovenski standard je istoveten z: FprEN 548

ICS:

97.150 Netekstilne talne obloge Non-textile floor coverings

kSIST FprEN 548:2010 **en,fr,de**

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
FprEN 548

August 2010

ICS 97.150

Will supersede EN 548:2004

English Version

Resilient floor coverings - Specification for plain and decorative linoleum

Revêtements de sol résilients - Spécification pour le linoléum uni et décoratif

Elastische Bodenbeläge - Spezifikation für Linoleum mit und ohne Muster

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 134.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Identification.....	5
5	Requirements	5
5.1	General requirements.....	5
5.2	Classification requirements.....	6
6	Marking	8
Annex A (informative) Optional properties		9
Bibliography		10

Foreword

This document (FprEN 548:2010) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by BSI.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 548:2004.

FprEN 548:2010 (E)

1 Scope

This European Standard specifies the characteristics of plain and decorative linoleum, supplied as either tiles or rolls.

To encourage the consumer to make an informed choice, the standard includes a classification system based on intensity of use, which shows where resilient floor coverings should give satisfactory service (see EN 685). It also includes requirements for marking.

The term 'linoleum' is frequently incorrectly applied to a range of floor coverings, often to those based on polyvinyl chloride or rubber. Such materials are not included in this standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 426, *Resilient floor coverings — Determination of width, length, straightness and flatness and of sheet material*

EN 427, *Resilient floor coverings — Determination of the side length, squareness and straightness of tiles*

EN 428, *Resilient floor coverings — Determination of overall thickness*

EN 429, *Resilient floor coverings — Determination of the thickness of layers*

EN 430, *Resilient floor coverings — Determination of mass per unit area*

EN 433, *Resilient floor coverings — Determination of residual indentation after static loading*

EN 435, *Resilient floor coverings — Determination of flexibility*

EN 669, *Resilient floor coverings — Determination of dimensional stability linoleum tiles, caused by changes in atmospheric humidity*

EN 670, *Resilient floor coverings — Identification of linoleum and determination of cement content and ash residue*

EN 685, *Resilient, textile and laminate floor coverings — Classification*

EN ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light (Xenon arc fading lamp test) (ISO 105-B02:1994, including amendment 1:1998)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
linoleum cement
binder in linoleum, consisting of a mixture of linseed oil and/or other vegetable drying oils, rosin and drying oil catalysts, which is converted to a semi-elastic mass by an oxidative curing process

3.2**linoleum**

product produced by calendaring one or more layers of a homogeneous mixture of linoleum cement, cork and/or woodflour, pigments and inorganic fillers containing a fibrous reinforcement and/or a fibrous backing. The product is then converted into its final form by an oxidative curing process

NOTE The only chemical cross-linking bondings in linoleum will be those which are formed during the oxidation process.

3.3**surface layer**

layer or layers with the same binder above a support material or backing

4 Identification

Linoleum shall be identified by its ability to be disintegrated in 0,5 mol/l potassium hydroxide/methanol solution and by the determination of cement content and ash residue.

The minimum amount of linoleum cement shall be 30 % when tested in accordance with EN 670.

The maximum amount of inorganic filler (ash residue) shall be 50 % when tested in accordance with EN 670.

5 Requirements**5.1 General requirements**

All classes of plain and decorative linoleum shall comply with the appropriate general requirements specified in Table 1, when tested in accordance with the methods given therein.

Table 1 — General requirements

Characteristic	Requirement	Test method
Roll form:		EN 426
length width	m mm Not less than the nominal values	
Tiles:		EN 427
side length	mm Deviation $\leq 0,15$ % of nominal length up to 0,5 mm maximum	
squareness and straightness	mm Deviation allowed at any point	
for side length ≤ 400 mm > 400 mm	$\leq 0,25$ $\leq 0,35$	
Dimensional stability of tiles caused by changes of atmospheric humidity	Variation $\leq 0,1$	EN 669
Overall thickness	mm	EN 428
average individual values	Nominal value $\pm 0,15$ Nominal value $\pm 0,20$	

Table 1 (continued)

Characteristic	Requirement	Test method
Calendared surface layer	minimum 0,80 mm	EN 429
Effect of a castor chair	No disturbance to the surface other than slight change in appearance and no delamination shall occur	EN 425
Mass per unit area average	g/m^2 Nominal value $\pm 10\%$	EN 430
Residual indentation after static loading average nominal thickness: $\leq 3,2$ mm $\geq 4,0$ mm	 $\leq 0,15$ $\leq 0,20$	EN 433
Flexibility of sheets Thickness (nominal) 2,0 mm 2,5 mm 3,2 mm 4,0 mm	Mandrel diameter 30 mm 40 mm 50 mm 60 mm Shall show no sign of cracking when bent around the appropriate mandrel	EN 435 Method A
Colour fastness to artificial light	6 minimum	EN ISO 105-B02: Method 3 ^a
^a Before comparing the test piece, expose the reference sample together with the Blue Wool cloth to the xenon arc lamp, until a contrast is produced on Blue Wool Reference 2 equal to the contrast illustrated by Grey Scale 3. This step is necessary to remove the inherent 'stove yellowing' of linoleum before the stable colouration is achieved.		

Plain and decorative linoleum complying with the requirements of this standard are suitable for use with castor chairs.

5.2 Classification requirements

The classification scheme for resilient floor coverings is described in EN 685. The requirements for plain and decorative linoleum in accordance with this scheme are related to the nominal overall thickness of the linoleum, as shown in Table 2.