



SLOVENSKI STANDARD
kSIST FprEN 652:2010

01-november-2010

Netekstilne talne obloge - Polivinilkloridne talne obloge s hrbtiščem na osnovi plute - Specifikacija

Resilient floor coverings - Polyvinyl chloride floor coverings with cork-based backing - Specification

Elastische Bodenbeläge - Polyvinylchlorid-Bodenbeläge mit einem Rücken auf Korkbasis - Spezifikation

Revêtements de sol résilients - Revêtements de sol à base de polychlorure de vinyle sur support à base de liège - Spécifications

Ta slovenski standard je istoveten z: FprEN 652

ICS:

97.150 Netekstilne talne obloge Non-textile floor coverings

kSIST FprEN 652:2010

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
FprEN 652

August 2010

ICS 97.150

Will supersede EN 652:1996

English Version

Resilient floor coverings - Polyvinyl chloride floor coverings with cork-based backing - Specification

Revêtements de sol résilients - Revêtements de sol à base
de polychlorure de vinyle sur support à base de liège -
Spécifications

Elastische Bodenbeläge - Polyvinylchlorid-Bodenbeläge mit
einem Rücken auf Korkbasis - Spezifikation

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 134.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Requirement	5
4.1	General requirements	5
4.2	Classification requirements	5
4.2.1	Wear groups classification	5
4.2.2	Level of use classification	5
5	Marking	10
Annex A (informative) Optional properties		11
Annex B (informative) Additional methods of test		12
Bibliography		13

Foreword

This document (FprEN 652:2010) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by BSI.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 652:1996.

FprEN 652:2010 (E)

1 Scope

This European Standard specifies the characteristics of floor coverings based on polyvinyl chloride and modifications thereof with a cork-based backing, supplied in either tile or roll form.

To encourage the consumer to make an informed choice, the standard includes a classification system (see EN 685) based on intensity of use, which shows where these floor coverings should give satisfactory service. It also specifies requirements for marking

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 424, *Resilient floor coverings — Determination of the effect of the simulated movement of a furniture leg*

EN 425, *Resilient and laminate floor coverings — Castor chair test*

EN 426, *Resilient floor coverings — Determination of width, length, straightness and flatness of sheet material*

EN 427, *Resilient floor coverings — Determination of the side length, squareness and straightness of tiles*

EN 428, *Resilient floor coverings — Determination of overall thickness*

EN 429, *Resilient floor coverings — Determination of the thickness of layers*

EN 430, *Resilient floor coverings — Determination of mass per unit area*

EN 431, *Resilient floor coverings — Determination of peel resistance*

EN 433, *Resilient floor coverings — Determination of residual indentation after static loading*

EN 434, *Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat*

EN 436, *Resilient floor coverings — Determination of density*

EN 660-2, *Resilient floor coverings — Determination of wear resistance — Part 2: Frick-Taber test*

EN 684, *Resilient floor coverings — Determination of seam strength*

EN 685, *Resilient, textile and laminate floor coverings — Classification*

EN ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02:1994, including amendment 1:1998)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

polyvinyl chloride floor covering

floor covering with surface layers which are produced using polyvinyl chloride (and modifications thereof) as binder

3.2

polyvinyl chloride floor covering with cork-based backing

floor covering with a homogeneous or heterogeneous polyvinyl chloride surface layer over a layer of corkment or of cork with a polyvinyl chloride binder

4 Requirement

4.1 General requirements

Floor coverings described in this standard shall conform to the appropriate general requirements specified in Table 1, when tested in accordance with the methods given therein.

4.2 Classification requirements

4.2.1 Wear groups classification

Floor coverings described in this standard shall be classified in the appropriate wear group i.e. group T, P, M or F specified in Table 2, when tested in accordance with EN 660-2.

Floor coverings with a transparent wear layer are *a priori* group T and need not be tested.

4.2.2 Level of use classification

Floor coverings described in this standard shall be classified as suitable for different levels of intensity of use in accordance with the performance requirements

specified in Table 3, when tested with the methods given therein. Classification shall comply with the scheme specified in EN 685.

Table 1 — General requirements

Characteristic	Requirement	Test method
Roll form: length width m mm	Not less than the nominal values	EN 426
Tiles: side length mm squareness and straightness for side length: mm ≤ 400 mm > 400 mm > 400 mm (intended for welding)	Deviation ≤ 0,13% of nominal length up to 0,5 mm maximum Deviation allowed at any point ≤ 0,25 ≤ 0,35 ≤ 0,50	EN 427
Overall thickness: average mm individual results	Nominal value + 0,18 - 0,15 Average value ± 0,20	EN 428
Thickness of cork-based backing mm	Nominal thickness shall be stated	EN 429
Total mass per unit area (average) g/m ²	Nominal value + 13% - 10%	EN 430
Density of the wear layer (average) kg/m ³	Nominal value ± 0,50	EN 436
Residual indentation after static loading (average) mm	≤ 0,40	EN 433
Dimensional stability after exposure to heat: % sheets and tiles intended for welding tiles intended for dry-joint laying	≤ 0,4 ≤ 0,25	EN 434
Curling after exposure to heat: mm sheets and tiles (intended for welding) tiles (intended for dry-joint laying)	≤ 8 ≤ 2	EN 434
Colour fastness to artificial light	6 minimum	EN ISO 105-B02 Method 3 ^a
Peel resistance N/50mm average individual results	≥ 50 ≥ 40	EN 431
^a Expose a full size of test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.		