



SLOVENSKI STANDARD
SIST EN 13501-1:2007+A1:2009
01-december-2009

**Požarna klasifikacija gradbenih proizvodov in elementov stavb - 1. del:
Klasifikacija po podatkih iz preskusov odziva na ogenj**

Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests

Klassifizierung von Bauprodukten und Bauarten zu ihrem Brandverhalten - Teil 1: Klassifizierung mit den Ergebnissen aus den Prüfungen zum Brandverhalten von Bauprodukten

standards.iteh.ai

Classement au feu des produits et éléments de construction - Partie 1: Classement à partir des données d'essais de réaction au feu

<https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009>

Ta slovenski standard je istoveten z: EN 13501-1:2007+A1:2009

ICS:

13.220.50	Požarna odpornost gradbenih materialov in elementov	Fire-resistance of building materials and elements
-----------	---	--

SIST EN 13501-1:2007+A1:2009 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13501-1:2007+A1:2009

<https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13501-1:2007+A1

September 2009

ICS 13.220.50

Supersedes EN 13501-1:2007

English Version

Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests

Classement au feu des produits et éléments de construction - Partie 1: Classement à partir des données d'essais de réaction au feu

Klassifizierung von Bauprodukten und Bauarten zu ihrem Brandverhalten - Teil 1: Klassifizierung mit den Ergebnissen aus den Prüfungen zum Brandverhalten von Bauprodukten

This European Standard was approved by CEN on 27 November 2006 and includes Amendment 1 approved by CEN on 17 July 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	5
Introduction	6
1 Scope	7
2 Normative references	7
3 Terms, definitions and symbols	7
3.1 Terms and definitions	7
3.2 Symbols and abbreviations	12
4 Classes of reaction to fire performance	13
5 A₁ Test methods and field of application rules A₁	13
5.1 General	13
5.2 Non-combustibility test (EN ISO 1182)	13
5.3 Heat of combustion test (EN ISO 1716)	13
5.4 Single burning item test (EN 13823)	13
5.5 Ignitability test (EN ISO 11925-2)	14
5.6 Determination of the burning behaviour of floorings, using a radiant heat source (EN ISO 9239-1)	14
6 A₁ Principles for testing, specimen preparation and field of application A₁	14
6.1 General requirements for specimen preparation	14
6.2 Specific requirements for non-combustibility and heat of combustion testing	14
6.3 Specific requirements for the single burning item test, the ignitability test and the test for the determination of the burning behaviour of floorings, using a radiant heat source	14
6.4 A₁ Field of application A₁	15
7 Number of tests for classification	15
8 Testing of construction products, excluding floorings (see Table 1)	16
8.1 Class E	16
8.2 Classes D, C, B	17
8.3 Classes A ₂ , A ₁	17
8.3.1 Homogenous products	17
8.3.2 Non-homogeneous products	17
8.3.3 Class A ₂ products	17
8.4 Additional classifications s ₁ , s ₂ , s ₃ for smoke production	17
8.5 Additional classifications d ₀ , d ₁ , d ₂ for flaming droplets/particles	17
9 Testing of floorings (see Table 2)	17
9.1 Class E _{fi}	17
9.2 Classes D _{fi} , C _{fi} , B _{fi}	18
9.3 Classes A _{2fi} , A _{1fi}	18
9.3.1 Homogeneous products	18
9.3.2 Non-homogeneous products	18
9.3.3 Class A _{2fi} products	18
9.4 Additional classifications s ₁ , s ₂ for smoke production	18
10 Testing of linear pipe thermal insulation products (see Table 3)	18
10.1 Class E _L	18
10.2 Classes D _L , C _L , B _L	18
10.3 Classes A _{2L} , A _{1L}	19
10.3.1 Homogenous products	19

10.3.2	Non-homogeneous products	19
10.3.3	Class A _{2L} products	19
10.4	Additional classifications s ₁ , s ₂ , s ₃ for smoke production	19
10.5	Additional classifications d ₀ , d ₁ , d ₂ for flaming droplets/particles	19
11	Classification criteria for construction products, excluding floorings (see Table 1)	19
11.1	General	19
11.2	Class F	20
11.3	Class E	20
11.4	Class D	20
11.5	Class C	20
11.6	Class B	21
11.7	Class A ₂	21
11.7.1	General	21
11.7.2	Homogeneous products	21
11.7.3	Non-homogeneous products	21
11.8	Class A ₁	22
11.8.1	Homogeneous products	22
11.8.2	Non-homogeneous products	22
11.9	Additional classifications s ₁ , s ₂ , s ₃ for smoke production	24
11.9.1	General	24
11.9.2	s ₁	24
11.9.3	s ₂	24
11.9.4	s ₃	24
11.10	Additional classifications d ₀ , d ₁ , d ₂ for flaming droplets and/or particles	24
11.10.1	Products classified A ₂ , B, C, D	24
11.10.2	Products classified E	24
12	Classification criteria for floorings (see Table 2)	25
12.1	General	25
12.2	Class F _{fl}	25
12.3	Class E _{fl}	25
12.4	Class D _{fl}	25
12.5	Class C _{fl}	26
12.6	Class B _{fl}	26
12.7	Class A _{2fl}	26
12.7.1	General	26
12.7.2	Homogeneous products	26
12.7.3	Non-homogeneous products	27
12.8	Class A _{1fl}	27
12.8.1	Homogeneous products	27
12.8.2	Non-homogeneous products	28
12.9	Additional classifications s ₁ , s ₂ for smoke production	28
12.9.1	General	28
12.9.2	s ₁	28
12.9.3	s ₂	28
13	Classification criteria for linear pipe thermal insulation products (see Table 3)	29
13.1	General	29
13.2	Class F _L	29
13.3	Class E _L	29
13.4	Class D _L	29
13.5	Class C _L	30
13.6	Class B _L	30
13.7	Class A _{2L}	30
13.7.1	General	30
13.7.2	Homogeneous products	30
13.7.3	Non-homogeneous products	31
13.8	Class A _{1L}	32
13.8.1	Homogeneous products	32
13.8.2	Non-homogeneous products	32

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13501-1:2007+A1:2009

[https://standards.iteh.ai/catalog/standards/sist/0206ff1-1-7e70-4cc2-b2eb-](https://standards.iteh.ai/catalog/standards/sist/0206ff1-1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009)

[5f7543360576/sist-en-13501-1-2007a1-2009](https://standards.iteh.ai/catalog/standards/sist/0206ff1-1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009)

EN 13501-1:2007+A1:2009 (E)

13.9	Additional classifications s1, s2, s3 for smoke production	33
13.9.1	General	33
13.9.2	s1	33
13.9.3	s2	33
13.9.4	s3	33
13.10	Additional classifications d0, d1, d2 for flaming droplets and/or particles	33
13.10.1	Products classified A _{2L} , B _L , C _L , D _L	33
13.10.2	Products classified E _L	34
14	Presentation of classification	34
14.1	Construction products, excluding floorings and linear pipe thermal insulation products	34
14.2	Floorings	35
14.3	Linear pipe thermal insulation products	35
15	Field of application of the classification	36
16	Classification report	36
16.1	General	36
16.2	Content and format	36
Annex A	(informative) Background information for the application of the Commission Decision of 8 February 2000 implementing Council Directive 89/106/EEC as regards the classification of the reaction to fire performance of construction products	41
A.1	General	41
A.2	Assumptions	41
A.3	Reference fire situations	42
A.4	Relationship between classes and reference fire situations	44
Annex B	(normative) Reaction to fire classification report	48
Bibliography	53

[SIST EN 13501-1:2007+A1:2009](https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009)

<https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009>

Foreword

This document (EN 13501-1:2007+A1:2009) has been prepared by Technical Committee CEN/TC 127 "Fire safety in buildings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2010, and conflicting national standards shall be withdrawn at the latest by March 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1, approved by CEN on 2009-07-17.

This document supersedes A1 EN 13501-1:2007 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

In addition to editorial corrections this document includes the reaction to fire classification procedure for linear pipe thermal insulation products.

A1 Amendment 1 provides for the use of extended application reports in the classification procedure. A1

CEN, CENELEC and EOTA committees preparing technical specifications, which contain performance requirements against reaction to fire tests, should make reference to the reaction to fire classification given in this European Standard and not refer directly to any specific fire test method.

EN 13501 *Fire classification of construction products and building elements* consists of the following parts:

Part 1: *Classification using data from reaction to fire tests*

Part 2: *Classification using data from fire resistance tests, excluding ventilation services*

Part 3: *Classification using data from fire resistance tests on products and elements used in building service installations: fire resisting ducts and fire dampers*

Part 4: *Classification using data from fire resistance tests on components of smoke control systems*

Part 5: *Classification using data from external fire exposure to roofs tests*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 13501-1:2007+A1:2009 (E)**Introduction**

The aim of this European Standard is to define a harmonized procedure for the classification of reaction to fire of construction products. This classification is based on the test procedures listed in ^{A1} Clause 5 and the relevant field of application procedures ^{A1}.

This European Standard has been prepared in support of the second essential requirement in the EC Construction Products Directive (89/106/EEC) and as detailed in the Interpretative Document Number 2: Safety in case of fire (OJ C62 Vol. 37).

Background information on the Commission Decision regarding the classification of the reaction to fire performance of construction products is given in Annex A.

The European Commission has drawn up a list of products which, under specified conditions, can be considered to be class A1 without testing. This information is given in the Commission Decision 96/603/EC (OJ L 267 19.10.1966 p23) as amended by 2000/605/EC (OJ L 258 12.10.2000 p36) and 2003/424/EC (OJ L 144 12.6.2003 p9).

Additionally there is a procedure by which certain products can be assigned a particular fire classification without the need for testing. Such products have well established reaction to fire performance and have been agreed by the Standing Committee on Construction. Agreements relating to such products which may be 'classified without further testing' (CWFT) are published in the Official Journal of the EC and are listed on the Nando-CPD database on the EC website (<http://europa.eu.int/comm/enterprise/construction>).

Parts 2, 3 and 4 of this European Standard are concerned with classification resulting from fire resistance tests. Part 5 covers classification resulting from tests for external fire exposure to roofs.

^{A1} NOTE 1 ^{A1} If the classification based on the tests and criteria given in Tables 1 and 2 is not appropriate, one or more reference scenarios (representative scale tests typifying agreed hazard scenarios) can be called upon within the context of a defined procedure. This procedure is intended to be the subject of a future European Standard or Commission Decision, on the basis of an agreement between the Commission and the Member States, in consultation with CEN/CENELEC and EOTA.

^{A1} NOTE 2 Test reports constitute the basis for extended application reports as explained in prEN 15725. ^{A1}

1 Scope

This European Standard provides the reaction to fire classification procedure for all construction products, including products incorporated within building elements.

Products are considered in relation to their end use application.

This document applies to three categories, which are treated separately in this European Standard:

- construction products, excluding floorings and linear pipe thermal insulation products;
- floorings;
- linear pipe thermal insulation products.

NOTE The treatment of some families of products is still under review and can necessitate amendments to this European Standard (see European Commission Decision 2000/147/EC).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

^[A1] prEN 15725, *Extended application reports on the fire performance of construction products and building elements* <https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-5f7543360576/sist-en-13501-1-2007a1-2009>

CEN/TS 15117, *Guidance on direct and extended application* ^[A1]

EN ISO 1182, *Reaction to fire tests for building products — Non-combustibility test (ISO 1182:2002)*

EN ISO 1716, *Reaction to fire tests for building products — Determination of the heat of combustion (ISO 1716:2002)*

EN ISO 9239-1, *Reaction to fire tests for floorings — Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002)*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2:2002)*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE Where the definitions are identical to those in EN ISO 13943, this is indicated.

EN 13501-1:2007+A1:2009 (E)**3.1.1****product**

material, element or component about which information is required

3.1.2**material**

single basic substance or uniformly dispersed mixture of substances, e.g. metal, stone, timber, concrete, mineral wool with uniformly dispersed binder or polymers

3.1.3**homogeneous product**

product consisting of a single material, having uniform density and composition throughout the product

3.1.4**non-homogeneous product**

product that does not satisfy the requirements of a homogeneous product.

NOTE

It is a product composed of one or more components, substantial and/or non-substantial.

3.1.5**substantial component**

material that constitutes a significant part of a non-homogeneous product. A layer with a mass/unit area $\geq 1,0 \text{ kg/m}^2$ or a thickness $\geq 1,0 \text{ mm}$ is considered to be a substantial component

3.1.6**non-substantial component**

material that does not constitute a significant part of a non-homogeneous product. A layer with a mass/unit area $< 1,0 \text{ kg/m}^2$ and a thickness $< 1,0 \text{ mm}$ is considered to be a non-substantial component

NOTE

Two or more non-substantial layers that are adjacent to each other (i.e. with no substantial component(s) in between the layers) are regarded as one non-substantial component when they collectively comply with the requirements for a layer being a non-substantial component

3.1.7**internal non-substantial component**

non-substantial component that is covered on both sides by at least one substantial component

3.1.8**external non-substantial component**

non-substantial component that is not covered on one side by a substantial component

3.1.9**flooring**

upper layer(s) of a floor, comprising any surface finish with or without an attached backing and with any accompanying underlay, interlayer and adhesives

3.1.10**linear pipe thermal insulation product**

length of insulation product designed to fit around pipes, with a maximum outer insulation diameter of 300 mm and not intended for use with cylindrical ducts

3.1.11**substrate**

product which is used immediately beneath the product about which information is required.

NOTE

For flooring, it is the floor on which it is mounted or the material which represents this floor.

3.1.12**standard substrate**

product which is representative of the substrate used in end-use applications

3.1.13**end use application**

real application of a product, in relation to all aspects that influence the behaviour of that product under different fire situations.

NOTE It covers aspects such as its quantity, orientation, position in relation to other adjacent products, and its method of fixing.

3.1.14**fire performance**

response of an item when exposed to a specific fire (EN ISO 13943)

3.1.15**reaction to fire**

response of a product in contributing by its own decomposition to a fire to which it is exposed, under specified conditions

3.1.16**fire scenario**

detailed description of conditions, including environmental, of one or more stages from before ignition to after completion of combustion at a specific location or in a real scale simulation (EN ISO 13943)

3.1.17**reference scenario**

hazard situation used as a reference for a given test method or classification system

3.1.18**fire situation**

stage in the development of a fire, characterised by the nature, severity and size of the thermal attack on the products involved

3.1.19**combustion**

exothermic reaction of a substance with an oxidizer (EN ISO 13943)

NOTE Combustion generally emits effluent accompanied by flames and/or visible light.

3.1.20**heat of combustion**

thermal energy produced by combustion of unit of mass of a given substance (EN ISO 13943)

NOTE It is expressed in joules per kilogram.

3.1.21**gross heat of combustion (PCS)**

heat of combustion of a substance when the combustion is complete and any produced water is entirely condensed under specified conditions (EN ISO 13943)

3.1.22**net heat of combustion (PCI)**

heat of combustion of a substance when the combustion is complete and any produced water is in the vapour state under specified conditions (EN ISO 13943)

NOTE The net heat of combustion may be calculated from the gross heat of combustion.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13501-1:2007+A1:2009](https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-ef7c7a110101/en-13501-1-2007-a1-2009)

[https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-](https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-ef7c7a110101/en-13501-1-2007-a1-2009)

[ef7c7a110101/en-13501-1-2007-a1-2009](https://standards.iteh.ai/catalog/standards/sist/0206ffc1-7e70-4cc2-b2eb-ef7c7a110101/en-13501-1-2007-a1-2009)

EN 13501-1:2007+A1:2009 (E)**3.1.23****contribution to fire**

energy released by a product influencing the fire growth both in pre- and post-flashover situations

3.1.24**ignitability**

measure of the ease with which an item can be ignited, under specified conditions (EN ISO 13943)

3.1.25**heat release**

calorific energy which is released by the combustion of an item under specified conditions (EN ISO 13943)

3.1.26**small fire attack**

thermal attack produced by a small flame like a match or a lighter

3.1.27**level of exposure**

intensity, duration and extent of the thermal attack on a product

3.1.28**flame spread**

vertical flame spread (F_s) is the highest point reached by the flame tip, as measured in the test in EN ISO 11925-2

NOTE Lateral flame spread is the furthest extent of travel of a sustained flame, as measured in the EN 13823 test.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.1.29**sustained flaming**

existence of flame on top over a surface for a minimum period of time (EN ISO 13943)

SIST EN 13501-1:2007+A1:2009

5f7543360576/sist-en-13501-1-2007a1-2009

NOTE The period of time required will vary across different standards, but it is usually of the order of 10 s.

3.1.30**fully developed fire**

state of total involvement of combustible materials in a fire (EN ISO 13943)

3.1.31**flashover**

transition to a state of total surface involvement in a fire of combustible materials within an enclosure (EN ISO 13943)

3.1.32**flaming droplets/particles**

material separating from the specimen during the fire test and continuing to flame for a minimum period as described by the test method

3.1.33**critical heat flux at extinguishment (CHF)**

incident heat flux (kW/m^2) at the surface of a specimen at the point where the flame ceases to advance and may subsequently go out.

NOTE The heat flux value reported is based on interpolations of measurements with a non-combustible calibration board.

3.1.34**heat flux at X minutes (HF-X)**

total heat flux (kW/m^2) received by the specimen at the most distant spread of flame position observed during the first X minutes of the test

3.1.35**critical heat flux (CHF)**

heat flux at which the flame extinguishes (CHF) or the heat flux after a test period of 30 min (HF-30), whichever is the lower value

NOTE It is the flux corresponding with the furthest extent of spread of flame within 30 min.

3.1.36**smoke hazard**

potential for injury and/or damage from smoke

3.1.37**FIGRA**

fire growth rate index used for classification purposes

EXAMPLE:

For the classes A2 and B, $FIGRA = FIGRA_{0,2MJ}$

For the classes C and D, $FIGRA = FIGRA_{0,4MJ}$

For the classes A2L, BL, and CL, $FIGRA = FIGRA_{0,2MJ}$

For the class DL, $FIGRA = FIGRA_{0,4MJ}$

iTech STANDARD PREVIEW
(standards.itech.ai)

3.1.38**FIGRA_{0,2MJ}**

maximum of the quotient of heat release rate from the specimen and the time of its occurrence using a THR-threshold of 0,2 MJ

NOTE $FIGRA_{0,2MJ}$ is defined in more detail in EN 13823.

3.1.39**FIGRA_{0,4MJ}**

maximum of the quotient of heat release rate from the specimen and the time of its occurrence using a THR threshold of 0,4 MJ

NOTE The $FIGRA_{0,4MJ}$ is defined in more detail in EN 13823.

3.1.40**SMOGRA**

smoke growth rate. The maximum of the quotient of smoke production rate from the specimen and the time of its occurrence

NOTE The SMOGRA is defined in more detail in EN 13823.

3.1.41**direct field of application**

outcome of a process (involving the application of defined rules) whereby a test result is deemed to be equally valid for variations in one or more of the product properties and/or intended end use applications

EN 13501-1:2007+A1:2009 (E)**3.1.42****extended field of application**

outcome of a process (involving the application of defined rules that may incorporate calculation procedures) that predicts, for a variation of a product property and/or its intended end use application(s), a test result on the basis of one or more test results to the same test standard

3.1.43**extended application result**

predicted result for performance parameter obtained following the process of extended field of application

3.1.44**extended application report**

document reporting extended application results, including all details of the process leading to those results, prepared in accordance with prEN 15725 ^(A1)

3.2 Symbols and abbreviations

The symbols and notations correspond to those given in the appropriate test method.

ΔT	temperature rise [K]
Δm	mass loss [%]
F_s	flame spread [mm]
<i>FIGRA</i>	fire growth rate index used for classification purposes
<i>FIGRA</i> _{0,2MJ}	fire growth rate index at <i>THR</i> threshold of 0,2 MJ
<i>FIGRA</i> _{0,4MJ}	fire growth rate index at <i>THR</i> threshold of 0,4 MJ
<i>LFS</i>	lateral flame spread [m]
<i>PCS</i>	gross calorific potential [MJ/kg or MJ/m ²]
<i>PCI</i>	net calorific potential [MJ/kg or MJ/m ²]
<i>SMOGRA</i>	smoke growth rate
t_f	duration of sustained flaming [s]
<i>THR</i> _{600s}	total heat release within 600 s [MJ]
<i>TSP</i> _{600s}	total smoke production within 600 s [m ²]
m'	mean value of the set of results of a continuous parameter determined in accordance with the relevant test method using the minimum number of tests as specified in the test method
m	mean value of the set of results of a continuous parameter determined in accordance with the procedure in 7.3 and used for classification

4 Classes of reaction to fire performance

The classes with their corresponding fire performance are given in:

- Table 1 for construction products excluding floorings;
- Table 2 for floorings;
- Table 3 for linear pipe thermal insulation products.

Products classified in a given class are deemed to satisfy all the requirements of any lower class.

Pipe-insulation and insulation of cylindrical ducts with a maximum outer insulation diameter larger than 300 mm and insulation product intended to be used on flat surfaces shall be tested as prescribed in Table 1.

A classification can only be obtained by undertaking $\boxed{A_1}$ the tests or the extended application process required $\boxed{A_1}$ for that particular product. A classification obtained for one product type, e.g. floorings, cannot be interpreted or accepted in a different classification system.

5 $\boxed{A_1}$ Test methods and field of application rules $\boxed{A_1}$

5.1 General

The following test methods are specified in relation to the envisaged reaction to fire classification. The relevant classification parameters are given in Tables 1, 2 and 3.

$\boxed{A_1}$ Direct and extended application shall be carried out as described in CEN/TS 15117 and in prEN 15725. $\boxed{A_1}$

5.2 Non-combustibility test (EN ISO 1182)

This test identifies products that will not, or not significantly, contribute to a fire, regardless of their end use.

The test is relevant for the classes A1, A2, A1_{fi}, A2_{fi}, A1_L and A2_L.

5.3 Heat of combustion test (EN ISO 1716)

This test determines the potential maximum total heat release of a product when completely burning, regardless of its end use.

The test is relevant for the classes A1, A2, A1_{fi}, A2_{fi}, A1_L and A2_L.

It allows the determination of both the gross heat of combustion (*PCS*) and the net heat of combustion (*PCI*).

5.4 Single burning item test (EN 13823)

This test evaluates the potential contribution of a product to the development of a fire, under a fire situation simulating a single burning item in a room corner near to that product. The test is relevant for the classes A2, A2_L, B, B_L, C, C_L, D and D_L. Under the conditions specified in 8.3.2 the test is also relevant for the class A1.