



Designation: E1797 – 04

# Standard Specification for Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings<sup>1</sup>

This standard is issued under the fixed designation E1797; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers minimum material performance requirements and laboratory test procedures for reinforced liquid coating encapsulation products (single- or multiple-coat systems) for leaded paint in buildings. Performance properties addressed in this specification are:

- 1.1.1 Impact Resistance,
- 1.1.2 Adhesion,
- 1.1.3 Dry Abrasion Resistance,
- 1.1.4 Water Vapor Transmission,
- 1.1.5 Water and Chemical Resistance,
- 1.1.6 Surface Burning Characteristics,
- 1.1.7 Volatile Organic Compound (VOC) Content,
- 1.1.8 Weathering,
- 1.1.9 Aging,
- 1.1.10 Scrub Resistance,
- 1.1.11 Mildew Resistance,
- 1.1.12 Paintability/Repairability,

1.2 This specification does not address the selection of an encapsulation product for specific use conditions. Specific use conditions may require performance values other than those stated in this specification. See Guide E1796 for guidance.

1.3 This specification complements Specification E1795 for non-reinforced liquid coating encapsulation products.

1.4 This specification does not cover the use of encapsulation products on industrial steel structures nor residential exterior coated metal surfaces because no corrosion control requirements are included.

1.5 This specification applies to any liquid-applied product incorporating reinforcement materials as part of the system. Reinforcement materials are continuous fabric or mesh and are applied in the field. These materials are typically applied between a base and top coat. These products are used to

encapsulate a leaded paint surface with the intent of reducing human exposure to lead in paint.

1.6 The results of the test methods included in this specification will not necessarily predict field performance.

1.7 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

D16 Terminology for Paint, Related Coatings, Materials, and Applications

D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels

D1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers

D1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base<sup>3</sup>

D1212 Test Methods for Measurement of Wet Film Thickness of Organic Coatings

D1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes

D1475 Test Method For Density of Liquid Coatings, Inks, and Related Products

D1653 Test Methods for Water Vapor Transmission of Organic Coating Films

D2486 Test Methods for Scrub Resistance of Wall Paints

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.23 on Lead Hazards Associated with Buildings.

Current edition approved April 1, 2004. Published April 2004. Originally approved in 1995. Last previous edition approved in 2003 as E1797 – 03. DOI: 10.1520/E1797-04.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

- D2794** Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)
- D3273** Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber
- D3274** Test Method for Evaluating Degree of Surface Disfigurement of Paint Films by Fungal or Algal Growth, or Soil and Dirt Accumulation

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[ASTM E1797-04](#)

<https://standards.itih.ai/catalog/standards/sist/223dbe0c-49bd-4ecb-919c-868ff3e3fda0/astm-e1797-04>

- D3359 Test Methods for Measuring Adhesion by Tape Test
- D3924 Specification for Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials
- D3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings
- D3960 Practice for Determining Volatile Organic Compound (VOC) Content of Paints and Related Coatings
- D3891 Practice for Preparation of Glass Panels for Testing Paint, Varnish, Lacquer, and Related Products
- D4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser
- D4214 Test Methods for Evaluating the Degree of Chalking of Exterior Paint Films
- D4414 Practice for Measurement of Wet Film Thickness by Notch Gages
- D4541 Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
- D4708 Practice for Preparation of Uniform Free Films of Organic Coatings
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E1605 Terminology Relating to Lead in Buildings
- E1795 Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings
- E1796 Guide for Selection and Use of Liquid Coating Encapsulation Products for Leaded Paint in Buildings
- E2239 Practice for Record Keeping and Record Preservation for Lead Hazard Activities
- G154 Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials
- 2.2 *Federal Test Methods Standard 141D*.<sup>4</sup>
- 2011 Preparation of Steel Panels
- 2012 Preparation of Tin Panels
- 3011 Condition in Container

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminologies **D16** and **E1605**.

### 4. Classification

4.1 *Type I: Interior Use Only*—Type I defines encapsulation products intended for interior use. These products shall meet the requirements of this specification except those for weathering and exterior aging (for example, test methods described in **10.9** and **10.10.1** not conducted).

4.2 *Type II: Exterior Use Only*—Type II defines encapsulation products intended for exterior use. These products shall meet the requirements of this specification except that for interior aging (for example, test method **10.10.2** not conducted).

4.3 *Type III: Either Exterior or Interior Use*—Type III defines encapsulation products intended for either interior or exterior use. These products shall meet all the requirements of this specification.

### 5. Performance Requirements

5.1 Performance requirements that shall be met for a reinforced liquid coating encapsulation product are given in **Table 1**.

NOTE 1—In addition to those given in **Table 1**, performance requirements for three other properties are of concern for liquid coating encapsulation products. These are combustion toxicity, emissions during application and curing, and lead accessibility. However, requirements for these properties cannot be included in this specification at this time because there are no adequate ASTM or Federal test methods for determining them. Requirements for two of these properties, combustion toxicity and emissions during application and curing, may be subject to regulations or ordinances promulgated by authorities having jurisdiction. The user of this specification is advised to determine whether such regulations or ordinances exist. The addition of requirements for these properties to this specification will be undertaken when suitable test methods are available.

### 6. Sampling

6.1 A 3.8-L (1-gal) sample of the encapsulant coating is usually sufficient for conducting the specified tests.

6.2 Prior to sampling, establish the condition of the container since damage to it may cause evaporation, skinning, or other undesirable effects. Excessive storage time and temperature fluctuations may cause settling or changes in viscosity. Materials beyond the manufacturer's stated shelf life shall not be sampled. Reinforcement materials shall be evaluated to ensure they are undamaged.

6.3 Thickening, settling, and separation are undesirable and objectionable if the coating cannot be readily made suitable for application with a reasonable amount of stirring. Determine the conditions in the container in accordance with Method **3011** of Federal Test Method Standard No. 141C.

6.4 Sample the encapsulation product in accordance with Practice **D3925**. Determine the density in accordance with Test Method **D1475**, and repeat until two successive readings agree within 90 g (0.2 lb). Samples for testing may then be taken.

6.5 Report the size of the container from which the sample was taken and product identification codes.

### 7. Number of Tests

7.1 The number of tests that shall be conducted for each performance property is given in **Table 1**.

### 8. Retesting

8.1 In cases where encapsulation products fail to pass one or more requirements of this specification, retesting shall be permitted. Both the original data and the retesting data for each requirement for which retesting was conducted shall be used in determining whether the requirement is met.

### 9. Test Specimens

9.1 An encapsulation product shall be comprised of all principal components in the system, including the base and topcoats, the reinforcement material, and primer, if specified, for field application. Except for dry abrasion and adhesion testing, where specialty primers may be used for flash rust resistance, primers shall not be used solely for product performance testing in accordance with this specification.

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.