
**Rubber hoses and hose assemblies for
bulk fuel delivery by truck — Specification**

*Tuyaux en caoutchouc et assemblages de tuyaux pour livraison en vrac
d'hydrocarbures liquides par camions-citernes — Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2929:2002](https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002)

<https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2929:2002

<https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Materials and construction	2
6 Dimensions	3
7 Physical properties	4
8 Electrical resistance	6
9 Types of test	6
10 Design verification testing	6
11 Marking	7
Annex A (normative) Method of test for strength of adhesion between components	8
Annex B (normative) Method of test for flexibility at 20 °C	9
Annex C (normative) Method of test for flammability	10
Annex D (normative) Test method for security of coupling attachment	12
Annex E (normative) Tests to be carried out as part of design verification and routine testing	13
Annex F (informative) Recommended tests for production acceptance testing	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2929 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This third edition cancels and replaces the second edition (ISO 2929:1991), which has been technically revised.

Annexes A to E form a normative part of this International Standard. Annex F is for information only.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 2929:2002
<https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>

Rubber hoses and hose assemblies for bulk fuel delivery by truck — Specification

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies the requirements for two groups of rubber hoses and rubber hose assemblies for loading and discharge of liquid hydrocarbon fuels with a maximum working pressure of 10 bar (1,0 MPa).

Both groups of hoses are designed for:

- a) use with hydrocarbon fuels having an aromatic-hydrocarbon content not exceeding 50 % by volume and containing up to 15 % of oxygenated compounds;
- b) operation within the temperature range of $-30\text{ }^{\circ}\text{C}$ to $+70\text{ }^{\circ}\text{C}$, undamaged by climatic conditions of $-50\text{ }^{\circ}\text{C}$ to $+70\text{ }^{\circ}\text{C}$ when stored in static conditions.

NOTE Hoses for use at temperatures lower than $-30\text{ }^{\circ}\text{C}$ should be the subject of discussion between manufacturer and end user.

This International Standard is not applicable to hoses and hose assemblies for LPG systems, aviation fuel systems, fuel station systems or marine applications.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1746, *Rubber or plastics hoses and tubing — Bending tests*

ISO 1817:1999, *Rubber, vulcanized — Determination of the effect of liquids*

ISO 4649:2002, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of dimensions*

ISO 4672:1997, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*

ISO 7233, *Rubber and plastic hoses and hose assemblies — Determination of suction resistance*

ISO 7326:1991, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8031, *Rubber and plastics hoses and hose assemblies — Determination of electrical resistance*

ISO 8033, *Rubber and plastics hose — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions given in ISO 8330 apply.

4 Classification

Hoses are designated as belonging to one of the following groups:

- a) Group D: delivery hose, or, with certain restrictions, for use in low-vacuum applications (see footnote to Table 3).
- b) Group SD: suction and delivery hose, helix-reinforced.

Both of these groups can be: <https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>

- a) electrically bonded, in which case the hose is designated and marked M-grade;
- or
- b) electrically conductive, using a conductive rubber layer, in which case the hose is designated and marked Ω-grade.

5 Materials and construction

If the hose is mandrel-built, particulate-type release agents shall not be used.

The hose shall be uniform in quality and free from porosity, air-holes, foreign inclusions and other defects.

The hose shall consist of the following:

- a) a lining of rubber resistant to hydrocarbon fuels;
- b) a reinforcement of layers of woven, braided or spirally wound textile material;
- c) an embedded helix reinforcement (group SD only);
- d) two or more low-resistance electrical bonding wires (M-grade only);
- e) an outer cover of rubber, resistant to abrasion, outdoor exposure and hydrocarbon fuels.

6 Dimensions

6.1 Nominal bore, internal diameter, outside diameter and their tolerances, service reeling diameter and minimum bend radius

When measured in accordance with ISO 4671, the internal diameter and outside diameter and their tolerances shall conform to the values specified in Table 1.

When determined in accordance with ISO 1746, the value of the minimum bend radius shall conform to the values specified in Table 1.

NOTE ISO 1746 is not suitable for internal diameters above 80 mm. It is intended to include internal diameters above 80 mm in the next revision of this standard.

Table 1 — Dimensions

Nominal bore	Internal diameter mm	Tolerance on internal diameter mm	Outside diameter mm	Tolerance on outside diameter mm	Minimum bend radius mm		Minimum external diameter of reeling drum used in service mm	
					Group D	Group SD	Group D	Group SD
19	19,0	± 0,5	31,0	± 1,0	125	100	250	250
25	25,0		37,0		150	125	300	300
32	32,0		44,0		200	150	400	350
38	38,0		51,0		250	175	500	400
50	50,0	± 0,7	66,0	± 1,2	300	225	600	500
51	51,0		67,0		300	225	600	500
63	63,0	± 0,8	79,0	± 1,2	400	275	800	600
75	75,0		91,0		450	350	900	750
76	76,0		92,0		450	350	900	750
100	100,0		116,0		600	450	N.A.	N.A.
101	101,5	± 1,6	118,0	± 1,6	600	450	N.A.	N.A.
150	150,0		170,0		± 2,0	900	750	N.A.

6.2 Concentricity

When determined in accordance with ISO 4671, the concentricity, based on a total indicator reading between the internal diameter and the outside surface of the cover, shall be no greater than 1,0 mm for hoses of nominal bore up to and including 76, and no greater than 1,5 mm for hoses of nominal bore greater than 76.

6.3 Tolerance on length

When measured in accordance with ISO 4671, the length of a hose or hose assembly shall be within ± 1 % of the required length.

6.4 Minimum thickness of lining and cover

When measured in accordance with ISO 4671, the minimum thickness of the lining of all hoses shall be 1,5 mm.

For hoses of nominal bore up to and including 50, the minimum thickness of the cover shall be 1,5 mm.

For hoses of nominal bore greater than 50, the minimum thickness of the cover shall be 2,0 mm.

7 Physical properties

7.1 Rubber compounds

When determined by the methods listed in Table 2, the physical properties of the compounds used for the lining and cover shall conform to the values specified in Table 2.

Tests shall be carried out either on samples taken from the hose or from separately vulcanized sheets, 2 mm in thickness and vulcanized to the same cured state as the production hoses.

Table 2 — Physical properties of rubber compound

Property	Requirement		Test method
	Lining	Cover	
Minimum tensile strength	7,0 MPa	7,0 MPa	ISO 37 (dumb-bell test piece)
Minimum elongation at break	250 %	250 %	ISO 37 (dumb-bell test piece)
Change in volume in fuel	50 %	—	7.3 of ISO 1817:1999 (72 h at 40 °C in liquid 3)
	—	100 %	7.3 of ISO 1817:1999 (48 h at 40 °C in liquid B)
Maximum abrasion resistance (relative volume loss ΔV)	—	180 mm ³	Method A of ISO 4649:2002
Resistance to ageing:			ISO 188 (7 days at 70 °C, air-oven method)
Change in tensile strength from original value	± 30 %	± 30 %	
Change in elongation at break from original value	± 30 %	± 30 %	

7.2 Finished hoses and hose assemblies

When determined by the methods listed in Table 3, the physical properties of finished hoses and hose assemblies shall conform to the values specified in Table 3.

Table 3 — Physical properties of finished hoses and hose assemblies

Property	Requirements	Test method
Hose tests		
Proof pressure	15 bar and no leakage or other signs of weakness	ISO 1402
Change in length (max.): at proof test pressure at – 0,8 bar (vacuum)	Group D: 0 % to + 8 % Group SD: 0 % to + 10 % Group SD: – 2 %	ISO 1402
Change in twist at proof test pressure (max.)	8°/m	ISO 1402
Resistance to vacuum (group SD only) at – 0,8 bar for 10 min (see footnote)	No structural damage	ISO 7233
Burst pressure (min.)	40 bar	ISO 1402
Adhesion between components: dry (min.) after contact with fuel (min.)	2,4 N/mm 1,8 N/mm	Annex A (clause A.1) Annex A (clause A.2)
Ozone resistance at 40 °C	No cracking observed under $\times 2$ magnification	ISO 7326:1991, method 3 [relative humidity (55 \pm 10) %, ozone concentration (50 \pm 5) pphm, elongation 20 %]
Flexibility: at 20 °C at – 30 °C	No permanent deformation or visible structural damage, no increase in electrical resistance, no impairment of electrical continuity and shall comply with the proof pressure requirements	Annex B Method B of ISO 4672:1997
Electrical resistance (max.)	M-grade: 10 ² Ω /length Ω -grade: 10 ⁶ Ω /length	ISO 8031
Deformation of hose external diameter under bending at minimum bend radius and internal pressure of 0,7 bar (group D only) (max.)	10 %	ISO 1746
Flammability test	No burning on removal of the burner flame, no visible glowing and no leakage of fluid	Annex C
Hose assembly tests		
Proof pressure	15 bar and no leakage or other signs of weakness	ISO 1402
Burst pressure (min.)	40 bar	ISO 1402
Electrical resistance (max.)	M-grade: 10 ² Ω /assembly	ISO 8031
	Ω -grade: 10 ⁶ Ω /assembly	
Security of coupling attachment	No leakage and no movement of the coupling out of the hose	Annex D
NOTE	Smaller sizes of group D hose, i.e. of nominal bore 51 and below, may be used for vacuum applications down to – 0,3 bar.	

8 Electrical resistance

8.1 General

Adequate electrical resistance of hoses and hose assemblies shall be obtained in accordance with 8.2 or 8.3.

During and after the hydrostatic tests as described in ISO 1402, the electrical continuity of each hose shall be maintained from end to end and electrical continuity of each hose assembly shall be maintained from one coupling to the other.

8.2 M-grade

Two low-resistance bonding wires, applied spirally, shall be incorporated into the hose construction.

When attaching fittings to group D hoses, the bonding wires shall be folded into the hose bore, positioned between the lining and the fitting tail and extended by approximately one-third of the length of the fitting tail into the bore.

When attaching fittings to group SD hoses, electrical bonding shall be achieved by using bonding wires as for group D or by using the helix with or without bonding wires attached.

When determined in accordance with ISO 8031, the resistance along the bonding wires in the case of hoses, or the resistance between fittings in the case of hose assemblies, shall not exceed $1 \times 10^2 \Omega$ per length or assembly. When obtaining electrical continuity by this method, the hose shall be marked with the symbol "M".

8.3 Ω -grade

iTeh STANDARD PREVIEW
(standards.iteh.ai)

In this type of construction, electrically conducting materials shall be incorporated into the hose lining.

When attaching fittings to this type of hose, an adequate connection between the end-fittings and the conductive layer shall be obtained. <https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>

When determined in accordance with ISO 8031, the resistance along the conductive lining in the case of hoses, or the resistance between the fittings in the case of hose assemblies, shall not exceed $1 \times 10^6 \Omega$ per length or assembly. When obtaining electrical resistance by this method, the hose shall be marked with the symbol " Ω ".

9 Types of test

The tests to be carried out as part of design verification and routine testing shall be as specified in annex E.

Tests for production acceptance testing are given, solely as a recommendation, in annex F.

Design verification tests are those required to confirm that the product meets all the requirements of this International Standard. Routine tests are those that must be carried out on each hose or hose assembly. Production acceptance tests are those carried out on a batch basis.

10 Design verification testing

Design verification testing shall be performed in order to supply evidence that all the material, construction and test requirements of this International Standard have been met by the method of manufacture and hose design.

Design verification tests shall be reported at least every five years or whenever a change in the method of manufacture or the materials occurs. The number, sizes and groups/grades of hoses shall be selected to cover all the hoses to which design verification applies, and this information shall be stated in the report.

11 Marking

11.1 Hoses

Each length of hose shall be legibly and durably marked on the outer cover, at intervals of no greater than 2 m, with the following information:

- a) the manufacturer's name or identification, e.g. Man;
- b) the number and year of publication of this International Standard, i.e. ISO 2929;
- c) the group, e.g. D;
- d) the nominal bore, e.g. 38;
- e) the maximum working pressure in bars, e.g. 10;
- f) the conductivity grade, e.g. M;
- g) the quarter and year of manufacture, e.g. 3Q01.

EXAMPLE Man/ISO 2929/group D/38/WP10/M/3Q01.

11.2 Hose assemblies

The couplings shall be permanently marked with the following information:

- a) the manufacturer's or assembler's name or identification mark;
- b) the date of assembly. <https://standards.iteh.ai/catalog/standards/sist/492bbfa0-7a90-4417-ad8c-18e2371b422d/iso-2929-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2929:2002