
**Plastics piping systems for soil and
waste discharge (low and high
temperature) inside buildings —
Acrylonitrile-butadiene-styrene (ABS)**

*Systèmes de canalisations en plastique pour l'évacuation des eaux-
vannes et des eaux usées (à basse et à haute température) à l'intérieur
des bâtiments — Acrylonitrile-butadiène-styrène (ABS)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 7682:2003](https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003)

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 7682:2003](https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003)

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Symbols and abbreviations	2
4 Material	3
5 General characteristics	4
6 Geometrical characteristics	4
7 Mechanical characteristics of pipes	21
8 Physical characteristics	23
9 Performance requirements	24
10 Sealing rings	25
11 Adhesives	25
12 Marking	25
13 Installation of piping systems	26
Annex A (informative) Additional characteristics of ABS pipes and fittings	28
Bibliography	29

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7682 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 1, *Plastics pipes and fittings for soil, waste and drainage (including land drainage)*.

iTeh STANDARD PREVIEW

This second edition cancels and replaces the first edition (ISO 7682:1991), which has been technically revised.

[ISO 7682:2003](https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003)

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

Introduction

Pipes and fittings conforming to this International Standard also meet the corresponding requirements of EN 1455-1 which are applicable to those pipes and fittings which, according to EN 1455-1, are intended to be used inside buildings (application area code “B”, see EN 1455-1) only.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 7682:2003](https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003)

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7682:2003

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

Plastics piping systems for soil and waste discharge (low and high temperature) inside buildings — Acrylonitrile-butadiene-styrene (ABS)

1 Scope

This International Standard specifies the requirements for solid-wall acrylonitrile-butadiene-styrene (ABS) pipes and fittings for soil and waste discharge (low and high temperature) above ground inside buildings, as well as the system itself. It does not include buried pipework.

It also specifies the test parameters for the test methods referred to in this International Standard.

This International Standard is applicable to ABS pipes and fittings, as well as assemblies of such pipes and fittings, intended to be used for the following purposes:

- a) soil and waste discharge pipework for the conveyance of domestic waste waters (low and high temperature);
- b) ventilation pipework associated with a);
- c) rainwater pipework inside the building.

It is applicable to pipes and fittings designed for jointing by means of elastomeric sealing rings, solvent cementing or integral dual-purpose sockets, i.e. for elastomeric ring seal joints and/or for solvent cement joints.

Two systems, system I and system II, are specified for type N ring seal sockets. Both systems are suitable for this field of application.¹⁾

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 265-1, *Pipes and fittings of plastics materials — Fittings for domestic and industrial waste pipes — Basic dimensions: Metric series — Part 1: Unplasticized poly(vinyl chloride) (PVC-U)*

ISO 3126:—²⁾, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 7245, *Pipes and fittings of acrylonitrile/butadiene/styrene (ABS) — General specification for moulding and extrusion materials*

ISO 7246, *Pipes and fittings of acrylonitrile/styrene/acrylester (ASA) — General specification for moulding and extrusion materials*

1) Individual countries may select either system I or system II for their national specifications.

2) To be published. (Revision of ISO 3126:1974)

ISO 8361-1, *Thermoplastics pipes and fittings — Water absorption — Part 1: General test method*

EN 681-1, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber*

EN 681-2, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 2: Thermoplastic elastomers*

EN 727, *Plastics piping and ducting systems — Thermoplastics pipes and fittings — Determination of Vicat softening temperature (VST)*

EN 743:1994, *Plastics piping and ducting systems — Thermoplastics pipes — Determination of the longitudinal reversion*

EN 744, *Plastics piping and ducting systems — Thermoplastics pipes — Test method for resistance to external blows by the round-the-clock method*

EN 763:1994, *Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Test method for visually assessing effects of heating*

EN 1053, *Plastics piping systems — Thermoplastics piping systems for non-pressure applications — Test method for watertightness*

EN 1054, *Plastics piping systems — Thermoplastics piping systems for soil and waste discharge — Test method for airtightness of joints*

EN 1055:1996, *Plastics piping systems — Thermoplastics piping systems for soil and waste discharge inside buildings — Test method for resistance to elevated temperature cycling*

EN 1411, *Plastics piping and ducting systems — Thermoplastics pipes — Determination of resistance to external blows by the staircase method*

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 7682:2003
<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

3 Symbols and abbreviations

3.1 Symbols

A	length of engagement
B	length of lead-in
C	depth of sealing zone
d_e	outside diameter (at any point)
d_{em}	mean outside diameter
d_n	nominal outside diameter
d_s	inside diameter of the socket
d_{sm}	mean inside diameter of the socket
DN	nominal size
DN/OD	nominal size (outside-diameter related)

e	wall thickness (at any point)
e_m	mean wall thickness
e_2	wall thickness of the socket
e_3	wall thickness at the groove
L_1	length of spigot
L_2	length of solvent cement socket
l	effective length of a pipe
N	effective insertion depth
R	radius of swept fittings
z	design length (z -length) of a fitting
α	nominal angle of a fitting

3.2 Abbreviations

ABS acrylonitrile-butadiene-styrene

ASA acrylonitrile-styrene-acrylester

TIR true impact rate

iTeH STANDARD PREVIEW
(standards.iteh.ai)
ISO 7682:2003
<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

4 Material

4.1 ABS compound

The compound for pipes and fittings shall be ABS copolymer or terpolymer conforming to ISO 7245 to which may be added ASA conforming to ISO 7246 and those additives that are needed to facilitate the manufacture of components conforming to the requirements of this International Standard.

In order to conform to national requirements on fire regulations, other additives may be used.

Fabricated fittings or parts of fabricated fittings shall be made from pipes and/or mouldings conforming to this International Standard, except for the requirements for the wall thickness of fabricated fittings and/or mouldings made from ABS which conform to material, mechanical and physical characteristics as required in this International Standard.

4.2 Reprocessable and recyclable material

In addition to virgin material, the use of reprocessible material obtained during the production and testing of products conforming to this International Standard is permitted. External reprocessible or recyclable material shall not be used.

NOTE Definitions concerning materials are given in EN 1455-1.

4.3 Sealing ring retaining means

Sealing rings may be retained, using means made from plastics other than ABS, provided the joints conform to the requirements given in Clause 9.

4.4 Fire behaviour

No specific requirements are set by this International Standard for fire behaviour. Attention is drawn to the need to comply with any relevant national regulations in this respect.

5 General characteristics

5.1 Appearance

When viewed without magnification, the following requirements shall be met:

- the internal and external surfaces of pipes and fittings shall be smooth, clean and free from grooving, blistering, impurities, pores or any other surface irregularity likely to prevent conformity of pipes and fittings to this International Standard;
- each end of a pipe or fitting shall be cleanly cut, if applicable, and shall be square to its axis.

5.2 Colour

Pipes and fittings shall be uniformly coloured through the whole wall.

The recommended colour for pipes and fittings is grey, black or white.

<https://standards.iteh.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

6 Geometrical characteristics

6.1 General

All dimensions shall be measured in accordance with ISO 3126.

The figures given in this International Standard are schematic sketches only, to indicate the relevant dimensions. They do not necessarily represent manufactured components. The dimensions given shall be conformed to however.

6.2 Dimensions of pipes

6.2.1 Outside diameters

The mean outside diameter, d_{em} , shall conform to Table 1 or Table 2, as applicable.

Table 1 — Mean outside diameters
(metric series)

Dimensions in millimetres

Nominal size DN/OD	Nominal outside diameter d_n	Mean outside diameter d_{em}	
		min.	max.
32	32	32,0	32,3
40	40	40,0	40,3
50	50	50,0	50,3
63	63	63,0	63,3
75	75	75,0	75,4
80	80	80,0	80,4
90	90	90,0	90,4
100	100	100,0	100,4
110	110	110,0	110,4
125	125	125,0	125,4
160	160	160,0	160,5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Table 2 — Mean outside diameters


(series based on inch dimensions)
<https://standards.iteh.ai/catalog/standards/sist/4ca6-ae8d-8019b6147736/iso-7682-2003>

Dimensions in millimetres

Nominal size DN/OD	Nominal outside diameter d_n	Mean outside diameter d_{em}	
		min.	max.
36	36	36,1	36,5
43	43	42,7	43,1
55	55	55,7	56,1

6.2.2 Effective length of pipes

The effective length, l , of a pipe shall not be less than that declared by the manufacturer and shall be measured as shown in Figure 1. For pipes with sockets, the effective length is considered to be the distance between the pipe ends minus the socket length. For practical reasons, this length is measured to the outside of the socket.



ISO 7682:2003

<https://standards.itech.ai/catalog/standards/sist/16b56412-2653-4ca6-ae8d-8019b6147736/iso-7682-2003>

Key

- 1 single socket pipe
- 2 ring seal pipe
- 3 plain-ended pipes
 - a) with chamfer
 - b) without chamfer

Figure 1 — Effective lengths of pipes

6.2.3 Chamfering

If a chamfer is applied, the angle of chamfering shall be between 15° and 45° to the axis of the pipe (see Figure 3). When pipes without chamfer are used, the pipe ends shall be deburred.

The remaining wall thickness of the end of the pipe shall be at least 1/3 of e_{min} .

6.2.4 Wall thickness

The wall thickness, e , shall conform to Table 3 or Table 4, as applicable, but for the metric series a maximum wall thickness at any point of up to $1,25e_{min}$ is permitted, provided that the mean wall thickness, e_m , is less than or equal to the specified $e_{m,max}$.