INTERNATIONAL STANDARD

ISO 19220

First edition 2004-09-15

Plastics piping systems for soil and waste discharge (low and high temperature) inside buildings — Styrene copolymer blends (SAN + PVC)

Systèmes de canalisations en plastique pour l'évacuation des eauxvannes et des eaux usées (à basse et à haute température) à l'intérieur des bâtiments — Mélanges de copolymères de styrène (SAN + PVC)

(standards.iteh.ai)

ISO 19220:2004 https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19220:2004 https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Со	ntents	Page
1	Scope	1
2	Normative references	1
3	Symbols and abbreviations	2
3.1	Symbols	2
3.2	Abbreviations	3
4	Material	3
4.1	SAN + PVC compound	3
4.2	Reprocessable and recyclable material	3
4.3	Sealing ring retaining means	3
4.4	Fire behaviour	3
5	General characteristics	4
5.1	Appearance	4
5.2		
6	Geometrical characteristics (standards.iteh.ai)	4
6.1	General	4
6.2	Dimensions of hips // standards.iuch.ai/catadog/standards/six/c4d600c4-a299-4ba9-a30f-	4
6.3	Dimensions of fittingsdt3ec121098d/iso-19220-2004	7
6.4	Dimensions of sockets and pipe ends	8
6.5	Types of fitting	16
7	Mechanical characteristics of pipes	24
7.1	General characteristics	24
7.2	Additional characteristics	25
8	Physical characteristics	25
8.1	Physical characteristics of pipes	25
8.2	Physical characteristics of fittings	26
9	Performance requirements	27
10	Sealing rings	27
11	Adhesives	27
12	Marking	27
12.1	General	27
12.2	Minimum required marking of pipes	28
12.3	Minimum required marking of fittings	28
13	Installation of piping systems	28
Ann	ex A (informative) Additional characteristics of (SAN + PVC) pipes and fittings	30
Bibl	iography	31

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 19220 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 1, *Plastics pipes and fittings for soil, waste and drainage (including land drainage).* **iTeh STANDARD PREVIEW**

(standards.iteh.ai)

ISO 19220:2004 https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004

Introduction

Pipes and fittings conforming to this International Standard also meet the corresponding requirements of EN 1565-1 which are applicable to those pipes and fittings which, according to EN 1565-1, are intended to be used inside buildings (application area code "B", see EN 1565-1) only.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19220:2004 https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 19220:2004

https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004

Plastics piping systems for soil and waste discharge (low and high temperature) inside buildings — Styrene copolymer blends (SAN + PVC)

1 Scope

This International Standard specifies the requirements for solid-wall styrene copolymer blend (SAN + PVC) pipes and fittings for soil and waste discharge (low and high temperature) above ground inside buildings, as well as the system itself. It does not include buried pipework.

It also specifies the test parameters for the test methods referred to in this International Standard.

This International Standard is applicable to SAN + PVC pipes and fittings, as well as assemblies of such pipes and fittings, intended to be used for the following purposes:

- a) soil and waste discharge pipework for the conveyance of domestic waste waters (low and high temperature);
- b) ventilation pipework associated with a); VDARD PREVIEW
- c) rainwater pipework inside the building ndards.iteh.ai)

It is applicable to pipes and fittings designed for jointing by means of elastomeric sealing rings, solvent cementing or integral dual-purpose sockets, i.e. for elastomeric ring seal joints and/or for solvent cement joints.

df3ec121098d/iso-19220-2004

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 265-1, Pipes and fittings of plastics materials — Fittings for domestic and industrial waste pipes — Basic dimensions: Metric series — Part 1: Unplasticized poly(vinyl chloride) (PVC-U)

ISO 3126:—1), Plastics piping systems — Plastics components — Determination of dimensions

ISO 8361-1, Thermoplastics pipes and fittings — Water absorption — Part 1: General test method

EN 681-1, Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber

EN 681-2, Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 2: Thermoplastic elastomers

EN 727, Plastics piping and ducting systems — Thermoplastics pipes and fittings — Determination of Vicat softening temperature (VST)

EN 743:1994, Plastics piping and ducting systems — Thermoplastics pipes — Determination of the longitudinal reversion

¹⁾ To be published. (Revision of ISO 3126:1974)

ISO 19220:2004(E)

EN 744, Plastics piping and ducting systems — Thermoplastics pipes — Test method for resistance to external blows by the round-the-clock method

EN 763:1994, Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Test method for visually assessing effects of heating

EN 1053, Plastics piping systems — Thermoplastics piping systems for non-pressure applications — Test method for watertightness

EN 1054, Plastics piping systems — Thermoplastics piping systems for soil and waste discharge — Test method for airtightness of joints

EN 1055:1996, Plastics piping systems — Thermoplastics piping systems for soil and waste discharge inside buildings — Test method for resistance to elevated temperature cycling

EN 1411, Plastics piping and ducting systems — Thermoplastics pipes — Determination of resistance to external blows by the staircase method

EN 1565-1, Plastics piping systems for soil and waste discharge (low and high temperature) within the building structure — Styrene copolymer blends (SAN + PVC) — Part 1: Specifications for pipes, fittings and the system

Symbols and abbreviations

wall thickness at the groove

length of solvent cement socket

effective length of a pipe

length of spigot

3.1	Symbols iTeh STANDARD PREVIEW
\boldsymbol{A}	length of engagement (standards.iteh.ai)
B	length of lead-in ISO 19220:2004
C	depth of sealing zohtes://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004
d_{e}	outside diameter (at any point)
d_{em}	mean outside diameter
d_{n}	nominal outside diameter
d_{s}	inside diameter of the socket
d_{sm}	mean inside diameter of the socket
DN	nominal size
DN/C	DD nominal size (outside-diameter related)
e	wall thickness (at any point)
e_{m}	mean wall thickness
e_{2}	wall thickness of the socket

 e_3

 L_1

 L_2

l

N effective insertion depth

R radius of swept fittings

z design length (z-length) of a fitting

 α nominal angle of a fitting

3.2 Abbreviations

PVC poly(vinyl chloride)

SAN styrene-acrylonitrile

SAN + PVC styrene copolymer blends

TIR true impact rate

4 Material

4.1 SAN + PVC compound iTeh STANDARD PREVIEW

The compound for pipes and fittings shall be a styrene copolymer blend consisting of SAN and PVC to which may be added those additives that are needed to facilitate the manufacture of components conforming to the requirements of this International Standard.

ISO 19220:2004

In order to conform to mational requirements on fire regulations other additives may be used.

df3ec121098d/iso-19220-2004

Fabricated fittings or parts of fabricated fittings shall be made from pipes and/or mouldings conforming to this International Standard, except for the requirements for the wall thickness of fabricated fittings and/or mouldings made from SAN + PVC which conform to material, mechanical and physical characteristics as required in this International Standard.

NOTE Material conforming to this requirement generally contains 40 % to 60 % of SAN.

4.2 Reprocessable and recyclable material

In addition to virgin material, the use of reprocessable material obtained during the production and testing of products conforming to this International Standard is permitted. External reprocessable or recyclable material shall not be used.

NOTE Definitions concerning materials are given in EN 1565-1.

4.3 Sealing ring retaining means

Sealing rings may be retained using means made from plastics other than SAN + PVC, provided the joints conform to the requirements given in Clause 9.

4.4 Fire behaviour

No specific requirements are set by this International Standard for fire behaviour. Attention is drawn to the need to comply with any relevant national regulations in this respect.

© ISO 2004 – All rights reserved

5 General characteristics

5.1 Appearance

When viewed without magnification, the following requirements shall be met:

- the internal and external surfaces of pipes and fittings shall be smooth, clean and free from grooving, blistering, impurities, pores or any other surface irregularity likely to prevent conformity of pipes and fittings to this International Standard;
- each end of a pipe or fitting shall be cleanly cut, if applicable, and shall be square to its axis.

5.2 Colour

Pipes and fittings shall be uniformly coloured through the whole wall.

The recommended colour for pipes and fittings is grey or black.

6 Geometrical characteristics

6.1 General

All dimensions shall be measured in accordance with ISO 3126.

eh S

The figures given in this International Standard are schematic sketches only, to indicate the relevant dimensions. They do not necessarily represent manufactured components. The dimensions given shall be conformed to however.

ISO 19220:2004

PREVIEW

6.2 Dimensions of pipestps://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-df3ec121098d/iso-19220-2004

6.2.1 Outside diameters

The mean outside diameter, d_{em} , shall conform to Table 1 or Table 2, as applicable.

Table 1 — Mean outside diameters (metric series)

Dimensions in millimetres

Nominal size	Nominal outside diameter	Mean outside diameter		
DN/OD	d_n	$d_{\sf em}$		
		min.	max.	
32	32	32,0	32,3	
40	40	40,0	40,3	
50	50	50,0	50,3	
63	63	63,0	63,3	
75	75	75,0	75,4	
80	80	80,0	80,4	
90	90	90,0	90,4	
100	100	100,0	100,4	
110	110	110,0	110,4	
125	125	125,0	125,4	
160	160	160,0	160,5	

Table 2 — Mean outside diameters (series based on inch dimensions)

(standards.iteh.ai)

Dimensions in millimetres

Nominal size	Nominal outside diameter Mean outside		de diameter
DN/OD	d_{n} ISO 19220	$\frac{0.2004}{}$	em
https://	standards.iteh.ai/catalog/standard	ls/sist/c4d600c4-a299-4ba9-a30f- 19220_2004	max.
36	36	36,1	36,5
43	43	42,7	43,1
55	55	55,7	56,1

6.2.2 Effective length of pipes

The effective length, l, of a pipe shall not be less than that declared by the manufacturer and shall be measured as shown in Figure 1. For pipes with sockets, the effective length is considered to be the distance between the pipe ends minus the socket length. For practical reasons, this length is measured to the outside of the socket.

6.2.3 Chamfering


If a chamfer is applied, the angle of chamfering shall be between 15° and 45° to the axis of the pipe (see Figure 3). When pipes without chamfer are used, the pipe ends shall be deburred.

The remaining wall thickness of the end of the pipe shall be at least 1/3 of $e_{\rm min}$.

6.2.4 Wall thickness

The wall thickness, e, shall conform to Table 3 or Table 4, as applicable, but for the metric series a maximum wall thickness at any point of up to 1,25 e_{\min} is permitted, provided that the mean wall thickness, e_{\min} , is less than or equal to the specified e_{\min} .

© ISO 2004 – All rights reserved 5



Key

- 1 solvent cement pipe
- 2 ring seal pipe
- 3 plain-ended pipes
 - a) with chamfer
 - b) without chamfer

Figure 1 — Effective lengths of pipes

Table 3 — Wall thicknesses (metric series)

Dimensions in millimetres

Nominal size	Nominal outside diameter	Wall thickness				
		Pipe series				
		S	25 ^a	S 1	6,7 ^a	
DN/OD	d_{n}	e	e_{m}	e	e_{m}	
		min.	max.	min.	max.	
32	32	1,8	2,2	2,2	2,7	
40	40	1,8	2,2	2,2	2,7	
50	50	1,8	2,2	2,2	2,7	
63	63	1,8	2,2	2,2	2,7	
75	75	1,8	2,2	2,5	3	
80	80	1,8	2,2	2,6	3,1	
90	90	1,8	2,2	2,7	3,3	
100	100	2	2,5	3	3,6	
110	110	2,2	2,7	3,2	3,8	
125	125	2,5	3	3,7	4,3	
160	Teh STINNDAR	3,2RF	3,8	4,7	5,3	
^a Pipe series are defined in ISO 4065.						
	(standard)	s.iten.ai	(Stanuarus.iten.ai)			

Table 4 — Wall thicknesses (series based on inch dimensions)

https://standards.iteh.ai/catalog/standards/sist/c4d600c4-a299-4ba9-a30f-

dPas121009d/ing 10220 2004				
Nominal size	Nominal outside diameter	Wall thickness		
DN/OD	d_{n}	e	e_{m}	
		min.	max.	
36	36	1,8	2,2	
43	43	1,9	2,3	
55	55	2	2,4	

6.3 Dimensions of fittings

6.3.1 Outside diameters

The mean outside diameter, $d_{\rm em}$, of the spigot end shall conform to Table 1 or Table 2, as applicable.

6.3.2 z-lengths

The design length(s) [z-length(s)] of fittings (see Figure 8 to Figure 21) shall be as given by the manufacturer.

NOTE The *z*-length(s) of a fitting are intended to assist in the design of moulds and are not intended to be used for quality control purposes. ISO 265-1 may be used as a guideline.

6.3.3 Wall thickness

The minimum wall thickness, e_{min} , of the body or the spigot end of a fitting shall conform to Table 3 or Table 4, as applicable, except that a reduction of 5 % resulting from core shifting is permitted. In such cases, the average