

Transformed.

**ISO**

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

ISO RECOMMENDATION

R 2232

DRAWN WIRE FOR GENERAL PURPOSE NON-ALLOY

STEEL WIRE ROPES

SPECIFICATIONS

1st EDITION

August 1971

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.



## BRIEF HISTORY

The ISO Recommendation R 2232, *Drawn wire for general purpose non-alloy steel wire ropes – Specifications*, was drawn up by Technical Committee ISO/TC 105, *Steel wire ropes*, the Secretariat of which is held by the Nederlands Normalisatie-Instituut (NNI).

Work on this question led to the adoption of Draft ISO Recommendation No. 2232, which was circulated to all the ISO Member Bodies for enquiry in October 1970. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Austria	Ireland	Spain
Belgium	Israel	Sweden
Denmark	Italy	Switzerland
France	Netherlands	U.A.R.
Germany	Portugal	United Kingdom
India	South Africa, Rep. of	

The following Member Bodies opposed the approval of the Draft :

Japan  
~~New Zealand~~  
U.S.A.

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.



**DRAWN WIRE FOR GENERAL PURPOSE NON-ALLOY  
STEEL WIRE ROPES  
SPECIFICATIONS**

**1. SCOPE**

This ISO Recommendation gives specifications for drawn wire intended for use in the manufacture of general purpose non-alloy steel wire ropes.

It specifies

- the dimensional tolerances;
- the mechanical characteristics, which are determined on the basis of the appropriate techniques described in the corresponding ISO Recommendations\*;
- the conditions with which their covering, if any, shall comply;
- the conditions of sampling and the terms of acceptance.

**2. FIELD OF APPLICATION**

This ISO Recommendation does not apply to steel wires taken from a rope; it applies to bright or galvanized wires only for use in the manufacture of general purpose wire ropes.

Wires for ropes for special applications, such as the ones listed below, are outside of its scope :

- winding ropes for mining purposes for use in vertical and inclined shafts reaching to the surface and in blind shafts;
- ropes for aircraft controls;
- ropes for deep drilling equipment;
- ropes for aerial ropeways;
- ropes for elevators;
- ropes for prestressed concrete.

**3. QUALITY OF COATING**

For galvanized wire, the galvanizing may, at the request of the user, be

- of quality B, for all wire diameters from 0.20 mm inclusive up to 3.7 mm exclusive;
- of quality AB for all wire diameters from 0.40 mm inclusive up to 1.9 mm exclusive;
- of quality A for all wire diameters from 0.40 mm inclusive up to 3.7 mm exclusive.

These quality grades correspond to the different minimum requirements indicated in Table 4; each of them has its own mechanical characteristics.

\* Unless particularly mentioned below for certain tests.

#### 4. DIAMETERS

##### 4.1 Nominal diameter of the wire

The nominal diameter of the wire is the diameter specified by the ropemaker on the order, in millimetres. It should be the basis on which the values of all characteristics are determined for acceptance of the wire.

##### 4.2 Actual diameter of the wire

The actual diameter of the wire is the diameter given by the arithmetic mean of two measurements, one being perpendicular to the other. These two measurements should not differ by more than half the total tolerance given in Table 1 and their arithmetic mean must be within the limits of tolerance specified in Table 1.

TABLE 1 Dimensional limits and tolerances

Values in millimetres

Diameter		Tolerances		
from (incl.)	to (excl.)	Bright and galvanized wire Quality B	Galvanized wire Quality AB	Galvanized wire Quality A
0.20	0.25	± 0.010	X	X
0.25	0.40			
0.40	0.50	± 0.015	± 0.015	± 0.030
0.50	0.60			
0.60	0.70			
0.70	0.80			
0.80	1.00			
1.00	1.20	± 0.020	± 0.020	± 0.040
1.20	1.30			
1.30	1.50			
1.50	1.60			
1.60	1.80	± 0.025	X	± 0.050
1.80	1.90			
1.90	2.00			
2.00	2.30			
2.30	2.40			
2.40	2.50	± 0.030	X	± 0.060
2.50	3.00			
3.00	3.20			
3.20	3.50			
3.50	3.70			

## 5. BREAKING STRENGTH

### 5.1 Nominal strength

This ISO Recommendation is prepared on the basis of three nominal breaking strengths, as follows :

- (1) for galvanized wires of quality A and AB only, strength referred to as 145, corresponding to 1420 N/mm<sup>2</sup> minimum (i.e. 145 kgf/mm<sup>2</sup>);
- (2) for all qualities of wire, strength referred to as 160, corresponding to 1570 N/mm<sup>2</sup> minimum (i.e. 160 kgf/mm<sup>2</sup>);
- (3) for bright wires, galvanized quality B wires and galvanized wires quality AB only, strength referred to as 180, corresponding to 1760 N/mm<sup>2</sup> minimum (i.e. 180 kgf/mm<sup>2</sup>).

These nominal values are the lower limits for strengths. The upper limits are equal to the lower limits plus :

- 390 N/mm<sup>2</sup> (40 kgf/mm<sup>2</sup>) for wires of diameter less than 0.5 mm;
- 350 N/mm<sup>2</sup> (36 kgf/mm<sup>2</sup>) for wires of diameter between 0.5 mm (inclusive) and 1 mm (exclusive);
- 320 N/mm<sup>2</sup> (33 kgf/mm<sup>2</sup>) for wires of diameter between 1 mm (inclusive) and 1.5 mm (exclusive);
- 290 N/mm<sup>2</sup> (30 kgf/mm<sup>2</sup>) for wires of diameter between 1.5 mm (inclusive) and 2 mm (exclusive);
- 260 N/mm<sup>2</sup> (27 kgf/mm<sup>2</sup>) for wires of 2 mm diameter and larger.

### 5.2 Testing

The tensile test should be carried out in accordance with the procedure given in ISO Recommendation R 89, *Tensile testing of steel wire*; however, in view of the number of tests on wire involved in the inspection of a batch, the speed of application of the load may be higher than that specified in ISO Recommendation R 89 but without exceeding a speed producing an elongation of 25 % of the distance between grips within 1 minute. A 150 mm test piece should preferably be used.

In the case of dispute, the tensile test should be performed strictly in accordance with ISO Recommendation R 89, particularly insofar as the speed of application of the load is concerned.

## 6. SIMPLE TORSION TEST

Depending on its diameter and tensile strength, the wire should be capable of withstanding before fracture the minimum number of turns indicated in Table 2.

The test relates only to wire having a diameter of 0.5 mm and over.

The test should be carried out in accordance with the procedure given in ISO Recommendation R 136, *Simple torsion testing of steel wire*. The length 100  $\phi$  of the test piece between grips is preferable. When this length is impracticable the alternative length is at the discretion of the wire manufacturer and then the minimum of twists which the wire should withstand should be in direct ratio to the number specified in Table 2 for a test length of 100  $\phi$ .

TABLE 2 - Minimum number of turns

Diameter mm		Bright and galvanized wire Quality B		Galvanized wire Quality AB			Galvanized wire Quality A			
from (incl.)	to (excl.)	Nominal strength		Nominal strength			Nominal strength			
		160	180	145	160	180	145	160		
0.20	0.25	X								
0.25	0.40									
0.40	0.50									
0.50	0.60									
0.60	0.70	30	28	30	28	26	20	19		
0.70	0.80									
0.80	1.00									
1.00	1.20	29	26	29	26	23	19	18		
1.20	1.30									
1.30	1.50									
1.50	1.60	28	25	28	25	22	18	17		
1.60	1.80									
1.80	1.90			26	24	21				
1.90	2.00	26	24	X			18	17		
2.00	2.30									
2.30	2.40									
2.40	2.50	24	22				16	14		
2.50	3.00									
3.00	3.20	22	20				14	12		
3.20	3.50									
3.50	3.70	20	18				12	10		

**7. REVERSE BEND TEST**

Depending on its diameter and nominal tensile strength, the wire should be capable of withstanding without fracture the minimum number of reverse bends indicated in Table 3; the bending radii for different wire diameters are also given.

The test relates only to wire having a diameter of 0.5 mm and over.

It should be carried out in accordance with the procedure given in ISO Recommendation R 144, *Reverse bend testing of steel wire*.



TABLE 3 - Minimum number of reverse bends\*

Diameter mm	Radius of curvature of the supports mm	Bright wire and galvanized wire Quality B		Galvanized wire Quality AB			Galvanized wire Quality A	
		Nominal strength		Nominal strength			Nominal strength	
		160	180	145	160	180	145	160
0.50	1.25	7	6	7	6	5	6	5
0.55	1.75	13	12	13	12	11	11	10
0.60		11	10	11	10	9	9	8
0.65		9	8	9	8	7	8	7
0.70		8	7	8	7	6	7	6
0.75	2.5	15	14	15	14	13	13	12
0.80		14	13	14	13	12	12	11
0.85		13	12	13	12	11	11	10
0.90		12	11	12	11	10	10	9
0.95		11	10	11	10	9	9	8
1.00		10	9	10	9	8	9	8
1.10	3.75	17	16	17	16	15	15	14
1.20		15	14	15	14	13	13	12
1.30		13	12	13	12	11	11	10
1.40		11	10	11	10	9	9	8
1.50		10	9	10	9	8	8	7
1.60	5	13	12	13	12	11	11	10
1.70		12	11	12	11	10	10	9
1.80		11	10	11	10	9	9	8
1.90		10	9	10	9	8	8	7
2.00		9	8				7	7
2.10	7.5	13	12	X			11	10
2.20		12	11				10	9
2.30		11	10				9	8
2.40		10	9				8	7
2.50		9	8				7	7
2.60		9	8				6	6
2.70		8	7				6	6
2.80		8	7				5	5
2.90		7	6				5	4
3.00		6	5				4	3
3.10	10	9	8	8	6			
3.20		8	7	7	6			
3.30		8	7	7	5			
3.40		7	6	6	5			
3.50		7	6	6	5			
3.60		7	6	6	5			
3.70		7	6	6	5			

NOTE. -- If the diameter of the wire is between two consecutive diameters of the table, the number of bends corresponding to the next larger diameter should be taken.

\* This table is likely to be amended following the revision of ISO Recommendation R 144.

#### 8. TENSILE TEST ON KNOTTED WIRE

This test is limited to wire having a diameter of less than 0.5 mm and replaces, for this wire, the simple torsion test and the reverse bend test.

The length of wire with a single knot should be capable of withstanding, without breaking, a load equal to not less than 50 % of that corresponding to the nominal strength.

The test should be carried out in accordance with the procedure given in ISO Recommendation R 89, with the qualification that a simple knot should be made in the middle of the test piece.

#### 9. GALVANIZED WIRE – INSPECTION OF ZINC COATING

The coating of the wire should comply with the requirements indicated in Table 4, relating to the minimum mass of zinc deposited per unit of surface area, the continuity and the uniformity of the deposit.

This test should be carried out in accordance with sections 4 and 5 of ISO Recommendation R 345, *Shipbuilding details – Tests on galvanized steel wire for ropes*.

It is recalled that the above-mentioned Recommendation specifies, for the immersion, the use of a saturated copper sulphate solution prepared from crystalline copper sulphate ( $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ ), using 360 g of the salt to each litre of distilled water at a temperature of  $20 \pm 2^\circ\text{C}$ .

For wires of quality A only, an adhesion test should be carried out in accordance with clauses 3.1 and 3.2 of ISO Recommendation R 345.

#### 10. ACCEPTANCE CONDITIONS

This ISO Recommendation will be completed by the acceptance and sampling conditions, at the present time under consideration, which will be in accordance with the methods of statistical control.

However, because of the novelty of these methods, the sampling and the acceptance may be dealt with during the intervening period according to the traditional practice which is described in ISO 2701\*, *Drawn wire for general purpose non-alloy steel wire ropes – Sampling and acceptance – Traditional method*.

\* At present at the stage of Draft.