



# SLOVENSKI STANDARD

## oSIST prEN 10025-4:2018

01-september-2018

---

### Vroče valjani izdelki iz konstrukcijskih jekel - 4. del: Tehnični dobavni pogoji za termomehansko obdelana valjana variva drobnozrnata konstrukcijska jekla

Hot rolled products of structural steels - Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels

Warmgewalzte Erzeugnisse aus Baustählen - Teil 4: Technische Lieferbedingungen für thermomechanisch gewalzte schweißgeeignete Feinkornbaustähle

Produits laminés à chaud en aciers de construction - Partie 4 : Conditions techniques de livraison pour les aciers de construction soudable à grains fins obtenus par laminage thermomécanique

**Ta slovenski standard je istoveten z: prEN 10025-4**

---

#### **ICS:**

77.140.10	Jekla za toplotno obdelavo	Heat-treatable steels
77.140.50	Ploščati jekleni izdelki in polizdelki	Flat steel products and semi-products

**oSIST prEN 10025-4:2018**

**en,fr,de**



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 10025-4**

June 2018

ICS 77.140.10; 77.140.50

Will supersede EN 10025-4:2004

English Version

## Hot rolled products of structural steels - Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels

Produits laminés à chaud en aciers de construction -  
Partie 4 : Conditions techniques de livraison pour les  
aciers de construction soudable à grains fins obtenus  
par laminage thermomécanique

Warmgewalzte Erzeugnisse aus Baustählen - Teil 4:  
Technische Lieferbedingungen für thermomechanisch  
gewalzte schweißgeeignete Feinkornbaustähle

This draft European Standard is submitted to CEN members for second enquiry. It has been drawn up by the Technical Committee ECIS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword .....	4
<b>1 Scope</b> .....	<b>6</b>
<b>2 Normative references</b> .....	<b>6</b>
2.1 General standards .....	6
2.2 Standards on dimensions and tolerances .....	7
2.3 Standards on testing .....	7
<b>3 Terms and definitions</b> .....	<b>8</b>
<b>4 Classification and designation</b> .....	<b>8</b>
4.1 Classification.....	8
4.1.1 Main quality classes .....	8
4.1.2 Grades and qualities .....	8
4.2 Designation .....	9
<b>5 Information to be supplied by the purchaser</b> .....	<b>9</b>
5.1 Mandatory information .....	9
5.2 Options.....	9
<b>6 Manufacturing process</b> .....	<b>9</b>
6.1 Steel making process .....	9
6.2 Deoxidation and grain structure.....	10
6.3 Delivery conditions .....	10
<b>7 Requirements</b> .....	<b>10</b>
7.1 General.....	10
7.2 Chemical composition .....	10
7.3 Mechanical properties .....	11
7.3.1 General.....	11
7.3.2 Impact properties .....	11
7.3.3 Improved deformation properties perpendicular to the surface .....	11
7.4 Technological properties.....	11
7.4.1 Weldability .....	11
7.4.2 Formability and flame straightening.....	12
7.4.3 Hot-dip zinc-coating.....	12
7.5 Surface properties .....	13
7.5.1 Strip.....	13
7.5.2 Plates and wide flats .....	13
7.5.3 Sections.....	13
7.5.4 Bars and rods.....	13
7.6 Internal soundness.....	13
7.7 Dimensions, tolerances on dimensions and shape, mass.....	13
<b>8 Inspection</b> .....	<b>14</b>
8.1 General.....	14
8.2 Type of inspection and inspection document.....	14
8.3 Tests to be carried out .....	14
<b>9 Frequency of testing and preparation of samples and test pieces</b> .....	<b>15</b>
9.1 Frequency of testing.....	15
9.1.1 Chemical analysis.....	15
9.1.2 Mechanical tests .....	15

9.2	Preparation of samples and test pieces.....	15
9.2.1	Selection and preparation of samples for chemical analysis .....	15
9.2.2	Location of samples and orientation of test pieces for mechanical tests.....	15
9.2.3	Preparation of test pieces for mechanical tests .....	15
9.3	Identification of samples and test pieces.....	16
10	Test methods.....	16
10.1	Chemical analysis .....	16
10.2	Mechanical tests.....	17
10.2.1	Tensile test.....	17
10.2.2	Impact test.....	17
10.3	Ultrasonic testing.....	17
10.4	Retests .....	17
11	Marking, labelling, packaging.....	17
12	Complaints .....	18
13	Options .....	18
Annex A (normative) Location of samples and test pieces.....		25
Bibliography .....		28

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 10025-4:2019](https://standards.iteh.ai/catalog/standards/sist/79bd037b-0446-4b23-aade-a6588a85fd6f/sist-en-10025-4-2019)

<https://standards.iteh.ai/catalog/standards/sist/79bd037b-0446-4b23-aade-a6588a85fd6f/sist-en-10025-4-2019>

**prEN 10025-4:2018 (E)****European foreword**

This document (prEN 10025-4:2018) has been prepared by Technical Committee ECISS/TC 103 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This document is currently submitted to the second CEN Enquiry.

This document will supersede EN 10025-4:2004.

This European Standard consists of the following parts, under the general title *Hot rolled products of structural steels*:

*Part 1: General*

*Part 2: Technical delivery conditions for non-alloy structural steels*

*Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*

*Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*

*Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*

*Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*

For a short transition period there will be a coexistence of EN 10025-1:2004 with EN 10025-2 to EN 10025-6:2018, since the new EN 10025-1 has to fulfil the requirements of the CPR and will therefore be published later. For this short transition period up-to-the publication of the next edition of part 1 the following has to be taken into account for EN 10025-1:2004:

- a) all dated and undated references to EN 10025-1:2004 to EN 10025-6:2004 are unchanged to this version with following exception: In 9.2.2.1 the reference must be 8.3.1 and 8.3.2 instead of 8.4.1 and 8.4.2,
- b) Clauses 5, 12 and 13 of EN 10025-1:2004 are no longer relevant.

The main changes with respect to the previous edition are listed below:

- a) part 4 is now a stand-alone standard for technical delivery conditions including the preparation of samples and test pieces, the test methods, the marking, labelling and packaging and the drawings;
- b) for construction purposes this standard and part 1 must be used together;
- c) requirements for elements not defined were added to 7.2.1 and 7.2.2;
- d) Option 33 was added, Option 3 was renumbered to Option 24 and Option 9 was deleted;
- e) Si-content in 7.2.4 was changed;
- f) 7.4.3 concerning hot-dip zinc coating was modified;
- g) key to Figure A.1 was updated;
- h) steel grade S500M was added;

- i) Annex B deleted;
- j) references were updated and document editorial revised.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10025-4:2019

<https://standards.iteh.ai/catalog/standards/sist/79bd037b-0446-4b23-aade-a6588a85fd6f/sist-en-10025-4-2019>

**prEN 10025-4:2018 (E)****1 Scope**

This document specifies technical delivery conditions for flat and long products of hot rolled weldable fine grain structural steels in the thermomechanical rolled condition in the grades and qualities given in Tables 1 to 3 (chemical composition) and Tables 4 to 6 (mechanical properties) in thickness  $\leq 150$  mm.

The steels specified in this document are especially intended for use in heavily loaded parts of welded structures such as, bridges, flood gates, storage tanks, water supply tanks, etc., for service at ambient and low temperatures.

**2 Normative references**

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

**2.1 General standards**

EN 1011-2, *Welding — Recommendations for welding of metallic materials — Part 2: Arc welding of ferritic steels*

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10025-1:2004, *Hot rolled products of structural steels — Part 1: General technical delivery conditions*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10079, *Definition of steel products*

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*

EN 10163-3, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 3: Sections*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

CR 10320, *Optical emission analysis of low alloy steels (routine method) — Method for determination of C, Si, S, P, Mn, Cr, Ni and Cu*

CEN/TR 10347, *Guidance for forming of structural steels in processing*

FprEN ISO 9443:2018, *Surface quality classes for hot-rolled bars and wire rod (ISO/FDIS 9443:2018)*



EN ISO 14713-2:2009, *Zinc coatings — Guidelines and recommendations for the protection against corrosion of iron and steel in structures — Part 2: Hot dip galvanizing (ISO 14713-2:2009)*

## 2.2 Standards on dimensions and tolerances

EN 10017, *Steel rod for drawing and/or cold rolling — Dimensions and tolerances*

EN 10024, *Hot rolled taper flange I sections — Tolerances on shape and dimensions*

EN 10029, *Hot-rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10034, *Structural steel I and H sections — Tolerances on shape and dimensions*

EN 10048, *Hot rolled narrow steel strip — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled strip and plate/sheet cut from wide strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

EN 10055, *Hot rolled steel equal flange tees with radiused root and toes — Dimensions and tolerances on shape and dimensions*

EN 10056-1, *Structural steel equal and unequal leg angles — Part 1: Dimensions*

EN 10056-2, *Structural steel equal and unequal leg angles — Part 2: Tolerances on shape and dimensions*

EN 10058, *Hot rolled flat steel bars for general purposes — Dimensions and tolerances on shape and dimensions*

EN 10059, *Hot rolled square steel bars for general purposes — Dimensions and tolerances on shape and dimensions*

EN 10060, *Hot rolled round steel bars for general purposes — Dimensions and tolerances on shape and dimensions*

EN 10061, *Hot rolled hexagon steel bars for general purposes — Dimensions and tolerances on shape and dimensions*

EN 10067, *Hot rolled bulb flats — Dimensions and tolerances on shape, dimensions and mass*

EN 10279, *Hot rolled steel channels — Tolerances on shape, dimensions and mass*

EN 10363, *Continuously hot-rolled patterned steel strip and plate/sheet cut from wide strip — Tolerances on dimensions and shape*

EN 10365, *Hot rolled steel channels, I and H sections — Dimensions and masses*

## 2.3 Standards on testing

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10306, *Iron and steel — Ultrasonic testing of H beams with parallel flanges and IPE beams*

EN 10308, *Non destructive testing — Ultrasonic testing of steel bars*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

**prEN 10025-4:2018 (E)**

EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377:2017)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

**3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 10079 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

**3.1****thermomechanical rolling**

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition with certain properties which cannot be achieved or repeated by heat treatment alone

Note 1 to entry: Thermomechanical rolling can include processes with an increasing cooling rate with or without tempering including self-tempering but excluding direct quenching and quenching and tempering.

Note 2 to entry: In some publications the word TMCP (Thermomechanical Control Process) is also used.

**3.2****fine grain steels**

steels with fine grain structure with an equivalent index of ferritic grain size  $\geq 6$

Note 1 to entry: For the determination of grain sizes see EN ISO 643.

**4 Classification and designation****4.1 Classification****4.1.1 Main quality classes**

All steel grades specified in this document shall be classified as alloy special steels according to EN 10020 except grade S275 which is a non-alloy quality steel.

**4.1.2 Grades and qualities**

This document specifies five steel grades S275, S355, S420, S460 and S500. All steel grades may be supplied in the following qualities as specified at the time of the order:

- with specified minimum values of impact energy at temperatures not lower than  $-20\text{ °C}$ , designated as M;
- with specified minimum values of impact energy at temperatures not lower than  $-50\text{ °C}$ , designated as ML.

## 4.2 Designation

**4.2.1** For the steel grades covered by this document the steel names shall be allocated in accordance with EN 10027-1; the steel numbers shall be allocated in accordance with EN 10027-2.

**4.2.2** The designation shall consist of:

- number of this document (EN 10025-4);
- steel name or the steel number; the steel name consisting of:
  - symbol S (for structural steel);
  - indication of the minimum specified yield strength for thickness  $\leq 16$  mm expressed in MPa;
  - delivery condition M;
  - capital letter L for the quality with specified minimum values of impact energy at temperatures not lower than  $-50$  °C.

**EXAMPLE** Thermomechanical rolled structural steel (S) with a specified minimum yield strength at room temperature of 355 MPa and with a specified minimum impact energy at  $-50$  °C:

EN 10025-4 - S355ML  
or  
EN 10025-4 - 1.8834

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

## 5 Information to be supplied by the purchaser

### 5.1 Mandatory information

SIST EN 10025-4:2019

<https://standards.iteh.ai/catalog/standards/sist/79bd037b-0446-4b23-aade->

The following information shall be supplied by the purchaser at the time of the order:

- a) quantity to be delivered;
- b) product form and the number of the standard for dimensions and tolerances (see 2.2);
- c) nominal dimensions and tolerances on dimensions and shape (see 7.7.1);
- d) steel designation (see 4.2.2);
- e) additional requirements of inspection and testing and all required options (see 5.2 and Clause 13);
- f) type of inspection document according to EN 10204 (see 8.1).

### 5.2 Options

A number of options are specified in Clause 13. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification, see 5.1 a) to d) and f).

## 6 Manufacturing process

### 6.1 Steel making process

The steel making process is at the discretion of the manufacturer with the exclusion of the open hearth (Siemens-Martin) process.

See **Option 1** (details of manufacturing process).

## prEN 10025-4:2018 (E)

### 6.2 Deoxidation and grain structure

Steels of EN 10025-4 shall

- be fully killed,
- have a fine grain structure,
- contain nitrogen binding elements in amounts sufficient to bind the available nitrogen (for example min. 0,020 % total aluminium). The usual guideline is a minimum aluminium to nitrogen ratio of 2:1, when no other nitrogen binding elements are present. Such other elements shall be reported in the inspection document (see Table 1).

### 6.3 Delivery conditions

The products shall be supplied in the thermomechanical rolled condition as defined in Clause 3.

## 7 Requirements

### 7.1 General

The requirements in 7.2 and 7.3 apply for sampling, preparation of test pieces and testing specified in Clauses 9 and 10.

### 7.2 Chemical composition

**7.2.1** The chemical composition determined by ladle analysis shall comply with the specified values of Table 1.

For elements not defined in the table for the chemical composition for ladle analysis, limit values of Table 1 of EN 10020:2000 shall apply as maximum values.

**7.2.2** The limits applicable for the product analysis are given in Table 2. The product analysis shall be carried out when specified at the time of the order.

See **Option 2** (product analysis).

For elements not defined in tables for the chemical composition for product analysis, limit values of Table 1 of EN 10020:2000 shall apply as maximum values.

**7.2.3** The maximum carbon equivalent values based on the ladle analysis, given in Table 3 shall apply.

For determining the carbon equivalent value the following IIW (International Institute of Welding) formula shall be used:

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

**7.2.4** When products are supplied with a control on Si e.g. for hot-dip zinc-coating so that there could be a need to increase the content of other elements like C and Mn to achieve the required tensile properties, the maximum carbon equivalent values of Table 3 shall be increased as follows:

- for Si ≤ 0,04 %, increase the value of the CEV by 0,02;
- for Si ≤ 0,25 %, increase the value of the CEV by 0,01.