

SLOVENSKI STANDARD
oSIST prEN 10025-6:2014

01-julij-2014

Vroče valjani izdelki iz konstrukcijskih jekel - 6. del: Tehnični dobavni pogoji za ploščate izdelke iz konstrukcijskih jekel z veliko plastično trdnostjo v kaljenem in popuščenem stanju

Hot rolled products of structural steels - Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition

Warmgewalzte Erzeugnisse aus Baustählen - Teil 6: Technische Lieferbedingungen für Flacherzeugnisse aus Stählen mit höherer Streckgrenze im vergüteten Zustand

Produits laminés à chaud en aciers de construction - Partie 6 : Conditions techniques de livraison pour produits plats des aciers à haute limite d'élasticité à l'état trempé et revenu

Ta slovenski standard je istoveten z: **prEN 10025-6**

ICS:

77.140.10	Jekla za topotno obdelavo	Heat-treatable steels
77.140.50	Ploščati jekleni izdelki in polizdelki	Flat steel products and semi-products

oSIST prEN 10025-6:2014

en,fr,de

**EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM**

**WHITE DRAFT
prEN 10025-6**

May 2014

ICS 77.140.10; 77.140.50

Will supersede EN 10025-6:2004+A1:2009

English Version

Hot rolled products of structural steels - Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition

Produits laminés à chaud en aciers de construction - Partie 6 : Conditions techniques de livraison pour produits plats des aciers à haute limite d'élasticité à l'état trempé et revenu

Warmgewalzte Erzeugnisse aus Baustählen - Teil 6: Technische Lieferbedingungen für Flacherzeugnisse aus Stählen mit höherer Streckgrenze im vergüteten Zustand

This draft European Standard is submitted to ECISS/COCOR before submission to CEN members for formal vote. It has been drawn up by the Technical Committee ECISS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword	3
1 Scope	4
2 Normative references	4
2.1 General Standards	4
2.2 Standards on dimensions and tolerances (see 7.7.1)	5
2.3 Standards on testing	5
3 Terms and definitions	5
4 Classification and designation	5
4.1 Classification	5
4.2 Designation	6
5 Information to be supplied by the purchaser	6
5.1 Mandatory information	6
5.2 Options	7
6 Manufacturing process	7
6.1 Steel making process	7
6.2 Deoxidation or grain size	7
6.3 Delivery conditions	7
7 Requirements	7
7.1 General	7
7.2 Chemical composition	7
7.3 Mechanical properties	8
7.4 Technological properties	8
7.5 Surface properties	10
7.6 Internal soundness	10
7.7 Tolerances on dimensions and shape, mass	10
8 Inspection	10
8.1 General	10
8.2 Type of inspection and inspection document	10
8.3 Frequency of testing	10
8.4 Tests to be carried out	11
9 Preparation of samples and test pieces	12
9.1 Selection and preparation of samples for chemical analysis	12
9.2 Location and orientation of samples and test pieces for mechanical tests	12
9.3 Identification of samples and test pieces	12
10 Test methods	12
10.1 Chemical analysis	12
10.2 Mechanical tests	12
10.3 Ultrasonic testing	13
10.4 Retests	13
11 Marking, labelling, packaging	13
12 Complaints	13
13 Options (see 5.2)	13
Annex A (informative) Minimum recommended inside bend radii for flanging	20
Bibliography	21

Foreword

This document (prEN 10025-6:2014) has been prepared by Technical Committee ECISS/TC 103 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This document is currently submitted to the COCOR Vote.

This document will supersede EN 10025-6:2004:2004+A1:2009.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

The titles of the other parts of this document are:

Part 1: General;

Part 2: Technical delivery conditions for non-alloy structural steels;

Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels;

Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels;

Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance

prEN 10025-6:2014 (E)

1 Scope

Part 6 of this document, in addition to part 1, specifies technical delivery conditions for flat products of high yield strength alloy special steels. The grades and qualities are given in Tables 1 to 3 (chemical composition) and Tables 4 to 6 (mechanical properties) and are supplied in the quenched and tempered condition as given in 6.3.

The steels specified in this document are applicable to hot-rolled flat products with a minimum nominal thickness of 3 mm and a maximum nominal thickness of 150 mm for grades S460, S500, S550, S620 and S690, a maximum nominal thickness of 100 mm for grades S890 and S960, in steels which, after quenching and tempering, have a specified minimum yield strength of 460 MPa¹⁾ to 960 MPa¹⁾.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

2.1 General Standards

EN 1011-2, *Welding — Recommendations for welding of metallic materials — Part 2: Arc welding of ferritic steels*

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

prEN 10025-1:2014, *Hot rolled products of structural steels — Part 1: General*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10079:2007, *Definition of steel products*

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plates and wide flats*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

EN ISO 14713-2:2009, *Guidelines and recommendations for the protection against corrosion of iron and steel structures — Zinc coating — Part 2: Hot dip galvanizing (ISO 14713-2:2009)*

1) 1 MPa = 1 N/mm².

2.2 Standards on dimensions and tolerances (see 7.7.1)

EN 10029, *Hot rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10048, *Hot rolled narrow steel strip — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

2.3 Standards on testing

EN 10160, *Ultrasonic testing of steel flat product of thickness equal to or greater than 6 mm (reflection method)*

EN ISO 148-1, *Metallic materials – Charpy pendulum impact test – Part 1: Test method (ISO 148-1:2009)*

EN ISO 6892-1, *Metallic materials – Tensile testing – Part 1: Method of test at room temperature (ISO 6892-1:2009)*

EN ISO 14284, *Steel and iron – Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in prEN 10025-1:2014 and the following apply.

3.1

quenching

operation which consists of cooling a ferrous product more rapidly than in still air

3.2

tempering

heat treatment applied to a ferrous product generally after quench hardening or other heat treatment to bring the properties to the required level

Note 1 to entry Tempering consists of heating to specific temperatures ($< A_{C1}$) and soaking one or more times followed by cooling at an appropriate rate.

4 Classification and designation

4.1 Classification

4.1.1 Main quality classes

The steel grades specified in this document shall be classified as alloy special steels according to EN 10020.

4.1.2 Grades and qualities

This document specifies seven steel grades. They differ in their minimum yield strength at room temperature.

All the grades can be delivered in the following qualities as specified at the time of the order:

- with specified minimum values of impact energy at temperatures not lower than -20 °C, designated as Q;
- with specified minimum values of impact energy at temperatures not lower than -40 °C, designated as QL₂;
- with specified minimum values of impact energy at temperatures not lower than -60 °C, designated as QL1.

prEN 10025-6:2014 (E)**4.2 Designation**

4.2.1 The designation shall be in accordance with prEN 10025-1.

4.2.2 The designation shall consist of:

- the number of this document (prEN 10025-6);
- the steel name or the steel number; the steel name consisting of:
 - the symbol S (for structural steel);
 - the indication of the minimum specified yield strength for thickness ≤ 50 mm expressed in MPa¹⁾;
 - the delivery condition Q;
 - the capital letter L or L1 for the quality with specified minimum values of impact energy at temperatures not lower than -40 °C or -60 °C.

EXAMPLE Structural steel (S) quenched and tempered (Q), with a specified minimum yield strength at room temperature of 460 MPa¹⁾ and with a specified minimum value of impact energy at -40 °C (L):

Steel prEN 10025-6 – S460QL

or

Steel prEN 10025-6 - 1.8906

5 Information to be supplied by the purchaser**5.1 Mandatory information**

The following information shall be supplied by the purchaser at the time of the order:

- a) quantity to be delivered;
- b) product form;
- c) number of the relevant part of this document;
- d) steel name or the steel number (see 4.2.2);
- e) nominal dimensions and tolerances on dimensions and shape (see 7.7.1);
- f) additional requirements of inspection and testing as specified in prEN 10025-6;
- g) type of inspection document according to EN 10204 (see 8.2);
- h) all required options (see 5.2).

1) 1 MPa = 1 N/mm².