
**Pulps — Laboratory beating —
Part 2:
PFI mill method**

Pâtes — Raffinage de laboratoire —

Partie 2: Méthode au moulin PFI
iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 5264-2:2002

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>



Reference number
ISO 5264-2:2002(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 5264-2:2002

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus and auxiliary materials	1
5 Sampling	2
6 Preparation of sample	2
7 Procedure	2
8 Test report	4

Annexes

A PFI mill	5
B Control and maintenance of the PFI mill	7
C Checking the stability of the PFI mill	9
Bibliography	10

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 5264-2:2002](https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002)

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 5264 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 5264-2 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulps*.

This second edition cancels and replaces the first edition (ISO 5264-2:1979), which has been technically revised.

ISO 5264 consists of the following parts, under the general title *Pulps — Laboratory beating*:

- Part 1: *Valley beater method*
- Part 2: *PFI mill method*
- Part 3: *Jokro mill method*

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

Annexes A and B form a normative part of this part of ISO 5264. Annex C is for information only.

Introduction

In view of the widespread use of the following beaters:

- Valley beater;
- PFI mill;
- Jokro mill;

it has been decided to provide guidance on the use of these beaters in order to achieve consistency of results with each instrument. Although all three beaters show similar trends in the effect on pulp properties, there is no correlation between the actual results obtained with the different types of beaters.

ISO 5264-1 specifies a method of laboratory beating using a Valley beater and ISO 5264-3 a method using a Jokro mill.

Beating is a preliminary step in the preparation of laboratory sheets for testing the physical properties of pulps. In the PFI mill, each beating is performed separately, i.e. a new test portion of unbeaten pulp is taken for each beating.

NOTE A complete test of physical properties normally comprises unbeaten pulp and several beatings of the same pulp, where the beating is carried out for different numbers of roll revolutions. The number of roll revolutions depends on the type of pulp and the beating load. After beating, the drainability is measured according to ISO 5267-1 or ISO 5267-2, and laboratory sheets are prepared according to ISO 5269-1 or ISO 5269-2.

(standards.iteh.ai)

ISO 5264-2:2002

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 5264-2:2002

<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

Pulps — Laboratory beating —

Part 2: PFI mill method

1 Scope

This part of ISO 5264 specifies a method, using a PFI mill, for the laboratory beating of pulp. The description is limited to the sampling and beating of the pulp, the withdrawal and distribution of samples, and the beating equipment.

NOTE Beating is a preliminary step in testing the physical properties of pulp.

In principle, this method is applicable to all kinds of chemical and semi-chemical pulps. In practice, the method may not give satisfactory results with certain pulps having extremely long fibres.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 5264. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 5264 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 638, *Pulps — Determination of dry matter content*

ISO 4119, *Pulps — Determination of stock concentration*

ISO 5263, *Pulps — Laboratory wet disintegration*

ISO 5267-1, *Pulps — Determination of drainability — Part 1: Schopper-Riegler method*

ISO 5267-2, *Pulps — Determination of drainability — Part 2: "Canadian Standard" freeness method*

ISO 7213, *Pulps — Sampling for testing*

ISO 14487, *Pulps — Standard water for physical testing*

3 Principle

A measured amount of pulp at a specified stock concentration is beaten between a roll with bars and a smooth beater housing, both rotating in the same direction, but at different peripheral speeds.

4 Apparatus and auxiliary materials

Ordinary laboratory equipment and the following.

4.1 PFI mill, as specified in annex A.

See normative annex B and informative annex C.

4.2 Disintegrator, as specified in ISO 5263.

4.3 Balance, capable of weighing the sample with an error of less than $\pm 0,2$ g.

4.4 Standard water, purified to an electrical conductivity $\leq 0,25$ mS/m at 25 °C, as specified in ISO 14487.

4.5 A reference pulp, kept for beating-control purposes and stored for a time sufficiently long to avoid further changes in physical properties. The reference pulp should, if possible, be of the same grade as that normally beaten in the beating equipment concerned. Since some pulp grades are not stable, it might be necessary to choose another grade.

To avoid the influence of storage time, the reference pulp should be kept at room temperature (not at too high a relative humidity) in a dark and dust-free place.

NOTE Stored under the recommended conditions, the reference pulp will, in most cases, be stable for approximately 10 years. Changes in the level of the tensile strength and tear strength values may be an indication that the reference pulp is no longer stable. The stability can be checked by measuring the viscosity of the reference pulp, e.g. twice a year.

5 Sampling

If the beating is being done to evaluate a lot of pulp, the sample shall be selected in accordance with ISO 7213.

If the beating is done on another type of sample, report the source of the sample and, if possible, the sampling procedure used.

Select the test portions so that they are representative of the gross sample received.

ISO 5264-2:2002
<https://standards.iteh.ai/catalog/standards/sist/0f7055df-079e-4dd7-b4c4-cd4c68e0c575/iso-5264-2-2002>

6 Preparation of sample

If the sample is wet or air-dry, weigh a test portion for the determination of dry-matter content in accordance with ISO 638. If the sample is in the form of an aqueous pulp suspension, determine the dry matter content in accordance with ISO 4119.

Take a test portion of the sample corresponding to $(30,0 \pm 0,5)$ g of oven-dry pulp. Do not cut pulp sheets and avoid the use of cut edges. If the sample is in the form of machine-dried sheets or flash-dried slabs, soak the pulp thoroughly in 0,5 litre of standard water (4.4) at room temperature for not less than 4 h. Tear the soaked pulp into pieces approximately 25 mm \times 25 mm in size. It is essential that the pulp sample be thoroughly softened by soaking, to ensure that the preliminary disintegration leads to only a minimal beating effect. Wet pulps may be disintegrated without soaking.

7 Procedure

7.1 General

For each test portion (each degree of beating), carry out the following procedure.

7.2 Disintegration

Disintegrate the initially wet portion or the soaked test portion as described in ISO 5263. Use standard water (4.4) at (20 ± 5) °C to give a total volume of $(2\ 000 \pm 25)$ ml. The mass fraction in the disintegrator (4.2) will then be about 1,5 %.

Pulps having an initial mass fraction of dry matter of 20 % or more shall be disintegrated for 30 000 revolutions of the propeller whereas pulps having an initial mass fraction of dry matter of less than 20 % shall be disintegrated for 10 000 revolutions of the propeller.

After disintegration, check visually that the pulp is completely disintegrated. If not, continue the disintegration until complete separation of fibres is achieved.

NOTE A temperature outside the range (20 ± 5) °C may be used for climatic reasons, provided that this is stated in the test report.

7.3 Thickening

After disintegration, drain the pulp suspension on a Büchner funnel or other suitable device to a mass fraction between 11 % and 20 %. To avoid any loss of fibres, refilter the filtrate through the fibre mat, if necessary several times.

Using a balance, dilute the thickened pulp with standard water (4.4) to a total mass of (300 ± 5) g, corresponding to a mass fraction of 10 % stock.

7.4 Beating

7.4.1 Beating conditions

Check that the beating conditions are correct (see A.2).

For most pulps, the beating force per unit bar length shall be $(3,33 \pm 0,10)$ N/mm, assuming that only one bar at a time makes contact with the housing. It is important that the distance screw is disengaged during beating, i.e. no fixed gap shall be used.

NOTE Experience has shown that, for some pulps, a lower beating force per unit bar length may be needed to be able to evaluate the physical properties of the pulp in a correct way. In such cases, the beating force per unit bar length could be $(1,77 \pm 0,10)$ N/mm. This deviation from the standard procedure must be reported.

7.4.2 Beating procedure

Bring the beating elements of the PFI mill (4.1) and the thickened pulp sample, prepared in accordance with 7.3, to a temperature of (20 ± 5) °C (see note to 7.2). Transfer the pulp sample to the beater housing, and distribute it as evenly as possible over the wall. A uniform band of pulp will ensure a smooth start-up, thus reducing unnecessary vibrations and attaining a more stable beating. Ensure that no pulp remains on the bottom of the beater housing within an area corresponding to the cross-section of the roll. Insert the roll in the beater housing, and press the cover correctly into position in the housing.

WARNING — When beating for a high number of revolutions, the temperature of the beating elements may increase. If necessary, cool the beating elements with water to bring the temperature within the specified range before the next beating.

Set the beater housing in rotation so that the pulp is slung against the wall and start the roll motor. When both beating elements have attained full speed, apply the required beating force per unit bar length. Apply the beating load at a constant rate over a period of 2 s. At the instant of full application of the load; release the revolution-counter lever arm to engage the counter.

When the required number of roll revolutions has been reached, stop the beating by releasing the beating force. Switch off the motors, and allow the roll and beater housing to come to a complete stop. Lift the lid and bring the roll to its starting position.