

**SLOVENSKI STANDARD  
SIST EN ISO 15614-12:2004**

**01-november-2004**

---

**Popis in kvalifikacija varilnih postopkov za kovinske materiale - Preskus postopka varjenja - 12. del: Točkovno, kolutno in projekcijsko varjenje (ISO 15614-12:2004)**

Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 12: Spot, seam and projection welding (ISO 15614-12:2004)

Anforderung und Qualifizierung von Schweißverfahren für metallische Werkstoffe - Schweißverfahrensprüfung - Teil 12: Widerstandspunkt-, Rollennaht- und Buckelschweißen (ISO 15614-12:2004)

**Open STANDARD REVIEW  
(standards.iteh.ai)**

Descriptif et qualification d'un mode opératoire de soudage pour les matériaux métalliques - Epreuve de qualification d'un mode opératoire de soudage - Partie 12: Soudage par points, à la molette et par bossages (ISO 15614-12:2004)

**Ta slovenski standard je istoveten z: EN ISO 15614-12:2004**

---

**ICS:**

25.160.10      Varilni postopki in varjenje      Welding processes

**SIST EN ISO 15614-12:2004**

**en**

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN ISO 15614-12:2004

<https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004>

**EUROPEAN STANDARD**  
**NORME EUROPÉENNE**  
**EUROPÄISCHE NORM**

**EN ISO 15614-12**

August 2004

ICS 25.160.10

English version

**Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 12: Spot, seam and projection welding (ISO 15614-12:2004)**

Descriptif et qualification d'un mode opératoire de soudage pour les matériaux métalliques - Epreuve de qualification d'un mode opératoire de soudage - Partie 12: Soudage par points, à la molette et par bossages (ISO 15614-12:2004)

Anforderung und Qualifizierung von Schweißverfahren für metallische Werkstoffe - Schweißverfahrensprüfung - Teil 12: Widerstandspunkt-, Rollennaht- und Buckelschweißen (ISO 15614-12:2004)

This European Standard was approved by CEN on 16 January 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

**THE STANDARD PREVIEW**  
**(standards.itch.ai)**

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[www.standards.itch.ai/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004](http://www.standards.itch.ai/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004)



EUROPEAN COMMITTEE FOR STANDARDIZATION  
 COMITÉ EUROPÉEN DE NORMALISATION  
 EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## EN ISO 15614-12:2004 (E)

## Contents

Page

<b>Foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>6</b>
<b>3 Terms and definitions</b> .....	<b>6</b>
<b>4 Preliminary welding procedure specification (pWPS)</b> .....	<b>6</b>
<b>5 Welding procedure test</b> .....	<b>6</b>
<b>6 Test piece</b> .....	<b>7</b>
<b>6.1 General</b> .....	<b>7</b>
<b>6.2 Shape and dimensions of test pieces and test specimens for destructive testing</b> .....	<b>7</b>
<b>6.2.1 General</b> .....	<b>7</b>
<b>6.2.2 Macrosection</b> .....	<b>7</b>
<b>6.3 Welding of components, test pieces or test specimens</b> .....	<b>7</b>
<b>7 Examination and testing</b> .....	<b>7</b>
<b>7.1 Extent of testing</b> .....	<b>7</b>
<b>7.2 Location and cutting of test specimens</b> .....	<b>9</b>
<b>(standards.iteh.ai)</b>	
<b>7.3 Visual testing</b> .....	<b>9</b>
<b>7.4 Re-testing</b> .....	<b>9</b>
<b>8 Range of qualification</b> ..... <b>SIST EN ISO 15614-12:2004</b>	<b>10</b>
<b>8.1 General</b> ..... <a href="https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004">https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004</a> .....	<b>10</b>
<b>8.2 Related to the manufacturer</b> .....	<b>10</b>
<b>8.3 Related to the material</b> .....	<b>10</b>
<b>8.4 Common to all welding procedures</b> .....	<b>10</b>
<b>8.4.1 Welding process</b> .....	<b>10</b>
<b>8.4.2 Type of current</b> .....	<b>10</b>
<b>8.4.3 Welding cycle</b> .....	<b>10</b>
<b>8.4.4 Postweld heat treatment in the welding equipment</b> .....	<b>10</b>
<b>8.4.5 Type of weld equipment</b> .....	<b>11</b>
<b>8.4.6 Welding electrodes</b> .....	<b>11</b>
<b>9 Welding Procedure Qualification Record form (WPQR)</b> .....	<b>11</b>
<b>Annex ZA (normative) Normative references to International publications with their relevant European publication</b> .....	<b>12</b>
<b>Bibliography</b> .....	<b>13</b>

## Foreword

This document (EN ISO 15614-12:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2005, and conflicting national standards shall be withdrawn at the latest by February 2005.

Normative references to International Standards are listed in normative annex ZA.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 15614-12:2004  
<https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004>

## EN ISO 15614-12:2004 (E)

### Introduction

All new welding procedure qualifications are to be in accordance with this standard from the date of its issue.

This standard does not invalidate previous welding procedure qualifications made to former national standards or specifications provided the intent of the technical requirements is satisfied and the previous procedure qualifications are relevant to the application and production work on which they are to be employed.

Also, where additional tests have to be carried out to make the qualification technically equivalent, it is only necessary to do the additional tests on a test piece which should be made in accordance with this standard.

### iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 15614-12:2004  
<https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004>

## 1 Scope

This standard specifies the tests which may be used for qualification of welding procedure specifications for spot, seam and projection welding processes.

This standard is part of a series of standards. Details of this series are given in EN ISO 15607:2003, annex A.

This standard defines the conditions for carrying out tests and the limits of validity of a qualified welding procedure for all practical welding operations covered by this standard.

The tests required to qualify the procedure for a particular component/assembly depend on the performance and quality requirements of the component/assembly and shall be established before any qualification is undertaken.

Tests shall be carried out in accordance with this standard unless more severe tests are specified by the relevant application standard or contract when these shall apply.

The acceptability of applying the principles of the standard to other resistance welding processes should be established before any qualification is undertaken.

**NOTE** Specific service, material or manufacturing conditions may require more comprehensive testing than is specified by this standard.

Such tests may include:

### iTeh STANDARD PREVIEW (standards.iteh.ai)

- method for fatigue testing for spot welded joints;
- specimen dimensions and procedure for impact, shear and cross tension testing resistance spot and projection welds;
- bend test; [SIST EN ISO 15614-12:2004](#)  
<https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-6a7e72a803ba/sist-en-iso-15614-12-2004>
- surface crack detection;
- ultrasonic tests, x-ray test;
- chemical analysis; corrosion tests;
- micro examination, including assessment of hot cracking behaviour;
- tests of components or complete welded assemblies.

This standard covers the following resistance welding processes, as defined in EN ISO 4063:

21 - spot welding;

    211 - indirect spot welding;

    212 - direct spot welding;

22 - seam welding;

    221 - lap seam welding;

    222 - mash seam welding;

    225 - fillet butt-seam welding;

    226 - seam welding with strip;

**EN ISO 15614-12:2004 (E)**

- 23 - projection welding;
- 231 indirect projection welding;
- 232 direct projection welding.

**2 Normative references**

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

**EN 1418, Welding personnel — Approval testing of welding operators for fusion welding and resistance weld setters for fully mechanized and automatic welding of metallic materials.**

**EN ISO 14270, Specimen dimensions and procedure for mechanized peel testing resistance spot, seam and embossed projection welds (ISO 14270: 2000).**

**EN ISO 14271, Vickers hardness testing of resistance spot, projection and seam welds (low load and micro hardness) (ISO 14271: 2000).**

**EN ISO 14272, Specimen dimensions and procedure for cross tension testing resistance spot and embossed projection welds (ISO 14272: 2000).**

**EN ISO 14273, Specimen dimensions and procedure for shear testing resistance spot, seam and embossed projection welds (ISO 14273: 2000).**

**EN ISO 17653, Destructive tests on welds in metallic materials — Torsion test of resistance spot welds (ISO 17653: 2003.)**

[SIST EN ISO 15614-12:2004](#)

**EN ISO 15607:2003, Specification and qualification of welding procedures for metallic materials — General rules (ISO 15607: 2003).**

**EN ISO 15609-5, Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding (ISO 15609-5: 2004).**

**ISO 669:2000, Resistance welding — Resistance welding equipment — Mechanical and electrical requirements.**

**ISO 10447, Welding - Peel and chisel testing of resistance spot, projection and seam welds.**

**3 Terms and definitions**

For the purposes of this European Standard, the terms and definitions given in EN ISO 15607:2003 and ISO 669:2000 apply.

**4 Preliminary welding procedure specification (pWPS)**

The preliminary welding procedure specification shall be prepared in accordance with EN ISO 15609-5.

**5 Welding procedure test**

The preparation and testing of test pieces shall be in accordance with clauses 6 and 7 of this standard.

NOTE The resistance weld setter who undertakes the welding procedure test satisfactorily in accordance with this standard is qualified for the appropriate range of qualification given in EN 1418.

## 6 Test piece

### 6.1 General

The welded assembly, to which the welding procedure will relate to in production, shall be represented by actual components or by preparing a standardized test piece in accordance with 6.2.

Test specimens shall be cut from the actual components, the test piece or welded separately according to 6.3.

Test specimens or test pieces from the same material with relevant flange widths or overlap length should be used. When applicable, shunting and inductive effects shall be taken into account.

If required by the application standard, the direction of plate rolling shall be marked on the test piece.

### 6.2 Shape and dimensions of test pieces and test specimens for destructive testing

#### 6.2.1 General

The shape and dimensions of the test pieces and test specimen and the test procedures are specified in the following standards: EN ISO 14270; EN ISO 14271; EN ISO 14272; EN ISO 14273; EN ISO 17653 and ISO 10447.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

The test specimens shall be prepared and etched to produce transverse and/or longitudinal sections in order to clearly show the nugget, the heat affected zone (HAZ) and, if necessary, the weld profile.

<https://standards.iteh.ai/catalog/standards/sist/243d4799-c31d-4e47-84c9-67e73a803ba/sist-en-iso-15614-12-2004>

The transverse macrosection shall include the unaffected parent material.

### 6.3 Welding of components, test pieces or test specimens

Preparation of components, test pieces or test specimens and welding of test pieces or test specimen shall be carried out in accordance with the pWPS, and under the general conditions of production welding (parameters, equipment, etc.) which they shall represent.

If tack welds are used in the case of seam welds, they should be included in the final test piece.

Welding and testing of the test pieces shall be witnessed by an examiner or examining body and the details of this shall be established before any qualification is undertaken.

## 7 Examination and testing

### 7.1 Extent of testing

The testing includes both non-destructive testing (NDT) and/or destructive testing.

The selection of test types and the number of test specimens depends on the performance and quality requirements of the component/assembly and shall be established before any qualification is undertaken, examples are given in Table 1.