

SLOVENSKI STANDARD
SIST EN ISO 28706-2:2012**01-januar-2012****Nadomešča:****SIST EN 14483-2:2004**

Steklasti in porcelanski emajli - Ugotavljanje odpornosti proti kemični koroziji - 2. del: Ugotavljanje odpornosti proti kemični koroziji s kislinami, ki vrejo, z nevtralnimi tekočinami in/ali njihovimi parami (ISO 28706-2:2008)

Vitreous and porcelain enamels - Determination of resistance to chemical corrosion - Part 2: Determination of resistance to chemical corrosion by boiling acids, boiling neutral liquids and/or their vapours (ISO 28706-2:2008)

Emails und Emaillierungen - Bestimmung der Beständigkeit gegen chemische Korrosion - Teil 2: Bestimmung der Beständigkeit gegen chemische Korrosion durch kochende Säuren, kochende neutrale Flüssigkeiten und/oder deren Dämpfe (ISO 28706-2:2008)

Émaux vitrifiés - Détermination de la résistance à la corrosion chimique - Partie 2: Détermination de la résistance à la corrosion chimique par des acides bouillants ou des liquides neutres bouillants, et/ou leurs vapeurs (ISO 28706-2:2008)

Ta slovenski standard je istoveten z: EN ISO 28706-2:2011

ICS:

25.220.50 Emajlne prevleke Enamels

SIST EN ISO 28706-2:2012**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 28706-2:2012

<https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 28706-2

May 2011

ICS 25.220.50

Supersedes EN 14483-2:2004

English Version

Vitreous and porcelain enamels - Determination of resistance to chemical corrosion - Part 2: Determination of resistance to chemical corrosion by boiling acids, boiling neutral liquids and/or their vapours (ISO 28706-2:2008)

Émaux vitrifiés - Détermination de la résistance à la corrosion chimique - Partie 2: Détermination de la résistance à la corrosion chimique par des acides bouillants ou des liquides neutres bouillants, et/ou leurs vapeurs (ISO 28706-2:2008)

Emails und Emailierungen - Bestimmung der Beständigkeit gegen chemische Korrosion - Teil 2: Bestimmung der Beständigkeit gegen chemische Korrosion durch kochende Säuren, kochende neutrale Flüssigkeiten und/oder deren Dämpfe (ISO 28706-2:2008)

This European Standard was approved by CEN on 15 April 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 28706-2:2012](https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012>

Foreword

The text of ISO 28706-2:2008 has been prepared by Technical Committee ISO/TC 107 “Metallic and other inorganic coatings” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 28706-2:2011 by Technical Committee CEN/TC 262 “Metallic and other inorganic coatings” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2011, and conflicting national standards shall be withdrawn at the latest by November 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14483-2:2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)
Endorsement notice

The text of ISO 28706-2:2008 has been approved by CEN as a EN ISO 28706-2:2011 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 28706-2:2012

<https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012>

INTERNATIONAL
STANDARDISO
28706-2First edition
2008-12-01

**Vitreous and porcelain enamels —
Determination of resistance to chemical
corrosion —**

Part 2:

**Determination of resistance to chemical
corrosion by boiling acids, boiling neutral
liquids and/or their vapours****(standards.iteh.ai)***Émaux vitrifiés — Détermination de la résistance à la corrosion
chimique —**SIST EN ISO 28706-2:2012*

<https://standards.iteh.ai/5630> *Partie 2: Détermination de la résistance à la corrosion chimique par des
acides bouillants ou des liquides neutres bouillants, et/ou leurs vapeurs*

Reference number
ISO 28706-2:2008(E)

© ISO 2008

ISO 28706-2:2008(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 28706-2:2012](https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/8eb9ad5d-9644-4053-bc0b-5630df36833c/sist-en-iso-28706-2-2012>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	2
5 Apparatus and materials	2
6 Packing rings	7
6.1 General	7
6.2 Packing A	7
6.3 Packing B	8
7 Test specimens	8
8 Procedure	8
9 Expression of results	9
9.1 Total loss in mass per unit area	9
9.2 Corrosion rate	9
10 Boiling citric acid	9
10.1 General	9
10.2 Citric acid test solution	10
10.3 Duration of the test	10
10.4 Test report	10
11 Boiling sulfuric acid	10
11.1 General	10
11.2 Test solution	10
11.3 Duration of the test	10
11.4 Test report	11
12 Boiling hydrochloric acid	11
12.1 General	11
12.2 Test solution	11
12.3 Duration of the test	11
12.4 Test report	12
13 Boiling distilled or demineralized water	12
13.1 General	12
13.2 Test solution	12
13.3 Duration of the test	12
13.4 Test report	13
14 Other test solutions and/or conditions	13
14.1 General	13
14.2 Test solution	13
14.3 Duration of the test	13
14.4 Test report	14
Bibliography	15

ISO 28706-2:2008(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 28706-2 was prepared by the European Committee for Standardization (CEN) (as EN 14483-2) and was adopted, under a special “fast-track procedure”, by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in parallel with its approval by the ISO member bodies.

It cancels and replaces ISO 2733:1983, ISO 2742:1998, ISO 2743:1986 and ISO 2744:1998, which have been technically revised.

ISO 28706 consists of the following parts, under the general title *Vitreous and porcelain enamels — Determination of resistance to chemical corrosion*.

- *Part 1: Determination of resistance to chemical corrosion by acids at room temperature*
- *Part 2: Determination of resistance to chemical corrosion by boiling acids, boiling neutral liquids and/or their vapours*
- *Part 3: Determination of resistance to chemical corrosion by alkaline liquids using a hexagonal vessel*
- *Part 4: Determination of resistance to chemical corrosion by alkaline liquids using a cylindrical vessel*
- *Part 5: Determination of resistance to chemical corrosion in closed systems*

Introduction

Corrosion of vitreous and porcelain enamels by aqueous solutions is a dissolution process. The main component of the enamel, SiO_2 , forms a three-dimensional silica network. After hydrolysis, it decomposes and forms silicic acid or silicates. These are released into the attacking medium. Other components, mainly metal oxides, are hydrolysed as well and form the corresponding hydrated metal ions or hydroxides. All corrosion products are more or less soluble in the attacking medium. The whole process results in a loss in mass per unit area.

For some aqueous solutions, the attack on the enamel proceeds linearly during the corrosion time; for other aqueous solutions, the attack on the enamel proceeds in a logarithmic manner during the corrosion time. Only for the first series of solutions can a scientifically exact rate of loss in mass per unit area ($\text{g/m}^2\cdot\text{h}$) be calculated as well as a corrosion rate (mm/year).

The most important parameters influencing aqueous corrosion of the enamel are the enamel quality, the temperature and the pH-value. Inhibition effects resulting from the limited solubility of silica can also contribute. The following list describes different types of enamel attack for different corrosion conditions:

- a) In aqueous alkali solutions like 0,1 mol/l NaOH (see Clause 9 of ISO 28706-4:2008), the silica network of the enamel is considerably attacked at 80 °C. Silicates and most of the other hydrolysed components are soluble in the alkali. Attack proceeds linearly during regular test times. Therefore, test results are expressed in terms of a rate of loss in mass per unit area (mass loss per unit area and time) and a corrosion rate (millimetres per year).
- b) At room temperature, in weak aqueous acids like citric acid (see Clause 9 of ISO 28706-1:2008) or also in stronger acids like sulfuric acid (see Clause 10 of ISO 28706-1:2008), there is only minor attack on the silica network of the enamel. Other constituents are leached to some extent from the surface. Highly resistant enamels will show no visual change after exposure. On less resistant enamels, some staining or surface roughening will occur.
- c) In boiling aqueous acids (see ISO 28706-2:2008), the silica network of the enamel is being attacked, and silica as well as the other enamel components are released into solution. However, the solubility of silica in acids is low. Soon, the attacking solutions will become saturated with dissolved silica and will then only leach the surface. The acid attack is inhibited and the rate of corrosion drops markedly.

NOTE The glass test equipment also releases silica by acid attack and contributes to the inhibition of the corrosion.

Inhibition is effectively prevented in vapour phase tests. The condensate formed on the test specimen is free of any dissolved enamel constituents.

Examples of enamel corrosion proceeding in a logarithmic manner [see 1)] and linearly [see 2)] are:

- 1) **Boiling citric acid (see Clause 10 of ISO 28706-2:2008) and boiling 30 % sulfuric acid (see Clause 11 of ISO 28706-2:2008)**

Since only minute amounts of these acids are found in their vapours, the test is restricted to the liquid phase. The attack is influenced by inhibition effects, and corrosion depends on the time of exposure. Therefore, test results are expressed in terms of loss in mass per unit area; no rate of loss in mass per unit area is calculated.

- 2) **Boiling 20 % hydrochloric acid (see Clause 12 of ISO 28706-2:2008)**

Since this is an azeotropic boiling acid, its concentration in the liquid and the vapour phase are identical, and liquid phase testing need not be performed. Vigorous boiling supplies an uninhibited condensate, and the attack proceeds linearly with time of exposure. Therefore, test results are only