



Designation: D 1582 – 98

Standard Test Method for Nonvolatile Content of Liquid Phenol, Resorcinol, and Melamine Adhesives¹

This standard is issued under the fixed designation D 1582; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of nonvolatile content or total solids of liquid phenol, resorcinol, and melamine adhesives with or without hardener (Note 1) added and containing high-boiling and low-boiling volatile organic solvents or water, or both.

NOTE 1—Some low molecular weight materials in the adhesive may be lost if hardener is not used. When a hardener is used, it must be mixed in accordance with the manufacturer's instructions.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific precautions, see Note 2.

2. Referenced Documents

- 2.1 *ASTM Standards:*
D 907 Terminology of Adhesives²

3. Terminology

3.1 *Definitions*—Many of the terms in this test method are defined in Terminology D 907.

4. Summary of Test Method

4.1 *Without Hardener*—A weighed amount of adhesive and quartz sand are oven-dried, cooled in a desiccator, and weighed. The percent nonvolatile content is calculated based on the amount remaining.

4.2 *With Hardener*—A weighed amount of mixed adhesive is oven dried, cooled in a desiccator, and weighed. The percent nonvolatile content is calculated based on the amount remaining.

5. Apparatus

5.1 *Petri Dish*, 100 by 22 mm or its equivalent.

5.2 *Circulating-Air Oven*, capable of maintaining temperatures of $70 \pm 1^\circ\text{C}$, $105 \pm 1^\circ\text{C}$, and $150 \pm 1^\circ\text{C}$.

NOTE 2—**Caution:** A safety (explosion-proof) oven should be used when volatile materials are likely to burn or explode.

5.3 *Desiccator*, with drying agent and tray.

5.4 *Analytical Balance*, accurate to 1 mg.

6. Sampling

6.1 Except in special cases, take a composite sample from three or more separate containers chosen at random. Also, take samples from containers which appear to be nonrepresentative and test such samples separately. Place the samples immediately in airtight containers, filled to prevent excessive air space above the adhesive, and take precautions to reduce evaporation or drying to a minimum. Mix the adhesive in the container thoroughly if there is a tendency for the materials to separate.

6.2 Test three specimens of each sample.

7. Procedure

7.1 *70°C Drying Temperature Without Hardener:*

7.1.1 Place approximately 20 g of the adhesive in a covered weighing bottle.

7.1.2 Place approximately 10 g of fine, oven-dried quartz sand in an open Petri dish, together with a small glass stirring rod, and weigh the dish, rod, and contents to the nearest 1 mg on the analytical balance. Weigh out to the nearest 1 mg approximately 2 g of the adhesive by difference from the weighing bottle, keeping the bottle covered as much as possible. Mix the adhesive and quartz sand intimately by means of the stirring rod and distribute uniformly over the bottom of the dish in as thin a layer as possible. Condition the specimen at $23 \pm 1^\circ\text{C}$ for at least 16 h.

7.1.3 Place the dish with the rod and contents in the oven at $70 \pm 1^\circ\text{C}$ until a constant weight is reached.

7.1.4 Place the warm dish immediately in the desiccator and allow to cool to room temperature before weighing to the nearest 1 mg.

7.2 *70°C Drying Temperature With Hardener:*

¹ This test method is under the jurisdiction of ASTM Committee D-14 on Adhesives and is the direct responsibility of Subcommittee D 14.30 on Wood Adhesives.

Current edition approved March 10, 1998. Published March 1999. Originally published as D 1582 – 58. Last previous edition D 1582 – 97.

² *Annual Book of ASTM Standards*, Vol 15.06.