



Designation: B628 – 98 (Reapproved 2004)

Standard Specification for Silver-Copper Eutectic Electrical Contact Alloy¹

This standard is issued under the fixed designation B628; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers 72 % silver-28 % copper (eutectic) alloy rod, wire, strip, and sheet material for electrical contacts.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[B277 Test Method for Hardness of Electrical Contact Materials](#)

[B476 Specification for General Requirements for Wrought Precious Metal Electrical Contact Materials](#)

3. General Requirements

3.1 Specification [B476](#) and Test Method [B277](#) shall apply to all materials produced to this specification.

4. Manufacture

4.1 Raw materials shall be of such quality and purity that the finished product will have the properties and characteristics prescribed in this specification.

4.2 The material shall be finished by such operations (cold working, heat treating, annealing, turning, grinding, or pickling) as are required to produce the prescribed properties.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved May 1, 2004. Published May 2004. Originally approved in 1977. Last previous edition approved in 1998 as B628 – 98. DOI: 10.1520/B0628-98R04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Chemical Composition

5.1 Material produced under the specification shall conform to the requirements as to chemical composition prescribed in [Table 1](#).

TABLE 1 Chemical Composition^A

Element	Weight %
Silver	71.0 to 73.0
Copper	balance
Total of all impurities	0.15
Zinc	0.06 max
Iron	0.05 max
Cadmium	0.05 max
Lead	0.03 max
Nickel	0.01 max
Aluminum	0.005 max
Phosphorus	0.03 max
Total others	0.06 max

^AAnalysis is regularly made for the elements for which specific limits are listed. If, however, the presence of "other" elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that the total of these "other" elements and the listed impurities are not in excess of the total impurities limit.

6. Mechanical Requirements

6.1 The material shall conform to the mechanical properties prescribed in [Table 2](#) or [Table 3](#).

6.2 All test specimens shall be full thickness or diameter when practical.

6.3 All tests are to be conducted at room temperature, about 68°F (20°C).

7. Inspection and Testing

7.1 Material furnished under this specification shall be inspected by the manufacturer as detailed in the applicable provisions of Specification [B476](#) and as listed below.

7.1.1 Visual inspection at 10 ×.

7.1.2 Temper test (hardness or tension, but not both). A tension test is recommended for strip below 0.030-in. (0.8-mm) thickness and for wire of any diameter. A tension test is preferred when permitted by part size and quantity.

7.1.3 Dimensional tests.