This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: A 132 – 04

Standard Specification for Ferromolybdenum¹

This standard is issued under the fixed designation A 132; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

- 1.1 This specification covers two grades of ferromolybdenum.
- 1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

- 2.1 ASTM Standards: ²
- A 1025 Specification for Ferroalloys, General Requirements
- E 11 Specification for Wire-Cloth Sieves for Testing Purposes

3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification A 1025, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A 1025 constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 1025, this specification shall prevail.

4. Chemical Requirements

4.1 The material shall conform to the requirements as to chemical composition specified in Table 1. The manufacturer shall furnish an analysis of each shipment showing the percentage of each element specified.

5. Size

5.1 The grades are available in sizes as listed in Table 2. . . .

5.2 The sizes listed in Table 2 are typical as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling.

6. Keywords

<u>ASTM A132-04</u>

6.1 ferromolybdenum; molybdenum; standards/sist/53961f27-f24d-4f79-afa7-67c96fd46640/astm-a132-04

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved May 1, 2004. Published May 2004. Originally approved in 1963. Last previous edition approved in 1989 as A 132 - 89 (2000).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.