



# SLOVENSKI STANDARD

## SIST EN 14362-1:2012

01-maj-2012

Nadomešča:

SIST EN 14362-1:2003

SIST EN 14362-1:2003/AC:2005

SIST EN 14362-2:2003

SIST EN 14362-2:2003/AC:2005

---

**Tekstilije - Metode za določevanje nekaterih aromatskih aminov, izvirajočih iz azo barvil - 1. del: Zaznavanje prisotnosti določenih azo barvil, dostopnih z ekstrahiranjem vlaken in brez njega**

iTeh STANDARD PREVIEW

Textiles - Methods for determination of certain aromatic amines derived from azo colorants - Part 1: Detection of the use of certain azo colorants accessible with and without extracting the fibres

[SIST EN 14362-1:2012](https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012)

[https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-](https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012)

Textilien - Verfahren für die Bestimmung bestimmter aromatischer Amine aus Azofarbstoffen - Teil 1: Nachweis der Verwendung gewisser Azofarbstoffen bestimmbar durch reduzierende Substanzen, mit oder ohne Extraktion

Textiles - Méthodes de détermination de certaines amines aromatiques dérivées de colorants azoïques - Partie 1: Détection de l'utilisation de certains colorants azoïques accessibles avec ou sans extraction

**Ta slovenski standard je istoveten z: EN 14362-1:2012**

---

**ICS:**

59.080.01      Tekstilije na splošno      Textiles in general

**SIST EN 14362-1:2012**      en,fr,de

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 14362-1:2012

<https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 14362-1**

February 2012

ICS 59.080.01

Supersedes EN 14362-1:2003, EN 14362-2:2003

English Version

**Textiles - Methods for determination of certain aromatic amines  
derived from azo colorants - Part 1: Detection of the use of  
certain azo colorants accessible with and without extracting the  
fibres**

Textiles - Méthodes de détermination de certaines amines  
aromatiques dérivées de colorants azoïques - Partie 1 :  
Détection de l'utilisation de certains azo-colorants  
accessibles avec ou sans extraction

Textilien - Verfahren für die Bestimmung bestimmter  
aromatischer Amine aus Azofarbstoffen - Teil 1: Nachweis  
der Verwendung bestimmter Azofarbstoffe mit oder ohne  
Extraktion

This European Standard was approved by CEN on 22 December 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

[SIST EN 14362-1:2012](https://standards.iteh.ai/catalog/standards/sis/01055b7-a6d4-4aed-9d57-sist/en/14362-1:2012)

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	4
1 Scope .....	5
2 Normative references .....	5
3 General.....	5
4 Principle.....	7
5 Safety precautions.....	7
6 Reagents.....	7
7 Apparatus .....	8
8 Test specimen sampling and preparation.....	10
8.1 General.....	10
8.2 Textile article.....	10
8.3 Fibre composition.....	10
8.4 Case of the fibre blends .....	11
8.5 Printed materials.....	11
8.6 Colours .....	11
8.6.1 General.....	11
8.6.2 Case of colour gathering .....	11
8.6.3 Preparation of the three colour test specimen .....	12
9 Procedure .....	12
9.1 Colorant extraction for disperse dyes.....	12
9.1.1 Extraction of disperse dyes with chlorobenzene.....	12
9.1.2 Textiles only dyed with disperse dyes .....	12
9.1.3 Textiles dyed with disperse dyes and/or other dyes .....	12
9.2 Textiles dyed with dyes other than disperse dyes.....	12
9.3 Reductive cleavage .....	12
9.4 Separation and concentration of the amines.....	13
9.5 Amine detection and quantification.....	13
9.6 Check procedure.....	13
9.6.1 General.....	13
9.6.2 Calibration using internal standard (quantification performed by gas chromatography).....	13
9.6.3 Calibration without internal standard.....	14
10 Evaluation.....	14
10.1 General.....	14
10.2 Calculation of amine in the sample.....	15
10.3 Reliability of the method .....	15
11 Test report .....	15
Annex A (informative) Chromatographic analyses .....	16
A.1 Preliminary remark .....	16
A.2 Thin layer chromatography (TLC).....	16
A.3 High performance liquid chromatography (HPLC).....	17
A.4 Capillary gas chromatography/mass selective detector (GC/MS).....	18
A.5 Capillary electrophoresis (CE) .....	18
Annex B (informative) Reliability of the method .....	20
Annex C (informative) Assessment guide-interpretation of analytical results .....	22
Annex D (informative) Explanatory table of dyestuffs used in various textile materials.....	23

D.1	General .....	23
D.2	Criteria for printed materials .....	24
<b>Annex E (informative) Procedure for liquid/liquid-extraction without diatomaceous earth.....</b>		<b>25</b>
E.1	Preliminary remark .....	25
E.2	Additional reagents used.....	25
E.3	Additional apparatus used .....	26
E.4	Procedure .....	26
<b>Annex F (normative) Colorants - Methods for determination of certain aromatic amines .....</b>		<b>28</b>
F.1	Scope .....	28
F.2	Principle.....	28
F.3	Test specimen preparation.....	28
F.4	Procedure .....	28
F.5	Evaluation.....	28
F.6	Test report.....	28
<b>Bibliography.....</b>		<b>29</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14362-1:2012](https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012)

<https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012>

## EN 14362-1:2012 (E)

## Foreword

This document (EN 14362-1:2012) has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14362-1:2003, EN 14362-2:2003.

EN 14362 is composed of the following parts:

- EN 14362-1, *Textiles — Methods for determination of certain aromatic amines derived from azo colorants — Part 1: Detection of the use of certain azo colorants accessible with and without extracting the fibres*;
- EN 14362-3, *Textiles — Methods for determination of certain aromatic amines derived from azo colorants — Part 3: Detection of the use of certain azo colorants which may release 4-aminoazobenzene*.

The following is a list of technical changes since the last edition:

- Part 2 of EN 14362 has been integrated into Part 1. This is mainly reflected in:
  - changes to Clause 4 "Principle";
  - insertion of a new Clause 8 "Test specimen sampling and preparation";
  - insertion of a new Subclause 9.1 "Colorant extraction for disperse dyes";
  - insertion of a new Subclause 9.2 "Textiles dyed with dyes other than disperse dyes";
  - addition of Annex D (informative) "Explanatory table of dyestuffs used in various textile materials".
- Addition of Annex F (normative) "Colorants - Methods for determination of certain aromatic amines";
- The calculation, previously Annex B (normative) has been moved to Subclause 9.6.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard describes a procedure to detect the use of certain azo colorants that may not be used in the manufacture or treatment of certain commodities made of textile fibres and that are accessible to reducing agent with and without extraction.

Azo colorants accessible to reducing agent without extraction are those used to dye:

- cellulosic fibres (e.g. cotton, viscose);
- protein fibres (e.g. wool, silk);
- synthetic fibres (e.g. polyamide, acrylic).

Azo colorants accessible with extraction are those used to dye man-made fibres with disperse dyes. The following man-made fibres can be dyed with disperse dyes: polyester, polyamide, acetate, triacetate, acrylic and chlorofibre.

For certain commodities made of cellulose and/or protein fibres blended with man-made fibres it is necessary to extract the dye first.

The method is relevant for all coloured textiles, e.g. dyed, printed and coated textiles.

## 2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 3696:1995, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987)*

## 3 General

Certain azo colorants may release, by reductive cleavage of azo group(s), one or more of the following aromatic amines, which are proscribed under Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), establishing a European Chemicals Agency.

Table 1 — Aromatic amines proscribed under Regulation REACH 1907/2006/Annex XVII

No.	CAS number	Index number	EC number	Substances
1	92-67-1	612-072-00-6	202-177-1	biphenyl-4-ylamine 4-aminobiphenyl xenylamine
2	92-87-5	612-042-00-2	202-199-1	benzidine
3	95-69-2	612-196-00-0	202-441-6	4-chloro-o-toluidine
4	91-59-8	612-022-00-3	202-080-4	2-naphthylamine
5 <sup>a</sup>	97-56-3	611-006-00-3	202-591-2	o-aminoazotoluene 4-amino-2',3-dimethylazobenzene 4-o-tolylazo-o-toluidine
6 <sup>a</sup>	99-55-8	612-210-00-5	202-765-8	5-nitro-o-toluidine 2-amino-4-nitrotoluene
7	106-47-8	612-137-00-9	203-401-0	4-chloroaniline
8	615-05-4	612-200-00-0	210-406-1	4-methoxy-m-phenylenediamine 2,4-diaminoanisole
9	101-77-9	612-051-00-1	202-974-4	4,4'-methylenedianiline 4,4'-diaminodiphenylmethane
10	91-94-1	612-068-00-4	202-109-0	3,3'-dichlorobenzidine 3,3'-dichlorobiphenyl-4,4'-ylenediamine
11	119-90-4	612-036-00-X	204-355-4	3,3'-dimethoxybenzidine o-dianisidine
12	119-93-7	612-041-00-7	204-358-0	3,3'-dimethylbenzidine 4,4'-bi-o-toluidine
13	838-88-0	612-085-00-7	212-658-8	4,4'-methylenedi-o-toluidine
14	120-71-8	612-209-00-X	204-419-1	6-methoxy-m-toluidine p-cresidine
15	101-14-4	612-078-00-9	202-918-9	4,4'-methylene-bis-(2-chloro-aniline) 2,2'-dichloro-4,4'-methylene-dianiline
16	101-80-4	612-199-00-7	202-977-0	4,4'-oxydianiline
17	139-65-1	612-198-00-1	205-370-9	4,4'-thiodianiline
18	95-53-4	612-091-00-X	202-429-0	o-toluidine 2-aminotoluene
19	95-80-7	612-099-00-3	202-453-1	4-methyl-m-phenylenediamine 2,4-toluyldiamine 2,4-diaminotoluene
20	137-17-7	612-197-00-6	205-282-0	2,4,5-trimethylaniline
21	90-04-0	612-035-00-4	201-963-1	o-anisidine 2-methoxyaniline
22 <sup>b</sup>	60-09-3	611-008-00-4	200-453-6	4-aminoazobenzene

<sup>a</sup> The CAS-numbers 97-56-3 (No. 5) and 99-55-8 (No. 6) are further reduced to CAS-numbers 95-53-4 (No. 18) and 95-80-7 (No. 19).

<sup>b</sup> Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline (CAS-number 62-53-3) and 1,4-phenylenediamine (CAS – number 106-50-3). Due to detection limits, only aniline may be detected. The presence of these colorants should be tested by EN 14362-3.



## 4 Principle

After selection of a coloured test specimen from the textile article, the test specimen is tested according to the method of colorant extraction for disperse dyes and/or the method of direct reduction for the other classes of dyes.

The application of the combined methods or one of the two methods is based on the nature of the fibre(s) of the test specimen (composed of pure fibre or of fibre blends) and the colour treatment (dyeing or printing process). When relevant, if the test specimen is not discoloured during the application of one of the two methods, the other one is carried out.

When the method of the colorant extraction for disperse dyes is carried out, the colorant is first extracted from the fibre in the headspace (see Figure 1) using chlorobenzene under reflux. The extract is concentrated and transferred to the reaction vessel with methanol for subsequent reduction with sodium dithionite in a citrate-buffered aqueous solution (pH = 6) at 70 °C. If the textile specimen is not completely discoloured after chlorobenzene extraction, the specimen is added to the reaction vessel with the methanolic solution of the dispersed dye for combined reduction.

When the method for the other classes of the dyes is carried out, the test specimen is treated with sodium dithionite in a citrate-buffered aqueous solution (pH = 6) at 70 °C in a closed vessel.

After the reduction, any amine released in the process is transferred to a t-butyl methyl ether phase by means of liquid-liquid extraction using diatomaceous earth columns. The t-butyl methyl ether extract is then concentrated, and the residue is taken up in a solvent appropriate for detection and determination of the amines using chromatography (see Annex A).

A screening method, using liquid/liquid extraction without diatomaceous earth columns, is described in Annex E.

If any amine is detected by one chromatographic method, then confirmation shall be made using one or more alternative methods.

<https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012>

## 5 Safety precautions

**5.1 WARNING — The substances [amines] listed in Clause 3 are classified as substances known to be or suspected of being human carcinogens.**

**Any handling and disposal of these substances shall be in strict accordance with the appropriate national health and safety regulations.**

**5.2** It is the user's responsibility to use safe and proper techniques in handling materials in this test method. Consult manufacturers for specific details such as material safety data sheets and other recommendations.

**5.3** Good laboratory practice should be followed. Wear safety glasses in all laboratory areas and a single-use dust respirator while handling powder colorants.

**5.4** Users should comply with any national and local safety regulations.

## 6 Reagents

Unless otherwise specified, analytical grade chemicals shall be used.

**6.1 Chlorobenzene.**

**6.2 Acetonitrile.**

**6.3 Methanol.**

**EN 14362-1:2012 (E)**

**6.4** *t*-butyl methyl ether.

**6.5** *n*-pentane.

**6.6** Citrate/sodium hydroxide buffer solution, pH = 6, c = 0,06 mol/l<sup>1)</sup>.

**6.7** Aqueous sodium dithionite solution,  $\rho$  = 200 mg/ml<sup>2)</sup> freshly (daily) prepared.

**6.8** Diatomaceous earth.

**6.9** Amine substances - amines 1 to 4, 7 to 21 (as specified in Table 1), and aniline and 1,4-phenylenediamine - all of highest available defined purity standard.

**6.10** Standard solutions.

**6.10.1** Stock solution of amines with a concentration of equal to or greater than 300  $\mu$ g of each amine per millilitre of an appropriate solvent.

NOTE Acetonitrile is an appropriate solvent for this stock solution, resulting in good stability of amines.

**6.10.2** Calibration solution of amines for daily use.

Dilute from the stock solution 6.10.1 to a concentration of  $\rho$  = 15,0  $\mu$ g of each amine per millilitre of an appropriate solvent.

**6.10.3** Calibration solutions of amines for quantification, concentration range from 2  $\mu$ g up to 50  $\mu$ g of each amine per millilitre of an appropriate solvent.

NOTE It is the responsibility of each lab to choose appropriate concentrations for the calibration.

**6.10.4** Internal standards in solution (IS),  $\rho$  = 1,0 mg of IS/ml of the appropriate IS solvent.

In case of GC-MS analysis, use one of the following internal standards:

- IS1: benzidine-d8, CAS No.: 92890-63-6;
- IS2: naphthalene-d8, CAS No.: 1146-65-2;
- IS3: 2,4,5-trichloroaniline, CAS No.: 636-30-6;
- IS4: anthracene-d10, CAS No.: 1719-06-8.

NOTE If the confirmation analysis for benzidine is done with DAD or TLC the use of IS1: benzidine-d8, CAS No.: 92890-63-6 is not feasible, because the peak cannot be separated from the none deuterated benzidine.

**6.11** Sodium hydroxide aqueous solution, a mass fraction of 10 %.

**6.12** Grade 3 water, complying with EN ISO 3696:1995.

## 7 Apparatus

**7.1** Extraction apparatus, according to Figure 1, consisting of:

- 
- 1) c is citrate concentration.
  - 2)  $\rho$  is the mass concentration.

- coil condenser NS 29/32;
- a hook, made from an inert material to hold the specimen in place so that the condensed solvent drips onto it;
- 100 ml round bottom flask NS 29/32;
- heating source.



Figure 1 — Apparatus

NOTE Similar apparatus may be used, if the same results are obtained.

**7.2 Ultrasonic bath**, controllable heating.

**7.3 Reaction vessel** (20 ml to 50 ml) of heat-resistant glass, with tight closure.

**7.4 Heating source** that generates  $(70 \pm 2) ^\circ\text{C}$ .

**7.5 Glass or polypropylene column**, inside diameter 25 mm to 30 mm, length 130 mm to 150 mm, packed with 20 g of diatomaceous earth (6.8), fitted with glass fibre filter at the outlet.

The diatomaceous earth columns are either bought pre-packed and used as is, or 20 g of diatomaceous earth can be packed into a glass or polypropylene column of the dimensions given.

**7.6 Vacuum rotary evaporator with vacuum control and water bath.**

NOTE Other kinds of evaporation apparatus may be used, e.g. a water bath with a controlled flow of nitrogen over the liquid.

**7.7 Pipettes** in required sizes or variables pipettes.

**7.8 Chromatographic equipment** selected from the following:

**7.8.1 Thin layer chromatography** (TLC) or high performance thin layer chromatography (HPTLC) equipment, including relevant detection.

**7.8.2 High performance liquid chromatography** (HPLC) with gradient elution and diode array detector (DAD) or mass selective detector (MS).

**7.8.3 Gas chromatography** (GC) with flame ionisation detector (FID) or mass selective detector (MS).

**7.8.4 Capillary electrophoresis** (CE) with diode array detector (DAD).

NOTE A description of the chromatographic equipment is given in Annex A.

**EN 14362-1:2012 (E)****8 Test specimen sampling and preparation****8.1 General**

The test specimen shall be selected based on the following criteria:

- Parts of the textile article;
- Nature of the fibre components (fibre composition);
- Printed materials;
- Colours.

Prepare the test specimen by cutting in order to obtain a total mass of 1 g. For specimens to be submitted to colorant extraction (9.1) cut into strips (if apparatus described in 7.1 is used) or cut into small pieces if other apparatus is used or for specimens to be submitted only to reductive cleavage (9.3).

**8.2 Textile article**

If the textile article is a semi-manufactured product, such as yarns, fabrics, etc., cut out test specimens from it.

If the textile article is composed of several parts of textile products, such as a garment, cut out test specimens from all the parts of the textile article that have direct and prolonged contact to skin or mouth, which can be:

- principal fabric(s);
- lining(s);
- pocket fabric(s);
- embroideries;
- label(s) for textile article;
- drawstring(s);
- fastener(s);
- false fur;
- sewing threads.

iTech STANDARD PREVIEW  
(standards.iteh.ai)  
SIST EN 14362-1:2012  
<https://standards.iteh.ai/catalog/standards/sist/91055bb7-a6d4-4ac4-94b7-7d016d90a6ba/sist-en-14362-1-2012>

If the mass of some parts (e.g. labels, sewing threads, embroideries of small size) does not reach the mass (1 g) to be tested, gather identical parts when possible. If the total mass of material is below 0,5 g, this material is defined as a minor component. (See NOTE 2, Annex C.)

Below 0,2 g of material the analysis is omitted.

Embroideries shall be weighed with the ground fabric.

**8.3 Fibre composition**

As the application of this standard is partly based on the extraction of colorants, identify the nature of the textile components so that the possible use of disperse dyestuffs can be determined.

Table 2 summarizes the four cases: