



SLOVENSKI STANDARD
SIST ISO 3082:2002

01-januar-2002

Železne rude -- Postopki vzorčenja in priprave vzorcev

Iron ores -- Sampling and sample preparation procedures

Minerais de fer -- Procédures d'échantillonnage et de préparation des échantillons

Ta slovenski standard je istoveten z: ISO 3082:2000

[SIST ISO 3082:2002](https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002)

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

ICS:

73.060.10 Železove rude Iron ores

SIST ISO 3082:2002

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 3082:2002

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

INTERNATIONAL STANDARD

**ISO
3082**

Third edition
2000-12-15

Iron ores — Sampling and sample preparation procedures

*Minerais de fer — Procédures d'échantillonnage et de préparation des
échantillons*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 3082:2002](https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002)

[https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-
29bad0e77572/sist-iso-3082-2002](https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002)



Reference number
ISO 3082:2000(E)

© ISO 2000

ISO 3082:2000(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 3082:2002](https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002)

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General considerations for sampling and sample preparation	3
4.1 Basic requirements	3
4.2 Establishing a sampling scheme	4
4.3 System verification	4
5 Fundamentals of sampling and sample preparation	5
5.1 Minimization of bias	5
5.2 Overall precision.....	7
5.3 Quality variation.....	9
5.4 Sampling precision and number of primary increments.....	10
5.5 Precision of sample preparation and overall precision.....	11
6 Methods of sampling.....	12
6.1 Mass basis sampling.....	12
6.2 Time basis sampling	14
6.3 Stratified random sampling within fixed mass or time intervals.....	15
7 Sampling from moving streams.....	15
7.1 General.....	15
7.2 Safety of operations.....	16
7.3 Robustness of sampling installation.....	16
7.4 Versatility of sampling system.....	16
7.5 Primary samplers.....	17
7.6 Secondary and subsequent samplers.....	21
7.7 On-line sample preparation	21
7.8 Checking precision and bias.....	26
7.9 Cleaning and maintenance	26
7.10 Example of a flowsheet.....	26
8 Sampling from stationary situations	28
8.1 General.....	28
8.2 Sampling from wagons	28
8.3 Sampling from ships, stockpiles and bunkers.....	29
9 Stopped-belt reference sampling.....	29
10 Sample preparation	30
10.1 Fundamentals.....	30
10.2 Method of constituting partial samples or a gross sample.....	32
10.3 Mechanical methods of division	34
10.4 Manual methods of division	38
10.5 Preparation of sample for size determination	42
10.6 Preparation of sample for moisture determination	42
10.7 Preparation of test sample for chemical analysis.....	43
10.8 Example of sample preparation process	46
11 Packing and marking of sample.....	46
Annex A (informative) Checklist for mechanical sampling systems	48
Annex B (normative) Equation for number of increments.....	53

ISO 3082:2000(E)

Annex C (informative) Alternative method of taking the reference sample	56
Annex D (normative) Procedure for determining the minimum mass of divided gross sample for size determination using other mechanical division methods	62
Annex E (normative) Riffle dividers	65
Bibliography	67

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 3082:2002](https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002)

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 3082 was prepared by Technical Committee ISO/TC 102, *Iron ore and direct reduced iron*, Subcommittee SC 1, *Sampling*.

This third edition cancels and replaces the second edition (ISO 3082:1998), together with ISO 3081:1986 and ISO 3083:1986, of which it constitutes a collation and technical revision.

Annexes B, D and E form a normative part of this International Standard. Annexes A and C are for information only.

SIST ISO 3082:2002

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 3082:2002

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

Iron ores — Sampling and sample preparation procedures

WARNING — This International Standard may involve hazardous materials, operations and equipment, and does not purport to address all of the safety issues associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard gives

- a) the underlying theory,
- b) the basic principles for sampling and preparation of samples,
- c) the basic requirements for the design, installation and operation of sampling systems

for mechanical sampling, manual sampling and preparation of samples taken from a lot under transfer to determine the chemical composition, moisture content and size distribution of the lot. Sampling and sample preparation procedures for physical testing are specified in ISO 10836.

The methods specified in this International Standard are applicable to both the loading and unloading of a lot by means of belt conveyors and other ore handling equipment to which a mechanical sampler may be installed or where manual sampling may safely be conducted.

The methods are applicable to all iron ores, whether natural or processed (e.g. concentrates and agglomerates, such as pellets or sinters).

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 565:1990, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*.

ISO 3084:1998, *Iron ores — Experimental methods for evaluation of quality variation*.

ISO 3085:—¹⁾, *Iron ores — Experimental methods for checking the precision of sampling and sample preparation and measurement*.

ISO 3086:1998, *Iron ores — Experimental methods for checking the bias of sampling*.

1) To be published. (Revision of ISO 3085:1996)

ISO 3082:2000(E)

ISO 3087:1998, *Iron ores — Determination of moisture content of a lot.*

ISO 4701:1999, *Iron ores — Determination of size distribution by sieving.*

ISO 10836:1994, *Iron ores — Method of sampling and sample preparation for physical testing.*

ISO 11323:1996, *Iron ores — Vocabulary.*

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions contained in ISO 11323 as well as those given below apply.

3.1**lot**

discrete and defined quantity of ore for which quality characteristics are to be assessed

3.2**increment**

quantity of ore collected in a single operation of a sampling device

3.3**sample**

relatively small quantity of ore, so taken from a lot as to be representative in respect of the quality characteristics to be assessed

3.4**partial sample**

sample, consisting of less than the complete number of increments needed for a gross sample

3.5**gross sample**

sample, comprising all increments, entirely representative of all quality characteristics of a lot

3.6**test sample**

sample, prepared to meet all specific conditions for a test

3.7**test portion**

part of a test sample that is actually and entirely subjected to the specific test

3.8**stratified sampling**

sampling of a lot carried out by taking increments from systematically specified positions and in appropriate proportions from identified parts called strata

NOTE Examples of strata, based on time, mass or space, include production periods (e.g. 5 min), production masses (e.g. 1 000 t), holds in vessels, wagons in a train or containers.

3.9**systematic sampling**

selection of increments at regular intervals from a lot

3.10**mass basis sampling**

sampling carried out so that increments are taken at equal mass intervals, increments being as near as possible of uniform mass

3.11**time basis sampling**

sampling carried out so that increments are taken from free falling streams, or from conveyors, at uniform time intervals, the mass of each increment being proportional to the mass flow rate at the instant of taking the increment

3.12**proportional sample division**

division of samples or increments such that the mass of each retained divided portion is a fixed proportion of the mass being divided

3.13**constant mass division**

division of samples or increments such that the retained divided portions are of almost uniform mass, irrespective of variations in mass of the samples or increments being divided

NOTE This method is required for sampling on a mass basis. "Almost uniform" means that variations in mass are less than 20 % in terms of the coefficient of variation.

3.14**split use of sample**

separate use of parts of a sample, as test samples for separate determinations of quality characteristics

3.15**multiple use of sample**

use of a sample in its entirety for the determination of one quality characteristic, followed by the use of the same sample in its entirety for the determination of one or more other quality characteristics

3.16**nominal top size**

smallest aperture size, within the range of the R20 Series (in ISO 565:1990, square opening), such that no more than 5 % by mass of an ore is retained on the sieve

ITEH STANDARD PREVIEW
(standards.iteh.ai)
SIST ISO 3082:2002
<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

4 General considerations for sampling and sample preparation

4.1 Basic requirements

The basic requirement for a correct sampling scheme is that all parts of the ore in the lot have an equal opportunity of being selected and becoming part of the partial sample or gross sample for analysis. Any deviation from this basic requirement can result in an unacceptable loss of accuracy and precision. An incorrect sampling scheme cannot be relied on to provide representative samples.

The best sampling location to satisfy the above requirement is at a transfer point between conveyor belts. Here, the full cross-section of the ore stream can be conveniently intercepted at regular intervals, enabling representative samples to be obtained.

In-situ sampling of ships, stockpiles, containers and bunkers is not permitted, because it is impossible to drive the sampling device down to the bottom and extract the full column of ore. Consequently, all parts of the lot do not have an equal opportunity of being sampled. The only effective procedure is sampling from a conveyor belt when ore is being conveyed to or from the ship, stockpile, container or bunker.

In-situ sampling from stationary situations such as wagons is permitted only for fine iron ore concentrates, provided the sampling device, e.g., a spear or an auger, penetrate to the full depth of the concentrate at the point selected for sampling and the full column of concentrate is extracted.

Sampling shall be carried out by systematic sampling either on a mass basis (see 6.1) or on a time basis (see 6.2), provided no bias is introduced by periodic variation in quality or quantity. If this is not the case, stratified random sampling within fixed mass or time intervals shall be carried out (see 6.3).

ISO 3082:2000(E)

The methods used for sampling and sample preparation depend on the final choice of the sampling scheme and on the steps necessary to minimize possible biases and obtain acceptable overall precision.

Moisture samples shall be processed as soon as possible and test portions weighed immediately. If this is not possible, samples shall be stored in impervious air-tight containers with a minimum of free air space to minimize any change in moisture content, but should be prepared without delay.

4.2 Establishing a sampling scheme

The procedure for establishing a sampling scheme is as follows:

- a) identify the lot to be sampled;
- b) ascertain the nominal top size;
- c) determine the mass of increment considering the nominal top size, the ore handling equipment and the device for taking increments;
- d) specify the precision required;
- e) ascertain the quality variation, σ_W , of the lot in accordance with ISO 3084, or, if this is not possible, assume "large" quality variation as specified in 5.3;
- f) determine the minimum number of primary increments, n_1 , to be taken from the lot for systematic or stratified random sampling;
- g) determine the sampling interval in tonnes for mass basis sampling or in minutes for time basis sampling;
- h) determine the sampling location and the method of taking increments;
- i) take increments having almost uniform mass for mass basis sampling or having a mass proportional to the flow rate of the ore stream at the time of sampling for time basis sampling. Increments shall be taken at the intervals determined in f) during the entire period of handling the lot;
- j) determine whether the sample is for split use or multiple use;
- k) establish the method of combining increments into a gross sample or partial samples;
- l) establish the sample preparation procedure, including division, crushing, mixing and drying;
- m) crush the sample, if necessary, except for the size sample;
- n) dry the sample, if necessary, except for the moisture sample;
- o) divide samples according to the minimum mass of divided sample for a given nominal top size, using constant mass or proportional division for mass basis sampling, or proportional division for time basis sampling;
- p) prepare the test sample.

4.3 System verification

Stopped-belt sampling is the reference method for collecting samples against which mechanical and manual sampling procedures may be compared in order to establish that they are unbiased in accordance with procedures specified in ISO 3086. However, before any bias tests are conducted, sampling and sample preparation systems shall first be inspected to confirm that they conform to the correct design principles specified in this International Standard. Inspections shall also include an examination of whether any loading, unloading or reclaiming procedures could produce periodic variations in quality in phase with the taking of increments. These periodic variations could include characteristics such as particle size distribution and moisture content. When such cyclic variations occur, the source of the variations shall be investigated to determine the practicability of eliminating the variations. If this is not possible, stratified random sampling shall be carried out (see 6.3).

An example of a suitable checklist is provided in annex A. This will quickly reveal any serious deficiencies in the sampling or sample preparation system and may alleviate the need for expensive bias testing. Consequently, sampling systems shall be designed and constructed in a manner that facilitates regular verification of correct operation.

Regular checks of quality variation and precision shall also be carried out in accordance with ISO 3084 and ISO 3085 to monitor variations in quality variation and to verify the precision of sampling, sample preparation and analysis. This is particularly important for new sampling systems or when significant changes are made to existing systems.

5 Fundamentals of sampling and sample preparation

5.1 Minimization of bias

5.1.1 General

Minimization of bias in sampling and sample preparation is vitally important. Unlike precision, which can be improved by collecting more increments or repeating measurements, bias cannot be reduced by replicating measurements. Consequently, the minimization or preferably elimination of possible biases should be regarded as more important than improvement of precision. Sources of bias that can be completely eliminated at the outset by correct design of the sampling and sample preparation system include sample spillage, sample contamination and incorrect extraction of increments, while sources that can be minimized but not completely eliminated include change in moisture content, loss of dust and particle degradation (for size determination).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.1.2 Minimization of particle size degradation

Minimization of particle size degradation of samples used for determination of size distribution is vital in order to reduce bias in the measured size distribution. To prevent particle size degradation, it is essential to keep free fall drops to a minimum.

<https://standards.iteh.ai/catalog/standards/sist/0946eb3f-5cad-40d3-846c-29bad0e77572/sist-iso-3082-2002>

5.1.3 Extraction of increments

It is essential that increments be extracted from the lot in such a manner that all parts of the ore have an equal opportunity of being selected and becoming part of the final sample for analysis, irrespective of the size, mass or density of individual particles. If this requirement is not respected, bias is easily introduced. This results in the following design requirements for sampling and sample preparation systems:

- a) a complete cross-section of the ore stream shall be taken when sampling from a moving stream (see 7.5);
- b) the aperture of the sample cutter shall be at least three times the nominal top size of the ore, or 30 mm for primary sampling and 10 mm for subsequent stages, whichever is the greater (see 7.5.4);
- c) the speed of the sample cutter shall not exceed 0,6 m/s, unless the cutter aperture is correspondingly increased (see 7.5.5);
- d) the sample cutter shall travel through the ore stream at uniform speed (see 7.5.3), both the leading and trailing edges of the cutter clearing the ore stream at the end of its traverse;
- e) the lips on the sample cutter shall be parallel for straight-path samplers and radial for rotary cutters (see 7.5.3), and these conditions shall be maintained as the cutter lips wear;
- f) changes in moisture content, dust losses and sample contamination shall be avoided;
- g) free fall drops shall be kept to a minimum to reduce size degradation of the ore and hence minimize bias in size distribution;

ISO 3082:2000(E)

- h) primary cutters shall be located as near as possible to the loading or discharging point in order to further minimize the effects of size degradation;
- i) a complete column of concentrate shall be extracted when sampling iron ore concentrate in a wagon (see 8.2).

Sampling systems shall be designed to accommodate the maximum nominal top size and flow rate of the ore being sampled. Detailed design requirements for sampling and sample preparation systems are provided in 7, 8, 9 and 10.

5.1.4 Increment mass

The increment mass required to obtain an unbiased sample can be calculated for typical sampling situations [see equations (1), (2) and (3)]. Comparing the calculated masses with the actual increment masses is useful for checking the design and operation of sampling systems. If the difference is significant, the cause shall be identified and corrective action taken to rectify the problem.

5.1.4.1 Increment mass for falling stream sampling

The mass of increment, m_1 , in kilograms, to be taken (mechanically or manually) by a cutter-type primary sampler from the ore stream at the discharge end of a conveyor belt is given by:

$$m_1 = \frac{ql_1}{3,6 v_C} \quad (1)$$

where

q is the flow rate, in tonnes per hour, of ore on the conveyor belt;

l_1 is the cutter aperture, in metres, of the primary sampler;

v_C is the cutter speed, in metres per second, of the primary sampler.

The minimum increment mass that can be taken, while still avoiding bias, is determined by the minimum cutter aperture specified in 7.5.4 and the maximum cutter speed specified in 7.5.5.

For practical reasons, e.g. in the case of lumpy ore, it may be necessary for the cutter aperture to exceed three times the nominal top size of the ore.

5.1.4.2 Increment mass for stopped-belt sampling

The mass of increment, m_1 , in kilograms to be taken manually from a stopped-belt is equal to the mass of a complete cross-section (of length l_2) of the ore on the conveyor. It is given by the equation:

$$m_1 = \frac{ql_2}{3\,600 v_B} \quad (2)$$

where

q is the flow rate, in tonnes per hour, of ore on the conveyor belt;

v_B is the speed of the conveyor belt, in metres per second.

The minimum increment mass that can be taken, while still avoiding bias, is determined by the minimum length of ore removed from the conveyor, i.e., $3d$, where d is the nominal top size of the ore, in millimetres, subject to a minimum of 10 mm.

5.1.4.3 Increment mass for manual sampling using spear or auger

The mass of increment, m_I , in kilograms to be taken from a wagon in a lot using a spear or an auger of diameter, l_3 , in millimetres, is given by:

$$m_I = \frac{\pi \rho l_3^2 L}{4\ 000} \quad (3)$$

where

ρ is the bulk density of the fine ore (particle size < 1 mm), in tonnes per cubic metre;

L is the depth of concentrate in the wagon, in metres.

The minimum increment mass that can be taken, while still avoiding bias, is determined by the minimum diameter of the spear or auger, i.e., 30 mm.

This method of extracting increments is only applicable to sampling fine iron ore concentrates.

5.2 Overall precision

This International Standard is designed to attain the overall precision, β_{SPM} , at a probability level of 95 %, given in Table 1, for total iron, silica, alumina, phosphorus and moisture contents and the percent size fraction of the lot. Greater precision may be adopted if required. The precision shall be determined in accordance with ISO 3085.

The overall precision, β_{SPM} , is a measure of the combined precision of sampling, sample preparation and measurement, and is twice the standard deviation of sampling, sample preparation and measurement, σ_{SPM} , expressed as an absolute percentage, i.e.

$$\sigma_{\text{SPM}} = \sqrt{\sigma_{\text{S}}^2 + \sigma_{\text{P}}^2 + \sigma_{\text{M}}^2} \quad (4)$$

$$\beta_{\text{SPM}} = 2\sigma_{\text{SPM}} = 2\sqrt{\sigma_{\text{S}}^2 + \sigma_{\text{P}}^2 + \sigma_{\text{M}}^2} \quad (5)$$

$$\sigma_{\text{S}} = \frac{\sigma_{\text{W}}}{\sqrt{n_1}} \quad (6)$$

where

σ_{S} is the sampling standard deviation;

σ_{P} is the sample preparation standard deviation;

σ_{M} is the measurement standard deviation;

σ_{W} is the quality variation of the ore;

n_1 is the number of primary increments.