



**SLOVENSKI STANDARD**  
**SIST EN ISO 1974:2012**

**01-oktober-2012**

**Nadomešča:**  
**SIST EN 21974:2000**

---

**Papir - Ugotavljanje raztržne odpornosti - Elmendorfova metoda (ISO 1974:2012)**

Paper - Determination of tearing resistance - Elmendorf method (ISO 1974:2012)

Papier - Bestimmung des Durchreißwiderstandes - Elmendorf Methode (ISO 1974:2012)

Papier - Détermination de la résistance au déchirement - Méthode Elmendorf (ISO 1974:2012)

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: EN ISO 1974:2012**  
SIST EN ISO 1974:2012  
http://www.sist.si/log/standard/2012-10-01/EN ISO 1974:2012/f6f-870e-6ac352dbf171/sist-en-iso-1974-2012

---

**ICS:**

85.060          Papir, karton in lepenka          Paper and board

**SIST EN ISO 1974:2012**          **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 1974:2012

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN ISO 1974**

May 2012

ICS 85.060

Supersedes EN 21974:1994

English Version

**Paper - Determination of tearing resistance - Elmendorf method  
(ISO 1974:2012)**

Papier - Détermination de la résistance au déchirement -  
Méthode Elmendorf (ISO 1974:2012)

Papier - Bestimmung des Durchreißwiderstandes -  
Elmendorf Methode (ISO 1974:2012)

This European Standard was approved by CEN on 10 May 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN ISO 1974:2012](https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012)

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

Page

Foreword.....3

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN ISO 1974:2012

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>

## Foreword

This document (EN ISO 1974:2012) has been prepared by Technical Committee ISO/TC 6 “Paper, board and pulps” in collaboration with Technical Committee CEN/TC 172 “Pulp, paper and board” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2012, and conflicting national standards shall be withdrawn at the latest by November 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 21974:1994.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
**Endorsement notice**

The text of ISO 1974:2012 has been approved by CEN as a EN ISO 1974:2012 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 1974:2012

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>

# INTERNATIONAL STANDARD

**ISO  
1974**

Fourth edition  
2012-05-01

---

---

## Paper — Determination of tearing resistance — Elmendorf method

*Papier — Détermination de la résistance au déchirement —  
Méthode Elmendorf*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 1974:2012](https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012)

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>



Reference number  
ISO 1974:2012(E)

© ISO 2012

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 1974:2012](https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012)

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland



<b>Contents</b>	<b>Page</b>
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>2</b>
<b>6 Sampling</b> .....	<b>4</b>
<b>7 Conditioning</b> .....	<b>4</b>
<b>8 Preparation of test pieces</b> .....	<b>4</b>
<b>9 Adjustment and calibration of apparatus</b> .....	<b>5</b>
<b>10 Procedure</b> .....	<b>5</b>
<b>11 Calculation and expression of results</b> .....	<b>6</b>
<b>11.1 Tearing resistance</b> .....	<b>6</b>
<b>11.2 Tear index</b> .....	<b>6</b>
<b>11.3 Coefficient of variation</b> .....	<b>7</b>
<b>12 Test report</b> .....	<b>7</b>
<b>Annex A (normative) Adjustment and maintenance of Elmendorf-type tear testers</b> .....	<b>8</b>
<b>Annex B (normative) Calibration of Elmendorf-type tear testers</b> .....	<b>10</b>
<b>Annex C (informative) Precision</b> .....	<b>12</b>
<b>Bibliography</b> .....	<b>14</b>

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-48f8-870e-6ac352dbf171/sist-en-iso-1974-2012>  
 SIST EN ISO 1974:2012

## ISO 1974:2012(E)

**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1974 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This fourth edition cancels and replaces the third edition (ISO 1974:1990), which has been technically revised. The specification for the tester has been moved from Annex A to Clause 5 and is given in more general terms so that this International Standard is applicable to a wider range of designs. In addition, new precision data have been inserted in Annex C.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 1974:2012](https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012)

<https://standards.iteh.ai/catalog/standards/sist/c5b066a0-e638-4f6f-870e-6ac352dbf171/sist-en-iso-1974-2012>

# Paper — Determination of tearing resistance — Elmendorf method

## 1 Scope

This International Standard specifies a method for determining the (out-of-plane) tearing resistance of paper. It can also be used for boards having a low grammage if the tearing resistance is within the range of the instrument.

This International Standard does not apply to corrugated fibreboard, but it may be applied to the components of such boards. It is not suitable for determining the cross-direction tearing resistance of highly directional paper (or board).

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 536, *Paper and board — Determination of grammage*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### tearing resistance

mean force per sheet required to continue the tearing started by an initial cut in the test piece

NOTE 1 If the initial cut is in the machine direction, the result is given as the machine-direction tearing resistance; similarly, if the initial cut is in the cross-direction, the result is given as the cross-direction tearing resistance.

NOTE 2 The tearing resistance is expressed in millinewtons (mN).

### 3.2

#### tear index

tearing resistance of the paper (or board) divided by its grammage

NOTE The tear index is expressed in millinewton square metres per gram (mN·m<sup>2</sup>/g).

### 3.3

#### test piece

pack of four rectangular sheets of the same size

NOTE The dimensions depend on the design of the apparatus clamp used (see Clause 8).

## 4 Principle

An initial cut is made in a test piece (of four superimposed sheets), which is then torn out-of-plane through a given distance along one single tear line using a pendulum. The work done in tearing the test piece is measured as the loss in energy of the pendulum.

The mean tearing force of a single sheet is calculated by dividing the work done by the distance torn and the number of sheets in a test piece.