



Designation: E897 – 88 (Reapproved 2004)

# Standard Test Method for Volatile Matter in the Analysis Sample of Refuse-Derived Fuel<sup>1</sup>

This standard is issued under the fixed designation E897; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the percentage of gaseous products, exclusive of moisture vapor, in the analysis sample which is released under specific conditions of the test. The knowledge of the volatile matter content assists in predicting burning characteristics of RDF.

1.2 This test method may be applicable to any waste material from which a laboratory analysis sample can be prepared.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals<sup>3</sup>

E790 Test Method for Residual Moisture in a Refuse-Derived Fuel Analysis Sample

E829 Practice for Preparing Refuse-Derived Fuel (RDF) Laboratory Samples for Analysis<sup>3</sup>

## 3. Terminology

3.1 *Definition:*

3.2 *refuse-derived fuel (RDF):*

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D34 on Waste Management and is the direct responsibility of Subcommittee D34.03 on Treatment, Recovery and Reuse.

Current edition approved April 1, 2004. Published May 2004. Originally published as E897 – 82. Last previous edition approved in 1998 as E897 – 88(1998). DOI: 10.1520/E0897-88R04.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

RDF-1—Waste used as a fuel in as-discarded form.

RDF-2—Waste processed to coarse particle size with or without ferrous metal separation.

RDF-3—shredded fuel derived from municipal solid waste (MSW) that has been processed to remove metal, glass, and other inorganics. This material has a particle size such that 95 weight % passes through a 2-in. square mesh screen.

RDF-4—Combustible waste processed into powder form—95 weight % passing a 10-mesh screen.

RDF-5—Combustible waste densified (compressed) into the form of pellets, slugs, cubettes or briquettes.

RDF-6—Combustible waste processed into liquid fuel.

RDF-7—Combustible waste processed into gaseous fuel.

## 4. Summary of Test Method

4.1 Volatile matter is determined by establishing the loss in weight resulting from heating refuse-derived fuel under rigidly-controlled conditions. The measured weight loss, corrected for moisture as determined in Test Method E790, establishes the volatile matter content.

## 5. Apparatus

5.1 *Platinum or Fused Quartz Crucible*, with closely fitting cover. The crucible shall be of not less than 10 nor more than 20 mL capacity, not less than 25 nor more than 35 mm in diameter, and not less than 30 nor more than 35 mm in height.

5.2 *Vertical Electric Tube Furnace*— It shall be regulated to maintain a temperature of  $950 \pm 20^\circ\text{C}$  in the crucible, as measured by a thermocouple positioned in the furnace.

## 6. Hazards

6.1 Due to the origins of RDF in municipal waste, common sense dictates that precautions should be observed when conducting tests on the samples. Recommended hygienic practices include use of gloves when handling RDF, wearing dust masks (NIOSH-approved type), especially while milling RDF samples, conducting tests under a negative-pressure hood when possible, and washing hands before eating or smoking. (**Warning**—Exercise care when placing the sample into the