
**Adhesives for thermoplastic piping
systems —**

**Part 1:
Determination of film properties**

*Adhésifs pour réseaux de tuyauteries en matières thermoplastiques —
Partie 1: Détermination des propriétés des films*

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

ISO 9311-1:2005

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9311-1:2005

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9311-1 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

[ISO 9311-1:2005](https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-32091e400000/iso-9311-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-32091e400000/iso-9311-1-2005>

ISO 9311 consists of the following parts, under the general title *Adhesives for thermoplastic piping systems*:

- *Part 1: Determination of film properties*
- *Part 2: Determination of shear strength*
- *Part 3: Test method for the determination of resistance to internal pressure*

Contents

	page
Foreword.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Safety	1
5 Principle.....	1
6 Apparatus	1
7 Procedure	3
8 Expression of results	6
9 Test report	6

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 193 "Adhesives" the secretariat of which is held by AENOR, in collaboration with Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2006, and conflicting national standards shall be withdrawn at the latest by February 2006.

This European Standard is one of a series of standards as listed below:

ISO 9311-1: Adhesives for thermoplastics piping systems - Part 1: Determination of film properties

ISO 9311-2: Adhesives for thermoplastic piping systems - Part 2: Determination of shear strength

ISO 9311-3: Adhesives for thermoplastic piping systems - Part 3: Test method for the determination of resistance to internal pressure

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom

[ISO 9311-1:2005](https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9311-1:2005

<https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>

1 Scope

This part of ISO 9311 specifies three test procedures suitable for the determination of the spreadability and film properties of solvent containing adhesives for thermoplastic piping systems. These methods do not produce directly comparable results.

One method is applicable to non-thixotropic adhesives and the other two methods are applicable to thixotropic adhesives.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references the latest edition of the referenced document (including any amendments) applies.

EN 923:1998, *Adhesives — Terms and definitions*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN 923:1998 apply.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Safety

Persons using this standard shall be familiar with normal laboratory practice.

This standard does not purport to address all the safety problems, if any, associated with its use.

It is the responsibility of the user to establish health and safety practices and to ensure compliance with any European and national regulatory conditions.

5 Principle

The adhesive under test is applied to a test plate using a specially designed applicator, at a predetermined speed and over a given length, and its spreadability is assessed by a system of scoring in comparison with a reference pattern.

The adhesive film is examined for continuity and lumps or foreign matter.

6 Apparatus

6.1 Adhesive applicator 1

(as shown in Figure 1)

This applicator has two different edges: one is used for non-thixotropic adhesives and the other for thixotropic adhesives.

Dimensions in millimetres




Figure 1 —Adhesive applicator 1

6.2 Adhesive applicator 2

(as shown in Figure 2, or a similar apparatus capable of applying a film of width 100 mm and thickness $(2 \pm 0,1)$ mm.)

This applicator is only used for thixotropic adhesives.

Dimensions in millimetres




Figure 2 — Adhesive applicator 2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.3 Glass plate

The recommended dimensions of the glass plate are:

Width: 150 mm or greater. <https://standards.iteh.ai/catalog/standards/sist/160aa4a4-3d87-4e90-98ef-2332361b148d/iso-9311-1-2005>

Length: 250 mm or greater

6.4 Plastic plate

(relevant to the intended use of the adhesive, that is, a PVC-U plate for a PVC-U adhesive.)

The recommended dimensions of the plastic plate are:

Width: 150 mm or greater.

Length: 250 mm or greater.

The plastic plate shall be smooth and untreated.

7 Procedure

7.1 General

Condition the adhesive, the applicator and the test plate at $(23 \pm 2) ^\circ\text{C}$ and $(50 \pm 5) \%$ relative humidity for at least 6 h. The test plate and adhesive applicator shall be clean and free of grease.

For each procedure apply a coating to each of three test plates.