



Designation: D 1640 – 95 (Reapproved 1999)

## Standard Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature<sup>1</sup>

This standard is issued under the fixed designation D 1640; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 These test methods cover the determination of the various stages and rates of film formation in the drying or curing of organic coatings normally used under conditions of ambient room temperature.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 202 Test Methods of Sampling and Testing Untreated Paper Used for Electrical Insulation<sup>2</sup>

D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels<sup>3</sup>

D 1005 Test Methods for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers<sup>3</sup>

D 2091 Test Method for Print Resistance of Lacquers<sup>4</sup>

#### 2.2 U.S. Government Standards:

Fed. Spec. No. CCC-C-440, Cheesecloth<sup>5</sup>

Fed. Spec. No. CCC-C-419b, Type III, Army Duck<sup>5</sup>

#### 2.3 TAPPI Standards:<sup>6</sup>

T 402 Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets, and Related Products

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Film.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as D 1640 – 59 T. Last previous edition D 1640 – 83 (1989)  $\epsilon^1$ .

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 10.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 06.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 06.02.

<sup>5</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

<sup>6</sup> Available from Technical Association of the Pulp and Paper Industry, Technology Park, P.O. Box 105113, Atlanta, GA 30348.

### 3. Significance and Use

3.1 These test methods are used to determine the various stages and rates of drying, curing, and film formation of organic coatings for the purpose of comparing types of coatings or ingredient changes, or both. This is significant in the development of organic coatings for various end uses and also for production quality control.

### 4. Coatings and Recommended Film Thicknesses

4.1 Whenever tests are to be performed on coatings not listed in Table 1, there should be a prior agreement between the purchaser and seller as to the substrate, film thickness, and application method for testing the specific coating involved.

### 5. Test Conditions

5.1 Conduct all drying tests in a well-ventilated room or chamber, free from direct drafts (Note 1), dust, products of combustion, laboratory fumes and under diffused light (see 5.4). Make all measurements at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 5\%$  relative humidity with the coated panels in a horizontal position while drying.

NOTE 1—A device to equalize air change conditions has been developed by F. Scofield.<sup>7</sup> Relative humidity should be controlled for moisture-cured and two-package urethane coatings, since their cure is greatly affected by the existing moisture conditions.

5.2 Tests should be carried out at practical viscosities at which films can be applied to the proper film thickness with resultant good flow and leveling properties. In the absence of any specific material specification, instructions for preparation of the film should be determined and agreed upon between the purchaser and the seller.

5.3 Films to be tested should have practical thicknesses commensurate with performance characteristics expected under actual usage for the type under test. All testing should be done within an area, any point of which is not less than  $\frac{1}{2}$  in. (15 mm) from the film edge.

<sup>7</sup> Gardner and Sward, *Paint Testing Manual*, ASTM STP 500, ASTM, 13th edition, 1972, p. 269.

**TABLE 1 Recommended Film Thickness of Materials to be Tested<sup>A</sup>**

Material	Dry Film Thickness
Drying oils	1.25 ± 0.25 mil (32 ± 6 µm) <sup>B</sup>
Varnishes	1 ± 0.1 mil (25 ± 2 µm) (See 7.4.2)
Lacquers	0.5 ± 0.1 mil (12.5 ± 2 µm) (See 7.5.2)
Resin solutions	0.5 ± 0.1 mil (12.5 ± 2 µm)
Enamels	1.5 ± 0.25 mil (36.5 ± 6 µm)
Oil paints	1.8 ± 0.2 mil (45 ± 2.5 µm) (See 6.1.2)
Water paints	1 ± 0.1 mil (25 ± 2 µm)

<sup>A</sup>This table is a general guide to be used when nothing more specific is agreed upon between the purchaser and the seller.

<sup>B</sup>See 6.1.2 and 7.5.1. Add driers a minimum of 24 h before test.

5.4 *Light Conditions*—Illumination of the films during the entire drying test period should be about 25 ft-candles (270 lx) from normal laboratory or sky sources, never from direct sunlight or other sources high in nonvisible radiant energy.

## 6. Preparation of Test Specimens

6.1 Carry out all tests as described in 6.1.1, 6.1.2 and 6.1.3, unless otherwise noted.

6.1.1 All test specimens shall be prepared and tested by one operator properly skilled in the methods to be used. Apply the specimens in duplicate at a time arranged so that examination intervals will fall within the normal working hours of the operator.

6.1.2 Apply the materials to be tested on clean glass panels or other specific substrate of suitable dimensions agreed upon between the purchaser and the seller. Ground-glass plates are more suitable for certain types of coatings that tend to crawl, such as low-viscosity drying oils. Suitable plates can be prepared by roughening the surface of polished glass by grinding a paste of silicon carbide (grit 1-F) and water between two glass plates.

6.1.3 The test films preferably shall be cast with a doctor blade having a clearance sufficient to give the recommended dry film thickness indicated in Table 1. When a suitable doctor blade is not available, or it has been agreed upon to apply the film in some other manner, the various conventional and automatic methods of spray, dip, flow, and brush application may be used, provided dry film thicknesses conform to the requirements given in Table 1. See Practices D 823 for a description of the spray and dip methods of application.

6.1.4 Measure the dry film thickness of test films with the proper film thickness gage. This shall be a micrometer, dial comparator, or dial indicator as described in Test Methods D 1005. When plates of small area are used, measurement of dry film thickness can be made by weighing plates before and after coating and calculating from plate area and coating solids.

## 7. Procedure

7.1 When test methods or end points other than those listed in 7.2-7.9 are used, there shall be a prior agreement between the purchaser and the seller.

7.2 *Set-To-Touch Time*—To determine set-to-touch time, lightly touch the test film with the tip of a clean finger and immediately place the fingertip against a piece of clean, clear glass. Observe if any of the coating is transferred to the glass. For the purpose of this test, the pressure of the fingertip against

the coating shall not be greater than that required to transfer a spot of the coating from 1/8 to 3/16 in. (3 to 5 mm) in cross section. The film is set-to-touch when it still shows a tacky condition, but none of it adheres to the finger.

### 7.3 Dust-Free Times:

7.3.1 *Cotton Fiber Test Method*—Separate a number of individual fibers from a mass of absorbent cotton with the aid of tweezers. At regular drying intervals, drop several of the cotton fibers from a height of 1 in. (25 mm) onto a marked section of the film. The film is considered to have dried dust free when the cotton fibers can be removed by blowing lightly over the surface of the film.

### 7.4 Tack-Free Times:

#### 7.4.1 Paper Test Method:

7.4.1.1 *Test Paper*—The test paper shall be K-4 Power Cable Paper<sup>8</sup> that when conditioned in accordance with the TAPPI Standard Method T 402, conforms to the following requirements:

Basis weight (24 by 36/500), lb	90 ± 5
Thickness, mils (µm)	6.65 (17)
Air resistance (s/100 cm <sup>2</sup> /in. <sup>2</sup> )	350
Coefficient of static friction <sup>A</sup>	0.5
Friction angle, °	22
Tensile strength, machine direction/cross direction	119/32
Tear, machine direction/cross direction	180/250
Elongation, machine direction/cross direction, %	3.0/7.0
pH of water extract	7.4
Ash content, max, %	0.6

<sup>A</sup>All tests except this one shall be run in accordance with Test Method D 202. All values for properties are typical values and not specification limits.

7.4.1.2 Lay a 2 by 3-in. (50 by 75-mm) piece of the special test paper on the film and place upon it a steel cylinder 2 in. in diameter, and of such weight 6.28 lb, (2.85 kg), as to produce a pressure of 2 psi (13.8 kPa). At the end of 5 s, remove the cylinder and invert the test panel. The film is considered free from after-tack when the paper drops off of the test film within 10 s.

7.4.2 A variation of the test method described in 7.4.1 using the same test paper can be used to test the tack-free time of insulating varnishes. In this method the piece of paper shall be 1½ in. (40 mm) in width and 6 in. (150 mm) in length. The varnish is considered tack-free when this strip of paper does not adhere to it when it is pressed on the surface of the varnish for 1 min by a cylindrical 1-lb (450-g) weight, 1 in. (25 mm) in diameter. In this test, apply the paper in the vicinity of the center of the specimen at right angles to the length of the coated specimen.

7.4.3 *Mechanical Test Method (Tack Tester)<sup>9</sup>*—The tack tester to be used in this method comprises essentially a base or surface-contacting portion 1-in. (25-mm) square and a counterbalancing portion 1 by 2 in. (25 by 50 mm) in area. Both portions are made up from a continuous metal strip 0.016 to 0.018 in. (0.41 to 0.46 mm) in thickness. To prepare the

<sup>8</sup> The sole source of supply of paper Grade R20-34, meeting these requirements known to the committee at this time is the Crocker Technical Papers, Inc., 431 Westminster St., Fitchburg, MA 01420. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>9</sup> The standard tack tester is fully described in the U. S. Patent 2,406,989, Sept. 3, 1946.