



**SLOVENSKI STANDARD**  
**SIST ISO 10378:2006**

01-oktober-2006

---

Prečiščeni koncentraciji sulfida bakra, svinca in cinka -- Določanje zlata in srebra --  
Metoda gravimetrična in metoda atomsko absorpcijske spektrometrije s plamnim  
atomsko absorpcijskim spektrometrom

Copper, lead and zinc sulfide concentrates -- Determination of gold and silver -- Fire  
assay gravimetric and flame atomic absorption spectrometric method

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Concentrés de sulfure de cuivre, de plomb et de zinc -- Dosage de l'or et de l'argent --  
Méthode gravimétrique par essai au feu et spectrométrie d'absorption atomique dans la  
flamme

Ta slovenski standard je istoveten z: **ISO 10378:2005**

---

**ICS:**

73.060.99 Druge rude

Other metalliferous minerals

**SIST ISO 10378:2006**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 10378:2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)

<https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006>

# INTERNATIONAL STANDARD

**ISO**  
**10378**

Second edition  
2005-07-01

---

---

## **Copper, lead and zinc sulfide concentrates — Determination of gold and silver — Fire assay gravimetric and flame atomic absorption spectrometric method**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

*Concentrés sulfurés de cuivre, de plomb et de zinc — Dosage de l'or et  
de l'argent — Méthode gravimétrique par essai au feu et spectrométrie  
d'absorption atomique dans la flamme*

[SIST ISO 10378:2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)

[https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-  
b7cbb550320e/sist-iso-10378-2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)



Reference number  
ISO 10378:2005(E)

© ISO 2005

**ISO 10378:2005(E)****PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 10378:2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)

<https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword.....	v
Introduction .....	vi
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Normative references</b> .....	<b>1</b>
<b>3</b> <b>Principle</b> .....	<b>2</b>
<b>3.1</b> <b>Fusion</b> .....	<b>2</b>
<b>3.2</b> <b>Cupellation</b> .....	<b>2</b>
<b>3.3</b> <b>Parting</b> .....	<b>2</b>
<b>3.4</b> <b>Retreatment</b> .....	<b>2</b>
<b>3.5</b> <b>Correction for blank contamination</b> .....	<b>2</b>
<b>4</b> <b>Reagents</b> .....	<b>2</b>
<b>5</b> <b>Apparatus</b> .....	<b>4</b>
<b>6</b> <b>Sample</b> .....	<b>5</b>
<b>6.1</b> <b>Test sample</b> .....	<b>5</b>
<b>6.2</b> <b>Test portion</b> .....	<b>5</b>
<b>7</b> <b>Procedure</b> .....	<b>5</b>
<b>7.1</b> <b>Number of determinations</b> .....	<b>5</b>
<b>7.2</b> <b>Trial fusion</b> .....	<b>5</b>
<b>7.3</b> <b>Blank tests</b> .....	<b>5</b>
<b>7.4</b> <b>Charge preparation</b> .....	<b>6</b>
<b>7.5</b> <b>Primary fusion</b> .....	<b>7</b>
<b>7.6</b> <b>Cupellation</b> .....	<b>7</b>
<b>7.7</b> <b>Retreatment of residues</b> .....	<b>8</b>
<b>7.8</b> <b>Determination of gold in the primary bead</b> .....	<b>8</b>
<b>7.9</b> <b>Determination of gold and silver in secondary beads and blanks, and of silver in prills</b> .....	<b>9</b>
<b>7.10</b> <b>Determination of silver in the parting solution</b> .....	<b>11</b>
<b>8</b> <b>Expression of results</b> .....	<b>11</b>
<b>8.1</b> <b>Mass fraction of gold</b> .....	<b>11</b>
<b>8.2</b> <b>Mass fraction of silver</b> .....	<b>12</b>
<b>9</b> <b>Precision</b> .....	<b>13</b>
<b>9.1</b> <b>Expression of precision</b> .....	<b>13</b>
<b>9.2</b> <b>Method for obtaining the final result (see Annex H)</b> .....	<b>14</b>
<b>9.3</b> <b>Precision between laboratories</b> .....	<b>15</b>
<b>9.4</b> <b>Check of trueness</b> .....	<b>17</b>
<b>9.4.1</b> <b>General</b> .....	<b>17</b>
<b>9.4.2</b> <b>Type of certified reference material (CRM) or reference material (RM)</b> .....	<b>17</b>
<b>10</b> <b>Test report</b> .....	<b>18</b>
<b>Annex A (normative) Procedure for the preparation and determination of the mass of a predried test portion</b> .....	<b>19</b>
<b>Annex B (normative) Trial fusion</b> .....	<b>21</b>
<b>Annex C (normative) Blank determination</b> .....	<b>22</b>
<b>Annex D (normative) Inquartation</b> .....	<b>23</b>
<b>Annex E (normative) Determination of vaporization loss of silver during the cupellation process</b> .....	<b>24</b>
<b>Annex F (normative) Sulfuric acid - Parting</b> .....	<b>25</b>

**ISO 10378:2005(E)**

<b>Annex G (normative) Determination of impurities in parting solutions and washings.....</b>	<b>27</b>
<b>Annex H (normative) Flowsheet of the procedure for the acceptance of analytical values for test samples (see 9.2) .....</b>	<b>31</b>
<b>Annex I (informative) Flowsheet of the method.....</b>	<b>32</b>
<b>Annex J (informative) Roasting method.....</b>	<b>33</b>
<b>Annex K (informative) Guide to the preparation of dilutions for the determination of silver in parting solutions and residues.....</b>	<b>34</b>
<b>Annex L (informative) Derivation of precision equations.....</b>	<b>35</b>
<b>Bibliography .....</b>	<b>52</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 10378:2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)

<https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10378 was prepared by Technical Committee ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

This second edition cancels and replaces the first edition (ISO 10378:1994), which has been technically revised.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 10378:2006  
<https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006>

ISO 10378:2005(E)

## Introduction

This International Standard describes a method for the determination of the mass fraction of gold and silver in copper, lead and zinc sulfide concentrates. This International Standard was prepared to enable laboratories to determine the mass fraction of gold and silver in suitable samples using instrumental methods.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 10378:2006](https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006)

<https://standards.iteh.ai/catalog/standards/sist/1ed1593c-ac14-410a-ba22-b7cbb550320e/sist-iso-10378-2006>



# Copper, lead and zinc sulfide concentrates — Determination of gold and silver — Fire assay gravimetric and flame atomic absorption spectrometric method

**WARNING** — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

## 1 Scope

This International Standard specifies a fire assay gravimetric and flame atomic absorption spectrometric method for the determination of the mass fraction of gold and silver in copper, lead and zinc sulfide concentrates as follows:

### — Copper concentrates:

The method is applicable to the determination of mass fractions of gold from 0,5 g/t to 300 g/t and of mass fractions of silver from 25 g/t to 1 500 g/t in copper sulfide concentrates containing mass fractions of copper from 15 % to 60 %.

### — Lead concentrates

The method is applicable to the determination of mass fractions of gold from 0,1 g/t to 25 g/t and of mass fractions of silver from 200 g/t to 3 500 g/t in lead sulfide concentrates containing mass fractions of lead from 10 % to 80 %.

### — Zinc concentrates

The method is applicable to the determination of mass fractions of gold from 0,1 g/t to 12 g/t and of mass fractions of silver from 10 g/t to 800 g/t in zinc sulfide concentrates containing mass fractions of zinc up to 60 %.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*

ISO 648:1977, *Laboratory glassware — One-mark pipettes*

ISO 1042:1998, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 4787:1984, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity*

ISO 9599:1991, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method*

**ISO 10378:2005(E)****3 Principle**

Fire assaying for the determination of gold and silver comprises a series of steps to separate firstly the precious metals from most of the associated metals, followed by separation of the gold from silver and other metals preconcentrated into a precious-metal alloy.

The stages that comprise the determinations are described in 3.1 to 3.5 inclusive.

**3.1 Fusion**

The samples are fused in a crucible after mixing with a litharge-based flux which, under reducing conditions, collects the precious metals in a metallic lead button.

**3.2 Cupellation**

The base metals present in the lead button are substantially separated from the precious metals by oxidizing fusion. Cupellation produces a bead largely comprising a silver-gold alloy with small quantities of other metals.

**3.3 Parting**

Gold is separated from the primary bead by treatment with nitric acid. The gold prill is weighed. Gold prills having a mass less than 50 µg are dissolved in aqua regia and the gold is determined by atomic absorption spectrometry (AAS). Silver is determined in the parting solution by AAS.

**3.4 Retreatment**

All residues are retreated to maximize the recovery of gold and silver. The addition of collectors for either gold or silver is not required, as both metals are present in sufficient amounts to be readily visible after the cupellation stage. The second bead is dissolved in acids followed by analysis of both metals by AAS.

**3.5 Correction for blank contamination**

Contamination by gold and silver impurities in the reagents is corrected for by fusing the reagents without the test portion.

**4 Reagents**

During the analysis, use only reagents of recognized analytical grade and water that complies with grade 2 of ISO 3696.

**4.1 Sodium carbonate**, anhydrous.

**4.2 Litharge** (PbO), assay grade having a mass fraction of gold of less than 0,01 g/t and a mass fraction of silver of less than 0,2 g/t.

**4.3 Silica**, precipitated.

**4.4 Potassium nitrate or sodium nitrate**

NOTE If sodium nitrate is used, the masses specified for potassium nitrate will have to be modified:

$$\text{g of KNO}_3 \times \frac{85,0}{101,1} = \text{g of NaNO}_3$$

**4.5 Flour**

**4.6 Borax**, fused anhydrous sodium tetraborate (borax glass powder).

**4.7 Nitric acid**, concentrated ( $\rho_{20}$  1,42 g/ml), chloride concentration < 0,5  $\mu\text{g/ml}$ .

**4.8 Nitric acid**, diluted 1+1.

Slowly add 500 ml of concentrated nitric acid (4.7) to 500 ml of water, while stirring.

**4.9 Lead**, foil, having a mass fraction of gold of less than 0,01 g/t and a mass fraction of silver of less than 0,2 g/t.

**4.10 Silver**, of minimum purity 99,99 %.

**4.11 Hydrochloric acid** ( $\rho_{20}$  1,16 g/ml to 1,19 g/ml).

**4.12 Thiourea**, 10 g/l solution.

Add 1 g of thiourea to 100 ml of water.

**4.13 Aqua regia**

Mix 3 parts of hydrochloric acid (4.11) with 1 part of nitric acid (4.7). Prepare freshly as required.

**4.14 Standard solutions**

Standard solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

**4.14.1 Silver**, standard stock solution A (500  $\mu\text{g}$  of Ag/ml).

Weigh 0,500 0 g of silver metal to the nearest 0,1 mg. Transfer to a 100 ml beaker, add 20 ml of diluted nitric acid (4.8) and warm to dissolve. Cool and add 20 ml of concentrated nitric acid (4.7). Transfer to a 1 000 ml volumetric flask, fill up with water nearly to the mark, mix and cool to room temperature; then fill up exactly to the mark and mix again.

**4.14.2 Silver**, standard solution B (50  $\mu\text{g}$  of Ag/ml).

Pipette 10,00 ml of silver standard stock solution A (4.14.1) into a 100 ml volumetric flask, fill up with water nearly to the mark, mix and cool to room temperature; then fill up exactly to the mark and mix again.

Prepare a fresh solution per batch.

**4.14.3 Gold**, standard solution (1000  $\mu\text{g}$  of Au/ml).

Weigh 1,000 g of gold metal to the nearest 0,1 mg. Transfer to a 200 ml beaker, add 25 ml of aqua regia solution (4.13) and warm to dissolve. Cool and transfer to a 1 000 ml volumetric flask. Add 75 ml of hydrochloric acid (4.11), fill up nearly to the mark with water, mix and cool to room temperature; then fill up exactly to the mark and mix again.

**4.14.4 Gold and silver**, standard solution (100  $\mu\text{g}$  of Au/ml + 50  $\mu\text{g}$  of Ag/ml).

Pipette 10,00 ml of silver standard stock solution A (4.14.1) into a 100 ml volumetric flask. Add 40 ml of hydrochloric acid (4.11). Pipette 10,00 ml of gold standard solution (4.14.3) into the volumetric flask. Fill up nearly to the mark with water, mix and cool to room temperature; then fill up exactly to the mark and mix again.

**4.15 Calibration solutions**

Calibration solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

**ISO 10378:2005(E)****4.15.1 Gold/silver calibration solutions**

Pipette 0,0 ml, 1,00 ml, 2,00 ml, 5,00 ml and 10,00 ml of gold and silver standard solution (4.14.4) into a series of 100 ml one-mark volumetric flasks.

Add 40 ml of hydrochloric acid (4.11) to each flask, fill up nearly to the mark with water, mix and cool to room temperature; then fill up exactly to the mark and mix again.

These solutions contain 0,0 µg of Au/ml, 1,00 µg of Au/ml, 2,00 µg of Au/ml, 5,00 µg of Au/ml and 10,00 µg of Au/ml; and 0,0 µg of Ag/ml, 0,50 µg of Ag/ml, 1,00 µg of Ag/ml, 2,50 µg of Ag/ml and 5,00 µg of Ag/ml and shall be freshly prepared.

**4.15.2 Silver calibration solutions**

Pipette 0,0 ml, 1,00 ml, 2,00 ml, 4,00 ml, 6,00 ml, 8,00 ml and 10,00 ml of silver standard solution B (4.14.2) into a series of 100 ml volumetric flasks. Add 10 ml of nitric acid (4.7), fill up nearly to the mark with water, mix and cool to room temperature; then fill up exactly to the mark and mix again.

These solutions contain 0,0 µg of Ag/ml, 0,50 µg of Ag/ml, 1,00 µg of Ag/ml, 2,00 µg of Ag/ml, 3,00 µg of Ag/ml, 4,00 µg of Ag/ml and 5,00 µg of Ag/ml, and shall be freshly prepared.

Contamination by gold and silver impurities in the reagents is corrected for by fusing the reagents without the test portion.

**5 Apparatus**

iTeh STANDARD PREVIEW

**5.1 Assay crucible furnace**, with a maximum required operating temperature of 1 200 °C.

**5.2 Muffle furnace**, with a maximum required operating temperature of 1 100 °C. Temperature indication, automatic temperature control and controlled air flow are preferable.

**5.3 Assay crucibles**, made of fire clay, of nominal capacity 200 ml to 600 ml, capable of withstanding corrosion by the samples and fluxes at 1 100 °C. The crucible shall be of such a size that the charge does not fill the crucible to a depth greater than 3/4 the depth of the crucible.

**5.4 Cupels**, made of magnesium oxide, or bone-ash cupels having a nominal capacity of 50 g of molten lead. The inside bottom of the cupel shall be concave, as recommended in the fire assay texts referred to in the Bibliography.

**5.5 Conical mould**, made of cast iron, of sufficient capacity to contain all of the molten lead plus slag from the crucible fusion.

**5.6 Analytical balance**, sensitive to 1 mg.

**5.7 Microbalance**, sensitive to 1 µg or less.

**5.8 Ordinary laboratory glassware**, washed free of chlorides.

**5.9 Volumetric glassware**, of class A complying with ISO 385-1, ISO 648 and ISO 1042, and used in accordance with ISO 4787.

**5.10 Atomic absorption spectrometer (AAS)**, equipped with background correction and a glass bead in the spray chamber.

**5.11 Inductively coupled plasma (ICP) atomic emission spectrometer**

**5.12 Pulverizer**

**5.13 Hotplate**

## 6 Sample

### 6.1 Test sample

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE A test sample is not required if predried test portions are to be used (see Annex A).

### 6.2 Test portion

Taking multiple increments, extract a test portion from the test sample in such a manner that it is representative of the whole contents of the dish or tray. Weigh to the nearest 1 mg approximately 10 g to 20 g of the test sample. At the same time as test portions are being weighed for analysis, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in Annex A may be used to prepare predried test portions directly from the laboratory sample.

If a mass fraction of arsenic above 2 % is present in the sample, this element should be removed by following the procedure in Annex J; otherwise, interference with the cupellation stage may occur.

NOTE If the mass fraction of copper is greater than 30 %, a 10 g or 15 g test portion is preferable (see the fourth paragraph of 7.4).

For lead concentrates, the test portion should be 10 g to ensure an adequate supply of lead.

## 7 Procedure

### 7.1 Number of determinations

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE 1 Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment, within short intervals of time.

NOTE 2 In the case where the ratio of silver to gold does not exceed 2,5 to 1 and the procedure specified in 7.10 is carried out for the silver determination, separate determinations for gold and silver will be necessary (see Annex D). Four test portions, therefore, are required, i.e. two for determinations of gold and two for silver.

### 7.2 Trial fusion

Carry out a trial fusion as described in Annex B, to ensure that the mass of the lead button is between 30 g and 45 g.

### 7.3 Blank tests

Carry out a reagent blank test as described in Annex C in parallel with the analysis, using the same quantities of all reagents, with the addition of sufficient flour (4.5) to the flux to give a lead button of between 30 g and 45 g. Omit the test portion and the potassium nitrate. The total blank should not exceed 5 µg of gold or 100 µg of silver.

## ISO 10378:2005(E)

## 7.4 Charge preparation

Determine the mass of potassium nitrate (4.4) and flour (4.5) required in the charge, as indicated by the trial fusion (see Annex B), and include this reagent in the flux mixture. Typical masses of the flux components for copper, lead and zinc concentrates are shown in Tables 1 to 3 respectively.

Thoroughly mix the test portion with a flux.

Intimate mixing of flux components and the test portion is very important. All flux components should be in a finely divided state with a preferred particle size of less than 0,5 mm.

**Table 1 — Typical masses of flux components for copper concentrates**

Flux components	Mass g
Sodium carbonate (4.1)	30
Litharge (4.2)	210
Silica (4.3)	25
Potassium nitrate (4.4)	—
Flour (4.5)	—
Test portion	20

NOTE If the mass fraction of copper is greater than 30 %, the mass of litharge should be 30 times that of copper plus 35 g for the lead button. Alternatively a 10 g or 15 g test portion can be used while retaining the flux composition given in Table 1. If there are difficulties experienced in achieving a fluid melt, the amount of silica recommended in Table 1 can be reduced to 19 g, while including 6 g borax.

**Table 2 — Typical masses of flux components for lead concentrates**

Flux components	Mass g
Sodium carbonate (4.1)	30
Litharge (4.2)	100
Silica (4.3)	10
Borax (4.6)	10
Potassium nitrate (4.4)	—
Flour (4.5)	—
Test portion	10

**Table 3 — Typical masses of flux components for zinc concentrates**

Flux components	Mass g
Sodium carbonate (4.1)	30
Litharge (4.2)	120
Silica (4.3)	10
Borax (4.6)	10
Potassium nitrate (4.4)	—
Flour (4.5)	—
Test portion	20

Place the mixture in an assay crucible (5.3).

## 7.5 Primary fusion

Place the crucibles in the furnace (5.1) preheated to approximately 900 °C.

If oil-fired or gas-fired furnaces are used, the fuel should be turned off immediately before opening the furnace.

Slowly raise the furnace temperature to 1 000 °C to 1 050 °C. Maintain this temperature until the fusion has been tranquil for at least 10 min.

The optimum furnace setting temperature depends on the furnace structure and the position of the thermometer. If unfused material remains in the bottom of assay crucibles, the setting temperature of the furnace should be raised and the assay repeated.

To minimize crucible corrosion and build-up of impurities in the lead button, the overall fusion time should not exceed 40 min. However, should the fusion take an extended time to settle, the fusion time may need to exceed 40 min.

It is recommended that a fire-clay lid or a layer of salt or borax approximately 12 mm thick be used with this fusion to prevent loss of material by dusting or ebullition. If borax is used as a cover, the amount used in the flux may be reduced accordingly. If some 'shotting' of the lead is noted in the slag (this is common for zinc concentrates), it is recommended that the extra borax be retained.

Pour the mixture into a dry conical mould (5.5), taking care that no loss of lead or slag occurs. Reserve the crucible for retreatment fusion.

Allow the mixture to cool and carefully separate the lead button from the slag. Hammer the lead button as necessary to remove any small particles of adhering slag. Reserve the slag for retreatment.

Weigh the lead button. If the button weighs less than 30 g or more than 45 g, discard the button and slag and repeat the assay after appropriate adjustment of the oxidizing agent (see Annex B).

NOTE Buttons weighing less than 30 g may show poor collection efficiencies, whereas those exceeding 45 g may contain higher amounts of copper and other base metals.

## 7.6 Cupellation

Place the lead button obtained in 7.5 into a preheated cupel (5.4) in a muffle furnace (5.2) at 900 °C. Allow the cupellation to proceed at the lower muffle temperature of approximately 860 °C with a steady air flow.

Variations depend on the cupel type and furnace conditions. In the case of cupels made of bone ash, a cupellation temperature of 820 °C is recommended.

NOTE 1 In the case where only gold is being determined, it could be effective to raise the furnace temperature to 900 °C to finish the cupellation after the visible lead melt on the cupel is approximately 10 mm in diameter [approximately 80 % (mass fraction) of lead absorbed].

High cupellation temperatures will cause higher silver losses and low temperatures can cause "freezing" of the bead and incomplete cupellation. It is recommended that loss of silver during the cupellation process be determined, to decide upon the furnace conditions (see Annex E).

Remove the cupel from the furnace and cool.

Carefully extract the primary bead and remove any adhering cupel material with a brush. Flatten the bead slightly and place in a 30 ml porcelain crucible.

NOTE 2 A test tube can be used instead of a porcelain crucible.

NOTE 3 If the ratio of silver to gold in the primary bead is greater than 2,5 to 1, the silver can be determined by the gravimetric method instead of the procedure specified in 7.10. For the gravimetric method, weigh the primary bead, in micrograms, to the nearest 1 µg ( $m_0$ ), carry out the parting by the procedure specified in 7.8, and determine the impurities in the parting solutions and washings by the procedure specified in Annex G.