



Standard Test Method for Evaluation of Corrosiveness of Diesel Engine Oil at 121°C¹

This standard is issued under the fixed designation D 5968; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The method described in this test method is based on the gas turbine lubricant corrosion and oxidation test described in **Federal Test Method Standard 791**, Method 5308. Because this test method relates to corrosion in diesel engines rather than in gas turbines, temperatures, metal coupons, and certain parts of the test procedure were modified to be more appropriate for heavy duty diesel engines.

The method described in this test method can be used by any properly equipped laboratory, without outside assistance. However, the ASTM Test Monitoring Center (TMC)² provides reference oils and an assessment of the test results obtained on those oils by the laboratory (see **Annex A1**). By these means, the laboratory will know whether their use of the test method gives results statistically similar to those obtained by other laboratories. Furthermore, various agencies require that a laboratory utilize the TMC services in seeking qualification of oils against specifications. For example, the U.S. Army imposes such a requirement in connection with several Army engine lubricating oil specifications.

Accordingly, this test method is written for use by laboratories that utilize the TMC services. Laboratories that choose not to use those services may simply ignore those portions of the test method that refer to the TMC.

This test method may be modified by means of Information Letters issued by the TMC. In addition, the TMC may issue supplementary memoranda related to the method (see **Annex A1**). For other information, refer to the research report on the Cummins Bench Corrosion Test.³

1. Scope

1.1 This test method is used to test diesel engine lubricants to determine their tendency to corrode various metals, specifically alloys of lead and copper commonly used in cam followers and bearings. Correlation with field experience has been established.⁴

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific hazard statements are given in **5.3.1, 6.6, 6.7, 6.8, 6.9, 6.10, 6.11, 7.1.1, 7.1.2, 7.1.5, and 7.4.1.**

2. Referenced Documents

2.1 *ASTM Standards:*⁵

D 130 Test Method for Detection of Copper Corrosion from Petroleum Products by the Copper Strip Tarnish Test

D 5185 Determination of Additive Elements, Wear Metals, and Contaminants in Used Lubricating Oils and Determination of Selected Elements in Base Oils by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.B0 on Automotive Lubricants.

Current edition approved May 1, 2004. Published June 2004. Originally approved in 1998. Last previous edition approved in 2001 as D 5968-01.

² ASTM Test Monitoring Center, 6555 Penn Ave., Pittsburgh, PA 15206-4489. (<http://www.astmtmc.cmu.edu/>)

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR: D02-1322. The research report and this test method are supplemented by Information Letters and Memoranda issued by the ASTM Test Monitoring Center. This edition incorporates revisions contained in all information letters through No. 03-1. Users of this test method shall contact the ASTM Test Monitoring Center to obtain the most recent of these.

⁴ Wang, J. C., and Cusano, C. M., "Development of A Bench Test to Detect Oils Corrosive to Engine Components," SAE Technical Paper No. 940790, 1994.

⁵ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.




FIG. 1 Sample Tube




FIG. 2 Sample Tube Head

2.2 U.S. Federal Test Method Standards:⁶

Federal Test Method Standard 791, Method 5308.7 Corrosiveness and Oxidation Stability of Light Oils (Metal Squares)

3. Summary of Test Method

3.1 Four metal coupons of copper, lead, tin, and phosphor bronze are immersed in a measured amount of engine oil. The oil, at an elevated temperature, is blown with air for a period of time. When the test is completed, the coupons and the stressed oil are examined to detect corrosion.

3.2 An industrial reference oil is tested with each group of tests to verify test acceptability.

4. Significance and Use

4.1 This test method is intended to simulate the corrosion process of non-ferrous metals in diesel lubricants. The corrosion process under investigation is that believed to be induced primarily by inappropriate lubricant chemistry rather than lubricant degradation or contamination. This test method has been found to correlate with an extensive fleet database containing corrosion-induced cam and bearing failures.

5. Apparatus

5.1 The main apparatus consists of the following items of standard wall borosilicate glassware as shown in Figs. 1-6.

- 5.1.1 Main Sample Tube, Fig. 1.
- 5.1.2 Sample Tube Head, Fig. 2.
- 5.1.3 Air Tube, Fig. 3.




FIG. 3 Air Tube

5.1.4 Thermocouple Tube, Fig. 4.

5.1.5 Condenser, Allihn Type, Fig. 5.

5.1.6 Assembled Apparatus, Fig. 6.

5.2 Additional glassware items and assembly accessories needed are:

5.2.1 Spacers (for metal specimen), of borosilicate glass, standard wall, 9-mm outside diameter, 6-mm length.

5.2.2 Oil Sampling Tube, Borosilicate Glass, 4-mm outside diameter, with sampling end approximately 600 mm to reach

⁶ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.




FIG. 4 Thermocouple Tube




FIG. 6 Assembled Apparatus




FIG. 5 Condenser, Allihn Type

into main sample tube. Tube is bent U-shape with exit end fitted by a one-hole stopper to a 25-mL filtering flask. Exit end may be any convenient length.

5.2.3 *Adapter*^{7,8}, Polytetrafluoroethylene for 10/18 joint for sealing of air tube to sample tube head.

⁷ A satisfactory source for this item is Kontes Glass Co., Vineland, NJ 08360.

⁸ The sole source of supply of the apparatus known to the committee at this time is noted in the adjoining footnote. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

iTeh Standards

(<https://standards.iteh.org/document/ASTM-D5968-04>)

<https://standards.iteh.org/catalog/standards/sist/4b12194a-4e14-88a8-537f660187d/astm-d5968-04>

5.3 Other items and equipment are:

5.3.1 *Heating Bath*, constant temperature control within $\pm 0.5^\circ\text{C}$ ($\pm 1^\circ\text{F}$) of test temperature with an immersion depth of 23 to 35 cm. Oil or aluminum baths are recommended. (**Warning**—There are exposed hot surfaces on apparatus. Avoid skin contact by use of protective equipment.)

5.3.2 *Hood Ventilation*, to adequately remove fumes during heating.

5.3.3 *Air Supply*, use air from a clean, dry source.

5.3.4 *Flowmeter*, capable of measuring 10 ± 1 L/h.

5.3.5 *Balance*, analytical sensitivity 0.1 mg.

5.3.6 *Balance, Laboratory*, 2500-g capacity, 0.1-g sensitivity.

5.3.7 *Microscope*, with 20-diameter magnification.

5.3.8 *Assembly Fixture*, wood slotted to hold coupons squares (assembly as shown in Fig. 7) for tying with wire.

5.3.9 When air needs to be conditioned there is a need for an air drier. The method used is optional provided the air characteristics of 5.3.3 are attained. For drying, a satisfactory method is the use of a glass column containing 8-mesh anhydrous calcium sulfate with a column diameter such that velocity of air does not exceed 1.2 m/min.

5.3.10 *Oven*, optional, to dry glassware at elevated temperature.

5.3.11 *Forceps*, stainless steel.

5.3.12 *Thermocouple*.

5.3.13 *Brush*, short-bristled, stiff (old-style typewriter cleaning brush or equivalent).

6. Reagents and Materials

6.1 *Purity of Reagents*—Use reagent grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents




FIG. 7 Arrangement of Metal Coupons

conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁹

6.2 Metal Specimens:^{8,10}

6.2.1 Coupons, 0.081 cm thick by 2.5 cm square, one each, with two drilled holes (as shown in Fig. 7), as follows:

- 6.2.1.1 Copper (R401-A),
- 6.2.1.2 Lead (R401-lead),
- 6.2.1.3 Tin (R401-tin), and
- 6.2.1.4 Phosphor Bronze (R401-LEADz).

6.3 Nichrome Wire, clean (for tying coupons together).

6.4 Abrasive Paper, 240 grit aluminum oxide and 400 grit silicon-carbide.¹¹ Do not use iron-containing abrasives such as natural emery.

6.5 Cotton, absorbent.

6.6 Acetone (ACS), sulfur-free. (**Warning**—Flammable. Health hazard.)

6.7 Degreasing Solvents, Trichlorotrifluoroethane or 1,1,1-trichloroethane. (**Warning**—Harmful if inhaled.)

⁹ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

¹⁰ Satisfactory metal specimens may be obtained from: Test Engineering, Inc. (TEI), 12718 Cimarron Path, San Antonio, TX 78249-3423. This is the only coupon source to be used for obtaining a valid reference run and data for certification.

¹¹ Suitable abrasive paper meeting these specifications is included with the metal coupons from the source indicated in 6.2.

6.8 Glassware Cleaning Solution, mix 35 mL of saturated sodium dichromate (aqueous) solution and 1000 mL of concentrated sulfuric acid. (**Warning**—Causes severe burns.)

6.9 Carbon Remover for Glassware^{8,12}, Oakite Stripper R-8. (**Warning**—Corrosive, causes severe burns.)

6.10 Tetrahydrofuran. (**Warning**—Toxic and flammable. Health hazard.)

6.11 Naphtha, Aromatic. (**Warning**—Flammable. Health hazard.)

6.12 Filter Paper.

6.13 Kimwipe Tissues, or similar.

6.14 Industrial Reference Oil.²

7. Preparation of Apparatus

7.1 Cleaning of Glassware from Previous Run:

7.1.1 Rinse all glassware items and the air tube adapter with degreasing solvent to remove residual oil, and air dry. (**Warning**—Harmful if inhaled.)

7.1.2 Fill or immerse the sample tube, air tube, and the 9-mm glass spacers in carbon remover at room temperature until carbonaceous deposits are removed. Water rinse after removal. (**Warning**—Corrosive, causes severe burns.)

7.1.3 Wash all glassware items and the air tube adapter with detergent.^{8,13} Rinse with water to remove detergent, and dry.

7.1.4 Store all items in a dust free cabinet until needed for test. If stored longer than one week, rinse again with distilled water before use, and dry.

7.1.5 A more elaborate glass cleaning procedure can be used, if it is for a given situation. This cleaning procedure is necessary in a referee situation unless a cleaning solution can be used which is satisfactory to all parties involved. Fill and immerse all glassware items with glassware cleaning solution and soak for 3 to 16 h. (**Warning**—Corrosive, causes severe burns.)

7.1.6 Remove glassware from cleaning solution, rinse several times with tap water, followed by distilled water, and oven dry.

7.2 Cleaning of Glassware (New):

7.2.1 Proceed as in 7.1.3 and 7.1.6 in that order (omit 7.1.1, 7.1.2, 7.1.4, and 7.1.5).

7.3 Assembly—Assemble as shown in Fig. 6 using only the test oil to lubricate glass joints during assembly.

7.4 Preparation of Metal Specimens:

7.4.1 Wash a length of the metal tying wire with tetrahydrofuran and acetone and allow to dry. (**Warning**—This and the following preparation processes should be performed under a fume hood.)

7.4.2 The metal squares are prepared as follows:

7.4.2.1 Using the 240 grit abrasive paper, remove all surface blemishes from both sides and all four edges of each square, and any burrs from the drilled holes. Finish polishing with 400 grit paper wetted by acetone to remove marks from previous polishing. A good technique is to place abrasive paper on a flat

¹² Oakite Stripper R-8 is available from Oakite Products, Inc., 50 Valley Rd., Berkeley Heights, NJ 07922. It has been found satisfactory for this purpose.

¹³ A detergent found satisfactory is Alconox made by Alconox, Inc., 215 Park Ave. S., New York, NY 10003.