



SLOVENSKI STANDARD SIST EN ISO 18278-1:2005

01-januar-2005

9`Y_fci dcfcj bc`j Uf`Yb`Y`E`J Uf`j cgh`E`%`XY.`CWb`Y`j Ub`Y`j Uf`j cgh`df`j`i dcfcj bYa
lc`_cj bYa ž`_c`i lbYa`]b`VfUXUj`] bYa`] Uf`Yb`1`_cj`]bg`_`]`a UHf`]Ucj`f`IGC`%`&+,`!
%&\$\$(Ł

Resistance welding - Weldability - Part 1: Assessment of weldability for resistance spot, seam and projection welding of metallic materials (ISO 18278-1:2004)

Widerstandsschweißen - Schweißeignung - Teil 1: Bewerten der Schweißeignung zum Widerstandspunkt-, Rollennaht- und Buckelschweißen von metallischen Werkstoffen (ISO 18278-1:2004)

Soudage par résistance - Soudabilité - Partie 1 : Evaluation de la soudabilité pour le soudage par points, à la molette et par bossages des matériaux métalliques (ISO 18278-1:2004)

Ta slovenski standard je istoveten z: EN ISO 18278-1:2004

ICS:

25.160.10 Varilni postopki in varjenje Welding processes

SIST EN ISO 18278-1:2005 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18278-1:2005

<https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1-435dee2baf9a/sist-en-iso-18278-1-2005>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 18278-1

November 2004

ICS 25.160.10

English version

**Resistance welding - Weldability - Part 1: Assessment of
weldability for resistance spot, seam and projection welding of
metallic materials (ISO 18278-1:2004)**

Soudage par résistance - Soudabilité - Partie 1 : Évaluation
de la soudabilité pour le soudage par résistance par points,
à la molette et par bossages des matériaux métalliques
(ISO 18278-1:2004)

Widerstandsschweißen - Schweißignung - Teil 1:
Bewerten der Schweißignung zum Widerstandspunkt-,
Rollennaht- und Buckelschweißen von metallischen
Werkstoffen (ISO 18278-1:2004)

This European Standard was approved by CEN on 24 June 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Test procedures	5
4.1 General.....	5
4.2 Basic test procedures	6
4.2.1 Determination of the ability to make a weld.....	6
4.2.2 Determination of the ability to continue making welds	6
4.2.3 Determination of the weld properties	7
4.3 Additional tests	8
4.3.1 General.....	8
4.3.2 Hold time sensitivity procedure	8
5 Further weld properties.....	8
6 Test report	9
Bibliography	10

iTeh STANDARD PREVIEW

(standards.iteh.ai)

SIST EN ISO 18278-1:2005

[https://standards.iteh.ai/catalog/standards/sist/1da154ed-c29b-4370-b7e1-](https://standards.iteh.ai/catalog/standards/sist/1da154ed-c29b-4370-b7e1-435dce2ba79a/sist-en-iso-18278-1-2005)[435dce2ba79a/sist-en-iso-18278-1-2005](https://standards.iteh.ai/catalog/standards/sist/1da154ed-c29b-4370-b7e1-435dce2ba79a/sist-en-iso-18278-1-2005)

Foreword

This document (EN ISO 18278-1:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2005, and conflicting national standards shall be withdrawn at the latest by May 2005.

This standard consists of the following parts:

- Part 1: Assessment of weldability for resistance spot, seam and projection welding of metallic materials;
- Part 2: Alternative procedures for the assessment of sheet steels for spot welding.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 18278-1:2005
https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1-435dee2baf9a/sist-en-iso-18278-1-2005](https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1-435dee2baf9a/sist-en-iso-18278-1-2005)

EN ISO 18278-1:2004 (E)**1 Scope**

This document recommends procedures for determining the generic weldability for resistance spot, seam and projection welding of metallic materials.

This procedure is applicable for the assessment of the weldability of uncoated/coated steels, stainless steels and non-ferrous alloys such as aluminium, titanium, magnesium and nickel and their alloys of single thickness lower than or equal to 5 mm.

The weldability of metallic materials in resistance welding is defined in terms of:

- the ability to make the weld in the first place;
- the ability to continue making welds;
- the ability of the weld to withstand the imposed service stresses.

The procedures recommended in this standard can be used to:

- compare the weldability of different metallic materials;
- compare the welding response of a particular welding equipment and allow comparisons between different equipment and determine the influence of the static/dynamic properties of different welding equipment;
- determine the weldability of a material when any welding configuration is changed e.g. electrode material and/or shape, water cooling requirements etc.;
- investigate the effect of welding parameters such as welding current, weld time, electrode force or complex welding schedules including pulse welding, current stepping etc. on weldability.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 8166, *Resistance welding — Procedure for the evaluation of the life of spot welding electrodes using constant machines settings (ISO 8166:2003).*

EN ISO 14270, *Specimen dimensions and procedure for mechanized peel testing resistance spot, seam and embossed projection welds (ISO 14270:2000).*

EN ISO 14271, *Vickers hardness testing of resistance spot, projection and seam welds (low load and microhardness) (ISO 14271:2000).*

EN ISO 14272, *Specimen dimensions and procedure for cross tension testing resistance spot and embossed projection welds (ISO 14272:2000).*

EN ISO 14273, *Specimen dimensions and procedure for shear testing resistance spot, seam and embossed projection welds (ISO 14273:2000).*

EN ISO 14327, *Resistance welding — Procedures for determining the weldability lobe for resistance spot, projection and seam welding (ISO 14327:2004).*

EN ISO 14329:2003, *Resistance welding — Destructive tests of welds — Failure types and geometric measurements for resistance spot, seam and projection welds (ISO 14329:2003)*.

EN ISO 15609-5, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding (ISO 15609-5:2004)*.

EN ISO 15614-12, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 12: Spot, seam and projection welding (ISO 15614-12:2004)*.

EN ISO 18278-2:2004, *Resistance welding — Weldability — Part 2: Alternative procedures for the assessment of sheet steels for spot welding (ISO 18278-2:2004)*.

ISO 669:2000, *Resistance welding — Resistance welding equipment — Mechanical and electrical requirements*.

ISO/DIS 14373, *Resistance welding — Procedure for spot welding of uncoated and coated low carbon steels*.

ISO/DIS 16432, *Resistance welding — Procedure for projection welding of uncoated and coated low carbon steels using embossed projection(s)*.

ISO/DIS 16433, *Resistance welding — Procedure for seam welding of uncoated and coated low carbon steels*.

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669:2000, EN ISO 14329:2003 and EN ISO 18278-2:2004 and the following apply.

3.1

ability to make a weld

characteristic of a component defined by the available welding current range

<https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1-435dee2ba9a/sist-en-iso-18278-1-2005>

3.2

ability to continue making welds

estimation of the electrode life as defined by the number of welds which can be made before the need for re-dressing or changing of the welding electrodes

3.3

service stresses

as used in this context, applies not only to static and dynamic loading, but also includes stresses imposed by environmental conditions such as corrosion, humidity, low, elevated or fluctuating temperatures etc.

4 Test procedures

4.1 General

Test procedures can be sub-divided into two groups as follows:

- those which are considered basic to an understanding of weldability. Such tests shall be carried out to assess the weldability of the material;
- those tests which provide additional information to any basic evaluation of a material. Such tests may be carried out depending on the end application.

Acceptance criteria for each test will depend on the requirements of the product being welded and shall be specified before commencing the test programme. The type of failure shall be determined according to EN ISO 14329.

EN ISO 18278-1:2004 (E)

The procedure for spot welding on uncoated and coated low carbon and high strength steels shall be used in accordance with ISO/DIS 14373, for seam welding in accordance with ISO/DIS 16433 and for projection welding with ISO/DIS 16432. Other welding procedures shall be also be specified, if necessary.

4.2 Basic test procedures**4.2.1 Determination of the ability to make a weld**

For the determination of the ability to make a weld a weldability lobe shall be determined according to procedures as specified in EN ISO 14327.

The purpose of this procedure is to provide information on suitable weld settings and the welding current range which can be used to give acceptable welds as defined within precise limits.

The weldability lobe is influenced by:

- the electrical and mechanical characteristics of the welding equipment;
- welding parameters;
- the electrical, mechanical and physical properties of the material being welded;
- the welding configuration used;
- the electrode material and design of the welding electrode;
- the test specimen or component being welded.

iTech STANDARD PREVIEW
(standards.iteh.ai)

4.2.2 Determination of the ability to continue making welds

<https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1->

For the determination of the ability to continue making welds the electrode life test determined at constant machine settings according to EN ISO 8166 shall be used.

The purpose of this test is to provide an indication of the number of acceptable welds which can be made from a pair of welding electrodes before the need to re-dress or change the electrodes.

If current stepping programs or pulse welding procedures are used, the test procedure shall be modified to take into account any necessary changes arising from the use of such welding schedules.

Factors which determine the value of electrode life include:

- electrode material and design;
- type of welding equipment;
- the electrical and mechanical characteristics of the welding equipment;
- welding conditions;
- welding rate;
- water cooling arrangements;
- transformer/electrode configuration;
- material being welded;
- shape of the test specimen or component being welded;

— surface conditions (e.g. pretreatment coating).

EN ISO 8166 does not apply to seam welding. Alternative procedures shall be specified or developed for the evaluation of electrodes for seam welding. Generally, special variants of the seam welding process are used to weld coated steels which eliminate the problems associated with electrode contamination. In these cases e.g. narrow wheel welding, continuous wire welding and foil butt welding, electrode life testing may be omitted.

In case where only slight modifications are made to the properties of the material being assessed and where there is adequate published information as to typical electrode life to be expected, then this test may be omitted.

4.2.3 Determination of the weld properties

4.2.3.1 General

The relevant tests to be used according 4.2.3.2 to 4.2.3.6 shall be specified, if necessary.

The type of failure obtained in a test will depend on the material being welded, for example:

- rephosphorised steels, some high strength and ultra high strength steels can be give interfacial failures and partial plug failures depending on the welding parameters and the testing conditions used;
- in the case of aluminium and aluminium alloys porosity and cracks may occur;
- with nickel alloys hot cracking may occur;
- for the same type of material, increasing the thickness favours interface failures;
- the type of failure and the weld diameter will be influenced by the type of test.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4.2.3.2 Shop floor tests

<https://standards.iteh.ai/catalog/standards/sist/1daf54ed-c29b-4370-b7e1-435dee2baf9a/sist-en-iso-18278-1-2005>

Shop floor tests are used to determine the type of failure and the weld diameter by chisel or peel tests according to ISO 10447 or torsion test according to EN ISO 17653 and can be used for determining the weldability lobe. The results obtained from such tests give information on the ability to control weld quality, for example the weld setter and the inspection personnel used for quality control on the shop floor.

4.2.3.3 Shear testing

The shear testing shall be carried out according to EN ISO 14273.

The purpose of this test is to determine the failure type and the maximum shear force that the test specimen can sustain.

4.2.3.4 Mechanised Peel testing

The peel testing shall be carried out according to EN ISO 14270.

The purpose of this test is to determine the failure type and the peel force that the test specimen can sustain.

4.2.3.5 Cross tension testing

The cross tension testing shall be carried out according to EN ISO 14272.

The purpose of this test is to determine the failure type and the tensile force that the test specimen can sustain.