



Designation: F1929 – 98(Reapproved 2004)

# Standard Test Method for Detecting Seal Leaks in Porous Medical Packaging by Dye Penetration<sup>1</sup>

This standard is issued under the fixed designation F1929; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method defines materials and a procedure that will detect and locate a leak equal or greater than a channel formed by a 50  $\mu\text{m}$  (0.002 in.) wire in package edge seals formed between a transparent film and a porous sheet material. A dye penetrant solution is applied locally to the seal edge to be tested for leaks. After contact with the dye penetrant for a specified time, the package is visually inspected for dye penetration.

1.2 This test method is intended for use on packages with edge seals formed between a transparent film and a porous sheet material. This test method is limited to porous materials which can retain the dye penetrant solution and prevent it from discoloring the entire seal area for a minimum of 20 s. Uncoated papers are especially susceptible to leakage and must be evaluated carefully for use with this test method.

1.3 This test method requires that the dye penetrant have good contrast to the opaque packaging material.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

F1327 Terminology Relating to Barrier Materials for Medi-

cal Packaging (Withdrawn 2007)<sup>3</sup>

2.2 *ANSI Standards*:<sup>4</sup>

Z1.4 Sampling Procedures and Tables for Inspection by Attributes

## 3. Terminology

3.1 *wicking*—The migration of a liquid into the body of a fibrous material. This is distinct from a leak as defined in Terminology F1327.

3.2 *dye penetrant*—An aqueous solution of a dye and a surfactant designed to penetrate and indicate a defect location in the time prior to the onset of wicking which could mask its presence.

3.3 *channel*—A small continuous open passage across the width of a package seal through which microorganisms could pass. It is the objective of this test method to visually observe the presence of these defects by the leakage of dye through them.

## 4. Significance and Use

4.1 Harmful biological or particulate contaminants may enter the device through leaks. These leaks are frequently found at seals between package components of the same or dissimilar materials. Leaks may also result from a pinhole in the packaging material.

4.2 This dye penetrant procedure is applicable only to individual leaks in a package seal. The presence of a number of small leaks, as found in porous packaging material, which could be detected by other techniques, will not be indicated.

4.3 There is no general agreement concerning the level of leakage that is likely to be deleterious to a particular package. However, since these tests are designed to detect leakage, components that exhibit any indication of leakage are normally rejected.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F02 on Flexible Barrier Materials and is the direct responsibility of Subcommittee F02.40 on Package Integrity.

Current edition approved June 1, 2004. Published June 2004. Originally approved in 1998. Last previous edition approved in 1998 as F1929 – 98. DOI: 10.1520/F1929-98R04.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.