



Designation: C 1488 – 04

## Standard Practice for Simulated Aging of Cellulosic Loose-Fill Insulation<sup>1</sup>

This standard is issued under the fixed designation C 1488; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This practice covers a procedure to simulate the aging process of cellulosic loose-fill insulation by subjecting it to controlled laboratory conditions of temperature and humidity so that the insulation will be further evaluated, particularly for critical radiant flux characteristics.

1.2 It is not the intent of this practice to establish aging conditions that represent all possible exposures.

1.3 The values stated in SI units are to be regarded as the standard. The values in parentheses are provided for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C 168 Terminology Relating to Thermal Insulation

C 687 Practice for Determination of Thermal Resistance of Loose-Fill Building Insulation

C 739 Specification for Cellulosic Fiber (Wood-Based) Loose-Fill Thermal Insulation

C 870 Practice for Conditioning of Thermal Insulating Materials

C 1485 Test Method for Critical Radiant Flux of Exposed Attic Floor Insulation Using an Electric Radiant Heat Energy Source

E 970 Test Method for Critical Radiant Flux of Exposed Attic Floor Insulation Using a Radiant Heat Energy Source

#### 2.2 Other Document:

NBSIR 84-2917 Environmental Cycling of Cellulosic Thermal Insulation and Its Influence on Fire Performance

### 3. Terminology

3.1 *Definitions*—Terminology C 168 shall be considered as applicable to the terms used in this practice.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *simulated aging, n*—condition resulting from exposing a specimen to a controlled cycle of temperature and humidity conditions.

### 4. Significance and Use

4.1 The purpose of this practice is to simulate the aging process of cellulosic loose-fill insulation. By identifying any changes in flame retardant permanency due to the aging process, producers can design loose-fill insulation to meet or exceed material specifications throughout the product life cycle.

### 5. Procedure

#### 5.1 Apparatus:

5.1.1 Air oven, humidity cabinet or appropriate conditioning chamber capable of temperature and humidity conditions allowing for successfully completing the prescribed procedure as defined in 5.2.

5.1.2 Material specimens to be tested after simulated aging shall be prepared and placed in the appropriate test container in accordance with the applicable material specification or Practice C 687. For specimen to be tested using Test Method E 970 or Test Method C 1485, prepare three specimen trays to allow for repeat testing if necessary.

5.2 *Conditioning*—Condition the specimen in the selected chamber under the following conditions and chronological sequence:

- $23.4 \pm 1.7^\circ\text{C}$  ( $75 \pm 3^\circ\text{F}$ ) and  $50 \pm 3\%$  RH until constant weight is achieved (constant weight is achieved when weight changes less than 1 % in 24 h)
- 24 h at  $82.2 \pm 1.7^\circ\text{C}$  ( $180 \pm 3^\circ\text{F}$ ) and  $90 \pm 3\%$  Relative Humidity (RH)
- 24 h at  $23.4 \pm 1.7^\circ\text{C}$  ( $75 \pm 3^\circ\text{F}$ ) and  $50 \pm 3\%$  RH
- 24 h at  $82.2 \pm 1.7^\circ\text{C}$  ( $180 \pm 3^\circ\text{F}$ ) and  $90 \pm 3\%$  RH
- 24 h at  $23.4 \pm 1.7^\circ\text{C}$  ( $75 \pm 3^\circ\text{F}$ ) and  $50 \pm 3\%$  RH
- 96 h at  $60.0 \pm 1.7^\circ\text{C}$  ( $140 \pm 3^\circ\text{F}$ ) Air Oven
- 21  $\pm 2^\circ\text{C}$  ( $69.8 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 3\%$  RH until constant weight is achieved

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.31 on Chemical and Physical Properties.

Current edition approved May 1, 2004. Published June 2004. Originally approved in 2001. Last previous edition approved in 2001 as C 1488 – 01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 6. Report

6.1 Report the following information:

6.1.1 Conditioning treatment followed,

6.1.2 Conditioned sample use; that is, tested in accordance with Test Method E 970, Specification C 739 or Test Method C 1485 as applicable, and

6.1.3 Any visible changes in the specimen after the conditioning treatment, such as a separation of components or a change in color or fluffiness, particularly when changes are not uniform.

## 7. Keywords

7.1 aging; cellulosic fiber loose-fill; conditioning; humidity/temperature cycling; thermal insulation

## APPENDIXES

### (Nonmandatory Information)

#### X1. NBSIR 84-2917, ENVIRONMENTAL CYCLING OF CELLULOSIC THERMAL INSULATION

X1.1 NBSIR 84-2917, Environmental Cycling of Cellulosic Thermal Insulation and Its Influence on Fire Performance, is a study conducted on climate data for eleven cities located throughout the United States. Findings from this environmental study were used to develop conditioning cycles for research on the influence of environment on the fire performance of

loose-fill cellulosic thermal insulation. Cellulosic thermal insulation was exposed to various simulated environmental cycles and tested for changes in fire performance. Results from this research showed that environmental exposure could effect fire performance.

#### X2. PROCEDURE TO DETERMINE CHANGE IN WEIGHT

X2.1 A change in weight due to conditioning can be useful information to the user of this standard in evaluating changes, if any, in performance characteristics. A change in weight can be calculated using the following procedure:

$$C = [(W_1 - W_3) / (W_1 - W_2)] \times 100 \quad (X2.1)$$

$C$  = percentage change in weight after conditioning treatment,

$W_1$  = weight of specimen and specimen holder before the conditioning treatment, grams,

$W_2$  = weight of empty specimen holder/tray, grams, and

$W_3$  = weight of specimen and specimen holder after the conditioning treatment, grams.

where:

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*