



Designation: D 2916 – 04

## Standard Specification for Isophorone<sup>1</sup>

This standard is issued under the fixed designation D 2916; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers isophorone<sup>2</sup> (98 % grade) for use in paint, varnish, lacquer, and related products.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E 29.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5 For specific hazard information and guidance, see the supplier’s Material Safety Data Sheet for materials listed in this specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

- D 268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Material
- D 1078 Test Method for Distillation Range of Volatile Organic Liquids
- D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)
- D 1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)
- D 1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used In Paint, Varnish, Lacquer,

and Related Products

D 2192 Test Method for Purity of Aldehydes and Ketones  
D 4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter

E 1 Specification for ASTM Thermometers

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 300 Practice for Sampling Industrial Chemicals

#### 2.2 U.S. Federal Specification:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>4</sup>

### 3. Properties

3.1 Isophorone shall conform to the following requirements:

Apparent specific gravity: 20/20°C	0.921 to 0.923
or 25/25°C	0.918 to 0.920
Color, Pt-Co scale, max	100
Distillation, °C	
Initial boiling point, min	210
95 % point, max	218
Purity, weight % min	98
Acidity as acetic acid, weight %, max	0.02
Water, weight %, max	0.1

### 4. Sampling

4.1 Sample the material in accordance with Practice E 300.

### 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM test methods:

5.1.1 *Apparent Specific Gravity*—Determine the apparent specific gravity by any method that is accurate to the third decimal place, the temperature of both specimen and water being 20 or 25°C. See either the Specific Gravity section of Guide D 268 or Test Method D 4052.

5.1.2 *Color*—Test Method D 1209.

5.1.3 *Distillation Range*—Test Method D 1078, using an ASTM Solvents Distillation Thermometer 105C having a range from 198 to 252°C and conforming to the requirements in Specification E 1.

5.1.4 *Purity*—Test Method D 2192.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings and Materials and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved June 1, 2004. Published June 2004. Originally approved in 1970. Last previous edition approved in 1988 as D 2916 – 88 (2001).

<sup>2</sup> This compound is also known under the name 3,5,5-trimethyl-2-cyclohexene-1-one.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098

\*A Summary of Changes section appears at the end of this standard.

5.1.5 *Acidity*—Test Method D 1613.

5.1.6 *Water*—Test Method D 1364.

## **6. Packaging and Package Marking**

6.1 Package size shall be agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or, when specified, shall conform to Fed. Spec. PPP-C-2020.

## **7. Keywords**

7.1 isophorone; ketones; solvents

## **SUMMARY OF CHANGES**

Subcommittee D01.35 has identified the location of selected changes to this standard since the last issue (D 2916 – 88 (2001)) that may impact the use of this standard.

(1) Permitted apparent specific gravity to be run at either 20/20°C or 25/25°C in 3.1.

(2) Added Practice E 29 to the Scope and Referenced Documents sections.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*

(<https://standards.iteh.ai>)  
**Document Preview**

[ASTM D2916-04](https://standards.iteh.ai/catalog/standards/astm/fb2cf47b-aeec8-419c-82d5-2292ffc6f288/astm-d2916-04)  
[/catalog/standards/astm/fb2cf47b-aeec8-419c-82d5-2292ffc6f288/astm-d2916-04](https://standards.iteh.ai/catalog/standards/astm/fb2cf47b-aeec8-419c-82d5-2292ffc6f288/astm-d2916-04)