INTERNATIONAL STANDARD

ISO 9772

Second edition 2001-04-01 **AMENDMENT 1** 2003-09-15

Cellular plastics — Determination of horizontal burning characteristics of small specimens subjected to a small flame

AMENDMENT 1: Specimens iTeh STANDARD PREVIEW

S Plastiques alvéolaires — Détermination des caractéristiques de combustion de petites éprouvettes en position horizontale, soumises à une petite flamme

https://standards.iteh.AMENDEMENTs/Is:Éprouvettes 2-4fce-82a3-97b0a8fd10f3/iso-9772-2001-amd-1-2003



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9772:2001/Amd 1:2003 https://standards.iteh.ai/catalog/standards/sist/c3ff5845-ad12-4fce-82a3-97b0a8fd10f3/iso-9772-2001-amd-1-2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 9772:2001 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

Cellular plastics — Determination of horizontal burning characteristics of small specimens subjected to a small flame

AMENDMENT 1: Specimens

Page 1

Update Clause 2 (normative references) by inserting 2001 as the year of publication of ISO 1043-1 and deleting the footnote.

Page 7

Replace Clause 6 "Specimens" by the following clause.

6 Specimens

- **6.1** It is possible that the results of tests carried out on test specimens taken from materials of different densities, colours and thicknesses will be different. For materials with properties which vary over a range, the test specimens shall be representative of the whole range.
- 6.2 Test specimens with densities at the extremes of the trange shall be tested and, if the test results yield the same flame test classification, iall specimens within the trange shall be considered representative of the range. If the burning characteristics are not essentially the same, the results of the evaluation shall be considered to apply only to materials with the densities tested. Additional test specimens with intermediate densities shall be tested to determine the range of applicability.
- **6.3** Uncoloured test specimens and test specimens with the highest level of organic and inorganic pigment loading shall be tested and, if the test results yield the same flame test classification, all specimens within this colour range shall be considered representative of the range. If the burning characteristics are not essentially the same, the results of the evaluation shall be considered to apply only to materials with the pigment loadings tested. If a material contains pigments which are known to affect the flammability characteristics, specimens containing these pigments shall also be tested. Thus the test specimens tested shall be those that
- a) contain no colouring;
- b) contain the highest level of organic pigments;
- c) contain the highest level of inorganic pigments;
- d) contain pigments which are known to adversely affect flammability characteristics.
- **6.4** All specimens shall be cut from a representative sample of the material (sheets or end products). After any cutting operation, care shall be taken to remove all dust and any particles from the surface. Cut edges shall have a smooth finish.
- **6.5** The standard test specimen shall be 150 mm \pm 10 mm long by 50 mm \pm 1 mm wide. Materials supplied in thicknesses over 13 mm shall be cut to 13 mm \pm 1 mm thickness with any skin on one side. Materials supplied in thicknesses of 13 mm or less shall be tested at the thickness supplied, without removing any skin (see 6.8). If materials with adhesive applied are to be tested, specimens having adhesive on one side only shall be used (see 6.8).

ISO 9772:2001/Amd.1:2003(E)

NOTE Tests made on test specimens of different thicknesses or directions of anisotropy are not comparable.

- **6.6** Prepare a minimum of 20 specimens for the test. This includes 10 additional specimens in the event that the situation described in 4.4, 4.5 or A.3 is encountered.
- **6.7** Mark each specimen across its width with lines at 25 mm, 60 mm and 125 mm from one end, referred to hereafter as gauge marks (see Figure 2).
- **6.8** Test specimens with a high-density exterior (skin) on one side shall be tested with this side facing down. Test specimens with adhesive on one side shall be tested with this side facing up.

iTeh STANDARD PREVIEW (standards.iteh.ai)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9772:2001/Amd.1:2003(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9772:2001/Amd 1:2003 https://standards.iteh.ai/catalog/standards/sist/c3ff5845-ad12-4fce-82a3-97b0a8fd10f3/iso-9772-2001-amd-1-2003

ICS 13.220.40; 83.100

Price based on 2 pages