



**SLOVENSKI STANDARD**  
**SIST ISO 844:2003**

01-julij-2003

---

DYb^Yb]`dc`]a Yfb]`a UHf]UJ]!`HfXY`dYbY`E`8 c`c Yj Ub^Y`Uglbcgh]`ghjg\_Ub^U

Rigid cellular plastics -- Determination of compression properties

Plastiques alvéolaires rigides -- Détermination des caractéristiques de compression

Ta slovenski standard je istoveten z: **ISO 844:2001**

[SIST ISO 844:2003](https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003)

<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

**ICS:**

83.100

Penjeni polimeri

Cellular materials

**SIST ISO 844:2003**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 844:2003

<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

# INTERNATIONAL STANDARD

**ISO  
844**

Third edition  
2001-06-01

---

---

## **Rigid cellular plastics — Determination of compression properties**

*Plastiques alvéolaires rigides — Détermination des caractéristiques de  
compression*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 844:2003](https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003)

[https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-  
2923034d5b49/sist-iso-844-2003](https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003)



Reference number  
ISO 844:2001(E)

© ISO 2001

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 844:2003](https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003)

<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.ch](mailto:copyright@iso.ch)  
Web [www.iso.ch](http://www.iso.ch)

Printed in Switzerland

**Contents**

Page

Foreword.....	iv
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	1
4 Symbols and abbreviated terms .....	2
5 Principle.....	2
6 Apparatus .....	3
7 Test specimens .....	3
8 Procedure .....	4
9 Expression of results .....	4
10 Precision.....	6
11 Test report .....	6

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 844:2003](https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003)

<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

## ISO 844:2001(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 844 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 10, *Cellular plastics*.

This third edition cancels and replaces the second edition (ISO 844:1998), which has been the subject of a minor revision to correct, in particular, the title, the units of  $E$  in clause 4 and the labelling of Figures 1 b) and 1 c).

INTERNATIONAL STANDARD PREVIEW  
(standards.iteh.ai)  
SIST ISO 844:2003  
<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

# Rigid cellular plastics — Determination of compression properties

## 1 Scope

This International Standard specifies a method of determining

a) the compressive strength and corresponding relative deformation

or

b) the compressive stress at 10 % relative deformation

and

c) when desired, the compressive modulus

of rigid cellular plastics.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

## 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing*.

ISO 1923:1981, *Cellular plastics and rubbers — Determination of linear dimensions*.

## 3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

### 3.1 relative deformation

$\varepsilon$

ratio of the reduction (in relation to its initial value) in thickness of the test specimen to its initial thickness

NOTE 1 It is expressed as a percentage.

NOTE 2  $\varepsilon_m$  is the relative deformation corresponding to  $\sigma_m$  (see 3.2).

**ISO 844:2001(E)****3.2****compressive strength** $\sigma_m$ 

maximum compressive force  $F_m$  divided by the initial cross-sectional area of the test specimen when the relative deformation  $\varepsilon$  is  $< 10\%$

**3.3****compressive stress at 10 % relative deformation** $\sigma_{10}$ 

ratio of the compressive force  $F_{10}$  at 10 % relative deformation ( $\varepsilon_{10}$ ) to the initial cross-sectional area of the test specimen

**3.4****compressive modulus of elasticity** $E$ 

compressive stress divided by the corresponding relative deformation below the proportional limit, i.e. when the relation is linear

**4 Symbols and abbreviated terms**

$A_0$  initial cross-sectional area, in square millimetres

$E$  compressive modulus of elasticity, in kilopascals

$F_e$  force corresponding to  $x_e$  (conventional proportional limit), in newtons

$F_m$  maximum force, in newtons

$F_{10}$  force at 10 % relative deformation, in newtons  
<https://standards.iteh.ai/catalog/standards/sist/5aac25ef-f132-4c65-93ab-2923034d5b49/sist-iso-844-2003>

$h_0$  initial thickness of test specimen, in millimetres

$\varepsilon_m$  relative deformation corresponding to compressive strength  $\sigma_m$ , in percent

$\sigma_m$  compressive strength, in kilopascals

$\sigma_{10}$  compressive stress at 10 % relative deformation, in kilopascals

$x_e$  displacement at  $F_e$  in the conventional elastic zone, in millimetres

$x_m$  displacement at maximum force, in millimetres

$x_{10}$  displacement at 10 % relative deformation, in millimetres

kPa kilopascals

Pa pascals

**5 Principle**

A compressive force is applied in an axial direction to the faces of a rectangular parallelepiped test specimen. The maximum stress supported by the test specimen is calculated.



If the value of the maximum stress corresponds to a relative deformation of less than 10 %, it is noted as the “compressive strength”. Otherwise, the compressive stress at 10 % relative deformation is calculated and its value noted as the “compressive stress at 10 % relative deformation”.

## 6 Apparatus

### 6.1 Compression-testing machine

Any compression-testing machine suited to the range of force and displacement involved and having two square or circular plane, parallel plates which are polished and cannot be deformed and of which the length of one side (or the diameter) is at least 10 cm may be used. One of the plates shall be fixed and the other movable; the latter shall be capable of moving at a constant rate of displacement in accordance with the conditions laid down in clause 8. Neither plate shall be self-aligning.

### 6.2 Measuring devices for displacement and force

#### 6.2.1 Measurement of displacement

The compression-testing machine shall be fitted with a system allowing continuous measurement of the displacement  $x$  of the movable plate with an accuracy of  $\pm 5\%$  or  $\pm 0,1$  mm if this latter value is a more accurate measurement (see note to 6.2.2).

#### 6.2.2 Measurement of force

A force sensor shall be fixed to one of the machine plates in order to measure the force  $F$  produced by the reaction of the test specimen upon the plates during the test. This sensor shall be such that its own deformation during the course of the measurement operation is negligible compared with that being measured and, in addition, it shall allow the continuous measurement of the force at any point in time with an accuracy of  $\pm 1\%$ .

NOTE It is recommended that a device be used for the simultaneous recording of the force  $F$  and the displacement  $x$  that allows, by obtaining a curve of  $F = f(x)$ , the graphical determination of the pair of values of  $F$ ,  $x$  required in clause 9 with the accuracy laid down in 6.2.1 and this subclause, and provides additional information on the behaviour of the product.

#### 6.2.3 Calibration

Devices for measuring, and if applicable recording graphically, the force and displacement produced by the test machine shall be checked periodically. The devices shall be checked by using a series of standard weights, the masses of which are known to accuracies exceeding  $\pm 1\%$  and which correspond to the forces applied during the test. To check the devices, spacers shall be used which have thicknesses known to accuracies better than either  $\pm 0,5\%$  or  $\pm 0,1$  mm, whichever is more restrictive.

### 6.3 Instruments for measuring the dimensions of the test specimens

These instruments shall be in accordance with ISO 1923.

## 7 Test specimens

### 7.1 Dimensions

The test specimens shall be  $(50 \pm 1)$  mm in thickness except for products with moulded skins which are intended to remain integral with the product in use. With such products, the specimens shall be the full thickness, provided that the minimum thickness is 10 mm or greater and that the maximum thickness is not greater than the width or diameter of the specimen.