



Designation: F 1083 – 04

# Standard Specification for Pipe, Steel, Hot-Dipped Zinc-Coated (Galvanized) Welded, for Fence Structures<sup>1</sup>

This standard is issued under the fixed designation F 1083; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers hot-dipped galvanized welded steel pipe in NPS 1 (Note 1) to NPS 8, inclusive, with nominal (average) wall thickness as given in Table 1 and Table 2. Pipe having other dimensions (Note 2) may be furnished provided such pipe complies with all other requirements of this specification. Pipe ordered under this specification is intended for use as a structural support for fencing in accordance with Specification F 1043, Group 1A.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this specification for such traditional terms as nominal diameter, size, and nominal size.

NOTE 2—A comprehensive listing of standardized pipe dimensions is contained in ANSI B 36.10.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in brackets are for information only.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- A 53 Specification for Pipe, Steel, Black and Hot-Dipped, Zinc-Coated Welded and Seamless
- A 90/A 90M Test Method for Weight of Coating on Zinc-Coated (Galvanized) Iron or Steel Articles
- A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment
- B 6 Specification for Zinc (Slab Zinc)
- E 8 Test Methods for Tension Testing of Metallic Materials
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>1</sup> This specification is under the jurisdiction of Committee F14 on Fences and is the direct responsibility of Subcommittee F14.40 on Chain Link Fence and Wire Accessories.

Current edition approved June 1, 2004. Published June 2004. Originally approved in 1987. Last previous edition approved in 1996 as F 1083 - 98(03).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

F 1043 Specification for Strength and Protective Coatings on Metal Industrial Chain Link Fence Framework

### 2.2 ANSI Standard:

B 36.10 Welded and Seamless Wrought Steel Pipe<sup>3</sup>

## 3. Ordering Information

3.1 Orders for material under this specification shall include the following as required, to describe the desired material adequately:

- 3.1.1 Specification designation,
- 3.1.2 Quantity (feet, metres, or number of lengths),
- 3.1.3 Name of material (steel pipe),
- 3.1.4 Method of manufacture (electric-resistance welded or furnace welded),
- 3.1.5 Grade (Regular or High Strength) *High Strength Grade available for sizes NPS 6 (150) and larger.*
- 3.1.6 Type (Table 1 or Table 2),
- 3.1.7 Size (NPS designator and weight class; or outside diameter and nominal wall),
- 3.1.8 Length (see Section 14),
- 3.1.9 Certification (see 18.1), and
- 3.1.10 Selection of applicable level of preservation and packaging required, if other than in accordance with Practices A 700 (see 20.1).

## 4. Process

4.1 The steel for welded pipe shall be made by one or more of the following processes: electric-furnace, open hearth, or basic-oxygen. The steel for welded pipe shall be of soft weldable quality.

4.2 Welded pipe NPS 4 and under may be butt-welded, unless otherwise specified. Welded pipe over NPS 4 shall be electric-welded.

## 5. Coating

5.1 Pipe shall be coated with zinc inside and outside by the hot-dip process.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

**TABLE 1 Dimensions, Nominal Weights (Plain Ends) for Standard Weight Pipe (Schedule 40)**

NOTE 1—Pipe furnished in accordance with this table will be standard pipe.

NOTE 2—The wall thickness is expressed in three decimal places, the fourth decimal place being carried forward or dropped, in accordance with Practice E 29.

NPS	Designator	Outside Diameter		Wall Thickness		Weight	
	Metric	in.	[mm]	in.	[mm]	lb/ft	[kg/m]
1	[25]	1.315	[33.4]	0.133	[3.38]	1.68	[2.5]
1¼	[32]	1.660	[42.2]	0.140	[3.56]	2.27	[3.4]
1½	[40]	1.900	[48.3]	0.145	[3.68]	2.72	[4.0]
2	[50]	2.375	[60.3]	0.154	[3.91]	3.65	[5.4]
2½	[65]	2.875	[73.0]	0.203	[5.16]	5.80	[8.6]
3	[80]	3.500	[88.9]	0.216	[5.49]	7.58	[11.3]
3½	[90]	4.000	[101.6]	0.226	[5.74]	9.12	[13.6]
4	[100]	4.500	[114.3]	0.237	[6.02]	10.80	[16.1]
6	[150]	6.625	[168.3]	0.280	[7.11]	18.99	[28.3]
8	[200]	8.625	[219.1]	0.322	[8.18]	28.58	[42.5]

**TABLE 2 Dimensions, Nominal Weights (Plain Ends) for Extra Strong Pipe (Schedule 80)**

NOTE 1—Pipe furnished in accordance with this table will be extra-strong pipe.

NOTE 2—The wall thickness is expressed in three decimal places, the fourth decimal place being carried forward or dropped, in accordance with Practice E 29.

NPS	Designator	Outside Diameter		Wall Thickness		Weight	
	Metric	in.	[mm]	in.	[mm]	lb/ft	[kg/m]
1	[25]	1.315	[33.4]	0.179	[4.55]	2.17	[3.23]
1¼	[32]	1.660	[42.2]	0.191	[4.85]	3.00	[4.47]
1½	[40]	1.900	[48.3]	0.200	[5.08]	3.63	[5.41]
2	[50]	2.375	[60.3]	0.218	[5.54]	5.03	[7.48]
2½	[65]	2.875	[73.0]	0.276	[7.01]	7.67	[11.41]
3	[80]	3.500	[88.9]	0.300	[7.62]	10.26	[15.27]
3½	[90]	4.000	[101.6]	0.318	[8.08]	12.52	[18.63]
4	[100]	4.500	[114.3]	0.337	[8.56]	15.00	[22.32]
6	[150]	6.625	[168.3]	0.432	[10.97]	28.60	[42.56]
8	[200]	8.625	[219.1]	0.500	[12.70]	43.43	[64.64]

5.2 The zinc used for the coating shall be any grade of zinc conforming to Specification B 6.

## 6. Tensile Requirements

6.1 Pipe furnished to this specification shall meet the following minimum tensile requirements when tested in accordance with Test Methods E 8.

### 6.1.1 Tensile Strength

6.1.1.1 *Regular Grade*—Minimum tensile strength shall be 48 000 psi [330 MPa].

6.1.1.2 *High Strength Grade*—Minimum tensile strength shall be 60 000 psi [414 MPa] for sizes NPS 6 (150) and larger.

### 6.1.2 Yield Strength

6.1.2.1 *Regular Grade*—Minimum yield strength shall be 30 000 psi [205 MPa].

6.1.2.2 *High Strength Grade*—Minimum yield strength shall be 50 000 psi [344 MPa] for sizes NPS 6 (150) and larger.

## 7. Weight of Coating

7.1 The weight of zinc coating shall be not less than 1.8 oz/ft<sup>2</sup> [550 g/m<sup>2</sup>], as determined from the average results of the two specimens taken for test in accordance with 10.1 and not less than 1.6 oz/ft<sup>2</sup> [490 g/m<sup>2</sup>] for either of these specimens. The weight of coating expressed in ounces per square foot shall be calculated by dividing the total weight of zinc, inside plus outside, by the total area, inside plus outside, of the surface

coated. Each specimen shall have not less than 1.3 oz/ft<sup>2</sup> [400 g/m<sup>2</sup>] of zinc coating on each surface, calculated by dividing the total weight of zinc on the given surface (outside or inside) by the area of the surface coated (outside or inside).

## 8. Weight of Coating Test

8.1 Determine the weight of zinc coating by a strip test in accordance with Test Method A 90/A 90M. The total zinc on each specimen shall be determined in a double stripping operation.

## 9. Test Specimens

9.1 Test specimens for determination of weight of coating shall be cut approximately 4 in. [102 mm] in length. Specimens of toprail and brace material shall be taken from the ends of mill lengths. Specimens of post material shall be cut from the length from which the post is to be cut. Under no circumstances shall specimens of post material be taken after the post is cut from the mill length.

9.2 Tensile and yield samples shall be of sufficient length to prepare specimens for testing in accordance with Test Methods E 8.

## 10. Number of Tests

10.1 Two test specimens for the determination of weight of coating shall be taken, one from each end of one length of