
**Steel flat products for pressure
purposes — Technical delivery
conditions —**

Part 1:
General requirements

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Produits plats en acier pour service sous pression — Conditions
techniques de livraison —*

Partie 1: Exigences générales

ISO 9328-1:2003

<https://standards.iteh.ai/catalog/standards/sist/6c55cee2-6dba-4d8e-bed1-f4d9fca7cd87/iso-9328-1-2003>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9328-1:2003

<https://standards.iteh.ai/catalog/standards/sist/6c55cee2-6dba-4d8e-bed1-f4d9fca7cd87/iso-9328-1-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references	1
3 Terms and definitions	2
4 Classification and designation	3
4.1 Classification.....	3
4.2 Designation.....	4
5 Information to be supplied by the purchaser.....	4
5.1 Mandatory information	4
5.2 Options.....	4
6 Requirements	5
6.1 Steelmaking process	5
6.2 Delivery condition	5
6.3 Chemical composition.....	5
6.4 Mechanical properties	6
6.5 Surface condition.....	6
6.6 Internal soundness	6
6.7 Dimensions and tolerances on dimensions.....	6
6.8 Calculation of mass	6
7 Inspection	6
7.1 Types of inspection and inspection documents.....	6
7.2 Tests to be carried out.....	7
7.3 Retests	7
8 Sampling	7
8.1 Frequency of testing.....	7
8.2 Selection and preparation of samples and test pieces.....	8
9 Test methods.....	8
9.1 Chemical analysis	8
9.2 Tensile test at room temperature	9
9.3 Tensile test at elevated temperature.....	9
9.4 Impact test	12
9.5 Other testing	13
10 Marking.....	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9328-1 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 10, *Steel for pressure purposes*.

This second edition cancels and replaces the first edition (ISO 9328-1:1991), all clauses and Table 4 of which have been technically revised. Further, Annexes A and B, and Tables 1 and 2 have been deleted; Figure 1 is now in tabular form and Table 3 is in two parts (Tables 2 and 3).

ISO 9328 consists of the following parts, under the general title *Steel flat products for pressure purposes — Technical delivery conditions*:

- *Part 1: General requirements*
- *Part 2: Non-alloy and alloy steels with specified elevated temperature properties*
- *Part 3: Weldable fine grain steels, normalized*
- *Part 4: Nickel-alloy steels with specified low temperature properties*
- *Part 5: Weldable fine grain steels, thermomechanically rolled*
- *Part 6: Weldable fine grain steels, quenched and tempered*
- *Part 7: Stainless steels*

NOTE The clauses marked with a bullet (●) contain information relating to agreements which are to be made at the time of enquiry and order. The clauses marked with a triangular bullet (▲) contain information relating to agreements which may be made at the time of enquiry and order.

Steel flat products for pressure purposes — Technical delivery conditions —

Part 1: General requirements

1 Scope

This part of ISO 9328 specifies the general technical delivery conditions for steel flat products (plate/sheet and strip) used principally for the construction of pressure equipment.

The general technical delivery requirements in ISO 404 also apply to products supplied in accordance with this part of ISO 9328.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148:1983, *Steel — Charpy impact test (V-notch)*

ISO 377:1997 *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404:1992, *Steel and steel products — General technical delivery requirements*

ISO 783:1999, *Metallic materials — Tensile testing at elevated temperature*

ISO 2566-1:1984, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels*

ISO 2566-2:1984, *Steel — Conversion of elongation values — Part 2: Austenitic steels*

ISO 3651-2:1998, *Determination of resistance to intergranular corrosion of stainless steels — Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid*

ISO 4885:1996, *Ferrous products — Heat treatments — Vocabulary*

ISO 4948-1:1982, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2:1981, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO/TS 4949, *Steel names based on letter symbols*

ISO 6892:1998, *Metallic materials — Tensile testing at ambient temperature*

ISO 6929:1987, *Steel products — Definitions and classification*

ISO 7452:2002, *Hot-rolled structural steel plates — Tolerances on dimensions and shape*

ISO 9328-1:2003(E)

ISO 7778:1983, *Steel plate with specified through-thickness characteristics*

ISO 7788:1985, *Steel — Surface finish of hot-rolled plates and wide flats — Delivery requirements*

ISO 9034:1987, *Hot-rolled structural steel wide flats — Tolerances on dimensions and shape*

ISO 9328-2, *Steel flat products for pressure purposes — Technical delivery conditions — Part 2: Non-alloy and alloy steels with specified elevated temperature properties*

ISO 9328-3, *Steel flat products for pressure purposes — Technical delivery conditions — Part 3: Weldable fine grain steels, normalized*

ISO 9328-4, *Steel flat products for pressure purposes — Technical delivery conditions — Part 4: Nickel-alloy steels with specified low temperature properties*

ISO 9328-5, *Steel flat products for pressure purposes — Technical delivery conditions — Part 5: Weldable fine grain steels, thermomechanically rolled*

ISO 9328-6, *Steel flat products for pressure purposes — Technical delivery conditions — Part 6: Weldable fine grain steels, quenched and tempered*

ISO 9328-7:—¹⁾, *Steel flat products for pressure purposes — Technical delivery conditions — Part 7: Stainless steels*

ISO 9444:2002, *Continuously hot-rolled stainless steel strip, plate/sheet and cut lengths — Tolerances on dimensions and form*

ISO 9445:2002, *Continuously cold-rolled stainless steel narrow strip, wide strip, plate/sheet and cut lengths — Tolerances on dimensions and form*

ISO 10474:1991, *Steel and steel products — Inspection documents*

ISO 14284:1996, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO 15510:2003, *Stainless steels — Chemical composition*

ISO 18286, *Hot rolled stainless steel plates — Tolerances on dimensions and shape*

3 Terms and definitions

For the purpose of this document the terms and definitions in ISO 4885, ISO 4948-1, ISO 4948-2 and ISO 6929 as well as the following apply.

Additionally to the definitions for thermomechanical treatment and quenching and tempering in ISO 4885 the following should be noted:

- a) Thermomechanical rolling (symbol M) may include processes of increased cooling rates with or without tempering, including self-tempering but excluding definitively direct quenching and tempering.
- b) Quenching and tempering (symbol QT) also includes direct hardening plus tempering.

NOTE In international publications for both the normalizing, as well as the thermomechanical rolling, the expression “controlled rolling” may be found. However in view of the different applicability of the products a distinction of the terms is necessary.


1) To be published.

3.1 normalizing rolling

rolling process in which final deformation is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing

See Figure 1.

NOTE The symbol for this delivery condition and for the normalized condition is N.



Key

- <https://standards.iteh.ai/catalog/standards/sist/6c55cee2-6dba-4d8e-bed1-f4d9fca7cd87/iso-9328-1-2003>
- T is the temperature in degrees Celsius
- t is the time in hours
- Ar_3 is the temperature at which ferrite starts to form on cooling
- a Recrystallized austenite region.
- b Non-recrystallized austenite region.
- c Austenite plus ferrite region.

Figure 1 — Time-temperature scheme of normalizing rolling

4 Classification and designation

4.1 Classification

4.1.1 The classification of the steel grades in accordance with ISO 4948-1 and ISO 4948-2 is given in ISO 9328-2, ISO 9328-3, ISO 9328-4, ISO 9328-5, ISO 9328-6 or ISO 9328-7 depending on the steel grade's chemical composition and treatment condition.

4.1.2 Steels covered in ISO 9328-7 are additionally classified according to their structure into:

- ferritic steels;
- martensitic steels;
- austenitic steels;
- austenitic-ferritic steels.

For more details see ISO 15510.

4.2 Designation

The steel grades specified in the individual parts of ISO 9328 are designated with steel names in accordance with ISO/TS 4949.

5 Information to be supplied by the purchaser

5.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) the quantity required;
- b) the type of flat product;
- c) the International Standard specifying the tolerances on dimensions, shape and mass (see 6.7) and, if the relevant International Standard permits the purchaser certain options, e.g. regarding edge finishes or tolerance classes, specific information on these aspects;
- d) the nominal dimensions of the product;
- e) the number of this International Standard, i.e. ISO 9328-1 and that of the relevant part, i.e. Part 2, 3, 4, 5, 6 or 7;
- f) the steel name;
- g) the delivery condition, if it differs from the usual condition specified in the individual parts of ISO 9328; for stainless steels, the process route selected from the relevant table of ISO 9328-7;
- h) whether impact testing is required, and the test direction (see 7.2.1 and 9.4);
- i) inspection document to be issued (see 7.1).

5.2 Options

A number of options are specified in this part of ISO 9328 and listed below. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see 5.1).

- a) Specification of the steelmaking process (see 6.1);
- b) mechanical properties after additional heat treatment (see 6.4.1);
- c) specification of special classes for the reduction of area (see 6.4.2);
- d) additional tests (see 6.6 and 7.2.2);
- e) deviating frequency of testing (see 8.1.1 and 8.1.3);
- f) deviating delivery condition (see 8.2.1.3);
- g) specification of an analytical method (see 9.1);
- h) temperature of the tensile test at elevated temperature (see 9.3);
- i) deviating testing temperature for the impact test (see 9.4);

- j) marking method (see 10.1);
- k) special marking (see 10.2 and 10.3);
- l) information to be given by marking (see Table 1).

Table 1 — Marking of the products

Marking of	Symbol ^a	Marking of	Symbol ^a
Manufacturer's name, trade mark or logo	+	Direction of rolling ^b	(+)
The number of this International Standard	(+)	Nominal thickness	(+)
Steel name	+	Nominal dimensions other than thickness	(+)
Type of finish	(+)	Inspector's mark	+ ^c
Identification number ^d	+ ^e	Purchaser's order No.	(+)

^a +: the marking shall be applied; (+): the marking shall be applied if so agreed, or at the manufacturer's discretion.

^b The direction of rolling is normally obvious from the shape of the product and the position of the marking. Marking may either be longitudinally applied by roller stamping or it may be near to one end of the piece and transverse to the rolling direction. A specific separate indication of the principal rolling direction will not normally be required, but may be requested by the customer.

^c The inspector's mark may be omitted if the relevant inspector can be identified in another way.

^d The numbers or letters used for identification shall allow the product(s) to be related to the relevant inspection certificate or inspection report.

^e This shall permit the traceability of the cast number.

iTeH STANDARD PREVIEW
(standards.iteh.ai)

6 Requirements

ISO 9328-1:2003

6.1 Steelmaking process

<https://standards.iteh.ai/catalog/standards/sist/6c55cee2-6dba-4d8e-bed1-f4d9fca7cd87/iso-9328-1-2003>

- ▲ **6.1.1** Unless a special steelmaking process has been agreed upon at the time of enquiry and order, the steelmaking process for steels in accordance with this part of ISO 9328 shall be at the discretion of the manufacturer. If a special steelmaking process has been specified this shall be reported in the inspection document.

6.1.2 Steels other than stainless steels shall be fully killed.

6.2 Delivery condition

See 3 and 3.1 and the individual parts of ISO 9328.

6.3 Chemical composition

6.3.1 Cast analysis

The cast analysis reported by the steel producer shall apply and comply with the requirements of the individual parts of ISO 9328 and shall be included in the relevant inspection document.

6.3.2 Product analysis

The permissible product analysis tolerances on the limiting values given for the cast analysis are specified in the individual parts of ISO 9328.